**TECHNISCHE
UNIVERSITÄT
DRESDEN**

Fakultät Umweltwissenschaften

Photogrammetrische Verfahren zur Risserkennung und -analyse im bautechnischen Versuchswesen

Dissertation zur Erlangung des akademischen Grades
Doktoringenieur (Dr.-Ing.)

vorgelegt von

Dipl.-Ing. Frank Liebold

geboren am 17. Mai 1987 in Schleiz

Gutachter:

Prof. Dr. sc. techn. habil. Hans-Gerd Maas

Technische Universität Dresden / Institut für Photogrammetrie und
Fernerkundung

Prof. Dr.-Ing. habil. Michael Möser

Technische Universität Dresden / Geodätisches Institut

Prof. Dr.-Ing. Johannes Lange

Technische Hochschule Köln / Institut für Konstruktiven Ingenieurbau

Verteidigung:

Dresden, den 09.06.2020

Danksagung

Diese Dissertation entstand während meiner Tätigkeit als Mitarbeiter am Institut für Photogrammetrie und Fernerkundung der Fakultät Umweltwissenschaften an der Technischen Universität Dresden.

Besonderer Dank gilt dabei meinem Doktorvater Prof. Hans-Gerd Maas, der mir die Möglichkeit bot, diese Arbeit zu erstellen. Er begleitete mich auf meinem Weg und ich bedanke mich für sein entgegengebrachtes Vertrauen sowie für die hilfreichen Fachdiskussionen und Anregungen.

Außerdem bin ich dankbar, dass Herr Prof. Johannes Lange und Herr Prof. Michael Möser als Gutachter zur Verfügung stehen.

Des Weiteren danke ich meinen Kollegen am Institut für Photogrammetrie und Fernerkundung für die gute Zusammenarbeit und die hilfreichen Anregungen.

Dank gilt auch meinen Projektpartnern vom Institut für Massivbau und dem Institut für Baustoffe, insbesondere Gregor Schacht und Iurie Curosu sowie meinen weiteren Kollegen im Graduiertenkolleg.

Die Arbeit war nur durch die Finanzierung der von mir bearbeiteten Forschungsprojekte möglich, zum einen durch das Bundesamt für Bauwesen und Raumordnung BBR (Forschungsprojekt im Rahmen der Forschungsinitiative „Zukunft Bau“) und zum anderen durch die Deutsche Forschungsgemeinschaft DFG (Graduiertenkolleg 2250/1).

Letztendlich möchte ich mich bei meiner Familie bedanken, die mich auf meinen Weg immer unterstützt hat.

Kurzfassung

Photogrammetrische Methoden gewinnen zunehmend an Bedeutung im bautechnischen Versuchswesen. Die Auswertung von Bildsequenzen ermöglicht eine kontaktlose, flächenhafte, hochaufgelöste und hochgenaue Veränderungsdetektion von Oberflächen in der Materialprüfung und Bauwerksüberwachung. Diese Arbeit behandelt einige Aspekte der Deformationsanalyse auf Basis von Bildsequenzen mit Hilfe triangulierter Verschiebungsfelder. Zunächst wird auf Untersuchungen zu Deformationen ebener Objektoberflächen, die mit monokularen Bildsequenzen beobachtet wurden, eingegangen. Im weiteren Verlauf wird auf Stereobildsequenzen übergegangen, die Deformationsmessungen für beliebige Oberflächen erlauben.

Im ersten Teil der Arbeit wird gezeigt, wie Verschiebungsfelder in monokularen Bildsequenzen bestimmt werden können. Die Bildpunkte, an welche die Verschiebungen geknüpft sind, werden zu einem Dreiecksnetz trianguliert. Jedes einzelne Dreieck wird auf Änderungen zu der Referenzepoche, die als die erste Epoche ohne jegliche Deformation definiert ist, untersucht. Ein gängiges Verfahren zur Analyse solcher Veränderungen ist die Berechnung von Hauptdehnungen für jedes Dreieck. Schwellwerte können zur Erkennung deformierter Bereiche und die farbkodierte Darstellung der Hauptdehnungen für eine visuelle Betrachtung genutzt werden.

In den räumlich verteilten Hauptdehnungen sowie im zeitlichen Ablauf treten Rauscheffekte auf. Deshalb werden verschiedene Filtermethoden zur Rauschunterdrückung untersucht. Dabei kommt ein Filter zum Einsatz, der gleichzeitig in der räumlichen sowie der zeitlichen Dimension filtert. Es werden aber auch Filter untersucht, die in beiden Dimensionen getrennt filtern.

Aus den Hauptdehnungen können nicht direkt Rissbreiten abgeleitet werden. Diese spielen für die Materialprüfung im Bauwesen allerdings eine wichtige Rolle, weswegen sich diese Arbeit auch mit der Berechnung von Rissbreiten in Dreiecksnetzen befasst. Als deformierte Dreiecke werden diejenigen detektiert, deren Hauptdehnung einen Schwellwert überschreiten. Für diese Kandidaten werden im Folgenden Rissbreiten bestimmt. Drei verschiedene Verfahren für die Ermittlung von Rissbreiten werden vorgestellt und verglichen.

Die Dehnbarkeit faserbewehrter Komposite, die unter anderem zur Verstärkung von Mauern und anderen Bauwerken verwendet werden, wird bei Belastung durch die Bildung multipler Rissstrukturen gewährleistet. Auf Grund dessen widmet sich ein weiterer Teil der Dissertation der Auswertung multipler Rissstrukturen. Hierzu werden dichte Verschiebungsfelder berechnet. Dann wird zunächst eine Auswahl der verfolgten Punkte genutzt, um ein grobes Dreiecksnetz zu generieren. Deformierte Dreiecke der ausgedünnten triangulierten Punktmenge werden mit dem Betrag des relativen Translationsvektors, der als Deformationsmaß eingeführt wird, detektiert. Eine iterative Verdichtung des Dreiecksnetzes in deformierten Bereichen ermöglicht die Auswertung enger Rissmuster. Zudem erlaubt eine Ausgleichung, dass nicht-triangulierte Punkte des dichten Verschiebungsfeldes in die Rissbreitenberechnung einbezogen werden können.

Ein weiterer Bestandteil der Arbeit ist die Betrachtung unebener Oberflächen, die mit Stereokamerasystemen beobachtet werden. Dazu werden die Algorithmen für die zweidimensionale Auswertung entsprechend übertragen und erweitert. Auf Basis von Verschiebungsfeldern dreidimensionaler Punkte wird auch hier ein Dreiecksnetz zur Änderungsdetektion genutzt.

So wird am Beispiel von dynamischen Dehnungstests an zylindrischen Probekörpern ein Algorithmus zur Rissbreitenmessung auf nicht ebenen Oberflächen vorgestellt. Dabei wird angenommen, dass die Deformationen ausschließlich tangential zur Oberfläche auftreten. Dies erlaubt die Transformation (Kongruenzabbildung) der Dreiecke in einen zweidimensionalen Raum und auch eine zweidimensionale Auswertung.

Außerdem wird eine Methode zur Berechnung des dreidimensionalen Rissöffnungsvektors präsentiert. Dieses Verfahren ist eine Erweiterung zum vorhergehenden Algorithmus und erlaubt zudem die Vermessung vertikaler Deformationen. Deformierte Dreiecke im triangulierten dreidimensionalen Verschiebungsfeld werden mit Hilfe des zweidimensionalen Relativtranslationsvektorbetrags der in den zweidimensionalen Raum transformierten Dreiecke detektiert. Anschließend folgt für alle deformierten Dreiecke durch Hinzunahme mindestens eines undeformierten Nachbardreiecks die Berechnung eines dreidimensionalen relativen Translationsvektors, mit Hilfe dessen die Komponenten des Rissöffnungsvektors ermittelt werden.

Abstract

Photogrammetric methods are gaining importance in civil engineering material testing and structural health monitoring. The analysis of image sequences ensures an extensive change detection of surfaces with a high spatial resolution and a high accuracy. This thesis deals with some aspects of deformation analysis based on image sequences and triangulated displacement fields. At the beginning, the examination of planar surfaces of specimens observed with monocular image sequences is considered. Later, a transition to stereo image sequences is given because they allow a deformation measurement of arbitrary surfaces.

The first part of the thesis shows how to derive displacement fields from monocular image sequences. The matching points corresponding to the displacements are triangulated into a mesh. Each triangle is compared to the reference epoch which is defined as the first time epoch under zero load without any deformation. As a current method, principal strains are used to detect deformations. Thresholds can be used to find deformed areas. In addition, color-coded maps of the principal strains are helpful for a visual detection.

In the field of the principal strains, noise effects appear in the spatial as well as in the temporal domain. Therefore, different filter methods are applied to reduce noise. In addition to filter techniques that are applied independently in the time and the spatial domain, a combined spatio-temporal filter is tested.

Crack widths cannot be derived directly from principal strains but crack widths are an important issue in civil engineering material testing. For this reason, this thesis also gives attention to the computation of crack widths in triangle meshes. The principal strains of the triangles are tested for exceeding a threshold to detect deformed triangles. For the deformed triangles, crack widths are computed. Three different methods for the crack width determination are presented and compared.

Multiple cracking ensures the ductility of loaded fiber-reinforced composites used to strengthen walls among other things. Therefore, another part of the dissertation deals with the photogrammetric analysis of multiple crack patterns. Herein, dense displacement fields are computed. Then, a thinned-out set of points is triangulated into a mesh. For each triangle, the norm of the relative

translations vector defined as a new quantity to detect deformations is determined and used to find cracked triangles. The mesh is densified iteratively in deformed areas to ensure an analysis of narrow crack structures. In addition, a least squares algorithm is presented which allows that points of the displacement field, that are not part of the mesh, can be included in the crack width computation.

A further part of the dissertation deals with non-planar surfaces observed with stereo camera systems. The algorithms of the two dimensional analysis are adapted and extended to use them for these applications. These methods are based on three dimensional displacement fields and also use triangle meshes to detect deformed areas.

One algorithm concentrates on the crack width measurement of non-planar surfaces with deformations that are only tangential to the surface. The method is applied on a cylindrical specimen in a dynamic tension test. The assumption that deformations are tangential to the surface allows the transformation of the triangles in the two dimensional space and also a two dimensional analysis.

In addition, an algorithm for the computation of the three dimensional crack opening vectors is presented. This method is an extension to the foregoing algorithm and is capable of measuring vertical deformations. To find deformed triangles in the triangulated three dimensional displacement field, the triangles are transformed in the two dimensional space in a first step. In a second step, the norm of the two dimensional relative translation vector is determined and tested if it exceeds a threshold. In the following, for each deformed triangle, the three dimensional relative translation vector is computed using a undeformed neighbor triangle. At the end, the three dimensional relative translation vectors can be transformed to the crack opening vectors.

Inhaltsverzeichnis

Kurzfassung.....	iii
Abstract.....	v
1 Einführung.....	1
1.1 Struktur der Arbeit.....	1
1.2 Motivation.....	2
1.3 Verwandte Arbeiten.....	4
1.4 Ziele der Arbeit.....	7
2 Photogrammetrische Deformationsmessung in monokularen Bild-	
sequenzen.....	8
2.1 Filtermethoden in Dreiecksnetzen.....	9
2.2 Rissbreitenberechnung mit Hilfe von Dreiecksnetzen.....	19
2.3 Strategie zur Rissbreitenmessung für multiple Rissstrukturen.....	29
3 Photogrammetrische Deformationsmessung in Stereobildsequenzen.....	50
3.1 Rissbreitenberechnung für tangentielle Deformationen auf nicht ebenen Oberflächen mit gegebenem 3D-Verschiebungsfeld.....	51
3.2 Berechnung des dreidimensionalen Rissöffnungsvektors bei gegebenem 3D-Verschiebungsfeld.....	59
4 Diskussion.....	70
5 Ausblick.....	77
5.1 Bestimmung der Anzahl der Risse.....	77
5.2 Rissspitzenbestimmung und -verfolgung.....	78
5.3 Anwendung der entwickelten Algorithmen auf Voxeldaten.....	78
5.4 Modellerweiterung durch Relativrotation.....	82
5.5 Genauigkeitssteigerungen für die Rissposition.....	82
5.6 Verbesserung der Rissnormalenschätzung.....	82
Literaturverzeichnis.....	83
Abkürzungsverzeichnis.....	89
Tabellenverzeichnis.....	90
Abbildungsverzeichnis.....	90

1 Einführung

1.1 Struktur der Arbeit

Die vorliegende Arbeit ist eine kumulative Dissertation. Sie basiert auf einer Reihe von vier wissenschaftlichen Fachartikeln in Journalen mit Fachgutachtersystem und einem weiteren thematisch passenden Konferenzbeitrag. Der Verfasser dieser Dissertation ist in allen Veröffentlichungen Erstautor. Kapitel 2 enthält die ersten drei Publikationen, die sich mit der Auswertung zweidimensionaler Daten befassen. In Kapitel 3 sind die restlichen zwei Aufsätze eingegliedert, welche sich mit der Auswertung dreidimensionaler Daten auseinandersetzen. Die Publikationen für die kumulative Dissertation sind im Folgenden aufgeführt und den Kapiteln zugewiesen:

Kap. 2. Photogrammetrische Deformationsmessung in monokularen Bildsequenzen

- P.I Liebold, F., Maas, H.-G., 2016: Advanced spatio-temporal filtering techniques for photogrammetric image sequence analysis in civil engineering material testing. *ISPRS Journal of Photogrammetry and Remote Sensing*, 111, 13-21.
- P.II Liebold, F., Maas, H.-G., 2018: Sub-pixel Accuracy Crack Width Determination on Concrete Beams in Load Tests by Triangle Mesh Geometry Analysis. *ISPRS Annals of the Photogrammetry, Remote Sensing and Spatial Information Sciences*, 4(2), 193-200.
- P.III Liebold, F., Maas, H.-G., 2020: Strategy for Crack Width Measurement of Multiple Crack Patterns in Civil Engineering Material Testing Using a Monocular Image Sequence Analysis. *PFG – Journal of Photogrammetry, Remote Sensing and Geoinformation Science*, 88(3), 219-238.

Kap. 3. Photogrammetrische Deformationsmessung in Stereobildsequenzen

- P.IV Liebold, F., Maas, H.-G., Heravi, A., A., 2019: Crack Width Measurement for Non-planar Surfaces by Triangle Mesh Analysis in Civil Engineering Material Testing. *International Archives of the Photogrammetry, Remote Sensing and Spatial Information Sciences*, 42(2)/W18, 107-113.
- P.V Liebold, F., Maas, H.-G., Deutsch, J., 2020: Photogrammetric determination of 3D crack opening vectors from 3D displacement fields. *ISPRS Journal of Photogrammetry and Remote Sensing*, 164, 1-10.

Im Anschluss an Kapitel 3 folgt mit dem Abschnitt Diskussion eine Darlegung des thematischen Zusammenhangs der Arbeiten. Die Dissertation endet mit dem Kapitel Ausblick, das sich mit möglichen Erweiterungen für zukünftige Arbeiten befasst. Zunächst werden aber in den nächsten Unterpunkten ins Thema eingeführt sowie auf verwandte Arbeiten und die Ziele der Dissertation eingegangen.

1.2 Motivation

Eine der Hauptaufgaben des Bauingenieurwesens ist die Gewährleistung der Sicherheit von Bauwerken. Zur Beurteilung dessen werden verschiedenste Materialien experimentellen Belastungsversuchen unterzogen und analysiert.

Im bautechnischen Mess- und Versuchswesen kommen dabei zahlreiche Messinstrumente zur Verformungs-, Riss- und Schädigungsanalyse zur Anwendung. Klassische Messtechniken sind beispielsweise Dehnmessstreifen, Inklinometer oder auch induktive Wegaufnehmer. Diese beruhen auf verschiedenen Funktionsprinzipien: Beim Dehnmessstreifen (DMS, Abb. 1.1a), der mit speziellen Klebern an der Oberfläche angebracht wird, ändert sich bei einer Längenänderung auch der ohmsche Widerstand, welcher durch eine Auswertelektronik erfasst wird und in eine Dehnung umgerechnet werden kann (Keil, 2017). Es gibt viele verschiedene Typen von DMS, z.B. Halbleiter-DMS oder Metallfolie-DMS. DMS ermöglichen die Messung von Dehnungen von kleiner als $1/1000$ und erreichen dabei relative Genauigkeiten bis $1/10000$ vom Messbereich (Möser et al., 2000).

Abbildung 1.1. a) Dehnmessstreifen; b) induktive Wegaufnehmer an der Oberfläche eines Betonbalkens; c) Neigungssensor.

Der größte Nachteil von DMS ist, dass nur punktuell gemessen werden kann. Weil die Position der Rissbildung im Vorfeld meist nicht hinreichend bekannt ist,

eignen sich DMS nur für bestimmte Anwendungen, z.B. bei Versuchen mit gekerbten Probekörpern. Weiterhin können DMS durch das Ankleben am Probekörper dessen Verhalten beeinflussen. Nachteilig ist auch, dass der Messbereich im Normalfall sehr klein ist, sodass bei größeren Rissen der DMS durchreißen kann.

Häufig werden auch induktive Wegaufnehmer (IWA) angewendet, die aus einem Spulensystem und einem ferromagnetischen Kern bestehen. Die Wegänderung wird durch ein elektrisches Signal messbar (Weichert & Wülker, 2000). Je nach Typ des induktiven Gebers sind Wege von kleiner 1 μm , aber auch Wege größer 1 dm messbar (Möser et al., 2000). Dabei werden relative Messunsicherheiten von kleiner 0,1 % des Messbereichs erreicht (Möser et al., 2012). Abb. 1.1b zeigt mehrere induktive Sensoren, die an einem Betonbalken vertikal bzw. diagonal angebracht sind. Auch diese Messgeräte ermöglichen nur punktweise Messungen.

Neben DMS und IWA kommen elektrische Inklinometer zur Anwendung, mit deren Hilfe auf Neigungsänderungen rückgeschlossen werden kann (Abb. 1.1c). Weiterhin existieren akustische Verfahren wie die Schallemissionsanalyse (SEA). Die durch die mechanische Beanspruchung im Bauteil entstehenden Verformungen und Risse emittieren Schall, der durch akustische Sensoren gemessen und analysiert werden kann. Mindestens vier Sensoren sind nötig, um aus Laufzeitdifferenzen der Schallwellen die Quelle des Signals zu bestimmen. Die Intensität gilt als Maß für die Rissbildung (Köppel, 2000). Abb. 1.2 zeigt 4 SEA-Sensoren, die an einem Betonbalken befestigt sind.

Abbildung 1.2. Sensoren für die Schallemissionsanalyse (rot umrandet).

Um Rissbreiten zu messen, kommen zum Teil Rissbreitenlineale (siehe Abb. 1.3) zum Einsatz, wobei die Breiten durch Anlegen an die Risse und visuellen Abgleich bestimmt werden.

Abbildung 1.3. Rissbreitenlineal.

Photogrammetrische Messsysteme bieten hingegen den Vorteil, Messoberflächen berührungsfrei, flächenhaft und hochauflösend mit hohen Genauigkeiten zu überwachen. Sie gehören mittlerweile zur Standardausrüstung in den meisten Messlaboren. Einige Auswertungsschritte in der Datenprozessierung werden jedoch noch manuell ausgeführt, sodass sich die Möglichkeit bietet, weitere Lösungsansätze zur Automatisierung zu entwickeln. Diese Arbeit soll einen Beitrag dazu leisten.

1.3 Verwandte Arbeiten

Zur Deformationsanalyse von Bauwerken und Materialien kommen schon seit einiger Zeit photogrammetrische Methoden zum Einsatz. In der Überwachung von Staumauern wurden beispielsweise Kamerasysteme eingesetzt (Kersten et al., 1995, Maas, 1998). Maas (1998) nutzte eine 6-Megapixelkamera, um Zielmarken zu vermessen, die an einem 100 m hohen und mit 480 m Kronenlänge breiten Staudamm angebracht waren. Die Messungen wurden mit Theodolitmessungen überprüft und es wurden Standardabweichungen von 4 mm und kleiner erreicht. Neben Staumauern lassen sich auch Deformationen an Brücken photogrammetrisch erfassen (Cooper et al., 1990, Albert et al., 2002). Aber auch in der Materialprüfung lässt sich die Photogrammetrie zu Nutze machen. Fraser & Riedel (2000) beobachteten thermische Deformationen von Stahlbalken, an denen Zielmarken angebracht waren, mit einem multiokularen Kamerasystem. Whiteman et al. (2002) beschrieben eine ähnliche Vorgehensweise mit einer Stereokamera bei der Untersuchung von Betonbalken und erreichten Genauigkeiten unter 1 mm für Messvolumina von ca. 7 m Breite. Benning et al. (2004) nutzten dichtere Raster von signalisierten Kreismarken, die auf Betonbalken aufgebracht waren. Mit einer aus drei Kameras bestehenden Anordnung wurde

das Raster in den Bildsequenzen verfolgt und Verschiebungen berechnet. Deformierte Bereiche wurden durch Streckenänderungen zwischen benachbarten Rasterpunkten detektiert. Weiterhin wurde ein Algorithmus zur Berechnung von 2D-Rissvektoren nach Görtz (2004) angewandt, der auf der Auswertung von Verschiebungen in 4-Punkt-Elementen basierte, während Rotationen zwischen den Epochen ignoriert wurden. Die Arbeiten von Lange & Benning (2006) sowie Lange et al. (2006) bauen auf den Publikationen von Benning et al. (2004) sowie Görtz (2004) auf. Zusätzlich wurden zusammenhängende 4-Punkt-Elemente, die zum gleichen Riss gehören, durch verschiedene Algorithmen bestimmt. Lange & Benning (2006) gehen auch auf den dreidimensionalen Rissöffnungsvektor ein und führen an, dass als Erweiterung der Methode von Görtz (2004) eine Helmerttransformation angewendet werden sollte. Zudem werden bei Lange (2009) neuronale Netze zur Rissdetektion einbezogen.

In der Veröffentlichung von Maas & Hampel (2003) werden unter anderem Experimente von Belastungsversuchen mit Betonprobekörpern mit einer Stereokamera und auch monokularen Systemen zur Verfolgung angebrachter Zielmarken beschrieben. Bei Maas & Hampel (2006) kam es zur Anwendung von Spiegeln, sodass mehrere Seiten eines Probekörpers gleichzeitig beobachtet werden konnten. Weiterhin berechneten sie wie auch Hampel & Maas (2009) ein dichtes Verschiebungsfeld mit subpixelgenauer Zuordnung von Oberflächenpunkten mit natürlicher bzw. künstlicher Textur. Durch die Auswertung von Profilen entlang der Koordinatenachsen wurden Risse durch vertikale Sprünge in Profilen detektiert bzw. Rissbreiten durch die Höhe der Versätze berechnet.

Barazzetti & Scaioni (2010) untersuchten belastete Betonbalken unter Nutzung verschiedener Ansätze mit und ohne Zielmarken. Es wurde ein Belastungsversuch mit einem regelmäßigen Raster von Zielmarken auf dem Balken beschrieben, der mit einer Kamera und induktiven Wegaufnehmern während eines Lasttests beobachtet wurde. In einem weiteren Versuch ohne Zielmarken wurden Punkte mit natürlicher oder künstlicher Textur zunächst mit einem Interest-Operator im Nulllastbild ermittelt und dann mit der Kreuzkorrelation und der Kleinste-Quadrate-Zuordnung in den Folgebildern verfolgt. Die Objektiverzeichnung der Kamera wurde dabei korrigiert. Es kam auch zur Anwendung des Wallis-Filter zur Kontrastverstärkung. In weiteren Experimenten wurden Stereokamerasysteme eingesetzt. Unter Nutzung des SIFT- bzw. SURF-Verfahrens (Lowe, 2004, Bay et al., 2008) wurden korrespondierende Punkte bestimmt und die relative Orientierung sowie Vorwärtsschnitte zur Ermittlung von 3D-Koor-

dinaten berechnet. Koschitzki & Maas (2012) beschränkten sich auf ein monokulares Kamerasystem zur Beobachtung von ebenen texturierten Oberflächen auf stahlbewehrten Betonbalken in Belastungsversuchen. Sie verfolgten Interessenspunkte in Bildsequenzen mit der Kleinste-Quadrate-Zuordnung. Durch Triangulation wurden Dreiecksnetze berechnet und Deformationen durch relative Flächenänderungen in Dreiecken detektiert.

Andere Arbeiten konzentrierten sich auf Kantendetektionsverfahren, die auf Einzelbilder angewendet werden können, um Risse auf Betonprobekörpern zu detektieren. Dare et al. (2002) wandten den Fly-Fisher- bzw. Routefinder-Algorithmus an, um Rissverläufe mit Polygonen zu approximieren. Weiterhin wurden Querprofile zur Rissbreitenbestimmung analysiert. Niemeier et al. (2007) nutzten zusätzlich eine zweiseitige schräge Beleuchtung mit roter bzw. blauer Farbe, um die Rissuferverläufe zu bestimmen. In diesem Zusammenhang ist auch die Veröffentlichung von Barazzetti & Scaioni (2009) zu nennen. Unter Verwendung einer Kamera und eines Orientierungsrahmens mit Zielmarken sowie zwei weiteren geradlinigen, flachen Aluplatten mit Zielmarken wurden Risse in mehreren Deformationswechseln photogrammetrisch vermessen. Zusätzlich zu Rissbreiten wurden auch Rissufer durch die Analyse von Querprofilen entlang des Rissverlaufs extrahiert.

Detchev et al. (2013) nutzten ein multiokulares Kamerasystem und einen Projektor zur Überwachung eines zyklischen Belastungsversuchs eines Betonbalkens mit überstehenden kleinen Platten an dessen Unterseite. Durch strukturierte Beleuchtung maßen sie für jede Epoche eine Punktwolke, deren Punkte in den Bildsequenzen nicht wie bei der Bildkorrelationsmethode zugeordnet werden können. Die Dachflächen des Probekörpers und der Platten wurden in jeder Epoche segmentiert und deren Mittelwerte berechnet. Sie konzentrierten sich auf die vertikalen Auslenkungen und bestimmten die Amplitude der Schwingung in einer Ausgleichung mit den gemittelten Vertikalkoordinaten als Beobachtungen. Ein ähnliches Verfahren wird durch Qi et al. (2014) unter Nutzung einer 3D-Kamera (Microsoft Kinect) zur Überwachung eines zyklischen Belastungsversuchs angewendet.

1.4 Ziele der Arbeit

Die Dissertation konzentriert sich auf die Deformationsanalyse für brüchige Materialien. An verschiedenen Stellen vergangener Arbeiten kann angesetzt werden, um den Automatisierungsgrad weiter zu erhöhen bzw. Algorithmen zu verbessern. In dieser Arbeit kommt es wie bei Koschitzki & Maas (2012) zur Anwendung von Dreiecksnetzen von Punkten mit gemessenen Verschiebungen in Bildsequenzen. Die Analyse von Dreiecksnetzen ist ein typisches geodätisches Herangehen in der Landes- und Ingenieurvermessung und wird zur Messung von Deformationen genutzt. Die Fortführung der Arbeit von Koschitzki & Maas (2012) zur Rissdetektion mit Hilfe von Dreiecksnetzen lässt die Möglichkeit einiger Erweiterungen, z.B. die Anwendung von Hauptdehnungen statt Flächendehnungen. Hauptdehnungen wurden bereits bei Benning (1985) für Dreiecksnetze angewendet und gehen auf Methoden aus der Kontinuumsmechanik zurück (Becker & Bürger, 1975). Bei der Anwendung des Algorithmus von Koschitzki & Maas (2012) unter Verwendung von Hauptdehnungen wie auch Flächendehnungen kommt es zu Rauscheffekten, sodass über Filtertechniken nachgedacht werden kann, um die Sensitivität des Messsystems zu erhöhen.

Weiterhin sind häufig Rissbreiten von Interesse, die sich aus den Dehnungen nicht direkt ableiten lassen. Wie oben beschrieben entwickelte Görtz (2004) ein Verfahren, das aus Verschiebungsvektoren in 4-Punkt-Elementen Rissöffnungsvektoren bestimmt, wobei Rotationen zwischen den Deformationsepochen ignoriert werden. Die Anwendung auf Dreiecknetze und die Beachtung von Rotationen zwischen den Epochen lässt Raum für Weiterentwicklungen.

Außerdem kommt es bei Anwendung spezieller faserbewehrter Materialien zu dichten Rissmustern, sodass Strategien zur Vermessung derartiger Strukturen gefragt sind.

Häufig werden auch Probekörper mit unebenen Oberflächen wie z.B. zylindrische Proben in Belastungstests untersucht, sodass auch die Erweiterung auf dreidimensionale photogrammetrische Deformationsanalyse von großem Interesse ist. Dazu gehört auch die Erfassung des dreidimensionalen Rissöffnungsvektors als Weiterentwicklung der Arbeit von Lange & Benning (2006).

2 Photogrammetrische Deformationsmessung in monokularen Bildsequenzen

Dieses Kapitel beinhaltet 3 Publikationen, die auf der Auswertung monokularer Bildsequenzen beruhen. Betrachtet werden deshalb Deformationen auf ebenen Oberflächen, wobei die optische Achse der verwendeten Kamera senkrecht zur Oberfläche ausgerichtet wurde. Weiterhin dürfen bei diesen Auswertungen Deformationen nur innerhalb der betrachteten Ebene stattfinden und nicht normal dazu. Es ist außerdem darauf zu achten, dass während eines Versuchs außer der Deformationen in der Ebene keine Relativbewegungen zwischen dem Probekörper und der Kamera auftreten.

2.1 Filtermethoden in Dreiecksnetzen

Kapitel 2.1 (P.I) wurde in ISPRS Journal of Photogrammetry and Remote Sensing, Volume 111, 2016 (ISSN 0924-2716) veröffentlicht als:

Advanced Spatio-temporal Filtering Techniques for Photogrammetric Image Sequence Analysis in Civil Engineering Material Testing

Titel in Deutsch:

Erweiterte raum-zeitliche Filtertechniken in der photogrammetrischen Bildsequenzanalyse im bautechnischen Versuchswesen

Autoren:

Liebold, F.¹, Maas, H.-G.¹

¹ Technische Universität Dresden, Institut für Photogrammetrie und Fernerkundung

Publikationsverlauf:

eingereicht Juli 2015, angenommen Oktober 2015, publiziert Januar 2016

Vollständige Referenz:

Liebold, F., Maas, H.-G., 2016. Advanced spatio-temporal filtering techniques for photogrammetric image sequence analysis in civil engineering material testing. *ISPRS Journal of Photogrammetry and Remote Sensing*, 111, 13-21.

DOI:

<https://doi.org/10.1016/j.isprsjprs.2015.10.013>

Contents lists available at ScienceDirect

ISPRS Journal of Photogrammetry and Remote Sensing

journal homepage: www.elsevier.com/locate/isprsjprs

Review Article

Advanced spatio-temporal filtering techniques for photogrammetric image sequence analysis in civil engineering material testing

F. Liebold*, H.-G. Maas

Institute of Photogrammetry and Remote Sensing, Technische Universität Dresden, D-01062 Dresden, Germany

ARTICLE INFO

Article history:

Received 27 July 2015

Received in revised form 30 October 2015

Accepted 30 October 2015

Available online 1 December 2015

Keywords:

Material testing

Deformation measurement

Spatio-temporal filtering

ABSTRACT

The paper shows advanced spatial, temporal and spatio-temporal filtering techniques which may be used to reduce noise effects in photogrammetric image sequence analysis tasks and tools. As a practical example, the techniques are validated in a photogrammetric spatio-temporal crack detection and analysis tool applied in load tests in civil engineering material testing. The load test technique is based on monocular image sequences of a test object under varying load conditions. The first image of a sequence is defined as a reference image under zero load, wherein interest points are determined and connected in a triangular irregular network structure. For each epoch, these triangles are compared to the reference image triangles to search for deformations. The result of the feature point tracking and triangle comparison process is a spatio-temporally resolved strain value field, wherein cracks can be detected, located and measured via local discrepancies. The strains can be visualized as a color-coded map. In order to improve the measuring system and to reduce noise, the strain values of each triangle must be treated in a filtering process. The paper shows the results of various filter techniques in the spatial and in the temporal domain as well as spatio-temporal filtering techniques applied to these data. The best results were obtained by a bilateral filter in the spatial domain and by a spatio-temporal EOF (empirical orthogonal function) filtering technique.

© 2015 International Society for Photogrammetry and Remote Sensing, Inc. (ISPRS). Published by Elsevier B.V. All rights reserved.

1. Introduction

Civil engineering material testing has become an interesting application field for photogrammetric measurement techniques, both in laboratory environments as well as on real objects. A typical task is crack measurement, aiming at the time-resolved detection, localization and measurement of cracks. Herein, image-based techniques have the essential advantage of offering both: spatial and temporal resolution, providing a basis for the qualitative and quantitative analysis of complex crack patterns over time. Using sub-pixel accuracy image analysis techniques, cracks with a width much smaller than a pixel can be detected, and their width can be determined with subpixel accuracy. Several papers about digital photogrammetry in civil engineering material testing have been published in recent years. Whiteman et al. (2002) used stereo image sequences to analyze vertical deflections of sparse photogrammetric targets on a concrete beam during load tests. They

achieved a standard deviation of 0.25 mm related to beams with a length of 6.4 m. Fraser and Riedel (2000) conducted a deformation monitoring of hot steel beams. Photogrammetric targets were observed with a trinocular camera system over 2 h. Hampel and Maas (2003) and Benning et al. (2004) presented multi-ocular photogrammetry systems for civil engineering material testing. The test bodies were prepared with a grid of targets that were tracked in an image sequence using image correlation techniques. Cracks could be located by an analysis of displacement fields of the targets, obtaining the crack width from the local target displacement itself. Measuring discrete targets offers the advantage of a high precision but the crack location resolution is small if the location of cracks in a probe is to be derived from variations in the distances between targets over an image sequence. Hampel and Maas (2009) presented a stereo image sequence based technique, which uses a cascaded image analysis approach: In the first step, least squares matching (LSM) is used to determine dense image point shift vector fields. In the second step, these vector fields are analyzed for local discrepancies, yielding the position and width of cracks. If, for instance, displacement vectors are determined for 11×11 pixel patches in image sequences of 4000×3000 px cameras, more than

* Corresponding author.

E-mail addresses: frank.liebold@tu-dresden.de (F. Liebold), hans-gerd.maas@tu-dresden.de (H.-G. Maas).URL: <http://photo.geo.tu-dresden.de/> (F. Liebold).<http://dx.doi.org/10.1016/j.isprsjprs.2015.10.013>

0924-2716/© 2015 International Society for Photogrammetry and Remote Sensing, Inc. (ISPRS). Published by Elsevier B.V. All rights reserved.

100,000 displacement vectors can be determined. This dense displacement vector field can again be considered as an image, allowing for image analysis techniques to be applied to detect local discrepancies caused by the development of cracks. Using sub-pixel accuracy image measurement techniques, cracks with a width of 5 μm can be detected in a $20 \times 20 \text{ cm}^2$ probe (Maas, 2012), and their width can be determined at a precision of about 1 μm . Koschitzki et al. (2011) presented a simplified technique, allowing for the quantitative analysis of crack pattern development from monocular image sequences. Barazzetti and Scaioni (2010) also conducted load tests with concrete beams and recorded image sequences with a stereo camera system. In addition to a grid of markers, a target-less method is described based on the Wallis filter for contrast improvement of the natural texture and the FAST interest operator. Correspondences were found with descriptor matching methods (SIFT and SURF). For tracking the features, cross-correlation and least squares matching is used. In Detchev et al. (2013), a target-less multi-camera and projector system is presented for deflection measurements. Qi et al. (2014) conducted experiments with range cameras for periodic surface movements, achieving half-millimeter accuracy. There are also approaches using digital image correlation techniques applied on image sequences to obtain two-dimensional dense displacement and strain fields (Guerrero et al., 2014; Fedele et al., 2014). Ghorbani et al. (2014) generated crack maps performing three-dimensional digital image correlation with a stereo system. Fedele et al. (2013) presented an approach also based on a Galerkin, finite element formulation for digital image correlation to compute displacement fields. In this context, hierarchical image pyramid techniques were applied to make it robust.

A general issue in the analysis of these spatio-temporal crack pattern development processes is noise in the measurement process, either caused by shortcomings of the image analysis procedures or by the imaging system or other external effects. The existence of noise will usually require filtering techniques to be applied in the data processing chain. Although, the method of Fedele et al. (2013) attenuates noise, we used another alternative approach to filter out noise. In the following, we will describe filtering techniques, which have been designed specifically for the requirements of the task described above. As the techniques are applied to a monocular image sequence analysis scheme as described in Koschitzki et al. (2011), their method will briefly be described in Section 2. In Section 3, we address both filters acting in the spatial domain as well as filtering acting in the temporal domain. Combining both, a spatio-temporal filtering procedure will also be presented. Finally, Section 4 will show and discuss practical results obtained by the different filtering techniques.

2. Image sequence analysis for crack patterns determinations

Fig. 1 shows an iconic image of the measurement process: A concrete beam is subject to a force F , which is increased continuously or in discrete load steps. With increasing load, the probe will deform and show cracks, which are to be detected and analyzed. When measuring a real world object rather than testing a probe in a lab, an early detection of local stress may be crucial as it can be used as an indicator for a non-destructive timely termination of a load experiment.

During an experiment, an image sequence of a concrete beam is recorded at a suitable temporal resolution. Depending on the dynamics of the load process (and the quality of the probe), the required temporal resolution may be in the order of minutes, seconds or even milliseconds. At moderate temporal resolution, the process can be observed in real-time, while high-speed camera image sequences will usually require image sequence storage

and offline processing. The monocular approach requires a planar surface on the test object, with the viewing direction approximately perpendicular to the surface. This requirement will usually not pose a severe restriction. Due to the lack of sufficient surface texture of the concrete beam, a fix artificial spray texture was applied. The first image of a sequence is defined as a reference image. Therein, points with high contrast are determined, using an interest operator, such as the Harris operator (Harris and Stephens, 1988). These interest points are triangulated into a mesh using Delaunay triangulation (TIN, triangulated irregular network). In the subsequent images, the interest points are tracked with sub-pixel precision using LSM (Förstner, 1984; Grün, 1985). In the case of cracks in the probe, the TIN meshes containing the cracks will change in area and shape. To analyze the differences of the triangles between the epochs a strain tensor is computed for each triangle. To achieve this, the parameters of an affine transform are computed between the coordinates of the triangle points in the different epochs.

$$\begin{pmatrix} u \\ v \end{pmatrix} = \begin{pmatrix} a_{11} + a_{12} \cdot x + a_{13} \cdot y \\ a_{21} + a_{22} \cdot x + a_{23} \cdot y \end{pmatrix} \quad (1)$$

where

u, v = coordinates of a later epoch
 x, y = coordinates of the reference epoch
 a_{ij} = affine parameters

The parameters of the affine transform contain translation, rotation and deformation. Translation and rotation are discarded because only deformation (strain) is relevant. At first, translation can be excluded (a_{11} and a_{21} are computed but ignored in the following). The strain tensor $\mathbf{V}$ can be extracted by decomposition of the deformation matrix $\mathbf{F}$ in a symmetric and an orthogonal matrix (see Eq. (2)).

$$\mathbf{F} = \begin{pmatrix} a_{12} & a_{13} \\ a_{22} & a_{23} \end{pmatrix} = \mathbf{V} \cdot \mathbf{R} \quad (2)$$

where

$\mathbf{F}$ = deformation tensor
 $\mathbf{R}$ = rotation matrix (orthogonal)
 $\mathbf{V}$ = left strain tensor (symmetric)

The decomposition can be obtained by the following steps: First, the left Cauchy–Green deformation tensor $\mathbf{V}^2$ is computed by multiplying $\mathbf{F}$ with its transposed.

$$\mathbf{V}^2 = \mathbf{V} \cdot \mathbf{V} = \mathbf{V} \cdot \mathbf{V}^T = \mathbf{F} \cdot \mathbf{F}^T \quad (3)$$

In a 2nd step, the eigenvalue decomposition of $\mathbf{V}^2$ is performed.

$$\mathbf{V}^2 = \mathbf{C} \cdot \mathbf{\Lambda} \cdot \mathbf{C}^T \quad (4)$$

where

$\mathbf{C}$ = eigenvector matrix (orthogonal matrix)
 $\mathbf{\Lambda}$ = eigenvalue matrix (diagonal matrix)

Finally, $\mathbf{V}$ can be computed by manipulating the matrix $\mathbf{\Lambda}$ containing the eigenvalues of $\mathbf{V}^2$ and multiplying the matrices as follows:

$$\begin{aligned} \mathbf{V} &= \mathbf{C} \cdot \mathbf{\Lambda}^{0.5} \cdot \mathbf{C}^T \\ \mathbf{R} &= \mathbf{V}^{-1} \cdot \mathbf{F} = \mathbf{C} \cdot \mathbf{\Lambda}^{-0.5} \cdot \mathbf{C}^T \cdot \mathbf{F} \end{aligned} \quad (5)$$

Fig. 1. Experimental setup for the load test.

Fig. 2. Strain map of an epoch.

It is not necessary to compute Eq. (5), as only the eigenvalues of the matrix $\mathbf{V}$ are essential for the next steps and as mentioned above rotation can be discarded. The eigenvalues of $\mathbf{V}$ (diagonal elements of $\Lambda^{0.5}$) are called the principal strains and can be obtained by building the square roots of the diagonal elements of Λ . The corresponding eigenvectors (columns of $\mathbf{C}$) can be considered as direction vectors of these principal strains. The greater eigenvalue is the strain that we use for the next steps. The strain is a dimensionless quantity. A triangle is stretched if its strain value >1 and it is compressed if it <1 .

As a result, a map can be generated, where the original image is blended with the color¹-coded mesh showing the strain values (Fig. 2). Thus, the crack generation and development process can be observed visually with the red triangles showing the areas affected by cracks.

If a crack runs through a LSM patch, sometimes LSM fails. In this case, the shift of the point is interpolated with the shifts of its neighbors. As the accuracy of the measuring system is limited, there will be some noise in these maps. If the scale for the color-code is set too sensitive, the noise will get very high, and it may become difficult to recognize cracks (Fig. 3); if the sensitivity is reduced too much, cracks may be missed by the observer. Of course, the same also holds for a quantitative analysis of crack patterns.

There are different reasons for the noise. One is the accuracy of the matching for point tracking. That is why, noise depends on the size of the triangles. Fig. 4 shows the behavior between the triangle side length and the standard deviation of the principal strain of an equilateral triangle. The standard deviation of the principal strain was computed by variance propagation. For the computation, it was assumed that the shift parameters of the tracking are uncorrelated and the standard deviation for the coordinates is 0.02 px (accuracy of LSM, see Grün (2012)). One can conclude that little side lengths lead to more noise in the maps. Thus, a trade-off have to be found between resolution (distance between tracking points and accordingly triangle side lengths) and accuracy (noise). In this approach, distances between interest points were at least 25 px.

The goal of the work shown in the following chapter is to reduce the noise by appropriate filtering techniques in order to facilitate the detection of cracks, to improve their measurement and visualization process.

3. Filtering techniques

Various filtering techniques known from image, signal or mesh processing may be applied in our task. The most relevant ones are

¹ For interpretation of color in Figs. 2 and 3, the reader is referred to the web version of this article.

Fig. 3. Strain maps with different thresholds (same epoch).

Fig. 4. Behavior between the side length and the standard deviation of the principal strain of an equilateral triangle.

discussed and analyzed in the following: Spatial filtering may for instance be performed by moving average, moving median, moving Gaussian or bilateral filtering applied on the triangular mesh. Temporal filtering may also be performed by the same techniques, applied on a time series of the processing results. Combining both

Fig. 5. Considered neighbors (red) of a triangle (green) for filtering. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of this article.)

domains, spatio-temporal filtering may be achieved by empirical orthogonal function (EOF) analysis. The EOF analysis is a principal component analysis (PCA) applied on a time series data group. If real-time is an issue (for instance in experiments on real buildings, which should be aborted early enough at a critical stadium), the computational effort of filtering is also crucial.

3.1. Filtering of TINs in spatial domain

Spatial filtering is used to reduce noise in the TIN mesh strain values based on a comparison with neighboring faces. In our work, only triangles with common edges or corners are considered (Fig. 5).

A well-known filter from image or mesh processing is the **Gaussian smoothing**. Herein, the weight of the strain values of a triangle depends on the distance between the triangle centers and a predefined standard deviation. The standard deviation should be in the order of magnitude of the triangular side lengths.

$$w_{ij} = \exp\left(-\frac{d_{ij}^2}{2 \cdot \sigma_G^2}\right) \quad (6)$$

$$\hat{f}_i = \frac{f_i + \sum_j^n w_{ij} \cdot f_j}{1 + \sum_k^n w_{ik}}$$

where w_{ij} = weight

$\hat{f}_i$ = filtered value of i th face

f_i = (strain) value of i th face

f_j = (strain) value of j th face

n = number of neighbor faces

i = index of the face to be filtered

j = index of a neighbor face

d_{ij} = distance between the i th and the j th face centers

σ_G = standard deviation

Another option is a **weighted moving average**. In this case, the weight depends on the inverse squared distance of the triangle centers and a preset parameter α , which should be in the order of magnitude of the squared triangle edge.

$$w_{ij} = \frac{\alpha}{d_{ij}^2} \quad (7)$$

$$\hat{f}_i = \frac{f_i + \sum_j^n w_{ij} \cdot f_j}{1 + \sum_k^n w_{ik}}$$

where α = parameter.

The **bilateral filter** is a non-linear smoothing filter, which preserve edges. It is often used in image processing and computer graphics. The filter is composed of two Gaussian filters. One term

depends on the distance and the other on the intensity (in this case: the strain) (Tomasi and Manduchi, 1998).

$$w_{ij} = \exp\left(-\frac{d_{ij}^2}{2 \cdot \sigma_G^2}\right) \cdot \exp\left(-\frac{(f_i - f_j)^2}{2 \cdot \sigma_R^2}\right)$$

$$= \exp\left(-\frac{d_{ij}^2}{2 \cdot \sigma_G^2} - \frac{(f_i - f_j)^2}{2 \cdot \sigma_R^2}\right) \quad (8)$$

$$\hat{f}_i = \frac{f_i + \sum_j^n w_{ij} \cdot f_j}{1 + \sum_k^n w_{ik}}$$

where

σ_G = standard deviation of the first Gaussian

σ_R = standard deviation of the second Gaussian

The standard deviation of the first Gaussian weight should be in the order of magnitude of the length of the triangular edges, the other standard deviation should be in the order of magnitude of the difference between the upper bound of the critical strain and 1.0.

Obviously, spatial filtering techniques do not consider noise on the time axis, as each epoch is filtered independently.

3.2. Filtering in time domain

Another option of reducing noise in the scalar triangle strain value field is filtering in the time domain. For each triangle, there exists a time series of triangle corner point positions and triangle strain values. On these time series, a 1D convolution filter can be applied. Due to its real-time processing potential, we use a saw tooth filter mask for weighting (Fig. 6), wherein only predecessors and the value itself are used to compute the filtered value. The value itself gets the biggest weight. The weight of the predecessors are linearly smaller depending on the time interval.

$$w_{ij} = l - (i - j)$$

$$\hat{f}_i = \frac{\sum_{j=i-l+1}^i w_{ij} \cdot f_j}{\sum_{k=i-l+1}^i w_{ik}} \quad (9)$$

where

$\hat{f}_i$ = filtered (strain) value of the i th time instant

f_i = (strain) value of time instant with index i

l = length of the filter = number of predecessors + 1

i, j = indices of the time instants

3.3. EOF filtering of spatio-temporal patterns

EOF (empirical orthogonal function) filtering is a method that can be used to treat data from irregularly distributed stations with observations in different time epochs. It is often used in meteorology and oceanography, but originally came from psychometry and biology (Preisendorfer, 1988). Furthermore, this technique is employed in satellite geodesy, too, where it is used in combination with a Gaussian smoothing filter for filtering Stokes coefficients, determined from the GRACE satellite mission (Wouters and Schrama, 2007). So far, the method is not common in photogrammetry.

Fig. 6. Saw tooth filter mask, continuous (left) and discrete signal (right).

3.3.1. The EOF filtering method

The method is performed on a data matrix $\mathbf{Z}$. One dimension represents the temporal component, the other one is for the locations with the observations (triangles with the corresponding strains). Each row contains the measurements of one epoch.

$$\mathbf{Z} = \begin{matrix} & \xrightarrow{x} \\ \downarrow t & \begin{pmatrix} z_{11} & z_{12} & \dots & z_{1p} \\ z_{21} & z_{22} & \dots & z_{2p} \\ \vdots & \vdots & \ddots & \vdots \\ z_{n1} & z_{n2} & \dots & z_{np} \end{pmatrix} \end{matrix} \quad (10)$$

where t = time
 x = location
 n = number of time epochs
 p = number of locations
 z_{ij} = strain of location j at time instant i

Then, the elements of $\mathbf{Z}$ are reduced by the temporal arithmetic mean of the corresponding column:

$$\hat{z}_j = \frac{1}{n} \sum_{i=1}^n z_{ij} \quad \text{for } j = 1 \dots p \quad (11)$$

$$\hat{\mathbf{Z}} = \begin{pmatrix} \hat{z}_1 & \hat{z}_2 & \dots & \hat{z}_p \\ \hat{z}_1 & \hat{z}_2 & \dots & \hat{z}_p \\ \vdots & \vdots & \ddots & \vdots \\ \hat{z}_1 & \hat{z}_2 & \dots & \hat{z}_p \end{pmatrix} \quad (12)$$

$$\mathbf{Z}_{\text{red}} = \mathbf{Z} - \hat{\mathbf{Z}} \quad (13)$$

In the next step, the scatter matrix $\mathbf{S}$ is computed.

$$\mathbf{S} = \mathbf{Z}_{\text{red}}^T \cdot \mathbf{Z}_{\text{red}} \quad (14)$$

The scatter matrix $\mathbf{S}$ is closely related to the covariance matrix $\mathbf{C}$.

$$\mathbf{C} = \frac{1}{n-1} \cdot \mathbf{Z}_{\text{red}}^T \cdot \mathbf{Z}_{\text{red}} = \frac{1}{n-1} \cdot \mathbf{S} \quad (15)$$

Then, the eigenvalue decomposition is performed on the scatter matrix $\mathbf{S}$.

$$\mathbf{S} = \mathbf{E} \cdot \mathbf{\Lambda} \cdot \mathbf{E}^T \quad (16)$$

where $\mathbf{\Lambda}$ = eigenvalue matrix (diagonal matrix)
 $\mathbf{E}$ = eigenvector matrix

Using the eigenvector matrix $\mathbf{E}$, the reduced data matrix $\mathbf{Z}_{\text{red}}$ can be transformed to the amplitude matrix $\mathbf{A}$ by multiplying them. This is called the analysis formula in Preisendorfer (1988).

$$\mathbf{A} = \mathbf{Z}_{\text{red}} \cdot \mathbf{E} \quad (17)$$

The columns of $\mathbf{A}$ are the principal component vectors that can be considered as uncorrelated time series. The corresponding synthesis formula is:

$$\mathbf{Z}_{\text{red reconstruct}} = \mathbf{A} \cdot \mathbf{E}^T = \sum_{i=1}^p \mathbf{a}_i \cdot \mathbf{e}_i^T \quad (18)$$

where $\mathbf{a}_i$ = i th column of $\mathbf{A}$
 $\mathbf{e}_i$ = i th column of $\mathbf{E}$

Each summand corresponds to a mode. The synthesis formula can be modified by rejecting some summands. Thus, the data is filtered by introducing the factors χ_i in the reconstruction formula.

$$\mathbf{Z}_{\text{red reconstruct}} = \sum_{i=1}^p \chi_i \cdot \mathbf{a}_i \cdot \mathbf{e}_i^T \quad (19)$$

$$\chi_i = \begin{cases} 1 & \text{if the time series is considered as signal} \\ 0 & \text{if the time series is considered as noise} \end{cases}$$

There are different methods to decide which summands should be retained in the synthesis formula (19), called selection rules. Preisendorfer (1988) suggests:

- Dominant variance rules: Time series corresponding to small eigenvalues are rejected by setting a threshold. This can be achieved by first sorting the eigenvalues in decreasing order and then computing the cumulative percentage of total variation (sum of variances). If a threshold is exceeded, the following time series with smaller variances (eigenvalues) are not used for the synthesis.
- Time history rules: The principal component time series (columns of $\mathbf{A}$) are tested for temporal noise. One of these rules uses the Kolmogorov–Smirnov test for spectral whiteness (It is called KS2 rule in Preisendorfer (1988)). This test is performed on each time series.
- Space map rules: These methods analyze the columns of $\mathbf{E}$ (eigenvectors). Some information about the spatial configuration have to be known. These rules were not tested in this approach.

The different methods can be combined. One can for instance remove time series that are considered as white noise, and another can then reject time series with a small variance. After the reconstruction of the reduced data matrix, the arithmetic means are added to the matrix again, and the filtered data set is computed.

$$\mathbf{Z}_{\text{filtered}} = \mathbf{Z}_{\text{red reconstruct}} + \hat{\mathbf{Z}} \quad (20)$$

3.3.2. Dominant variance rules

For these rules, consider formula (17). The reduced data matrix $\mathbf{Z}_{\text{red}}$ can also be decomposed with a singular value decomposition.

$$\mathbf{Z}_{\text{red}} = \mathbf{U} \cdot \mathbf{D} \cdot \mathbf{V}^T = \sum_{i=1}^{\min(n,p)} d_i \cdot \mathbf{u}_i \cdot \mathbf{v}_i^T \quad (21)$$

where $\mathbf{U}$ = left orthogonal matrix
 $\mathbf{V}$ = right orthogonal matrix
 $\mathbf{D}$ = diagonal matrix containing the singular values
 $\mathbf{u}_i$ = i th column of $\mathbf{U}$
 $\mathbf{v}_i$ = i th column of $\mathbf{V}$
 d_i = i th singular value

To integrate the filter functionality, the factors χ_i are introduced in the synthesis formula:

$$\mathbf{Z}_{\text{red reconstruct}} = \sum_{i=1}^{\min(n,p)} \chi_i \cdot d_i \cdot \mathbf{u}_i \cdot \mathbf{v}_i^T \quad (22)$$

The singular values d_i can be substituted by the square root of the corresponding eigenvalues and the vectors $\mathbf{v}_i$ accord with the eigenvectors of the scatter matrix $\mathbf{S}$, so we can write:

$$\mathbf{Z}_{\text{red reconstruct}} = \sum_{i=1}^{\min(n,p)} \chi_i \cdot \sqrt{\lambda_i} \cdot \mathbf{u}_i \cdot \mathbf{e}_i^T \quad (23)$$

The principal components vectors $\mathbf{a}_i$ can be expressed as follows:

$$\mathbf{a}_i = \sqrt{\lambda_i} \cdot \mathbf{u}_i \quad (24)$$

This formula shows the relation between the principal component vectors $\mathbf{a}_i$ and the eigenvalues of the scatter matrix $\mathbf{S}$. We suppose that principal components corresponding to eigenvalues less than a defined threshold can be considered as noise, and the factor χ_{λ_i} can be set to zero for the synthesis. Preisendorfer (1988) describes some methods to find this threshold automatically, one of these methods is called Rule N based on Monte Carlo simulations of random fields.

The sampling error of the eigenvalues (Eq. (25)) should also be taken into consideration (North et al., 1982). If the spacing between neighboring (sorted) eigenvalues is comparable to their uncertainty, then these eigenvalues are degenerate. In this case, the eigenvectors associated with these eigenvalues cannot be resolved and they will distinguish from data set to data set. This makes truncation difficult.

$$\begin{aligned}\delta\lambda_i &\approx \lambda_i \cdot \sqrt{\frac{2}{n}} \\ \delta\mathbf{e}_i &\approx \frac{\delta\lambda_i}{\Delta\lambda_i} \cdot \mathbf{e}_i \\ \Delta\lambda_i &= \min(|\lambda_i - \lambda_{i-1}|, |\lambda_i - \lambda_{i+1}|)\end{aligned}\quad (25)$$

where $\delta\lambda_i$ = sampling error of the eigenvalue λ_i
 n = number of independent samples
 $\delta\mathbf{e}_i$ = sampling error of the eigenvector $\mathbf{e}_i$
 $\Delta\lambda_i$ = difference of neighboring eigenvalues

The number of independent samples n is less than or equal to the sample size n (length of principal component $\mathbf{a}_i$) depending on the autocorrelation of the time series.

But these methods have not been tested in our application yet, so far, the threshold for the remaining sum of variance was set manually.

3.3.3. Time series rules

Using these selection rules, the principal component time series (columns of $\mathbf{A}$) are analyzed whether they are to be considered as white noise. We used one of the rules proposed in Preisendorfer (1988), which uses the Kolmogorov–Smirnov test (KS2 rule). The Kolmogorov–Smirnov test is a nonparametric statistical test to compare two probability distributions. The time series are tested for spectral whiteness. The theoretical power spectrum density (PSD) of white noise is constant (uniform probability distribution) and the corresponding normalized cumulative distribution function (CDF) is also known (a straight line between origin and $(q; 1)$). The following steps are performed for each principal component vector (column of $\mathbf{A}$). First, the discrete Fourier transform (DFT) of the principal component time series has to be computed:

$$\begin{aligned}a_j(i) &= \frac{A_0}{2} + \sum_{k=1}^q \left[A_k \cdot \cos \frac{2\pi ki}{n} + B_k \cdot \sin \frac{2\pi ki}{n} \right] \\ q &= \text{floor} \left(\frac{n-1}{2} \right)\end{aligned}\quad (26)$$

where A_k, B_k = Fourier coefficients
 $a_j(i) = a_{ij}$ = i th element of the j th column of $\mathbf{A}$
 n = number of elements in the time series
 $=$ number of rows of $\mathbf{A}$
 i = index for the instant of time

A_0 may be set to zero, as the data is centered in time domain. For the following steps, only the Fourier coefficients with $1 \leq j \leq q$ are used. If n is an even number, A_{q+1} is ignored, because it is inessential. In the next step, the periodogram (PSD) is computed:

Table 1

Kolmogorov–Smirnov variable for the threshold.

α	0.01	0.05	0.1	0.25
K_α	1.63	1.36	1.22	1.02

$$I_k = 0.5 \cdot (A_k^2 + B_k^2) \text{ for } k = 1 \dots q \quad (27)$$

The factor 0.5 can be ignored because of the normalization in the next step. Then, the normalized cumulative periodogram of the PSD is determined:

$$Y_k = \frac{\sum_{p=1}^k I_p}{\sum_{p=1}^q I_p} \text{ for } k = 1 \dots q \quad (28)$$

In a further step, the Kolmogorov–Smirnov test for spectral whiteness is performed by comparing the differences of this CDF to the CDF of white noise with the level of significance α set to 5%. A null hypothesis has to be formulated:

$$H_0: \text{The power spectrum of the principal component vector follows a uniform distribution.} \quad (29)$$

After this, the test value d has to be obtained (maximum distance to the white noise CDF):

$$d = \max \left\{ \left| Y_k - \frac{k}{q} \right|, \left| Y_k - \frac{k+1}{q} \right| : k = 1 \dots q-1 \right\} \quad (30)$$

The critical value for the statistical test has to be computed.

$$\delta_{q,1-\alpha} \approx \frac{K_\alpha}{\sqrt{q}} \text{ for } q > 50 \quad (31)$$

The variable K_α depends on the significance level α . Some values can be found in Table 1.

In the next step, the variable d is tested. If $d < \delta_{q,1-\alpha}$, then the null hypothesis is not rejected and the principal component vector $\mathbf{a}_j$ is considered as a white noise time series. In this case, the factor χ_{λ_j} is set to 0 (not used for the synthesis), otherwise χ_{λ_j} is set to 1.

3.3.4. Practical application

For the practical application of the EOF filtering procedure, the data matrix $\mathbf{Z}$ is filled with the strain values in a first step. Each row contains the strain values of one time epoch. Then the approach as described in Section 3.3.1 is applied to the data. For the reconstruction of the reduced data matrix (the actual filtering), the following methods for rejecting summands are performed:

- First, all principal component time series (columns of $\mathbf{A}$) are tested on white noise applying the Kolmogorov–Smirnov test for spectral whiteness. If the test is rejected, the principal component vector is retained in the synthesis formula (19).
- Then, the sum of the variance of the retained time series is computed.
- Principal components are retained if their cumulative percentage of variances is below a preset threshold.

The definition of the threshold is rather crucial; in our experiments, it has so far been set manually.

4. Results

The spatial, temporal and spatio-temporal filtering techniques as described above were applied to selected number of time instances of an experiment, using varying parameterizations and combinations of the techniques. The final results of the series of filtering experiments are shown and discussed below.

Fig. 7 shows the results of various filter settings in the EOF filtering. First, only principal components that are to be considered as white noise were rejected (marked with KS for Kolmogorov–Smirnov test). Then, a part of the remaining variance was excluded with different thresholds, too (the two lower maps in Fig. 7).

As one can see in the second row in Fig. 7, noise can be reduced only partly if only white noise time series are rejected using the Kolmogorov–Smirnov test. In the rows below, 1% and in the second

case 5% of the remaining variance was excluded additionally. Looking at the 3rd map from top (1%), one can see that a lot of noise could be reduced and the signal remains. If too much of the variance is rejected (5%, 4th row), effects as shown in the lowest map may occur, where some artifacts of later epochs (for instance cracks of later epochs) become visible. Too strong filtering causes mistakes like the blue (compressed) triangles. Generally, the method is rather sensitive for finding the right threshold for the

Fig. 7. EOF filtering of triangle strain value of two epochs (early and late, left and right column).

Fig. 8. Strain maps of the different filters.

Fig. 9. Strain maps of the different filters of another (later) epoch.

Table 2
Comparison of filters (rt = real-time capable).

Filter	rt	Advantages	Disadvantages
Gaussian	+	Good reduction of noise	Discards some signal, signal is smeared to the neighbors, variance must be set
Weighted moving average	+	Good reduction of noise	Discards some signal, signal is smeared to the neighbors, filter parameter must be set
Median	+	Very good reduction of noise, nonparametric	Some loss of information
Bilateral	+	Good reduction of noise, conservation of signal	Two variance parameters must be set
Saw tooth filter in time domain	+	Reduction of noise	Loss of signal, length of the filter must be set
EOF filter (time history rule)	–	Spatio-temporal filtering	Almost no effect for reduction of noise
EOF filter (time history rule + dominant variance rule)	–	Spatio-temporal filtering, good reduction of noise	Threshold for the remaining variance has to be set carefully

remaining variance, which may differ between experiments. In this case, the best results were obtained with a clear advantage of this method is the spatio-temporal filtering character. However, it is not real-time capable due to the bidirectional time axis.

For comparison, results obtained by applying the other filtering methods, presented in Sections 3.1 and 3.2, are shown in Figs. 8 and 9 and in Table 2. In the upper left map, one can see the original raw triangle strain value map with quite some noise. The Gaussian and the weighted moving average filter show a similar behavior. They reduce most of the noise, but also a part of information is discarded. In addition, the signal (i.e. the cracks to be detected) is smeared to the neighboring triangles as a typical effect of low-pass filtering. Both require one parameter to be preset. The median filter also reduces most of the noise, but it leads to a partial loss of essential signal. Especially the salt and pepper noise can be discarded. It is not necessary to preset a threshold or a parameter. The saw tooth filter on the time axis reduces noise only partly and also discards some of the signal. The filter length has to be preset. Rather good results were obtained by the bilateral filter in the spatial domain. It reduces the noise well and preserves the signal. The result is further improved when combining it with the saw

tooth filter in the time domain (see lower right of Figs. 8 and 9). All filters described in this paragraph have the advantage of being suited for real-time systems.

The advantages and disadvantages of the various filtering techniques, which have been shown in this section, are summarized in Table 2. The analyses made in this chapter were performed with the focus on a visual photogrammetric crack monitoring system. If the effects of noise in the maps are reduced, the threshold for color scales can be lowered and the measurement system (i.e. the visual display of the results) becomes better. But obviously, the same considerations also hold if the focus is on the quantitative output of crack development parameters rather than on a visual analysis.

Together with the image sequence recording, some other measurement techniques (inductive displacement transducers, acoustic emission sensors, inclinometer, strain gauges) were used in the experiments. These techniques are not really qualified to be used as a reference to judge the results of photogrammetric image sequence processing, as they lack of spatial resolution. However, the time instances of crack formation, which can be detected in the crack image sequences after spatio-temporal filtering, match well with the time instances detected from inclinometer and

acoustic emission sensors. More details to the comparison between the sensors can be found in Schacht (2014).

5. Conclusion and outlook

A variety of filtering techniques were validated concerning their potential to reduce noise effects in a photogrammetric crack monitoring system. Adapted to the nature of the task, spatial, temporal as well as spatio-temporal filtering techniques were evaluated. The best results were obtained with a bilateral filter in the spatial domain (optionally combined with a saw tooth filter in the time domain) and with an EOF (empirical orthogonal function, using a combined time series – dominant variance rule) spatio-temporal filtering technique. The focus of the paper is on the spatio-temporal filtering of crack image sequences and not on techniques to actually detect cracks therein. However, beyond analyses in a visual crack monitoring system, the techniques will form a crucial pre-processing step in an automatic real-time photogrammetric crack detection and monitoring procedure. The results can also be ported to related tasks in using photogrammetric measurement systems for spatio-temporal analysis tasks, such as strain monitoring. Future work may go further into automatic setting of filter parameters. Furthermore, the method could be extended to 3D by tracking points in a stereo camera sequence and deriving strain from triangle meshes in 3D.

Acknowledgements

The work, presented in this paper, arose during a research project funded by the German Federal Office for Building and Regional Planning (BBR). The practical experiments have been realized in cooperation with the Institute of Concrete Structures at Dresden University of Technology and with the Institute of Concrete Structures at Leibniz Universität Hannover.

References

- Barazzetti, L., Scaioni, M., 2010. Development and implementation of image-based algorithms for measurement of deformations in material testing. *Sensors* 10, 7469–7495. <http://dx.doi.org/10.3390/s100807469>.
- Benning, W., Lange, J., Schwermann, R., Effkemann, C., Görtz, S., 2004. Monitoring crack origin and evolution at concrete elements using photogrammetry. In: ISPRS Congress Istanbul Commission V.
- Detchev, I., Habib, A., El-Badry, M., 2013. Dynamic beam deformation measurements with off-the-shelf digital cameras. *J. Appl. Geodesy* 7 (3), 147–157. <http://dx.doi.org/10.1515/jag-2012-0052>.
- Fedele, R., Galantucci, L., Ciani, A., 2013. Global 2d digital image correlation for motion estimation in a finite element framework: a variational formulation and a regularized, pyramidal, multi-grid implementation. *Int. J. Numer. Meth. Eng.* 96 (12), 739–762. <http://dx.doi.org/10.1002/nme.4577>.
- Fedele, R., Scaioni, M., Barazzetti, L., Rosati, G., Biolzi, L., 2014. Delamination tests on CFRP-reinforced masonry pillars: optical monitoring and mechanical modeling. *Cem. Concr. Compos.* 45, 243–254. <http://dx.doi.org/10.1016/j.cemconcomp.2013.10.006>.
- Förstner, W., 1984. Quality assessment of object location and point transfer using digital image correlation techniques. *Int. Arch. Photogramm.* 25 (3a), 197–219.
- Fraser, C.S., Riedel, B., 2000. Monitoring the thermal deformation of steel beams via vision metrology. *ISPRS J. Photogramm. Remote Sens.* 55 (4), 268–276. [http://dx.doi.org/10.1016/S0924-2716\(00\)00024-1](http://dx.doi.org/10.1016/S0924-2716(00)00024-1).
- Ghorbani, R., Matta, F., Sutton, M., 2014. Full-field deformation measurement and crack mapping on confined masonry walls using digital image correlation. *Exp. Mech.* 55 (1), 227–243. <http://dx.doi.org/10.1007/s11340-014-9906-y>.
- Grün, A., 1985. Adaptive least squares correlation: a powerful image matching technique. *S. Afr. J. Photogramm. Remote Sens. Cartogr.* 14 (3), 175–187.
- Grün, A., 2012. Development and status of image matching in photogrammetry. *Photogramm. Rec.* 27 (137), 36–57. <http://dx.doi.org/10.1111/j.1477-9730.2011.00671.x>.
- Guerrero, N., Martinez, M., Picón, R., Marante, M.E., Hild, F., Roux, S., Florez-Lopez, J., 2014. Experimental analysis of masonry infilled frames using digital image correlation. *Mater. Struct.* 47 (5), 873–884. <http://dx.doi.org/10.1617/s11527-013-0099-0>.
- Hampel, U., Maas, H.-G., 2003. Application of digital photogrammetry for measuring deformation and cracks during load tests in civil engineering material testing. In: *Proceedings of Optical 3-D Measurement Techniques VI*, vol. 2. A. Grün, pp. 80–88.
- Hampel, U., Maas, H.-G., 2009. Cascaded image analysis for dynamic crack detection in material testing. *ISPRS J. Photogramm. Remote Sens.* 64 (4), 345–350. <http://dx.doi.org/10.1016/j.isprsjprs.2008.12.006>.
- Harris, C., Stephens, M., 1988. A combined corner and edge detector. In: *Proceedings of Fourth Alvey Vision Conference*, pp. 147–151.
- Koschitzki, R., Schacht, G., Schneider, D., Marx, S., Maas, H.-G., 2011. Integration of photogrammetry and acoustic emission analysis for assessing concrete structures during loading tests. In: *Proceedings of SPIE Optical Metrology*, vol. 8085. International Society for Optics and Photonics. <http://dx.doi.org/10.1117/12.889558>.
- Maas, H.-G., 2012. Digitale Nahbereichsphotogrammetrie im bautechnischen Versuchswesen. *Bautechnik* 89 (11), 786–793.
- North, G.R., Bell, T.L., Cahalan, R.F., Moeng, F.J., 1982. Sampling errors in the estimation of empirical orthogonal functions. *Mon. Weather Rev.* 110 (7), 699–706. <http://dx.doi.org/10.1175/JCLI3500.1>.
- Preisendorfer, R.W., 1988. *Principal Component Analysis in Meteorology and Oceanography*. Developments in Atmospheric Science. Elsevier, Amsterdam.
- Qi, X., Lichti, D.D., El-Badry, M., Chan, T.O., El-Halawany, S.I., Lahamy, H., Steward, J., 2014. Structural dynamic deflection measurement with range cameras. *Photogramm. Rec.* 29 (145), 89–107. <http://dx.doi.org/10.1111/phor.12047>.
- Schacht, G., 2014. Experimentelle Bewertung der Schubtragsicherheit von Stahlbetonbauteilen. Dissertation. Technische Universität Dresden. <<http://nbn-resolving.de/urn:nbn:de:bsz:14-qucosa-153446>>.
- Tomasi, C., Manduchi, R., 1998. Bilateral filtering for gray and color images. In: *Proceedings of the Sixth International Conference on Computer Vision*. IEEE, pp. 839–846. <http://dx.doi.org/10.1109/ICCV.1998.710815>.
- Whiteman, T., Litchi, D., Chander, I., 2002. Measurement of deflections in concrete beams by close range photogrammetry. *Int. Arch. Photogramm. Remote Sens.* 34 (4), 9.
- Wouters, B., Schrama, E.J.O., 2007. Improved accuracy of GRACE gravity solutions through empirical orthogonal function filtering of spherical harmonics. *Geophys. Res. Lett.* 34 (23). <http://dx.doi.org/10.1029/2007GL032098>.

2.2 Rissbreitenberechnung mit Hilfe von Dreiecksnetzen

Kapitel 2.2 (P.II) wurde in ISPRS Annals of Photogrammetry, Remote Sensing and Spatial Information Sciences, Volume 4(2), 2018 (ISSN 2194-9042) veröffentlicht als:

Sub-pixel Accuracy Crack Width Determination on Concrete Beams in Load Tests by Triangle Mesh Geometry Analysis

Titel in Deutsch:

Subpixelgenaue Rissbreitenbestimmung an Betonbalken bei Belastungsversuchen mit Hilfe der geometrischen Analyse von Dreiecksnetzen

Autoren:

Liebold, F.¹, Maas, H.-G.¹

¹ Technische Universität Dresden, Institut für Photogrammetrie und Fernerkundung

Publikationsverlauf:

eingereicht Januar 2018, angenommen März 2018, publiziert Mai 2018

Vollständige Referenz:

Liebold, F., Maas, H.-G., 2018. Sub-pixel accuracy crack width determination on concrete beams in load tests by triangle mesh geometry analysis. *ISPRS Annals of Photogrammetry, Remote Sensing and Spatial Information Sciences*, 4(2), 193-200.

DOI:

<https://doi.org/10.5194/isprs-annals-IV-2-193-2018>

SUB-PIXEL ACCURACY CRACK WIDTH DETERMINATION ON CONCRETE BEAMS IN LOAD TESTS BY TRIANGLE MESH GEOMETRY ANALYSIS

F. Liebold, H.-G. Maas

Institute of Photogrammetry and Remote Sensing, Technische Universität Dresden, Germany
frank.liebold@tu-dresden.de, hans-gerd.maas@tu-dresden.de

Commission II, WG II/5

KEY WORDS: Material Testing, Deformation Measurement, Triangle Mesh, Crack Width, Principal Strain

ABSTRACT:

This paper deals with the determination of crack widths of concrete beams during load tests from monocular image sequences. The procedure starts in a reference image of the probe with suitable surface texture under zero load, where a large number of points is defined by an interest operator. Then a triangulated irregular network is established to connect the points. Image sequences are recorded during load tests with the load increasing continuously or stepwise, or at intermittently changing load. The vertices of the triangles are tracked through the consecutive images of the sequence with sub-pixel accuracy by least squares matching. All triangles are then analyzed for changes by principal strain calculation. For each triangle showing significant strain, a crack width is computed by a thorough geometric analysis of the relative movement of the vertices.

1. INTRODUCTION

For the examination of the behavior of concrete structures, civil engineers conduct load tests on concrete beams. For the understanding of the evolution of cracks during the process, the automatic measurement of quantities such as the number of cracks, crack localization and crack widths is important. Different measuring systems are used, for instance strain gauges, inclinometers, inductive displacement transducers or acoustic emission sensors. In addition to these sensors, photogrammetric methods are applied because they offer their high spatial resolution and a high accuracy. Several publications deal with photogrammetry in civil engineering material testing. (Whiteman et al., 2002) and (Fraser and Riedel, 2000) measured vertical displacements of targets placed on a line on the specimens surface with multi-ocular camera systems. There are also methods that are not based on image comparison to reference images. For instance, (Dare et al., 2002) computed polygons along the crack using the fly-fisher algorithm and the route-finder algorithm. Furthermore, they presented a method for crack width measurement based on the analysis of profiles perpendicular to the polygons. (Hampel and Maas, 2003) and (Benning et al., 2004) used multi-ocular camera systems for displacement measurement in image sequences of planar plates with a grid of targets. The advantage of discrete targets is the high accuracy of the displacement that could be achieved. But due to the distance between the targets, there is a poor crack location resolution. (Maas and Hampel, 2006) and (Hampel and Maas, 2009) used least squares matching (LSM) to determine dense image point shifts and compared it with target grids. Crack widths were estimated by the analysis of profiles in x and y direction of the image coordinate systems. (Benning et al., 2004) and (Lange, 2009) presented an algorithm to compute crack widths for each square of a grid based on the method of (Görtz, 2004), where the direction of the crack was considered. (Koschitzki et al., 2011) computed interest points in a zero load image (reference image) and tracked them with LSM in an monocular image sequence. The points were meshed to a triangulated irregular network (TIN), and the ratio of their areas to the reference were visualized. The surface of the concrete specimen had to be

textured for matching. (Barazzetti and Scaioni, 2010) presented three image-based methods for displacement measurement in civil engineering material testing. They applied the Wallis filter on natural texture for contrast enhancement. The FAST interest operator (Rosten et al., 2010) was used to get points that were tracked with LSM and cross correlation techniques. (Detchev et al., 2013) used a multi-camera and projector configuration to measure deformations at loaded concrete beams. (Fedele et al., 2013) and (Fedele et al., 2014) combined digital image correlation with finite element methods to obtain dense displacement fields.

The approach presented in this paper continues the work described in (Liebold and Maas, 2016) and (Koschitzki et al., 2011). A short overview of this approach is given in the following chapter. The sections after this concentrate on crack width determination in triangle meshes. The experimental data of quasi-static load tests was obtained together with the Institute for Concrete Structures at Leibniz Universität Hannover and the Institute for Concrete Structures at Dresden University of Technology. Comparisons between other sensors were done by (Schacht, 2014).

2. IMAGE ANALYSIS FOR DEFORMATION MEASUREMENT

A load test is conducted on a concrete specimen with a planar surface applying a force F to the beam. The optical axis of the camera should be perpendicular to the side face of the beam to be able to analyze the deformations in 2D, see Figure 1.

In the approach presented here, the area of the surface of the beam was about 2.4 m x 0.3 m. For the photogrammetric setup, a Nikon D300 camera with a focal length of 20 mm was used and the frame rate was set to 0.5 fps. The observed region of interest was about 3600 x 1000 px in the image space or 1.1 m x 0.3 m in the object space and is according to one half of the beam. The distance between camera and object was about 1 m.

Due to the low contrast texture of concrete, the surface to be observed has to be prepared with a suitable artificial pattern to guar-

Figure 1. Experimental setup for the load test of a concrete beam

antee a reliable image template matching. During the experiment, an image sequence is recorded. The probe will develop a crack pattern with increasing load. The first image of the sequence is taken as reference image. In this image under zero load, points are defined on a regular grid or by applying an interest operator, for instance the Harris operator (Harris and Stephens, 1988). The points in the subsequent images are tracked by Least Squares Matching ((Ackermann, 1984); (Förstner, 1984); (Grün, 1985)). Initial values for the shifts can be obtained with normalized cross-correlation. The points are triangulated into a mesh using the Delaunay algorithm (Figure 2). Each triangle is tested for changes in each time epoch by computing principal strains.

Figure 2. Triangle mesh of interest points

In order to calculate the principal strains for each triangle, an affine transformation is computed with given coordinate pairs $(\tilde{x}, \tilde{y})$ and (x, y) of the triangle vertices:

$$\begin{pmatrix} \tilde{x} \\ \tilde{y} \end{pmatrix} = \begin{pmatrix} a_{11} + a_{12} \cdot x + a_{13} \cdot y \\ a_{21} + a_{22} \cdot x + a_{23} \cdot y \end{pmatrix} \quad (1)$$

where $\tilde{x}, \tilde{y}$ = coordinates of the subsequent epoch
 x, y = coordinates of the reference epoch
 a_{ij} = affine parameters

The deformation tensor $\mathbf{F}$ is filled with affine parameters $(a_{12}, a_{13}, a_{22}, a_{23})$. The translation (a_{11}, a_{21}) is discarded. The matrix $\mathbf{F}$ can be decomposed in a symmetric and rotation matrix (polar decomposition):

$$\mathbf{F} = \begin{pmatrix} a_{12} & a_{13} \\ a_{22} & a_{23} \end{pmatrix} = \mathbf{V} \cdot \mathbf{R} \quad (2)$$

where $\mathbf{F}$ = deformation tensor
 $\mathbf{R}$ = rotation matrix (orthogonal)
 $\mathbf{V}$ = left strain tensor (symmetric)

The left Cauchy-Green deformation tensor $\mathbf{V}^2$ is the product of the deformation matrix and its transpose:

$$\mathbf{V}^2 = \mathbf{V} \cdot \mathbf{V} = \mathbf{V} \cdot \mathbf{V}^T = \mathbf{F} \cdot \mathbf{F}^T \quad (3)$$

In text next step, an eigenvalue decomposition of left Cauchy-Green deformation tensor is conducted.

$$\mathbf{V}^2 = \mathbf{C} \cdot \mathbf{\Lambda} \cdot \mathbf{C}^T \quad (4)$$

where $\mathbf{C}$ = eigenvector matrix (orthogonal matrix)
 $\mathbf{\Lambda}$ = eigenvalue matrix (diagonal matrix)

The principal strains are the eigenvalues of $\mathbf{V}$. That is why, the square root of the eigenvalues of $\mathbf{V}^2$ are computed. The corresponding eigenvectors (columns of matrix $\mathbf{C}$) define the directions of the strains.

The square root of the larger eigenvalue is the principal strain s that is used for the next steps, see equation 5. The principal strain is a dimensionless quantity that describes a ratio of a distance to its reference. Values larger than 1 stand for an extension. The rotation matrix is discarded because it has no influence to the strain.

$$\lambda_1 > \lambda_2$$

$$s = \sqrt{\lambda_1} \quad (5)$$

The principal strains of each triangle can be visualized in color-coded map, see Figure 3. If a crack runs through a triangle, the triangle will become extended and will thus have a larger principal strain.

Figure 3. Color-coded visualization of the principal strains on the right half of a concrete beam under load

Because of the typical accuracy of the matching algorithm (in extrem cases 0.10 px and even better, see (Grün, 2012)), some noise occurs in the principal strain values. To get rid of these noise effects, a bilateral filter can be applied (Liebold and Maas, 2016). The extended triangles with principal strains larger than a threshold can be merged to a region and labeled, see Figure 4. Each region represents one crack.

3. CRACK WIDTHS IN TRIANGLE MESHES

The principal strain represents a ratio of the current distance to its reference. Whereas crack widths are absolute (metric) values, the strain depends on the size of a triangle in the images. Hence, it is easier to interpret crack widths. Therefore, metric crack widths shall be derived in a next step.

Figure 4. Labeled regions with triangles with principal strains being larger than a threshold are merged together.

Figure 5. Separated triangle caused by a crack

Figure 5 shows a triangle that is separated because a crack runs through it. $\vec{n}$ describes the direction of the crack normal.

As a first idea, it seems obvious that the crack normal is parallel to the principal strain direction. Based on this assumption, the following two sections show two ways how to compute the crack width in a triangle. Later on, shifts along the crack direction are also taken into consideration that leads to systematic errors in the assumption.

3.1 Crack widths with differences of the distances in crack normal direction

If a crack runs through a triangle, there will be one vertex on one side and two vertices on the other side of the crack. For the first presented algorithm, the vertex on the first side of the crack is kept fixed. Because of that, the other two vertices are shifted, see Figure 6.

Figure 6. (a): crack through the reference triangle; (b): new triangle in the deformed state; (c): both triangles, vertex p_{1ref} in reference and deformed state have the same position

A line is defined by p_1 and the crack normal and is intersected with the edge s_{12} . The difference of the distances between the intersection point f and p_1 and its corresponding value in the reference state is the crack width, see Figure 7.

First, the edge vectors in the deformed triangle are calculated:

$$\begin{aligned}\vec{s}_{12} &= \vec{p}_2 - \vec{p}_1 \\ \vec{s}_{13} &= \vec{p}_3 - \vec{p}_1 \\ \vec{s}_{23} &= \vec{p}_3 - \vec{p}_2\end{aligned}\quad (6)$$

Figure 7. Reference and deformed triangle, vertex p_{1ref} in reference and deformed state have the same position

It is also done for the reference state:

$$\begin{aligned}\vec{s}_{12ref} &= \vec{p}_{2ref} - \vec{p}_{1ref} \\ \vec{s}_{13ref} &= \vec{p}_{3ref} - \vec{p}_{1ref} \\ \vec{s}_{23ref} &= \vec{p}_{3ref} - \vec{p}_{2ref}\end{aligned}\quad (7)$$

The vector of the crack normal $\vec{n}$ should be normalized:

$$|\vec{n}| = 1 \quad (8)$$

The following equation for the deformed state can be set up with simple vector algebra, see Figure 7.

$$d \cdot \vec{n} = \vec{s}_{12} + v \cdot \vec{s}_{23} \quad (9)$$

where d = distance between p_3 and f
 v = second unknown, factor of the edge $\vec{s}_{23}$

Equation 9 can be reordered and can be considered as a linear system:

$$\vec{n} \cdot d + \vec{s}_{23} \cdot (-v) = (\vec{n} \quad \vec{s}_{23}) \cdot \begin{pmatrix} d \\ -v \end{pmatrix} = \vec{s}_{12} \quad (10)$$

Cramer's rule (Cramer, 1750) is used for the computation of the distance d between p_1 and the edge $\vec{s}_{23}$ in the deformed state:

$$d = \frac{\det(\vec{s}_{12} \quad \vec{s}_{23})}{\det(\vec{n} \quad \vec{s}_{23})} \quad (11)$$

The factor v for the edge $\vec{s}_{23}$ can also be calculated with Cramer's rule:

$$v = -\frac{\det(\vec{n} \quad \vec{s}_{12})}{\det(\vec{n} \quad \vec{s}_{23})} \quad (12)$$

The length factor v for the edge $\vec{s}_{23}$ should be constant for the reference and the deformed state:

$$v_{ref} = v \quad (13)$$

Hence, the intersection point of the crack normal and the edge $\vec{s}_{23}$ can be determined as follows:

$$\vec{f}_{ref} = \vec{p}_{2ref} + v_{ref} \cdot \vec{s}_{23ref} = \vec{p}_{2ref} + v \cdot \vec{s}_{23ref} \quad (14)$$

The distance between p_{1ref} and the edge $\vec{s}_{23ref}$ in reference state is computed in the next step:

$$d_{ref} = |\vec{p}_{1ref} - \vec{f}_{ref}| \quad (15)$$

The crack width r corresponds to the difference between the distances in the deformed and the reference state:

$$r = d - d_{ref} \quad (16)$$

3.2 Crack widths with differences of the altitudes of the triangles

In the following algorithm, one edge ($\vec{s}_{12}$) of the triangle is considered as constant. Because of that, the third point (p_3) is shifted, see Figure 8.

Figure 8. (a): crack through the reference triangle; (b): new triangle in the deformed state; (c): both triangles, where the edges $\vec{s}_{12}$ and $\vec{s}_{12ref}$ in reference and deformed state are identical

As one can see in Figure 9, the crack width can be computed with the help of the heights in the triangles and the angle between the crack normal and altitude:

Figure 9. Crack width, the constant edge $\vec{s}_{12ref}$ is shifted to edge $\vec{s}_{12}$

At first, the perpendicular foot $\vec{f}$ is calculated with the projection of edge $\vec{s}_{13}$ on edge $\vec{s}_{12}$:

$$\vec{f} = \vec{p}_1 + |\vec{s}_{13}| \frac{\vec{s}_{13}^T \cdot \vec{s}_{12}}{|\vec{s}_{13}| \cdot |\vec{s}_{12}|} = \vec{p}_1 + \frac{\vec{s}_{13}^T \cdot \vec{s}_{12}}{|\vec{s}_{12}|} \quad (17)$$

The same is also be done for the reference state:

$$\vec{f}_{ref} = \vec{p}_{1ref} + \frac{\vec{s}_{13ref}^T \cdot \vec{s}_{12ref}}{|\vec{s}_{12ref}|} \quad (18)$$

The altitude vector in the deformed ($\vec{h}$) and the reference ($\vec{h}_{ref}$) triangle is the difference between p_3 and the foot point f :

$$\begin{aligned} \vec{h} &= \vec{p}_3 - \vec{f} \\ \vec{h}_{ref} &= \vec{p}_{3ref} - \vec{f}_{ref} \end{aligned} \quad (19)$$

In the next step, the difference of the lengths of the altitude vectors is computed:

$$\Delta h = |\vec{h}| - |\vec{h}_{ref}| \quad (20)$$

The cosine of the angle α between the crack normal and altitude can be determined with the dot product of the altitude vector and the crack normal in the deformed state:

$$\cos \alpha = \frac{\vec{h}^T \cdot \vec{n}}{|\vec{h}| \cdot |\vec{n}|} \quad (21)$$

The crack width r is then computed with the trigonometric function:

$$r = \frac{\Delta h}{|\cos \alpha|} \quad (22)$$

3.3 Crack width considering shift effects along the crack

Additional considerations are required if there are mechanical shear forces along the crack (Figure 10). The shifts in this direction cause a change in the principal strain directions obtained from the triangles, in a way, that the principal strain direction is not parallel to the crack normal anymore. Therefore, the crack normal has to be obtained in another way.

Figure 10. Triangle mesh, red: extended triangles; blue: triangles without strains; shear forces affect along crack direction in opposite direction; the principal strain vector $\vec{s}$ is not parallel to the crack normal $\vec{n}$ anymore

3.3.1 Determination of the crack normal: The crack normal in the deformed state under the presence of shear effects can be obtained as follows: At first, only triangles with principal strains larger than a threshold are considered as crack candidates. For each triangle in this crack region, the second order neighbor triangles are determined. Triangles are considered as neighbors if they share at least one vertex. Second order neighbors are neighbors of neighbors. If the triangles of the second neighborhood also belong to the crack region, their geometric centers are used

for a weighted Principal Component Analysis (PCA, (Pearson, 1901)). The direction of the second principal component corresponds to the crack normal direction. This method can be seen as a local line fit, see also Figure 11.

Figure 11. Crack triangle (bright red) and its second order neighbors (red), non-extended triangles (blue), second principal component direction (blue arrows), fitted line (green)

Each neighbor triangle center j , that is used for the PCA of triangle i , gets a Gaussian weight ω'_{ij} that penalizes greater distances:

$$\omega'_{ij} = \exp\left(-\frac{|\vec{m}_j - \vec{m}_i|^2}{\sigma^2}\right) \quad (23)$$

where $\vec{m}_i$ = geometric center of triangle i
 $\vec{m}_j$ = geometric center of a neighborhood triangle j
 σ = distance where the weight gets $\frac{1}{e}$
 e = Euler's number

The weights ω_{ij} are normed for each neighbor triangle j :

$$\omega_{ij} = \frac{\omega'_{ij}}{1 + \sum_{j \in N_i} \omega'_{ij}} \quad (24)$$

In the next step, the weighted barycenter $\vec{b}$ is computed:

$$\vec{b} = \vec{m}_i + \sum_{j \in N_i} \omega_{ij} \cdot \vec{m}_j \quad (25)$$

Then, the weighted covariance matrix $\mathbf{Z}$ can be computed:

$$\mathbf{Z} = (\vec{m}_i - \vec{b}) \cdot (\vec{m}_i - \vec{b})^T + \sum_{j \in N_i} \omega_{ij} \cdot (\vec{m}_j - \vec{b}) \cdot (\vec{m}_j - \vec{b})^T \quad (26)$$

Next, an eigenvalue decomposition is applied on the covariance matrix $\mathbf{Z}$:

$$\mathbf{Z} = \mathbf{C} \cdot \mathbf{\Lambda} \cdot \mathbf{C}^T \quad (27)$$

where $\mathbf{C}$ = eigenvector matrix (orthogonal matrix)
 $\mathbf{\Lambda}$ = eigenvalue matrix (diagonal matrix)

The second principal component is the column of eigenvector matrix $\mathbf{C}$ that corresponds to the smallest eigenvalue. It is regarded as the direction of the crack normal $\vec{n}$.

3.3.2 Crack widths and translation: The two methods for the crack width determination shown in 3.1 and 3.2 will not work correctly if there are significant shifts along the crack direction. Shifts along the crack direction can be incorporated by using vector algebra, see Figure 12 and Figure 13.

Figure 12. (a): crack through the reference triangle with a shift in crack direction; (b): new triangle in the deformed state; (c): both triangles, where the edges $\vec{s}_{12}$ and $\vec{s}_{12ref}$ in reference and deformed state are identical

Figure 13. Reference triangle and deformed triangle with shifts along crack direction, the edge $\vec{s}_{12ref}$ is shifted to the edge $\vec{s}_{12}$ in the deformed state

First, the coordinates of the triangle in the reference state have to be transformed in a way, that the base edges of the reference and the deformed state have the same orientation. Therefore, p_{1ref} should have the same coordinates as p_1 . Because of that, p_{1ref} has to be transformed:

$$\vec{p}_{1ref,t} = \vec{p}_{1ref} \quad (28)$$

The edge $\vec{s}_{12ref}$ should have the same direction as $\vec{s}_{12}$:

$$\vec{s}_{12ref,t} = \frac{|\vec{s}_{12ref}|}{|\vec{s}_{12}|} \cdot \vec{s}_{12} \quad (29)$$

The x-coordinate $dx_{13ref,t}$ of the edge $\vec{s}_{12ref,t}$ can be determined by projecting the edge $\vec{s}_{13ref}$ onto the edge $\vec{s}_{12ref}$:

$$\begin{aligned} dx_{13ref,t} &= |\vec{s}_{13ref}| \cdot \cos(\angle \vec{s}_{12ref}, \vec{s}_{13ref}) \\ &= \frac{\vec{s}_{12ref}^T \cdot \vec{s}_{13ref}}{|\vec{s}_{12ref}|} \end{aligned} \quad (30)$$

The x direction $\vec{e}_{x,t}$ is set parallel to $\vec{s}_{12ref,t}$:

$$\vec{e}_{x,t} = \frac{\vec{s}_{12}}{|\vec{s}_{12}|} \quad (31)$$

The y component is computed with the help of the Pythagorean theorem:

$$dy_{13ref,t} = \sqrt{|\vec{s}_{13ref}|^2 - dx_{13ref,t}^2} \quad (32)$$

The y direction $\vec{e}_{y,t}$ is set perpendicular to $\vec{s}_{12ref,t}$:

$$\vec{e}_{y,t} = \frac{1}{|\vec{s}_{12ref,t}|} \cdot \begin{pmatrix} -s_{12ref,t,y} \\ s_{12ref,t,x} \end{pmatrix} \quad (33)$$

$$\vec{e}_{y,t} = \begin{cases} \vec{e}_{y,t}^j, & \text{for } \det(\vec{s}_{12ref} \quad \vec{s}_{13ref}) >= 0 \\ -\vec{e}_{y,t}^j, & \text{else} \end{cases}$$

The transformed edge $\vec{s}_{13ref,t}$ is composed of its x and y components:

$$\vec{s}_{13ref,t} = dx_{13ref,t} \cdot \vec{e}_{x,t} + dy_{13ref,t} \cdot \vec{e}_{y,t} \quad (34)$$

The third vertex $\vec{p}_{3ref,t}$ is computed by adding the edge vector $\vec{s}_{13ref,t}$ to the first vertex:

$$\vec{p}_{3ref,t} = \vec{p}_{1ref,t} + \vec{s}_{13ref,t} \quad (35)$$

As one can derive from Figure 13, the crack width r is calculated as follows:

$$r = |\vec{p}_3 - \vec{p}_{3ref,t}| \cdot |\cos \beta| = |(\vec{p}_3 - \vec{p}_{3ref,t})^T \cdot \vec{n}| \quad (36)$$

Optionally, the translation $\vec{t}$ along the crack can be determined by vector subtraction:

$$\vec{t} = \begin{cases} (\vec{p}_3 - \vec{p}_{3ref,t}) - r \cdot \vec{n}, & \text{for } \vec{n}^T \cdot \vec{s}_{13} >= 0 \\ (\vec{p}_3 - \vec{p}_{3ref,t}) + r \cdot \vec{n}, & \text{else} \end{cases} \quad (37)$$

4. EXPERIMENTAL RESULTS

First, the algorithms are numbered due to an easier description:

number of algorithm	corresponding section
1	3.1
2	3.2
3	3.3

Table 1. Numbering of algorithms

For each extended triangle, a crack width can be computed and displayed in a color-coded map, see Figure 15. The visualizations of the three algorithms look very similar. In the center of the right crack, some differences of the crack widths can be seen. Applying algorithm 3, translations in crack direction could also be computed and the length of the vector could be visualized. There exist some shifts of up to 1.5 px in crack direction in the center of the right crack.

One could expect that algorithm 1 and algorithm 2 have identical results. To prove this, the residuals between them are computed (equation 38) and analyzed, see Table 2 and Figure 14.

Considering the average and median, the values are nearly the same because the values are almost zero. But looking at the histogram in Figure 14, there is a small tendency to the negative side. $r_{algorithm1}$ seems to be a little bit larger due to the one-sided histogram, the negative median and average. The RMS_{12} is 0.11 px.

$$\epsilon_{12} = r_{algorithm2} - r_{algorithm1} \quad (38)$$

where ϵ_{12} = residual between algorithm 1 and 2
 $r_{algorithm1}$ = crack width with algorithm 1
 $r_{algorithm2}$ = crack width with algorithm 2

RMS	max $ \epsilon_{12} $	Median	Average
0.11	1.16	-0.01	-0.04

Table 2. Statistical values of the residuals between algorithm 1 and algorithm 2 in px

Figure 14. Histograms of the residuals between algorithm 1 and algorithm 2

To verify the results, some points were set manually next to the crack in a way that the line between these points is perpendicular to the crack direction. In Figure 16, these points are white. The colored points between the white were set on the crack in order to find the corresponding triangle.

This can only be done in the deformed image where the crack is visible. The shift of the points to the reference image is determined with LSM. With the help of this, the crack width can be determined as the difference of the distances between these points in the deformed and the reference state (equation 39). The corresponding triangle can be found by a nearest neighbor query of the center points of the triangles in the deformed state.

$$r_{manual} = \Delta d_{manual} = d_{deformed} - d_{reference} \quad (39)$$

where r_{manual} = crack width of the manual method
 $d_{reference}$ = distance between the points (reference)
 $d_{deformed}$ = distance between the points (deformed)

As this procedure comes with its own error budget, it rather has the character of a plausibility check. A procedure for providing rigorous reference measurements to verify the accuracy potential of the crack width determination procedure yet has to be developed.

Table 3 shows some statistical analysis concerning the residuals. The RMS is about 0.3 px. The corresponding histograms are plotted in Figure 17. For algorithm 3, two residuals are computed.

Figure 15. (a): crack width visualization with algorithm 1; (b): crack width visualization with algorithm 2; (c): crack width visualization with algorithm 3; (d): visualization of the absolute values of translations of algorithm 3

Figure 16. White points: manually set points being perpendicular to the crack; colored points: points set on the crack manually; color-code is computed by the differences of distances between the white points compared to the reference

Concerning the values marked with algorithm 3a, the translation is ignored for the residual. In case of algorithm 3b, the translation $\bar{t}$ along the crack is included in the difference because the manual

measurement should contain both movements, see equation 40.

$$\begin{aligned}\epsilon_1 &= r_{\text{manual}} - r_{\text{algorithm1}} \\ \epsilon_2 &= r_{\text{manual}} - r_{\text{algorithm2}} \\ \epsilon_{3a} &= r_{\text{manual}} - r_{\text{algorithm3}} \\ \epsilon_{3b} &= \Delta d_{\text{manual}} - \sqrt{r_{\text{algorithm3}}^2 + t_{\text{algorithm3}}^2}\end{aligned}\quad (40)$$

where $\epsilon_{1,2,3a}$ = residual of algorithm 1, 2 and 3a
 ϵ_{3b} = residual of algorithm 3b

Some outliers appear in the histograms. The reason for this might be points of discontinuities or path nodes. The 3σ -rule is used for the outlier detection. If the outliers are eliminated from the data, the RMS value drops to about 0.25 px, see Table 4. The residuals of the three algorithms are very similar. Overall, the obtained precision is a about five times worse than the LSM accuracy (0.05 px). This can partly be explained by variance propagation and some uncertainties of the normals concerning algorithm 3. An independent measuring system with a higher precision would be required for a better analysis of the accuracy.

	RMS	max $ \epsilon $	Median	Average
algorithm 1	0.31	1.42	-0.08	-0.11
algorithm 2	0.30	1.35	0.01	0.02
algorithm 3a	0.26	1.05	-0.04	-0.03
algorithm 3b	0.37	1.46	-0.11	-0.16

Table 3. Statistical values of the residuals to the manual measurements in px

	RMS	max $ \epsilon $	Median	Average
algorithm 1	0.25	0.79	-0.08	-0.10
algorithm 2	0.23	0.63	0.00	0.02
algorithm 3a	0.21	0.67	-0.04	-0.03
algorithm 3b	0.27	0.75	-0.10	-0.12

Table 4. Statistical values of the residuals to the manual measurements in px without outliers

Figure 17. Histograms of the residuals to the manual crack width

5. CONCLUSION AND OUTLOOK

An algorithm for crack detection in image sequences was introduced in this paper. The method is based on the analysis of triangle changes with principal strains. Different algorithms for crack

width computation based on a thorough geometric analysis of deformed triangles were presented. First results are visualized in color-coded maps. The crack widths can be determined with sub-pixel accuracy. Future work should concentrate on further tests and evaluations including other independent measuring methods with a higher precision. In addition, the method could be extended towards handling 3D meshes.

ACKNOWLEDGEMENTS

The research work presented in the paper has been performed within the DFG-funded research training group GRK-2250 at TU Dresden. The practical experiments have been realized in cooperation with the Institute of Concrete Structures at Technische Universität Dresden and with the Institute of Concrete Structures at Leibniz Universität Hannover in a project funded by the German Federal Office for Building and Regional Planning (BBR).

REFERENCES

- Ackermann, F., 1984. Digital image correlation: Performance and potential application in photogrammetry. *The Photogrammetric Record* 11(64), pp. 429–439.
- Barazzetti, L. and Scaioni, M., 2010. Development and implementation of image-based algorithms for measurement of deformations in material testing. *Sensors* 10, pp. 7469–7495.
- Benning, W., Lange, J., Schwermann, R., Effkemann, C. and Görtz, S., 2004. Monitoring crack origin and evolution at concrete elements using photogrammetry. In: *ISPRS Congress Istanbul Commission V*.
- Cramer, G., 1750. *Introduction à l'analyse des lignes courbes algébriques*. À Genève, chez les frères Cramer et C. Philibert.
- Dare, P., Hanley, H., Fraser, C., Riedel, B. and Niemeier, W., 2002. An operational application of automatic feature extraction: The measurement of cracks in concrete structures. *The Photogrammetric Record* 17(99), pp. 453–464.
- Detchev, I., Habib, A. and El-Badry, M., 2013. Dynamic beam deformation measurements with off-the-shelf digital cameras. *Journal of Applied Geodesy* 7(3), pp. 147–157.
- Fedele, R., Galantucci, L. and Ciani, A., 2013. Global 2d digital image correlation for motion estimation in a finite element framework: a variational formulation and a regularized, pyramidal, multi-grid implementation. *International Journal for Numerical Methods in Engineering* 96(12), pp. 739–762.
- Fedele, R., Scaioni, M., Barazzetti, L., Rosati, G. and Biolzi, L., 2014. Delamination tests on cfrp-reinforced masonry pillars: optical monitoring and mechanical modeling. *Cement and Concrete Composites* 45, pp. 243–254.
- Förstner, W., 1984. Quality assessment of object location and point transfer using digital image correlation techniques. *International Archives of Photogrammetry* 25(3a), pp. 197–219.
- Fraser, C. S. and Riedel, B., 2000. Monitoring the thermal deformation of steel beams via vision metrology. *ISPRS Journal of Photogrammetry and Remote Sensing* 55(4), pp. 268–276.
- Görtz, S., 2004. *Zum Schubrissverhalten von Stahlbeton- und Spannbetonbalken aus Normal- und Hochleistungsbeton*. PhD thesis, Technische Hochschule Aachen, Aachen. Aachen, Techn. Hochsch., Diss., 2004.
- Grün, A., 1985. Adaptive least squares correlation: a powerful image matching technique. *South African Journal of Photogrammetry, Remote Sensing and Cartography* 14(3), pp. 175–187.
- Grün, A., 2012. Development and status of image matching in photogrammetry. *The Photogrammetric Record* 27(137), pp. 36–57.
- Hampel, U. and Maas, H.-G., 2003. Application of digital photogrammetry for measuring deformation and cracks during load tests in civil engineering material testing. In: *Proceedings of Optical 3-D Measurement Techniques VI*, Vol. 2, A. Grün, pp. 80–88.
- Hampel, U. and Maas, H.-G., 2009. Cascaded image analysis for dynamic crack detection in material testing. *ISPRS Journal of Photogrammetry and Remote Sensing* 64(4), pp. 345–350.
- Harris, C. and Stephens, M., 1988. A combined corner and edge detector. In: *Proceedings of Fourth Alvey Vision Conference*, pp. 147–151.
- Koschitzki, R., Schacht, G., Schneider, D., Marx, S. and Maas, H.-G., 2011. Integration of photogrammetry and acoustic emission analysis for assessing concrete structures during loading tests. In: *Proceedings of SPIE Optical Metrology*, Vol. 8085, International Society for Optics and Photonics.
- Lange, J., 2009. *Mess- und Auswertungstechnik zur Riss- und Faserdetektion bei Betonbauteilen*. PhD thesis, Technische Hochschule Aachen.
- Liebold, F. and Maas, H.-G., 2016. Advanced spatio-temporal filtering techniques for photogrammetric image sequence analysis in civil engineering material testing. *ISPRS Journal of Photogrammetry and Remote Sensing* 111, pp. 13–21.
- Maas, H.-G. and Hampel, U., 2006. Photogrammetric techniques in civil engineering material testing and structure monitoring. *Photogrammetric Engineering and Remote Sensing* 72(1), pp. 39–45.
- Pearson, K., 1901. LIII. On lines and planes of closest fit to systems of points in space. *The London, Edinburgh, and Dublin Philosophical Magazine and Journal of Science* 2(11), pp. 559–572.
- Rosten, E., Porter, R. and Drummond, T., 2010. Faster and better: A machine learning approach to corner detection. *Pattern Analysis and Machine Intelligence, IEEE Transactions on* 32(1), pp. 105–119.
- Schacht, G., 2014. *Experimentelle Bewertung der Schubtragfähigkeit von Stahlbetonbauteilen*. Dissertation, Technische Universität Dresden.
- Whiteman, T., Lichti, D. and Chandler, I., 2002. Measurement of deflections in concrete beams by close-range digital photogrammetry. In: *Proceedings of the Joint International Symposium on Geospatial Theory, Processing and Applications*, Ottawa.

Errata

zum Artikel

Sub-pixel Accuracy Crack Width Determination on Concrete Beams in Load Tests by Triangle Mesh Geometry Analysis

S. 196 Formel 17:

alt:

$$\vec{f} = \vec{p}_1 + |\vec{s}_{13}| \frac{\vec{s}_{13}^T \cdot \vec{s}_{12}}{|\vec{s}_{13}| \cdot |\vec{s}_{12}|} = \vec{p}_1 + \frac{\vec{s}_{13}^T \cdot \vec{s}_{12}}{|\vec{s}_{12}|}$$

berichtigt:

$$\vec{f} = \vec{p}_1 + |\vec{s}_{13}| \frac{\vec{s}_{13}^T \cdot \vec{s}_{12}}{|\vec{s}_{13}| \cdot |\vec{s}_{12}|} \cdot \frac{\vec{s}_{12}}{|\vec{s}_{12}|} = \vec{p}_1 + \frac{\vec{s}_{13}^T \cdot \vec{s}_{12}}{|\vec{s}_{12}|^2} \cdot \vec{s}_{12}$$

S. 196 Formel 18:

alt:

$$\vec{f}_{ref} = \vec{p}_{1ref} + \frac{\vec{s}_{13ref}^T \cdot \vec{s}_{12ref}}{|\vec{s}_{12ref}|}$$

berichtigt:

$$\vec{f}_{ref} = \vec{p}_{1ref} + \frac{\vec{s}_{13ref}^T \cdot \vec{s}_{12ref}}{|\vec{s}_{12ref}|^2} \cdot \vec{s}_{12ref}$$

S. 197 Formel 28:

alt:

$$\vec{p}_{1ref,t} = \vec{p}_{1ref}$$

berichtigt:

$$\vec{p}_{1ref,t} = \vec{p}_1$$

2.3 Strategie zur Rissbreitenmessung für multiple Rissstrukturen

Kapitel 2.3 (P.III) wurde in PFG – Journal of Photogrammetry, Remote Sensing and Geoinformation Science, Volume 88(3), 2020 (ISSN 2512-2789) veröffentlicht als:

Strategy for Crack Width Measurement of Multiple Crack Patterns in Civil Engineering Material Testing Using a Monocular Image Sequence Analysis

Titel in Deutsch:

Strategie zur Rissbreitenmessung multipler Rissstrukturen in monokularen Bildsequenzen bei der Materialprüfung im Bauwesen

Autoren:

Liebold, F.¹, Maas, H.-G.¹

¹ Technische Universität Dresden, Institut für Photogrammetrie und Fernerkundung

Publikationsverlauf:

eingereicht September 2019, angenommen Februar 2020, publiziert Februar 2020

Vollständige Referenz:

Liebold, F., Maas, H.-G., 2020. Strategy for Crack Width Measurement of Multiple Crack Patterns in Civil Engineering Material Testing using a Monocular Image Sequence Analysis, *PFG – Journal of Photogrammetry, Remote Sensing and Geoinformation Science*, 88(3), 219-238.

DOI:

<https://doi.org/10.1007/s41064-020-00103-2>

Strategy for Crack Width Measurement of Multiple Crack Patterns in Civil Engineering Material Testing Using a Monocular Image Sequence Analysis

F. Liebold¹ · H.-G. Maas¹

Received: 11 September 2019 / Accepted: 4 February 2020 / Published online: 26 February 2020
© The Author(s) 2020

Abstract

An image sequence analysis procedure is developed to quantitatively analyze complex multiple crack patterns in tension tests of fiber-reinforced composite specimens. Planar textured surfaces of such specimens can be observed with a monocular image sequence using a camera of suitable spatial and temporal resolution. Due to the narrow crack paths, a dense high-precision displacement vector field is computed applying least-squares image matching techniques. Some uniformly distributed matching points are triangulated into a mesh. To measure deformations, principal strains and crack widths are computed for each face. Stretched triangles presumably containing one or multiple cracks are subdivided into three new triangles in order to densify the mesh in critical regions. The subdivision is repeated for some iterations. The crack width computation of the triangles requires at least three vertices and its displacements. Due to the dense displacement vector field, there are more points available. In this paper, an algorithm for the crack width computation in a least-squares fit is presented.

Keywords Crack width · Multiple crack pattern · Deformation measurement · Triangle mesh

Zusammenfassung

Strategie zur Rissbreitenmessung multipler Rissstrukturen in monokularen Bildsequenzen bei der Materialprüfung im Bauwesen

Zur quantitativen Untersuchung komplexer multipler Rissmuster in Dehnungsversuchen mit Probekörpern bestehend aus faserbewährten Kompositen wird eine auf Bildsequenzanalyse basierende Methode vorgestellt. Planare, texturierte Oberflächen solcher Probekörper können mit monokularen Bildsequenzen unter Nutzung einer Kamera mit geeigneter räumlicher und zeitlicher Auflösung beobachtet werden. Aufgrund der engen Risspfade wird ein dichtes, hochgenaues Verschiebungsvektorfeld mit der Punktverfolgungstechnik der Kleinsten-Quadrate-Anpassung berechnet. Eine gleichverteilte Auswahl der verfolgten Punkte bildet eine ausgedünnte Punktmenge, mit Hilfe derer ein Dreiecksnetz bestimmt wird. Um Deformationen zu messen, werden Hauptdehnungen und Rissbreiten für jede Facette berechnet. Gedehte Dreiecke, die möglicherweise von einem oder mehreren Risse durchlaufen werden, werden in 3 neue Dreiecke unterteilt, um das Netz in kritischen Regionen zu verdichten. Die Unterteilung wird mehrfach wiederholt. Für die Rissbreitenberechnung von Dreiecken werden mindestens 3 Punkte mit ihren Verschiebungen benötigt. Wegen des dichten Verschiebungsfeldes stehen mehr Punkte zur Verfügung. In dieser Publikation wird ein Algorithmus zur Rissbreitenberechnung in Form einer Ausgleichung vorgestellt.

1 Introduction

1.1 Review of Related Work

Photogrammetry has a high potential in deformation measurement in civil engineering material testing due to its high accuracy and high resolution. Classical methods such as inductive displacement transducers, inclinometers, or strain gauges offer only point-wise measurements. During the

✉ F. Liebold
frank.liebold@tu-dresden.de

H.-G. Maas
hans-gerd.maas@tu-dresden.de

¹ Institute of Photogrammetry and Remote Sensing,
Technische Universität Dresden, Helmholtzstr. 10,
01069 Dresden, Germany

last few years, several contributions about photogrammetry in material testing were published. Early photogrammetric applications in the field of deformation measurement dealt with artificial targets that were tracked in an image sequence of monocular or multi-ocular camera systems (Maas 1998; Fraser and Riedel 2000; Whiteman et al. 2002; Benning et al. 2004; Lange et al. 2006; Hampel and Maas 2003; Barazzetti and Scaioni 2010). For example, Barazzetti and Scaioni (2009) presented a 2D image-based method for crack analysis using a digital camera, an orientation frame, and a pair of signalized supports. Other authors used digital image correlation techniques for tracking natural points or artificial random patterns on the surface of the probe (Maas and Hampel 2006; Hampel and Maas 2009; Koschitzki et al. 2011; Liebold and Maas 2016, 2018). There are further publications considering image processing techniques (edge detection) to extract cracks as the Route-Finder algorithm as well as the Fly-Fisher algorithm (Dare et al. 2002; Nie-meier et al. 2008; Detchev et al. 2012). In addition, Detchev et al. (2016) also used a multi-camera system to observe beams in a cyclic load test. There, the amplitudes and offsets of a sinusoidal function for each coordinate as a function of time were determined in a least-squares fit. Concerning crack movements, Lange and Benning (2006) pointed out that the crack opening vector has got three components. The first one is the crack width that is normal to the crack, the second one is parallel to the crack course, and the third one is perpendicular to the first two components (perpendicular to the surface). Lange and Benning (2006) also refer to Irwin (1958) describing several theoretical modes of fracture. Not all of them can be captured correctly by monocular image observations. In case of movements perpendicular to the surface (out-of-plane movements), 3D systems like stereo cameras have to be used. Görtz (2004) presented an algorithm to compute crack widths in rectangle elements based on the displacement vectors of the vertices. He considered two components: parallel and perpendicular to the crack course. However, global rotations between the reference and the subsequent epochs are not considered.

Furthermore, there exist several companies offering stereo systems and software using digital image correlation (DIC) techniques (e.g., GOM ARAMIS from GOM or VIC-3D from Correlated Solutions, Inc.). These commercial software packages analyze image sequences, compute displacement fields, and visualize principal strains. However, actual metric crack widths have to be measured manually by clicking points to define distances that should be observed. In the work of Liebold and Maas (2018), three approaches for automatic crack width computation in triangle meshes are presented. These methods also consider rotations between the epochs of monocular image sequences and represent an extension to the approach of Görtz (2004). In this publication, the work of Liebold and Maas (2018) is continued.

One of the algorithms is extended and applied to analyze multiple crack patterns rather than single cracks. The extension includes the subdivision of the mesh in critical areas and a least-squares refinement for the crack width computation. Multiple crack structures appear in tension tests of specimens consisting of special composites (here, SHCC: Strain-Hardening Cement-based Composites). This multiple cracking ensures the ductility behaviour that is intended for special applications in civil engineering and the measurement of crack widths is an important issue (Curosu et al. 2017). Figure 1 shows an example of a multiple crack pattern of a deformed SHCC specimen.

1.2 Image Analysis—Basic Algorithm

The basic algorithm of crack detection on the basis of analyzing discontinuities in deformation vector fields determined by least-squares matching has been described in detail by Liebold and Maas (2018). An overview is also given here: a tension test is performed on an SHCC specimen with a planar surface. This experiment is observed by a monocular camera system whose optical axis is perpendicular to the surface. During the whole experiment, the relative orientation between camera and surface must not change and deformations must only appear in the plane to be observed. In addition, the surface must show a suitable natural or artificial pattern, such that there is enough texture for the matching process. During the tension test, an image sequence is recorded whose first image under zero load is defined as the reference image. In this image, a set of points is defined. These vertices can be arranged in a regular grid or can be computed by an interest operator; for instance, the Harris operator (Harris and Stephens 1988). In the subsequent images, the displacements of the points are determined with sub-pixel accuracy by least-squares matching (Ackermann 1984; Förstner 1984; Grün 1985, 2012). In each epoch, the vertices are triangulated into a mesh using the Delaunay algorithm, see Fig. 2.

Fig. 1 Example of a multiple crack structure

Fig. 2 Triangle mesh of interest points (according to Liebold and Maas 2018)

Subsequently, the triangles are analyzed for changes. Deformations can be detected by the computation of principal strains (Appendix A) as shown by Liebold and Maas (2016). A visualization of these values is depicted in Fig. 3.

The principal strains only show deformed regions. However, there is no information about the actual crack widths yet.

1.3 Limitations of Monocular Observations

Monocular observations of crack patterns require some assumptions. If these assumptions are not fulfilled, systematic errors can influence the measurements:

- There are alignment errors if the optical axis is not perfectly perpendicular to the surface.
- Moreover, errors due to relative movements between camera and specimen during the experiment are possible.
- In addition, there are perspective errors due to out-of-plane movements on the surface of the specimen.
- If the measured values are transformed from image to object space, scaling errors can appear.

Fig. 3 Colour-coded visualization of the principal strains

- There are further errors due to lens distortion which are minimized by camera calibration for instance using the Brown parameters (Brown 1971).

The projective errors of the first and the second point could be minimized using an orientation frame with at least four targets with known coordinates (similar to approach of Barazzetti and Scaioni 2009). The inner geometry of the frame has to stay constant during the load test and the frame has to be attached to the surface, such that it stays undeformed but parallel to it. The measured image coordinates can then be corrected using a projective transformation to the frame system. However, this is not applied in the experiments of this publication.

1.4 Differences of Principal Strains and Crack Widths

This subsection explains why we use another model for the deformation measurement (crack width algorithm). Several free and commercial software packages as well as Liebold and Maas (2016) use the computation of principal strains to detect deformed areas as it is shown for triangle meshes in Appendix A. Another way for deformation detection is the determination of crack widths in triangle meshes is presented by Liebold and Maas (2018), a short overview is given in Appendix B. An important difference between both quantities is the underlying model. For principal strains, it is assumed that the surface element is deformed in a nonrigid way. Mathematically, the model is based on an affine transformation (see Appendix A). On the other hand, the crack width computation assumes that the triangle is split into two parts and one of these parts has experienced a relative rigid movement, see also Appendix B, Figs. 4 and 5 for the effect in the mesh.

Another difference is that the principal strain is a unit-less quantity, whereas the crack width is a metric quantity. The principal strain can be interpreted as a ratio of lengths, while

Fig. 4 Differences of models. **a** Reference triangle, **b** model of non-rigid deformation which is assumed for principal strains, and **c** splitting the triangle into two parts at the crack front and relative rigid movement of the upper part (assumed for crack width computation)

Fig. 5 Differences of the models in the meshes. **a** Reference state with the crack line of a later crack, **b** mesh in the deformed epoch with nonrigid model, and **c** mesh in deformed epoch with the split triangles

Fig. 6 Effect of the triangle size on the strains if the crack width r is constant; n : crack normal; h : height of the triangle

the crack width represents the distance of the perpendicular movement between the parts left and right of the crack.

In the following, some additional considerations to the work of Liebold and Maas (2018) are presented. First, the effect of the triangle size on principle strains is considered. The principle strains are varying according to the size, because they represent a relative change. The following example illustrates this effect, see Fig. 6. There are two triangles; the bigger one has twice the size of the smaller one. Due to a crack opening with the width r , the triangles are deformed.

We consider the simple case that the heights h_i of the triangles are parallel to the crack normal. Then, the principal strain for the smaller triangle can be computed as follows: it can be obtained by the stretch ratio d_1 of the heights of the subsequent and the reference triangle:

$$d_1 = \frac{h_1 + r}{h_1}. \quad (1)$$

Or rather, the Cauchy strain e_1 is:

$$e_1 = d_1 - 1 = \frac{r}{h_1}. \quad (2)$$

The strain d_2 of the second triangle with twice the size of the first triangle ($h_2 = 2 \cdot h_1$) and the same crack width r is:

$$d_2 = \frac{h_2 + r}{h_2} = \frac{2 \cdot h_1 + r}{2 \cdot h_1} = \frac{h_1 + \frac{r}{2}}{h_1}. \quad (3)$$

Fig. 7 **a** Triangulation of the reference points (black nodes); **b** triangulation of the points (black nodes) of the subsequent epoch with successful matches, matching fails for the red points. The matching patches are shown as grey squares

Fig. 8 Possible cases of the course of the crack if the same relative translation vector (red) is given: **a** translation of the upper part, **b** translation of the upper part but the crack is shifted, **c** translation of the upper part but the crack has another direction, and **d** translation and rotation of the upper part

And the Cauchy strain e_2 is:

$$e_2 = d_2 - 1 = \frac{r}{2 \cdot h_1}. \quad (4)$$

The Cauchy strain is halved if the triangle edge sizes are doubled in this example:

$$e_1 = 2 \cdot e_2. \quad (5)$$

In particular, this effect leads to two problems: first, if there are different triangle sizes in a mesh, then the principal strain values are not comparable. Second, it is difficult to define thresholds for critical strains if the sizes differ. Figure 7 depicts the latter case. In the figure, some matches fail (red points), because the crack runs through the corresponding patches (grey squares). Therefore, some triangles are larger in the crack region.

The computation of crack widths avoids these problems, as the crack width is an absolute quantity and not a ratio as the strain. Therefore, crack widths are used for the analysis in this paper. Nevertheless, the calculation of crack widths also has got some limits. An important intermediate result is the relative translation vector. Different relative movements within a triangle mesh could lead to the same relative translation vector of the upper point (single point on one side of the crack) in the triangle, see Fig. 8. The cases (a) and (b)

illustrate that it is not possible to say where the crack runs through the triangle. It is somewhere between the baseline and the upper point. Moreover, it is not unambiguous which direction the crack has got if only the displacements of the triangle vertices are analyzed; compare (a) and (c). Further information is required. With the help of the crack normal $\vec{n}$, the direction of the crack is given and the crack width can be computed by projecting the relative translation vector $\vec{t}_{rel}$ onto this normal vector $\vec{n}$. Otherwise, only an upper limit for the crack width can be computed with the length of the relative translation vector. Appendix C shows the computation of the crack normals as shown by Liebold and Maas (2018). As one can see from Fig. 8d, it is possible that the upper part has an additional relative rotation. If only the displacements of the triangle vertices are given, the relative rotation cannot be derived. In the model, it is assumed that there is no relative rotation.

Although the whole SHCC specimen has a ductile behaviour, the concrete between cracks can be considered as a stiff material, especially if there are multiple cracks, such that the model with two rigid parts inside the triangle fits better than the affine model using the principle strains. For other, more ductile materials as steel, the affine model should be used, especially if cracks do not appear.

2 Image Analysis for Multiple Crack Patterns

In this section, a strategy for the deformation analysis of multiple crack patterns is presented. The single steps are explained in the following subsections. Figure 9 depicts the steps of the presented algorithm in a flowchart. The algorithm is designed hierarchically to analyze critical regions by a denser mesh. The workflow begins with the tracking of a dense point grid due to the narrow crack paths. In the second step, a uniformly distributed selection of these points is triangulated into a mesh to avoid small triangles due to inaccuracies in computing crack widths. Next, the mesh is densified in regions where cracks appear. Then, the relative translation vectors are computed including points inside the triangles from the dense point grid. At the end, crack normals and widths are calculated for deformed triangles.

2.1 Dense Displacement Field

Due to the narrow crack structures of the fiber-reinforced probes, a dense regular grid of points is used, such that the patches have a big overlap. These points are tracked using least-squares matching (LSM) in the following epochs. If cracks cross matching patches, the assumption of a linear patch deformation in LSM may not be justified, and either the standard deviation of the shifts becomes large or the algorithm does not converge and fails, see Fig. 10a. The first

Fig. 9 Flowchart of the analysis. δ and ϵ are user-defined thresholds

Fig. 10 **a** Cracks are running through a grid of points (black points) enclosed by their matching patches. Crossed patches are labeled as red squares; the other patches are depicted in green. **b** Adaption of patch size in cases where cracks are running through. The crack does not cross the blue adapted patches (blue triangles) anymore. Some patches are still crossed by the crack (red rectangles)

case is typical for thin cracks and large patch sizes. In this approach, it is considered to be failed if the standard deviations of the shifts exceed a threshold. To increase the success

rate, the patches of the matching points where LSM fails can be adapted, such that the crack does not cross the patch anymore. LSM is repeated with different predefined patch sizes, but in several cases, LSM fails for all these patch sizes. As shown in Fig. 10b, LSM succeeds for the blue patches now, but it still fails for the red patches. In Fig. 10, possible overlap of the patches is not shown. Successful matching requires suitable texture within the patch in both coordinate directions, and, thus, requires a certain minimum patch size.

2.2 Triangle Mesh Creation and Analysis

The crack width analysis for small triangles is inaccurate. In addition, when using larger triangles, areas not affected by cracks can be detected more efficiently. Therefore, a coarse set of points is used for the triangulation. These points can be obtained as follows: all successful matching points from the dense grid are inserted in a regular grid with a defined grid size. Then, the nearest neighbours to the centers of the grid cells are used to define the coarse set of points, see also Fig. 11a. If the cell is empty (no successful matching points inside), it is not considered. After this, the coarse set of points (red encircled points in Fig. 11) is triangulated into a mesh using the Delaunay algorithm, see Fig. 11b. The blue points are the centers of the grid cells. Points where matching fails have a grey colour. The triangle edges of the thinned-out mesh are depicted in green.

Figure 12 shows a thinned-out triangle mesh of a regular coarse set of points from an experiment.

Next, for each triangle, the norm of the relative translation vector $||\vec{t}_{rel}||$ is computed using the algorithm shown in Appendix B.

Fig. 11 **a** Regular grid cells with the matching points inside (black, matching patches are not shown). The red encircled points are the nearest neighbours to the center of the cells (blue points). Points where matching fails are depicted in grey. **b** Triangulation (green edges) of those points that are the nearest neighbours of the cell centers (blue points) and that are also matched successfully

Fig. 12 Example of a thinned-out triangle mesh of the coarse set of points

2.3 Densification of the Mesh

Subsequently, the resolution of the mesh is increased in regions where cracks appear. To achieve the densification, triangles with lengths of the relative translation vectors (Appendix B) larger than a user-defined threshold ($||\vec{t}_{rel}|| > \delta$) are split into three parts, see Fig. 13. The threshold δ should be in the same order of magnitude as the precision of least-squares matching [sub-pixel precision, in bad cases 0.1 px (Grün 2012)]. In the experiments presented in this approach, a threshold δ of 0.075 px is used. The triangle is split as follows: the new vertex for the mesh is in the set of successful matching points inside the triangle (green points in Fig. 13) and it is also the nearest neighbour to the triangle center (red point in Fig. 13). A triangle will not be subdivided if the new triangles would have too small edge lengths. The minimal possible edge length is set to 5 px. This subdivision procedure is repeated for some iterations (here, five iterations).

The effect of densification is visualized in Fig. 14.

2.4 Crack Width Computation in a Dense Displacement Field

This section deals with the refinement of the relative translation vectors, which is the central innovation of the algorithm presented in this paper.

2.4.1 Model

First, the displacement vectors of the matching points are computed as follows:

$$\vec{A}_j = \vec{p}_j - \vec{p}_{ref,j}. \quad (6)$$

To model the crack movement, the displacement vectors are partitioned into two clusters (set M_1 and set M_2). Each set

Fig. 13 Subdivision of a triangle crossed by a crack. Points being inside the triangle are shown in green, for the grey points, matching fails, because the crack crosses their patches (patches are not shown here), the center point of the triangle is depicted in red, and the black points are outside the triangle. The nearest neighbour of the green points to the red center is added to the mesh

Fig. 14 Triangle mesh after densification in critical regions

Fig. 15 Sets of displacements belonging to two crack sides

belongs to one side of the crack, see Fig. 15. A method for clustering is described in the following subsection.

The mathematical description can be done as follows: The points of set M_1 are transformed using a rigid transformation with the parameters $\vec{t}$ and $\mathbf{R}$ due to some movement in the

planar space as a consequence of the application of a force to the specimen. For the second set (M_2), a relative translation vector $\vec{t}_{rel}$ is added to the transformation due to the crack opening, see Eq. (7). The presented model is a simplification of the model used for extended finite-element method (Moes et al. 1999). For each triangle, there is a separate set of parameters:

$$\vec{p}_j = \begin{cases} \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j} & \forall j \in M_1 \\ \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j} + \vec{t}_{rel} & \forall j \in M_2, \end{cases} \quad (7)$$

where $\vec{p}_j$ includes the coordinates of the subsequent epoch, $\vec{p}_{ref,j}$ includes the coordinates of the reference epoch, $\vec{t}$ is the translation vector, $\mathbf{R}$ is the rotation matrix, and $\vec{t}_{rel}$ is the relative translation vector.

The rotation matrix $\mathbf{R}$ is parameterized with two parameters (c and s , see Eq. 8). They are linear in the observation equations, but necessitate a constraint:

$$\mathbf{R} = \begin{pmatrix} c & s \\ -s & c \end{pmatrix} \text{ subject to } c^2 + s^2 = 1, \quad (8)$$

where c is $\cos \alpha$, first rotation parameter, s is $\sin \alpha$, second rotation parameter, and α is the rotation angle.

The first step for the computation is the cluster analysis to know which point belongs to which set. The next subsection concentrates on this.

2.4.2 Clustering

For the classification, the parameters from Appendix B ($\mathbf{R}$, $\vec{t}$, $\vec{t}_{rel}$) derived from the three vertices of the triangle can be used. According to Eq. (7), it is tested for each point inside the triangle if the upper part or the lower part of the equation leads to a smaller deviation ϵ_i .

Equation 9 shows how to decide whether the point with index k is assigned to the set M_1 or to the set M_2 :

$$\begin{aligned} \epsilon_1 &= \|\vec{p}_j - \vec{t} - \mathbf{R} \cdot \vec{p}_{ref,j}\| \\ \epsilon_2 &= \|\vec{p}_j - \vec{t} - \mathbf{R} \cdot \vec{p}_{ref,j} - \vec{t}_{rel}\| \end{aligned} \quad (9)$$

If $\epsilon_1 < \epsilon_2$, then $k \in M_1$, otherwise $k \in M_2$.

Figure 16 shows an example from experimental data. One triangle is shown, and the red and blue points belong to the two sets of the clustering result. The crack running through the triangle is visible and separates the two sets.

2.4.3 Alternative Method for Clustering

There are also alternatives to partition sets. Several methods are known from machine learning. In our case, the unsupervised k -means algorithm (Lloyd 1982) with $k = 2$ can be used. The input data for k -means are the displacement vectors of the matching points. Due to the relative translation

Fig. 16 Experimental example of the clustering method

Fig. 17 **a** Displacement vectors due to global translation and relative translation from reference to subsequent epoch. **b** *k*-means clustering of the displacement vector coordinates

of set M_2 , the displacement vectors should differ from the first set. Initial centroids for the clusters can be obtained with *k*-means++ (Arthur and Vassilvitskii 2007). Figure 17a depicts the displacement vectors between the epochs if there is only a translation and a relative shift. Figure 17b shows the two clusters of their coordinates. The scattering is only caused by random errors in the matching process.

If there are global rotations, the displacement vectors will show according systematic effects. Figure 18a, b depict an example. The scattering of the vector clusters that is visible is only caused by the global rotation, not by random errors from matching. This could lead to wrong classifications if the relative translations are smaller than the systematic scattering. In most of our experiments, global rotations were very small such that the effect can be ignored in the clustering with *k*-means.

If there are significant rotations, the *k*-means method can fail. In that case, the first presented algorithm should be preferred for clustering.

Fig. 18 **a** Displacement vectors due to global translation, global rotation and relative translation from reference to subsequent epoch. **b** Variations of the displacement vectors of M_1 (magenta) and M_2 (cyan) due to a global rotation

2.4.4 Least-Squares Adjustment

The dense displacement field offers the possibility to consider more than the three triangle vertices for computing the relative translation vector. Therefore, the model is over-determined and the parameters can be calculated in a least-squares fit. The observation equations are derived from Eq. 7:

$$\vec{p}_j + \vec{v}_j = \begin{cases} \vec{t} + \mathbf{R} \cdot \vec{p}_{\text{ref},j} & \forall j \in M_1 \\ \vec{t} + \mathbf{R} \cdot \vec{p}_{\text{ref},j} + \vec{t}_{\text{rel}} & \forall j \in M_2 \end{cases} \quad (10)$$

where $\vec{v}_j$ is the residual vector of point j .

The number of points n is equal to the cardinality (#) of the union of sets M_1 and M_2 and is also the sum of the individual cardinalities of the sets.

$$n = n_1 + n_2 = \#M_1 + \#M_2 = \#(M_1 \cup M_2). \quad (11)$$

The coordinates of the subsequent epoch are considered as observations. The translation vector $\vec{t}$, the rotation matrix $\mathbf{R}$ of the rigid body transformation and the relative translation vector $\vec{t}_{\text{rel}}$ are unknowns. Next, the observation equations have to be linearized. Only rotation parameters are linearized applying Taylor's theorem because they are nonlinear in the constraint equation:

$$c_0^2 + s_0^2 + 2 \cdot c_0 \cdot dc + 2 \cdot s_0 \cdot ds = 1 \quad (12)$$

where c_0 and s_0 are the initial values of c and s , dc and ds are the corrections to c and s .

If there are small global rotations, the initial value of c_0 can be set to 1 and s_0 can be set to 0. The linearized observation equations can be expressed as:

$$\begin{aligned} \vec{t}_j + \vec{v}_j &= \begin{cases} \vec{t} + \mathbf{dR} \cdot \vec{p}_{\text{ref},j} & \forall j \in M_1 \\ \vec{t} + \mathbf{dR} \cdot \vec{p}_{\text{ref},j} + \vec{t}_{\text{rel}} & \forall j \in M_2 \end{cases} \\ \text{with} & \\ \vec{t}_j &= \vec{p}_j - \mathbf{R}_0 \cdot \vec{p}_{\text{ref},j}, \\ \mathbf{R}_0 &= \begin{pmatrix} c_0 & s_0 \\ -s_0 & c_0 \end{pmatrix} \text{ and } \mathbf{dR} = \begin{pmatrix} dc & ds \\ -ds & dc \end{pmatrix} \end{aligned} \quad (13)$$

where $\vec{t}_j$ is the reduced observation for $\vec{p}_j$, $\mathbf{R}_0$ is the initial rotation matrix, $\mathbf{dR}$ is the matrix with corrections to $\mathbf{R}$.

The parameters are collected in the vector of unknowns $\mathbf{x}$:

$$\mathbf{x} = (t_x \ t_y \ c \ s \ t_{\text{rel},x} \ t_{\text{rel},y})^T \quad (14)$$

and it can be decomposed in the vector of initial parameters $\mathbf{x}_0$ and the vector of corrections to the unknowns $\mathbf{dx}$.

$$\mathbf{x} = \mathbf{x}_0 + \mathbf{dx}. \quad (15)$$

The initial parameter vector $\mathbf{x}_0$ is

$$\mathbf{x}_0 = (0 \ 0 \ c_0 \ s_0 \ 0 \ 0)^T. \quad (16)$$

The vector of corrections to the unknowns $\mathbf{dx}$ is

$$\mathbf{dx} = (t_x \ t_y \ dc \ ds \ t_{rel,x} \ t_{rel,y})^T. \quad (17)$$

In matrix notation, the linearized observation equations can be written as:

$$\mathbf{l} + \mathbf{v} = \mathbf{A} \cdot \mathbf{dx} \text{ subject to } \mathbf{B} \cdot \mathbf{dx} = \mathbf{w} \quad (18)$$

where $\mathbf{l}$ is the reduced observation vector, $\mathbf{v}$ is the residual vector, $\mathbf{A}$ is the Jacobian matrix, $\mathbf{B}$ is the condition matrix, $\mathbf{w}$ is the vector of inconsistencies.

$$\mathbf{A}^T \cdot \mathbf{A} = \begin{pmatrix} n \ 0 & \sum_{i=1}^n x_{ref,i} & \sum_{i=1}^n y_{ref,i} & n_2 & 0 \\ n & \sum_{i=1}^n y_{ref,i} & -\sum_{i=1}^n x_{ref,i} & 0 & n_2 \\ \sum_{i=1}^n (x_{ref,i}^2 + y_{ref,i}^2) & 0 & \sum_{i \in M_2} x_{ref,i} & \sum_{i \in M_2} y_{ref,i} \\ \sum_{i=1}^n (x_{ref,i}^2 + y_{ref,i}^2) & \sum_{i \in M_2} y_{ref,i} & -\sum_{i \in M_2} x_{ref,i} \\ n_2 & 0 & n_2 \end{pmatrix} \quad (25)$$

The Jacobian matrix $\mathbf{A}$ is

$$\mathbf{A} = \begin{pmatrix} 1 & 0 & x_{ref,1} & y_{ref,1} & 0 & 0 \\ 0 & 1 & y_{ref,1} & -x_{ref,1} & 0 & 0 \\ \vdots & \vdots & \vdots & \vdots & \vdots & \vdots \\ 1 & 0 & x_{ref,n_1} & y_{ref,n_1} & 0 & 0 \\ 0 & 1 & y_{ref,n_1} & -x_{ref,n_1} & 0 & 0 \\ 1 & 0 & x_{ref,n_1+1} & y_{ref,n_1+1} & 1 & 0 \\ 0 & 1 & y_{ref,n_1+1} & -x_{ref,n_1+1} & 0 & 1 \\ \vdots & \vdots & \vdots & \vdots & \vdots & \vdots \\ 1 & 0 & x_{ref,n} & y_{ref,n} & 1 & 0 \\ 0 & 1 & y_{ref,n} & -x_{ref,n} & 0 & 1 \end{pmatrix} \quad (19)$$

where

n_1 is the number of points in set M_1 .

The reduced observation vector $\mathbf{l}$ is

$$\mathbf{l} = \begin{pmatrix} x_1 - c_0 \cdot x_{ref,1} - s_0 \cdot y_{ref,1} \\ y_1 + s_0 \cdot x_{ref,1} - c_0 \cdot y_{ref,1} \\ \vdots \\ x_n - c_0 \cdot x_{ref,n} - s_0 \cdot y_{ref,n} \\ y_n + s_0 \cdot x_{ref,n} - c_0 \cdot y_{ref,n} \end{pmatrix} \quad (20)$$

The condition matrix $\mathbf{B}$ is

$$\mathbf{B} = (0 \ 0 \ 2 \cdot c_0 \ 2 \cdot s_0 \ 0 \ 0). \quad (21)$$

The vector of inconsistencies $\mathbf{w}$ can be written as:

$$\mathbf{w} = (1 - c_0^2 - s_0^2). \quad (22)$$

Due to the constraint, the Gauss–Markov model is extended with the method of the Lagrange multipliers λ .

$$\Omega = \mathbf{v}^T \cdot \mathbf{v} + \lambda^T \cdot (\mathbf{B} \cdot \mathbf{dx} - \mathbf{w}) \rightarrow \min_{\mathbf{dx}}. \quad (23)$$

The solution of this system can be obtained with the extended normal equations:

$$\begin{pmatrix} \mathbf{A}^T \cdot \mathbf{A} & \mathbf{B}^T \\ \mathbf{B} & \mathbf{0} \end{pmatrix} \cdot \begin{pmatrix} \mathbf{dx} \\ \lambda \end{pmatrix} = \begin{pmatrix} \mathbf{A}^T \cdot \mathbf{l} \\ \mathbf{w} \end{pmatrix} \quad (24)$$

where $\mathbf{k} = \frac{1}{2} \cdot \lambda$, vector of Lagrangian multipliers.

where n_2 is the number of points in set M_2 .

$$\mathbf{A}^T \cdot \mathbf{l} = \begin{pmatrix} \sum_{i=1}^n x_i - c_0 \cdot \sum_{i=1}^n x_{ref,i} - s_0 \cdot \sum_{i=1}^n y_{ref,i} \\ \sum_{i=1}^n y_i - c_0 \cdot \sum_{i=1}^n y_{ref,i} + s_0 \cdot \sum_{i=1}^n x_{ref,i} \\ \sum_{i=1}^n (x_{ref,i} \cdot x_i + y_{ref,i} \cdot y_i) - c_0 \cdot \sum_{i=1}^n (x_{ref,i}^2 + y_{ref,i}^2) \\ \sum_{i=1}^n (y_{ref,i} \cdot x_i - x_{ref,i} \cdot y_i) - s_0 \cdot \sum_{i=1}^n (x_{ref,i}^2 + y_{ref,i}^2) \\ \sum_{i \in M_2} x_i - c_0 \cdot \sum_{i \in M_2} x_{ref,i} - s_0 \cdot \sum_{i \in M_2} y_{ref,i} \\ \sum_{i \in M_2} y_i - c_0 \cdot \sum_{i \in M_2} y_{ref,i} + s_0 \cdot \sum_{i \in M_2} x_{ref,i} \end{pmatrix} \quad (26)$$

The upper part of the normal matrix $\mathbf{A}^T \cdot \mathbf{A}$ can be computed directly (see Eq. 25) such that it is not necessary to compute the Jacobian matrix $\mathbf{A}$ and the observation vector $\mathbf{l}$ in order to be more efficient. The right hand side vector $\mathbf{A}^T \cdot \mathbf{l}$ is expressed in Eq. 26.

The parameter vector $\mathbf{dx}$ is obtained by solving the extended normal equations (Eq. 24). The translation parameters $\tilde{t}$ and $\tilde{t}_{rel}$ can be found directly in the $\mathbf{dx}$ vector. The rotation parameters c and s have to be corrected:

$$\begin{aligned} c &= c_0 + dc \\ s &= s_0 + ds. \end{aligned} \quad (27)$$

The process of the computing of the normal equations with the new $\mathbf{B}$ -matrix should be repeated until the absolute corrections to the unknowns dc and ds fall below a threshold. Considering the relative translation vector $\tilde{t}_{rel}$, it can be

decomposed in a part perpendicular to the crack and another part parallel to the crack. The crack width r is computed by the scalar projection of the relative translation vector $\vec{t}_{\text{rel}}$ onto the crack normal $\vec{n}$, see Appendix B (crack width computation in triangles), Appendix C (crack normal determination), Fig. 32b and Eq. 28.

$$r = \frac{||\vec{n}^T \cdot \vec{t}_{\text{rel}}||}{||\vec{n}||} \leq ||\vec{t}_{\text{rel}}||. \quad (28)$$

The algorithm for the computation of the absolute value of the relative translation vector $||\vec{t}_{\text{rel}}||$ can also be applied on triangles on 3D surfaces. The 3D coordinates of the vertices of the triangle can be transformed to a local 2D system in the reference and in the subsequent epoch. Then, the 2D algorithm can be applied. Global translation and rotation have to be discarded due to the transformation to 2D.

3 Experimental Results

In this section, some results of a quasi-static tension test of a SHCC specimen are shown. The loading force is increased stepwise that leads to increasing multiple cracking. The resolution of the observing camera is 5184×2912 px. The width of the probe is 4 cm and the length between the clamps is approximately 10 cm. The following parameters are used for the geometric analysis:

- The size of the grid cells for the definition of the coarse subset of points is set to 150 px.
- The number of iterations for the densification of the mesh is set to 5.
- A triangle is subdivided if $||\vec{t}_{\text{rel}}|| > \delta = 0.075$ px and if the side lengths of the new triangles are greater than or equal to 5 px.
- The 1st method of Sect. 2.4.2 is used for clustering in the least-squares method.
- If $||\vec{t}_{\text{rel}}|| > \epsilon = 0.15$ px, the triangle is considered as crack candidate (Appendices B and C).

The crack widths r (or rather $||\vec{t}_{\text{rel}}||$ for triangles with $||\vec{t}_{\text{rel}}|| \leq \delta$) can be visualized in a colour-coded map. The triangle crack widths are depicted for four epochs of an experiment in Fig. 19. The increasing multiple cracking is shown and this behaviour is typical for SHCC. It ensures the ductility of the material.

Furthermore, it is possible to create 3D visualizations where triangles are transformed to prisms whose heights correspond to the crack widths in addition to the colour code, see Fig. 20.

As already described in Sect. 1.4, principal strains depend on triangle size, whereas the crack width values should not

Fig. 19 Colour-coded visualization of the crack widths of different epochs: **a** epoch 10, **b** epoch 30, **c** epoch 50, **d** epoch 80

Fig. 20 Colour-coded 3D visualization of the crack widths. The heights of the prisms as well as their colours correspond to the crack widths

Fig. 21 Upper part: visualization of principal strains in triangle meshes using different triangle sizes. Lower part: crack widths

change. In Fig. 21, the influence of different triangle sizes on the principal strains and on the crack widths is shown. In the right images, the edge lengths of the triangles are divided in half, and as expected, the strains appear much greater in the right image. Considering the crack widths, only small differences caused by discretization can be seen.

As already mentioned, the presented results in this section show a typical behaviour of a tension test with a SHCC specimen. The comparison to other measuring methods is very difficult: Strain gauges cannot be fixed to the probe, because they would influence the development of the multiple cracking. Two inductive displacement transducers are used to measure the entire extension between the measuring area between the clamps, but they only give single values.

4 Detailed Test of the Algorithm on the Basis of Synthetic Image Data

The photogrammetric crack pattern analysis procedure as described above delivers results with rather high internal precision figures and rather high spatial resolution. As a consequence, it is almost impossible to provide independent

reference measurements which could serve for an external accuracy test. Therefore, we decided to use a synthetic data set with synthetic images containing defined deformations as a basis to test the developed algorithms.

Herein, precision, accuracy, and reliability are analyzed. Accuracy describes the deviations between the measurements and the true values including systematic errors, whereas precision shows how measurements differ from each other due to random errors. In this paper, reliability describes the robustness of the algorithm, and therefore, the ratio of outliers is used for the evaluation. The given shifts are compared to the measured vectors in two ways: the first one is the analysis of the 2D relative translation vectors and the second one is the 1D analysis of the computed crack widths. The following parameters are used for the geometric analysis:

- The size of the grid cells for the definition of the coarse subset of points is set to 75 px.
- The number of iterations for the densification of the mesh is set to 5.
- A triangle is subdivided if $||\vec{t}_{rel}|| > \delta = 0.075$ px and if the side lengths of the new triangles are greater than or equal to 5 px.
- The 1st method of Sect. 2.4.2 is used for clustering in the least-squares method.
- If $||\vec{t}_{rel}|| > \epsilon = 0.15$ px, the triangle is considered as crack candidate (Appendices B and C).

4.1 Generation of the Images

To get a reference image (undeformed state), a random pattern is generated onto a grey (almost white) background. The resolution of the image is set to 300×2000 px. Because of sharp edges, the image is blurred with a Gaussian smoothing filter, see Fig. 22a. For the deformed state, a rotation with an angle of $\vartheta = 2^\circ$ (rotation about the image center $(x_c; y_c)^T$) and a translation of $\vec{t} = (3 \text{ px}; -1 \text{ px})^T$ was simulated for the whole image. For the right part of the image, an additional relative

Fig. 22 **a** Random pattern, **b** only relative shift in x, **c** relative shift in y, and **d** relative shift in x and y

translation $\vec{t}_{\text{rel}}$ is applied. The left and the right parts are transformed in different ways. The grey values of the deformed images are computed according to the indirect method using bicubic interpolation, while the grey values of the crack are set to zero. Equation (29) shows the transformation formula applied to the right and the left side of the image:

For the left side of the crack:

$$\begin{pmatrix} x_{\text{ref}} \\ y_{\text{ref}} \end{pmatrix} = \mathbf{R}^T \cdot \vec{A} + \begin{pmatrix} x_c \\ y_c \end{pmatrix}$$

For the right side of the crack:

$$\begin{pmatrix} x_{\text{ref}} \\ y_{\text{ref}} \end{pmatrix} = \mathbf{R}^T \cdot \vec{A} + \begin{pmatrix} x_c \\ y_c \end{pmatrix} - \vec{t}_{\text{rel,ref}}$$

with

$$\vec{A} = \begin{pmatrix} x \\ y \end{pmatrix} - \begin{pmatrix} x_c \\ y_c \end{pmatrix} - \vec{t} \text{ and}$$

$$\begin{pmatrix} x_c \\ y_c \end{pmatrix} = \begin{pmatrix} 0.5 \cdot \text{number of columns} \\ 0.5 \cdot \text{number of rows} \end{pmatrix} \text{ and}$$

$$\mathbf{R} = \begin{pmatrix} \cos \vartheta & \sin \vartheta \\ -\sin \vartheta & \cos \vartheta \end{pmatrix}, \quad (29)$$

where $x_{\text{ref}}, y_{\text{ref}}$ are the coordinates in the reference, $x_{\text{ref}}, y_{\text{ref}}$ are the coordinates in the reference image, and x, y are the coordinates in the deformed image.

In addition, a zero mean Gaussian noise with a standard deviation of $\sigma_{\text{Gauss}} = 5$ is added to each pixel for each image. 14×3 deformed images were generated with different relative translation vectors. Fourteen different shifts v are simulated (0.2 px; 0.3 px; 0.4 px; 0.5 px; 0.6 px; 0.7 px; 0.8 px; 0.9 px; 1 px; 1.5 px; 2 px; 3 px; 4 px; 5 px) with the three cases: $\vec{t}_{\text{rel,ref}} = (v; 0)^T$, $\vec{t}_{\text{rel,ref}} = (0; v)^T$ and $\vec{t}_{\text{rel,ref}} = (v; v)^T$. Figure 22b–d shows three examples of the three different cases of relative translation vectors.

4.2 Measurements

For all generated images, the procedure of Sect. 2 is applied. For each triangle, the relative translation vector and the crack width are computed and the data are analyzed below. The test is done with the three-point algorithm (labeled with 3p, Appendix B) where only the three vertices of the triangle are used and it is done with the least-squares adjustment algorithm (labeled with ls, Sect. 2.4) including also the matching points not belonging to the mesh inside the triangle. Figure 23 shows the result of the algorithm for the crack width computation of one of the cases. The deformed triangles are detected correctly.

4.3 Statistics of the Relative Translation Vectors

First, the relative translation vectors are considered. The relative shifts are measured in the coordinate system of the deformed state. To compare the given values used in the

Fig. 23 **a** Colour-coded visualization of crack widths, **b** extracted crack triangles

image generation step (Sect. 4.1), these reference vectors have to be transformed:

$$\vec{\mu} = \mathbf{R} \cdot \vec{\mu}_{\text{ref}} = \begin{pmatrix} \cos \vartheta & \sin \vartheta \\ -\sin \vartheta & \cos \vartheta \end{pmatrix} \cdot \vec{\mu}_{\text{ref}}, \quad (30)$$

where $\vec{\mu}$ is the expected relative translation vector in the deformed state, $\vec{\mu}_{\text{ref}}$ is the expected relative translation vector in the undeformed state.

The vectors of the measurements are composed of x and y coordinates:

$$\vec{t}_{\text{rel},i} = \begin{pmatrix} x_i \\ y_i \end{pmatrix}, \quad (31)$$

where i is the index of the crack triangle. The mean of the n relative translation vectors for all crack triangles is:

$$\vec{x}_m = \begin{pmatrix} \frac{1}{n} \cdot \sum_{i=1}^n x_i \\ \frac{1}{n} \cdot \sum_{i=1}^n y_i \end{pmatrix}, \quad (32)$$

where

n is the number of crack triangles/observations.

The empirical covariance matrix Σ is computed as follows:

$$\Sigma = \begin{pmatrix} s_x^2 & s_{xy} \\ s_{xy} & s_y^2 \end{pmatrix} \quad \text{with} \quad (33)$$

$$s_x^2 = \frac{1}{n-1} \cdot \sum_{i=1}^n (x_i - x_m)^2$$

$$s_y^2 = \frac{1}{n-1} \cdot \sum_{i=1}^n (y_i - y_m)^2$$

$$s_{xy} = \frac{1}{n-1} \cdot \sum_{i=1}^n (x_i - x_m) \cdot (y_i - y_m),$$

where s_x^2 is the variance of the x values of $\vec{t}_{\text{rel}}$, s_y^2 is the variance of the y values of $\vec{t}_{\text{rel}}$, and s_{xy} is the covariance of x and y of $\vec{t}_{\text{rel}}$.

To find multivariate outliers, the Mahalanobis distance can be used if the data is normally distributed. The squared Mahalanobis distance MD^2 is distributed according to the χ^2 distribution:

$$MD^2(\vec{x}_i) = (\vec{x}_i - \vec{x}_m)^T \cdot \Sigma^{-1} \cdot (\vec{x}_i - \vec{x}_m) \sim \chi_b^2, \quad (34)$$

where b is the dimension (here $b = 2$).

According to the $3\text{-}\sigma$ rule in the one-dimensional case, the confidence level $\gamma = 1 - \alpha$ is set to 99.73%. A data vector is considered as outlier if the following condition for the squared Mahalanobis distance is fulfilled:

$$\vec{x}_i \text{ is an outlier if } MD^2(\vec{x}_i) > \chi_{b,1-\alpha}^2, \quad (35)$$

where α is the significance level.

The outlier test is done in an iterative process. The mean vector and the empirical covariance matrix are computed in each iteration and only the data vector with the highest Mahalanobis distance is rejected if Eq. (35) is fulfilled. The process is repeated until the maximum of the squared Mahalanobis distances is below the critical value from the χ^2 distribution.

To evaluate the precision, an eigenvalue decomposition of the empirical covariance Σ is conducted:

$$\Sigma = V \cdot \Lambda \cdot V^T = V \cdot \begin{pmatrix} s_1^2 & 0 \\ 0 & s_2^2 \end{pmatrix} \cdot V^T, \quad (36)$$

where V is the eigenvector matrix; Λ is the eigenvalue matrix (diagonal).

s_1 and s_2 are the square roots of the eigenvalues and can be used as a quantity for the precision measurement.

Figure 24 shows the scatter plots for the smallest shift distance of $v = 0.2$ px computed with the three-point algorithm. Table 1 depicts the relative translation vectors in the reference coordinate system and the corresponding vectors in the deformed state. On the left side of Fig. 24, some outliers are visible. In the center plots, the outliers are removed and the confidence ellipses with a confidence level of 95 % (red dashed ellipses) and 99.73 % (red dotted ellipses) are plotted. On the right side, the histograms of the crack widths and the kernel density estimation (magenta dashed line) are depicted. There, the red dotted vertical lines mark the reference values.

Figure 25 depicts the plots for the simulated shift $v = 0.2$ px computed with the least-squares algorithm. In Figs. 26 and 27, there are the plots for the simulated shift of $v = 0.6$ px.

To evaluate the accuracy, the empirical covariance matrix Σ^* is computed using the given expected vector $\vec{\mu}$ used for the image generation:

Fig. 24 Simulated shift of $v = 0.2$ px with different relative translation directions (from top to bottom); left: scatter plot of relative translation vectors with the three-point algorithm for all triangles along the crack; center: scatter plot without outliers; blue: reference vector; red: mean vector and confidence ellipses with 95 % and 99.73 %; right: histogram of the corresponding crack widths, the expected value is shown as red vertical dotted line, and the kernel density estimate (Gaussian kernel) is depicted as magenta dashed line

Table 1 Expected relative translation vectors in the undeformed state $\vec{\mu}_{\text{ref}}$ and in the deformed state $\vec{\mu}$ with $v = 0.2$ px used for the analysis

	$\vec{\mu}_{\text{ref}}$	$\vec{\mu}$
Case 1	$\begin{pmatrix} 0.2 \text{ px} \\ 0 \end{pmatrix}$	$\begin{pmatrix} 0.20 \text{ px} \\ -0.01 \text{ px} \end{pmatrix}$
Case 2	$\begin{pmatrix} 0 \\ 0.2 \text{ px} \end{pmatrix}$	$\begin{pmatrix} 0.01 \text{ px} \\ 0.20 \text{ px} \end{pmatrix}$
Case 3	$\begin{pmatrix} 0.2 \text{ px} \\ 0.2 \text{ px} \end{pmatrix}$	$\begin{pmatrix} 0.21 \text{ px} \\ 0.19 \text{ px} \end{pmatrix}$

$$\Sigma^* = \begin{pmatrix} s_x^{*2} & s_{xy}^* \\ s_{xy}^* & s_y^{*2} \end{pmatrix}$$

with

$$s_x^{*2} = \frac{1}{n} \cdot \sum_{i=1}^n (x_i - \mu_x)^2 \quad (37)$$

$$s_y^{*2} = \frac{1}{n} \cdot \sum_{i=1}^n (y_i - \mu_y)^2$$

$$s_{xy}^* = \frac{1}{n} \cdot \sum_{i=1}^n (x_i - \mu_x) \cdot (y_i - \mu_y),$$

where s_x^{*2} is the variance of the x values of $\vec{t}_{\text{rel}}$, s_y^{*2} is the variance of the y values of $\vec{t}_{\text{rel}}$, and s_{xy}^* is the covariance of x and y of $\vec{t}_{\text{rel}}$.

Fig. 25 Simulated shift of $v = 0.2$ px with different relative translation directions (from top to bottom); left: scatter plot of relative translation vectors with the least-squares algorithm for all triangles along the crack; center: scatter plot without outliers; blue: reference vector; red: mean vector and confidence ellipses with 95 % and 99.73 %; right: histogram of the corresponding crack widths; the expected value is shown as red vertical dotted line; the kernel density estimate (Gaussian kernel) is depicted as magenta dashed line

The principal standard deviations can be obtained by an eigenvalue decomposition of the empirical covariance matrix Σ^* :

$$\Sigma^* = \mathbf{V}^* \cdot \Lambda^* \cdot \mathbf{V}^{*T} = \mathbf{V}^* \cdot \begin{pmatrix} s_1^{*2} & 0 \\ 0 & s_2^{*2} \end{pmatrix} \cdot \mathbf{V}^{*T}, \quad (38)$$

where $\mathbf{V}^*$ is the eigenvector matrix; Λ^* is the eigenvalue matrix (diagonal).

s_1^* and s_2^* can be used as a quantity for the accuracy measurement. In addition, the accuracy can also be estimated by the following three quantities:

The distance from the mean to the reference vector is:

$$d_{\mu-m} = \|\bar{\mathbf{x}}_m - \bar{\boldsymbol{\mu}}\|. \quad (39)$$

The mean distance to reference vector is:

$$\bar{d}_\mu = \frac{1}{n} \sum_{i=1}^n \|\bar{\mathbf{x}}_i - \bar{\boldsymbol{\mu}}\|. \quad (40)$$

The maximum distance to reference vector is:

$$\hat{d}_\mu = \max_i (\|\bar{\mathbf{x}}_i - \bar{\boldsymbol{\mu}}\|). \quad (41)$$

To conclude the results, the precision and accuracy measurements are plotted in diagrams, see Fig. 28. The plots for

Fig. 26 Simulated shift of $v = 0.6$ px with different relative translation directions (from top to bottom); left: scatter plot of relative translation vectors with the three-point algorithm for all triangles along the crack; center: scatter plot without outliers; blue: reference vector; red: mean vector and confidence ellipses with 95 % and 99.73 %; right: histogram of the corresponding crack widths; the expected value is shown as red vertical dotted line; the kernel density estimate (Gaussian kernel) is depicted as magenta dashed line

the precision and accuracy are very similar. The maximum principal standard deviations are about 0.06 px. The maximum distance between the mean and the expected value is $\max(d_{\mu-m}) = 0.026$ px in case of a relative shift $v = 0.2$ px along the crack ($\bar{\mathbf{t}}_{\text{rel}} = (0.01 \text{ px}; 0.20 \text{ px})^T$). This deviation can also be seen in Fig. 24 and in Fig. 25. It is much greater than the distance between the red point and the blue point in Figs. 26 and 27 with $v = 0.6$ px. Considering all the other experiments, the distances between the mean and the expected value $d_{\mu-m}$ are below 0.015 px. The mean distance to the expected value is about $\bar{d}_\mu \approx 0.05$ px in all experiments. The maximum distances to the expected values $\hat{d}_\mu$ are in a range of 0.1–0.2 px.

The reliability is evaluated with the help of the outlier ratio. The Gaussian noise added to the images leads to noise in the displacements. Sometimes, the wrong base edge is determined by Eq. 51 in Appendix B due to noise effects. In such cases, outliers appear. Figure 29 depicts the outlier ratios of all the experiments. The mean outlier ratio is approximately 2%. The highest outlier ratio appears in the experiment with $\bar{\mathbf{t}}_{\text{rel}} = (0.05 \text{ px}; 1.50 \text{ px})^T$. Again, the experiment with $\bar{\mathbf{t}}_{\text{rel}} = (0.01 \text{ px}; 0.20 \text{ px})^T$ shows a special behaviour, too. It has one of the highest outlier ratios and it has a high number of crack triangles that were not detected

Fig. 27 Simulated shift of $v = 0.6$ px with different relative translation directions (from top to bottom); left: scatter plot of relative translation vectors with the least-squares algorithm for all triangles along the crack; center: scatter plot without outliers; blue: reference vector; red: mean vector and confidence ellipses with 95 % and 99.73 %; right: histogram of the corresponding crack widths; the expected value is shown as red vertical dotted line; the kernel density estimate (Gaussian kernel) is depicted as magenta dashed line

(false negatives). In this case, the small relative shift is almost perpendicular to one triangle edge crossed by the crack, such that its length rarely changes (smaller than the precision of LSM). Because of that, there are two edges that have almost constant side lengths. In such cases, it is difficult for the algorithm to decide which edge is the baseline for the crack width computation. If the wrong side is chosen, the computed relative translation vector is an outlier.

In conclusion, the precision and accuracy of the relative translation vector components is below 0.06 px. Under suboptimal conditions, the accuracy may reach values up to 0.2 px. The ratio of outliers as a measure of reliability is on average 2%, but the maximum value is about 7%.

4.4 Statistics of the Crack Widths

After computing the crack width by projecting the relative translation vector onto the crack normal (Eq. 28), these values can also be analyzed statistically. Because of the projection, the crack normal $\vec{n}$ is a further quantity that influences the scattering. It is to be expected that the accuracy of the crack normal $\vec{n}$ is not that high due to discretization errors (line fit with the center points of the crack triangle and its neighbours, see Appendix C), such that the accuracy of the crack widths should be worse than the accuracy of the relative translation vectors.

Fig. 28 Precision and accuracy of the relative translation vectors for all reference crack widths for the three-point (3p) and the least-squares algorithm (ls). Left: precision using principle standard deviations from the empirical covariance matrix; center: accuracy using principle standard deviations from the covariance matrix with the

given reference shift as average; right: other quantities for accuracy measurement, distance from the mean to the reference relative shift, mean distance from the single to the reference relative translation vector, and maximum distance to the reference relative shift vector

Fig. 29 Reliability: outlier ratio β in percent for all experiments [three-point algorithm (3p) and the least-squares algorithm (ls)]

The expected crack widths μ_r are the x components of the relative translation vector $\vec{t}_{\text{rel,ref}}$ used for image generation:

$$\mu_r = t_{\text{rel,ref},x} \quad (42)$$

The mean of the measured crack widths r_m is:

$$r_m = \frac{1}{n} \cdot \sum_{i=1}^n r_i \quad (43)$$

where r_i is the crack width of the i th crack triangle; n is the number of crack triangles.

The standard deviation of the crack widths s_r is used as a quantity for precision:

$$s_r = \sqrt{\frac{1}{n-1} \cdot \sum_{i=1}^n (r_i - r_m)^2} \quad (44)$$

The standard deviation s_r^* with the reference crack width μ_r as expected value is used as a quantity for the accuracy:

$$s_r^* = \sqrt{\frac{1}{n} \cdot \sum_{i=1}^n (r_i - \mu_r)^2} \quad (45)$$

Fig. 30 Accuracy and precision of crack widths

Figure 30 shows the precision and accuracy of the crack widths of all experiments in two charts. The difference between the three-point and the least-squares algorithm is very small. Considering the experiments with the relative translation vector in x -direction ($\vec{t}_{\text{rel,ref}} = (v; 0)^T$), the precision and the accuracy values are similar and on a constant level at 0.03 px. In case of $\vec{t}_{\text{rel,ref}} = (v; v)^T$, the precision and the accuracy of the crack widths are also similar. Only the y -direction ($\vec{t}_{\text{rel,ref}} = (0; v)^T$) is an exception, because the mean and the expected value differ ($s_{r,y} < s_{r,y}^*$). The expected value $\mu_{r,y}$ is zero, because there are only movements along the crack, whereas the mean is greater than zero, because all computed crack widths are positive (absolute values), see also the histograms in the second rows of Figs. 24, 25, 26, and 27. The crack widths are not normally distributed. For the shifts in y as well as in x and y , the precision and accuracy values are higher in case of higher shifts v . This behaviour is expected due to the fluctuation in the crack normal estimation. Higher relative shifts should lead to higher deviations.

In summary, the precision and accuracy of the crack widths is better than 0.10 px for crack widths below 2 px. The accuracy and the precision depends on the crack width itself. Crack widths up to 5 px can lead to accuracy values up to 0.25 px.

4.5 Further Remarks

In real monocular experiments, there are further systematic errors. Some of the points are already listed in Sect. 1.3. In addition to these points, in case of measurements with inductive displacement transducers as comparing method, clamps can cause occlusions.

However, the error analysis in this section only considers the computation of displacements as well as the geometric analysis and is separated from the other effects mentioned in Sect. 1.3 and at the begin of this subsection, although the results may be too optimistic.

5 Conclusion and Outlook

This paper presents a strategy to detect cracks and compute their widths in multiple crack structures. The method is based on the deformation analysis of triangle meshes. The reliability, the precision, and the accuracy are checked using different simulated images with known deformations. Crack widths can be determined with an accuracy of better than 0.1 px in most cases, with lesser accuracy up to 0.25 px under suboptimal conditions. Further work should concentrate on model extensions using angles obtained by least-squares matching. Another extension could be the rotation of the upper part of the triangle. In addition, the accuracy can be determined with other reference measurements. A further interesting issue would be the application of the algorithm on triangle meshes of 3D surfaces.

Acknowledgements Open Access funding provided by Projekt DEAL. The research work presented in this paper has been performed within the research training group GRK-2250 at TU Dresden funded by the German Research Council (DFG).

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

Appendix A: Computation of Principal Strains of Triangles

This section gives a short overview of the calculation of principal strains in triangle meshes according to the work of Liebold and Maas (2016). The principal strains of triangles are computed using the coordinates of its vertices in the reference and in the subsequent epoch. First, the parameters of an affine transformation between the coordinates are calculated:

$$\begin{pmatrix} x \\ y \end{pmatrix} = \begin{pmatrix} a_{11} + a_{12} \cdot x_{\text{ref}} + a_{13} \cdot y_{\text{ref}} \\ a_{21} + a_{22} \cdot x_{\text{ref}} + a_{23} \cdot y_{\text{ref}} \end{pmatrix}, \quad (46)$$

where x, y are the coordinates of the subsequent epoch; $x_{\text{ref}}, y_{\text{ref}}$ are the coordinates of the reference epoch; a_{ij} are the affine parameters.

The deformation gradient $\mathbf{F}$ is composed of four of the affine parameters. It is a product of a symmetric matrix $\mathbf{V}$ and rotation matrix $\mathbf{R}$:

$$\mathbf{F} = \begin{pmatrix} a_{12} & a_{13} \\ a_{22} & a_{23} \end{pmatrix} = \mathbf{V} \cdot \mathbf{R}. \quad (47)$$

To compute the polar decomposition, the left Cauchy–Green deformation tensor $\mathbf{V}^2$ is calculated:

$$\mathbf{V}^2 = \mathbf{V} \cdot \mathbf{V} = \mathbf{V} \cdot \mathbf{V}^T = \mathbf{F} \cdot \mathbf{F}^T. \quad (48)$$

After this, an eigenvalue decomposition of the left Cauchy–Green deformation tensor is applied:

$$\mathbf{V}^2 = \mathbf{C} \cdot \mathbf{\Lambda} \cdot \mathbf{C}^T = \mathbf{C} \cdot \begin{pmatrix} \lambda_1 & 0 \\ 0 & \lambda_2 \end{pmatrix} \cdot \mathbf{C}^T, \quad (49)$$

where $\mathbf{C}$ is the eigenvector matrix (orthogonal matrix), $\mathbf{\Lambda}$ is the eigenvalue matrix (diagonal matrix), and λ_i is the i th eigenvalue, diagonal element of $\mathbf{\Lambda}$.

The greater eigenvalue λ_2 is used to compute the principal strain s using the square root (Eq. 50). The principal strain s is a dimensionless quantity.

$$s = \sqrt{\lambda_2}. \quad (50)$$

In case of cracks running through a triangle, there will be an extension and the triangle will thus have a larger principle strain s . The direction of the strain is given by the corresponding eigenvector (column of $\mathbf{C}$).

Appendix B: Crack Width Computation in Triangles

In this appendix, a short overview of the algorithm according to the approach of Liebold and Maas (2018) is given. Between the reference and the subsequent epoch, a rigid movement for the three vertices of the triangle is assumed, and in case of a crack running through the triangle, an additional relative translation is added to one of the vertices. Figure 31 shows an example of the movement of the vertices of a crack triangle.

Fig. 31 Movement of a crack triangle

First, the rigid transformation concerning all vertices has to be separated from the relative translation concerning only one vertex. For that purpose, the minimal absolute difference of the edge lengths between the reference and the subsequent epoch is determined and the corresponding edge is considered as constant base edge. The indices of the vertices corresponding to the edge with the minimal absolute distance change $i_{\min}$ and $j_{\min}$ are the baseline indices b_1 and b_2 :

$$b_1, b_2 = i_{\min}, j_{\min} = \underset{i,j}{\operatorname{argmin}} \Delta d_{i,j} \quad (51)$$

with

$$\Delta d_{i,j} = |||\vec{p}_j - \vec{p}_i|| - ||\vec{p}_{\text{ref},j} - \vec{p}_{\text{ref},i}|||.$$

The remaining index of the triangle belongs to the upper point. The coordinates of the two vertices of the base edges in the reference and subsequent epoch are used to compute the parameters of the rigid body transformation ($\vec{t}$ and $\mathbf{R}$):

$$\begin{aligned} \vec{p}_{b1} &= \vec{t} + \mathbf{R} \cdot \vec{p}_{\text{ref},b1} \\ \vec{p}_{b2} &= \vec{t} + \mathbf{R} \cdot \vec{p}_{\text{ref},b2}, \end{aligned} \quad (52)$$

where $\vec{t}$ the translation vector; $\mathbf{R}$ is the rotation matrix.

The formula is extended with the relative translation vector $\vec{t}_{\text{rel}}$ for the upper vertex $\vec{p}_{\text{up}}$:

$$\vec{p}_{\text{up}} = \vec{t} + \mathbf{R} \cdot \vec{p}_{\text{ref},\text{up}} + \vec{t}_{\text{rel}}. \quad (53)$$

Then, the upper vertex of the reference epoch is transformed in the subsequent epoch using the parameters $\vec{t}$ and $\mathbf{R}$. According to Eq. (53), the relative translation is computed by the difference of the upper point in the subsequent epoch and transformed reference point:

$$\vec{t}_{\text{rel}} = \vec{p}_{\text{up}} - \vec{t} - \mathbf{R} \cdot \vec{p}_{\text{ref},\text{up}}. \quad (54)$$

The relative shift $\vec{t}_{\text{rel}}$ is composed of a component perpendicular to the crack and another part parallel to the crack $\vec{t}_{\parallel}$, see Fig. 32a, b.

Fig. 32 **a** Transformed reference and subsequent triangle according to Liebold and Maas (2018); **b** components of the relative translation vector

The crack width r is the absolute value of the part of the relative translation vector $\vec{t}_{\text{rel}}$ that is perpendicular to the crack course. It is computed by the scalar projection of the relative translation vector $\vec{t}_{\text{rel}}$ onto the crack normal $\vec{n}$, see Eq. 55 and Fig. 32b:

$$r = ||\vec{t}_{\text{rel}}|| \cdot ||\cos \beta|| = \frac{||\vec{n}^T \cdot \vec{t}_{\text{rel}}||}{||\vec{n}||} \leq ||\vec{t}_{\text{rel}}||. \quad (55)$$

The determination of the crack normal $\vec{n}$ is described in Appendix C. If there is no information about the normal direction $\vec{n}$, the translation along the crack $\vec{t}_{\parallel}$ can be ignored; the crack width is approximately:

$$r \approx ||\vec{t}_{\text{rel}}||. \quad (56)$$

The perpendicular part and the parallel part to the crack cannot cancel each other out. Because of that, the absolute value of the relative translation vector $||\vec{t}_{\text{rel}}||$ can be used as an upper bound for the crack width r because $0 \leq ||\cos \beta|| \leq 1$. The crack width r is an absolute quantity and also has a unit. In the image space, it is measured in pixels.

Appendix C: Crack Normal Computation

The crack normal describes the direction that is perpendicular to the crack course. As a first assumption, the principal strain direction can be used as crack normal. In case of mechanical shear forces, the relative movement between the

Fig. 33 Mechanical shear forces; red: extended triangles; blue: triangles with $||\vec{t}_{\text{rel}}|| \leq \epsilon$; direction of the relative translation vector $\vec{t}_{\text{rel}}$ is not parallel to the crack normal $\vec{n}$ anymore. This figure is according to Liebold and Maas (2018)

Fig. 34 Crack normal determination according to Liebold and Maas (2018)

left side and right side of the crack is composed of a perpendicular part and a parallel part, see Fig. 32b. The presented algorithm is based on the approach of Liebold and Maas (2018).

In case of shear effects, the crack normal can be determined as follows:

- First of all, the approximate crack width is computed with Eq. (56) for each triangle. If the absolute value of the relative shift is greater than a threshold ($|\vec{t}_{rel}| > \epsilon$), the triangle is considered as a critical candidate.
- Then, for each critical candidate, all critical triangles of the second-order neighbourhood (neighbours and neighbours of neighbours) are determined. Triangles are considered as neighbours if they have at least one common vertex.
- After this, a line fit of the center points of the critical triangles is computed.
- The perpendicular on this line is an approximation for the crack normal $\vec{n}$ (Fig. 33).

In Fig. 34, the line fit is visualized.

References

- Ackermann F (1984) Digital image correlation: performance and potential application in photogrammetry. *Photogramm Rec* 11(64):429–439. <https://doi.org/10.1111/j.1477-9730.1984.tb00505.x>
- Arthur D, Vassilvitskii S (2007) K-means++: the advantages of careful seeding. In: Proceedings of the eighteenth annual ACM-SIAM symposium on discrete algorithms. Society for Industrial and Applied Mathematics, Philadelphia, SODA '07, pp 1027–1035. <http://dl.acm.org/citation.cfm?id=1283383.1283494>
- Barazzetti L, Scaioni M (2009) Crack measurement: development, testing and applications of an automatic image-based algorithm. *ISPRS J Photogramm Remote Sens* 64:285–296. <https://doi.org/10.1016/j.isprsjprs.2009.02.004>
- Barazzetti L, Scaioni M (2010) Development and implementation of image-based algorithms for measurement of deformations in material testing. *Sensors* 10:7469–7495. <https://doi.org/10.3390/s100807469>
- Benning W, Lange J, Schwermann R, Effkemann C, Görtz S (2004) Monitoring crack origin and evolution at concrete elements using photogrammetry. In: International archives of photogrammetry, remote sensing and spatial information science, vol XXXV-B5, pp 678–683. <https://www.isprs.org/proceedings/XXXV/congress/comm5/papers/638.pdf>
- Brown C Duane (1971) Close-range camera calibration. *Photogramm Eng* 37(8):855–866. http://www.vision.caltech.edu/bouguetj/calib_doc/papers/Brown71.pdf
- Curosu I, Mechtcherine V, Forni D, Cadoni E (2017) Performance of various strain-hardening cement-based composites (SHCC) subject to uniaxial impact tensile loading. *Cement Concrete Res* 102:16–28. <https://doi.org/10.1016/j.cemconres.2017.08.008>
- Dare P, Hanley H, Fraser C, Riedel B, Niemeier W (2002) An operational application of automatic feature extraction: the measurement of cracks in concrete structures. *Photogramm Rec* 17(99):453–464. <https://doi.org/10.1111/0031-868X.00198>
- Detchev I, Habib A, El-Badry M (2012) Extraction of cracks from concrete beam images. In: Proceedings of ASPRS 2012 annual conference, Sacramento
- Detchev I, Habib A, Lichti D, El-Badry M (2016) Structural 3D monitoring using a new sinusoidal fitting adjustment. *ISPRS Ann Photogramm Remote Sens Spatial Inf Sci* III-5:3–10. <https://doi.org/10.5194/isprs-annals-III-5-3-2016>. <https://www.isprs-ann-photogramm-remote-sens-spatial-inf-sci.net/III-5/3/2016/>
- Förstner W (1984) Quality assessment of object location and point transfer using digital image correlation techniques. In: International archives of photogrammetry, vol XXV-3A, pp 197–219. https://www.isprs.org/proceedings/XXV/congress/part3/197_XXV-part3.pdf
- Fraser CS, Riedel B (2000) Monitoring the thermal deformation of steel beams via vision metrology. *ISPRS J Photogramm Remote Sens* 55(4):268–276. [https://doi.org/10.1016/S0924-2716\(00\)00024-1](https://doi.org/10.1016/S0924-2716(00)00024-1)
- Görtz S (2004) Zum Schubbrissverhalten von Stahlbeton- und Spannbetonbalken aus Normal- und Hochleistungsбетон. PhD thesis, RWTH Aachen. <http://publications.rwth-aachen.de/record/53027>
- Grün A (1985) Adaptive least squares correlation: a powerful image matching technique. *S Afr J Photogramm Remote Sens Cartogr* 14(3):175–187. <http://citeseerx.ist.psu.edu/viewdoc/download?doi=10.1.1.93.6891&rep=rep1&type=pdf>
- Grün A (2012) Development and status of image matching in photogrammetry. *Photogr Rec* 27(137):36–57. <https://doi.org/10.1111/j.1477-9730.2011.00671.x>
- Hampel U, Maas HG (2003) Application of digital photogrammetry for measuring deformation and cracks during load tests in civil engineering material testing. In: Proceedings of optical 3-D measurement techniques VI, A. Grün, vol 2, pp 80–88. https://tu-dresden.de/bu/umwelt/geo/ipf/photogrammetrie/ressourcen/dateien/forschung/publikationen/pubdocs/2003/2003_Hampel_U_Maas_Opt3D2003.pdf?lang=de
- Hampel U, Maas HG (2009) Cascaded image analysis for dynamic crack detection in material testing. *ISPRS J Photogramm Remote Sens* 64(4):345–350. <https://doi.org/10.1016/j.isprsjprs.2008.12.006>
- Harris C, Stephens M (1988) A combined corner and edge detector. In: Proceedings of fourth Alvey vision conference, pp 147–151.

- <http://citeseer.ist.psu.edu/viewdoc/download?doi=10.1.1.231.1604&rep=rep1&type=pdf>
- Irwin GR (1958) *Fracture*. Springer, Berlin, pp 551–590. https://doi.org/10.1007/978-3-642-45887-3_5
- Koschitzki R, Schacht G, Schneider D, Marx S, Maas HG (2011) Integration of photogrammetry and acoustic emission analysis for assessing concrete structures during loading tests. In: *Proceedings of SPIE optical metrology, International Society for Optics and Photonics*, vol 8085. <https://doi.org/10.1117/12.889558>
- Lange J, Benning W (2006) Crack detection using photogrammetry. In: *Proceedings of 9th European conference on non-destructive testing*, Berlin, NDT, German Society for Non-Destructive Testing, vol BB 103-CD, pp 1–8. <https://www.ndt.net/article/ecndt2006/doc/Th.2.4.2.pdf>
- Lange J, Benning W, Siering K (2006) Crack detection at concrete construction units from photogrammetric data using image processing procedures. In: *International archives of photogrammetry, remote sensing and spatial information science*, vol XXXVI-7, pp 493–496. <https://www.isprs.org/proceedings/XXXVI/part7/PDF/015.pdf>
- Liebold F, Maas HG (2016) Advanced spatio-temporal filtering techniques for photogrammetric image sequence analysis in civil engineering material testing. *ISPRS J Photogramm Remote Sens* 111:13–21. <https://doi.org/10.1016/j.isprsjprs.2015.10.013>. <http://www.sciencedirect.com/science/article/pii/S0924271615002452>
- Liebold F, Maas HG (2018) Sub-pixel accuracy crack width determination on concrete beams in load tests by triangle mesh geometry analysis. *ISPRS Ann Photogramm Remote Sens Spatial Inf Sci* IV-2:193–200. <https://doi.org/10.5194/isprs-annals-IV-2-193-2018>. <https://www.isprs-ann-photogramm-remote-sens-spatial-inf-sci.net/IV-2/193/2018/>
- Lloyd SP (1982) Least squares quantization in PCM. *IEEE Trans Inf Theory* 28(2):129–137. <https://doi.org/10.1109/TIT.1982.1056489>
- Maas HG (1998) Photogrammetric techniques for deformation measurements on masonry reservoir walls. In: *IAG SC4 symposium on geodesy for geotechnical and structural engineering*, Eisenstadt, pp 319–324. http://webarchiv.ethz.ch/geometh-data/student/eg1/2006/06/nalps_Photo.pdf
- Maas HG, Hampel U (2006) Photogrammetric techniques in civil engineering material testing and structure monitoring. *Photogramm Eng Remote Sens* 72(1):39–45. <https://doi.org/10.14358/PERS.72.1.39>
- Moes N, Dolbow J, Belytschko T (1999) A finite element method for crack growth without remeshing. *Int J Numer Methods Eng* 46(1):131–150. [https://doi.org/10.1002/\(SICI\)1097-0207\(19990910\)46:1<131::AID-NME726>3.0.CO;2-J](https://doi.org/10.1002/(SICI)1097-0207(19990910)46:1<131::AID-NME726>3.0.CO;2-J). <https://onlinelibrary.wiley.com/doi/abs/10.1002/%28SICI%291097-0207%2819990910%2946%3A1%3C131%3A%3AAID-NME726%3E3.0.CO%3B2-J>
- Niemeier W, Riedel B, Fraser C, Neuss H, Stratmann R, Ziem E (2008) New digital crack monitoring system for measuring and documentation of width of cracks in concrete structures. In: *Proceedings of 13th FIG international symposium on deformation measurements and analysis*, Lisbon, pp 12–15
- Whiteman T, Lichti D, Chandler I (2002) Measurement of deflections in concrete beams by close-range digital photogrammetry. In: *International archives of photogrammetry, remote sensing and spatial information science*, vol XXXIV-4. <https://www.isprs.org/proceedings/XXXIV/part4/pdfpapers/181.pdf>

3 Photogrammetrische Deformationsmessung in Stereobildsequenzen

Messungen mit Stereokameras bieten die Möglichkeit, Oberflächen dreidimensional abzutasten. Dies geschieht, indem dreidimensionale Punkte auf der Objektoberfläche durch räumliche Vorwärtsschnitte korrespondierender Bildpunktpaare in dem Stereobildpaar berechnet werden. Voraussetzung dafür ist, dass die relative und auch die innere Orientierung des Stereokamerasystems bekannt sind. Beides kann in einer Systemkalibrierung bestimmt werden, welche üblicherweise vor Beginn einer Messung durchgeführt wird. Die Kalibrierung erfolgt mit einem bewegten Testfeld mit mindestens einer bekannten Strecke in einer Bündelblockausgleichung. Eine Folge von Stereobildpaaren bildet eine Zeitreihe, in welcher Deformationen auf Basis der Verschiebungsfelder der Objektpunktkoordinaten gemessen werden können. Dazu müssen nicht nur die korrespondierenden Bildpunktpaare des Stereobildpaars gefunden werden, sondern auch diejenigen der aktuellen Epoche zu den Bildpunkten der 1. Epoche. Dieses Kapitel beinhaltet zwei Publikationen, die sich mit der Analyse dreidimensionaler Verschiebungsfelder befassen.

3.1 Rissbreitenberechnung für tangentielle Deformationen auf nicht ebenen Oberflächen mit gegebenem 3D-Verschiebungsfeld

Kapitel 3.1 (P.IV) wurde in International Archives of the Photogrammetry, Remote Sensing and Spatial Information Sciences, Volume 42(2)/W18, 2019 (ISSN 1682-1750) veröffentlicht als:

Crack Width Measurement for Non-planar Surfaces by Triangle Mesh Analysis in Civil Engineering Material Testing

Titel in Deutsch:

*Rissbreitenbestimmung für nicht ebene Oberflächen durch Analyse von
Dreiecksnetzen im bautechnischen Versuchswesen*

Autoren:

Liebold, F.¹, Maas, H.-G.¹, Heravi, A., A.²

¹ Technische Universität Dresden, Institut für Photogrammetrie und
Fernerkundung

² Technische Universität Dresden, Institut für Baustoffe

Publikationsverlauf:

eingereicht Oktober 2019, publiziert November 2019

Vollständige Referenz:

Liebold, F., Maas, H.-G., Heravi, A., A., 2019. Crack width measurement for non-planar surfaces by triangle mesh analysis in civil engineering material testing. *International Archives of Photogrammetry, Remote Sensing and Spatial Information Sciences*, 42(2)/W18, 107-113.

DOI:

<https://doi.org/10.5194/isprs-archives-XLII-2-W18-107-2019>

CRACK WIDTH MEASUREMENT FOR NON-PLANAR SURFACES BY TRIANGLE MESH ANALYSIS IN CIVIL ENGINEERING MATERIAL TESTING

F. Liebold¹, H.-G. Maas¹, A. A. Heravi²

¹ Institute of Photogrammetry and Remote Sensing, Technische Universität Dresden, Germany -
(frank.liebold, hans-gerd.maas)@tu-dresden.de

² Institute of Construction Materials, Technische Universität Dresden, Germany - ali.a.heravi@tu-dresden.de

Commission II

KEY WORDS: Material Testing, Deformation Measurement, Crack Width Measurement, Triangle Mesh, Non-planar Surface

ABSTRACT:

This publication concentrates on the photogrammetric crack width measurement of crack patterns of concrete probes under impact loading in high-speed stereo image sequences. The presented algorithm works for non-planar specimens with deformations that only appear tangential to the surface and the method is based on triangle mesh analysis. Experiments were conducted with cylindrical specimens with an impact load affecting parallel to the main axis of the cylinder.

1. INTRODUCTION

To reduce damage from impact loading due to natural catastrophes, buildings and walls can be strengthened with material-bonded composites. These composites are analyzed in dynamic tests where photogrammetric deformation measurement techniques are used. High-speed stereo systems offer the possibility to analyze impact tests due to their high temporal resolution. For civil engineers, the detection of cracks and the measurement of the according widths are an interesting issue. In recent years, several publications were contributed in the field of photogrammetric crack width determination. (Dare et al., 2002) applied edge detection techniques such as the Fly-Fisher algorithm and the Route-Finder algorithm to detect cracks in single images of crack patterns and also measured crack widths by the analysis of profiles perpendicular to the crack courses. In (Lange, Benning, 2006), the theoretical crack opening vector is expressed as follows:

$$\vec{t}_c = \begin{pmatrix} \text{crack width} \\ \text{crack edge displacement along the crack course} \\ \text{vertical crack edge displacement} \end{pmatrix} \quad (1)$$

where $\vec{t}_c$ = crack opening vector

This vector bases on the theoretical modes of fracture referring to (Irwin, 1958). (Lange, Benning, 2006) measured artificial targets on concrete specimens with a multi-ocular camera system and computed crack widths with a method given by (Görtz, 2004) using averages of displacements in 4-point-elements, also including the direction of the cracks. However, global rotations between the epochs were neglected. (Barazzetti, Scaioni, 2009) presented a 2D image sequence analysis procedure to determine crack deformations using artificial targets and an orientation frame. (Maas, Hampel, 2006) and (Hampel, Maas, 2009) used digital image correlation techniques to compute a dense displacement field and to analyze crack openings in horizontal and vertical profiles. (Liebold, Maas, 2018) show how to compute crack widths of concrete probes in monocular image sequences using triangle mesh analysis.

Monocular image sequences can only be used for planar surfaces and if the deformations only appear in this plane. The approach presented in this publication gives an extension to the work of (Liebold, Maas, 2018). It will be shown how to detect deformations on non-planar surfaces in triangle meshes between two epochs. Herein, the triangles are transformed into 2D space using the parametrization of a known surface and are analyzed with the 2D algorithm of (Liebold, Maas, 2018). A stereo system is used to measure 3D surface points for each epoch of the sequence. With the mesh analysis of 3D surface points, it is possible to work with non-planar surfaces, for example, from cylindrical specimen. Another advantage of stereo systems is the robustness against relative movements between the object and the camera system. A prerequisite for the algorithm presented here are deformations that are only tangential to the surface (only opening and in-plane shear). Our experiments are designed such that this condition is fulfilled. It is assumed that there is no out-of-plane shear, what means that the z component in Eq. 1 is zero.

The next chapter deals with the description of the experimental setup. In the following part, the method for the crack width determination is presented. After this, the application in the experiment is shown. At the end, a conclusion and an outlook is given.

2. EXPERIMENTAL SETUP

Cylindrical concrete specimens are tested in a gravity-driven split-Hopkinson tension bar to investigate performance of the material at high strain rates (Heravi et al., 2019), see Fig. 1. The height of the specimen is approximately 4 cm.

During the experiment, an image sequence is recorded with a high-speed stereo camera system consisting of two FASTCAM SA-X2 cameras (Fig. 2). The frame rate is set to 100,000 frames per second at an image resolution of 128 × 504 px such that 1 px in image space corresponds to 0.1 mm in object space.

Figure 1. Gravity-driven split-Hopkinson tension bar and cylindrical specimen.

Figure 2. High-speed stereo camera system.

3. CRACK WIDTH MEASUREMENT IN 3D DISPLACEMENT FIELDS

3.1 Preparation and acquisition of the data

First, the inner and the relative orientation of the stereo camera system is determined in a system calibration. Furthermore, the surface of the specimen must have a suitable texture for the matching process. In case of concrete, the surface to be measured may have to be prepared with an artificial pattern. During the experiment, an image sequence is recorded. The first image pair is acquired under zero load without any deformation. The first step of the analysis is the matching of a grid of points between the stereo image pair and between the epochs (current epoch to the reference epoch under zero load). For each epoch, the 3D coordinates are computed by intersection of the corresponding points in the stereo image pair, see Fig. 3.

For each epoch, all 3D points that could be matched successfully in the current time step are triangulated into a mesh using Delaunay triangulation as it is done in (Koschitzki et al., 2011), (Liebold, Maas, 2016) and (Liebold, Maas, 2018), see Fig. 4.

3.2 Workflow of the algorithm

Fig. 5 shows the steps of the presented algorithm for the crack width computation in a flow chart. The single steps of the algorithm are explained in the following sections. The workflow begins after computing the 3D displacements and the triangulation for each epoch.

Figure 3. Matching in the stereo image pair and between epochs.

Figure 4. Triangle mesh of the 3D points.

Figure 5. Flow chart of the algorithm: $\vec{t}_{rel}$ is the relative translation vector. δ is a threshold. $\vec{n}_{crack}$ is the crack normal.

3.3 Transformation to 2D

First, the edge vectors between the triangle vertices in the reference (undeformed) and the deformed state are calculated, see Eq. 2. The triangle indices are 1, 2 and 3.

$$\begin{aligned}\vec{s}_{12ref} &= \vec{p}_{2ref} - \vec{p}_{1ref} \\ \vec{s}_{13ref} &= \vec{p}_{3ref} - \vec{p}_{1ref} \\ \vec{s}_{23ref} &= \vec{p}_{3ref} - \vec{p}_{2ref}\end{aligned}\quad (2)$$

where $\vec{s}_{ijref}$ = vector from vertex i to j (reference state)

and

$$\begin{aligned}\vec{s}_{12} &= \vec{p}_2 - \vec{p}_1 \\ \vec{s}_{13} &= \vec{p}_3 - \vec{p}_1 \\ \vec{s}_{23} &= \vec{p}_3 - \vec{p}_2\end{aligned}\quad (3)$$

where $\vec{s}_{ij}$ = vector from vertex i to j (deformed state)

The following two terms are computed for the transformation in 2D space for the reference state:

$$\begin{aligned}dx_{13,ref} &= \|\vec{s}_{13,ref}\| \cdot \cos(\angle \vec{s}_{12,ref}, \vec{s}_{13,ref}) \\ &= \frac{\vec{s}_{12,ref}^T \cdot \vec{s}_{13,ref}}{\|\vec{s}_{12,ref}\|} \\ dy_{13,ref} &= \sqrt{\|\vec{s}_{13,ref}\|^2 - dx_{13,ref}^2}\end{aligned}\quad (4)$$

The transformed 2D coordinates in the reference state are:

$$\begin{aligned}\vec{q}_{1,ref} &= (0 \quad 0) \\ \vec{q}_{2,ref} &= (\|\vec{s}_{12,ref}\| \quad 0) \\ \vec{q}_{3,ref} &= (dx_{13,ref} \quad dy_{13,ref})\end{aligned}\quad (5)$$

For the deformed state, the two terms are:

$$\begin{aligned}dx_{13} &= \|\vec{s}_{13}\| \cdot \cos(\angle \vec{s}_{12}, \vec{s}_{13}) = \frac{\vec{s}_{12}^T \cdot \vec{s}_{13}}{\|\vec{s}_{12}\|} \\ dy_{13} &= \sqrt{\|\vec{s}_{13}\|^2 - dx_{13}^2}\end{aligned}\quad (6)$$

The transformed 2D coordinates in the deformed state are:

$$\begin{aligned}\vec{q}_1 &= (0 \quad 0) \\ \vec{q}_2 &= (\|\vec{s}_{12}\| \quad 0) \\ \vec{q}_3 &= (dx_{13} \quad dy_{13})\end{aligned}\quad (7)$$

3.4 Computation of the relative translation vector

In order to compute the relative translation vector in the 2D space, the algorithm from (Liebold, Maas, 2018) is applied using the point triples from Eq. 5 and Eq. 7. Fig. 6 shows the movement of the triangle in 2D. In the deformed state, the upper point has an additional relative translation.

The edge with the minimal distance change is considered as the constant base line edge:

$$b_1, b_2 = i_{min}, j_{min} = \operatorname{argmin}_{i,j} \|\vec{s}_{ij}\| - \|\vec{s}_{ij,ref}\| \quad (8)$$

where b_1 = index of the first base line vertex
 b_2 = index of the second base line vertex

Figure 6. Movement of a triangle crossed by a crack.

For the base line vertices, a Helmert transformation (rigid transformation with fixed scale) is applied:

$$\begin{aligned}\vec{q}_{b1} &= \vec{t}_{2D} + \mathbf{R}_{2D} \cdot \vec{q}_{b1,ref} \\ \vec{q}_{b2} &= \vec{t}_{2D} + \mathbf{R}_{2D} \cdot \vec{q}_{b2,ref}\end{aligned}\quad (9)$$

where $\vec{t}_{2D}$ = translation vector
 $\mathbf{R}_{2D}$ = rotation matrix

The Helmert parameters $\vec{t}_{2D}$, $\mathbf{R}_{2D}$ can be computed with the coordinates of base line vertices in the reference and the deformed state.

For the upper point, the formula is extended:

$$\vec{q}_{up} = \vec{t}_{2D} + \mathbf{R}_{2D} \cdot \vec{q}_{up,ref} + \vec{t}_{rel,2D} \quad (10)$$

where $\vec{t}_{rel,2D}$ = relative translation vector

Figure 7. Deformed and transformed reference triangle. r : crack width. $q_{j,ref,t}$: transformed reference points with index j .

The relative translation vector can be computed by reorganizing Eq. 10:

$$\vec{t}_{rel,2D} = \vec{q}_{up} - \vec{t}_{2D} - \mathbf{R}_{2D} \cdot \vec{q}_{up,ref} \quad (11)$$

The norm of the relative translation vector $\|\vec{t}_{rel,2D}\|$ is used to detect deformed triangles including cracks.

If $\|\vec{t}_{rel,2D}\| > \delta$: the triangle is considered as crack candidate where δ is a threshold depending on the quality of the displacement field. The threshold should be in the order of magnitude of the precision of the 3D object coordinates.

3.5 Computation of the crack normal

For each deformed triangle (crack candidate), the deformed triangles of the second order neighborhood (neighbors and neighbors of neighbors) are determined. Neighbor triangles have at least one common vertex with the crack candidate. Then, a line fit through the center points of these triangles is computed in order to determine the line direction $\vec{l}$, see Fig. 8.

Figure 8. Determination of direction of the crack edge $\vec{l}$. The triangle with the strong red color is the triangle which $\vec{l}$ is computed for. The center points of the triangle and the deformed neighbor triangles are shown as black points, the deformed neighbor triangles have a less strong red color. The blue triangles are undeformed. The fitted line direction vector $\vec{l}$ is depicted in black.

The normal of the triangle is also needed for the computation of the crack normal in addition to the line direction:

$$\vec{n}_{triangle} = \vec{s}_{12} \times \vec{s}_{13} \quad (12)$$

The crack normal is calculated using the cross product of the normal vector of the triangle and the line direction vector, see Eq. 13 and Fig. 9.

$$\vec{n}_{crack} = \frac{\vec{n}_{triangle} \times \vec{l}}{\|\vec{n}_{triangle} \times \vec{l}\|} \quad (13)$$

Figure 9. The crack normal is perpendicular to the line direction and the normal of the triangle.

After this, the crack normal is transformed into 2D space. Therefore, the crack normal can be expressed as a linear combination of the edges in the deformed state:

$$\vec{n}_{crack} = v_1 \cdot \vec{s}_{12} + v_2 \cdot \vec{s}_{13} \quad (14)$$

Eq. 14 can be written as a linear system using matrices:

$$\begin{pmatrix} \vec{s}_{12} & \vec{s}_{13} \end{pmatrix} \cdot \begin{pmatrix} v_1 \\ v_2 \end{pmatrix} = \vec{n}_{crack} \quad (15)$$

The system is overdetermined such that the reduced form of the singular value decomposition can be used to solve it:

$$\begin{pmatrix} \vec{s}_{12} & \vec{s}_{13} \end{pmatrix}_{3 \times 2} = \mathbf{U}_0 \cdot \mathbf{S}_0 \cdot \mathbf{V}^T \quad (16)$$

where $\mathbf{U}_0$ = reduced matrix of the left singular vectors
 $\mathbf{S}_0$ = reduced matrix of the singular values
 $\mathbf{V}$ = matrix of the right singular vectors

The components v_1 and v_2 can be obtained as follows:

$$\begin{pmatrix} v_1 \\ v_2 \end{pmatrix} = \mathbf{V} \cdot \mathbf{S}_0^{-1} \cdot \mathbf{U}_0^T \cdot \vec{n}_{crack} \quad (17)$$

The reconstruction in the 2D system leads to the transformed 2D crack normal:

$$\vec{n}_{crack,2D} = v_1 \cdot (\vec{q}_2 - \vec{q}_1) + v_2 \cdot (\vec{q}_3 - \vec{q}_1) \quad (18)$$

3.6 Computation of the crack width and the horizontal displacement

The crack width r is calculated by the projection of the relative translation vector (Eq. 11) onto the normal in 2D as shown in (Liebold, Maas, 2018):

$$r = \|\vec{t}_{rel,2D}\| \cdot \|\cos\beta\| = \frac{\vec{n}_{crack,2D}^T \cdot \vec{t}_{rel,2D}}{\|\vec{n}_{crack,2D}\|} \quad (19)$$

Furthermore, it is possible to compute the shift along the crack (in-plane displacement/shear). The absolute value is:

$$\|\vec{t}_{||}\| = \sqrt{\|\vec{t}_{rel,2D}\|^2 - r^2} \quad (20)$$

The direction vector in the 2D space without correct orientation (sign) is:

$$\vec{t}_{||,2D,temp} = \begin{pmatrix} -n_{crack,2D,y} \\ n_{crack,2D,x} \end{pmatrix} \quad (21)$$

The correct orientation can be obtained using the dot product to $\vec{t}_{rel,2D}$:

$$\vec{t}_{||,2D} = \begin{cases} \vec{t}_{||,2D,temp} & \text{if } \vec{t}_{rel,2D}^T \cdot \vec{t}_{||,2D,temp} > 0 \\ -\vec{t}_{||,2D,temp} & \text{else} \end{cases} \quad (22)$$

To get the direction in the 3D space, $\vec{t}_{||,2D}$ has to be transformed. First, the system of Eq. 23 has to be solved for $\vec{v}_1$ and $\vec{v}_2$. Then, the vector is reconstructed in 3D space and normalized (Eq. 24).

$$\begin{aligned} \vec{t}_{||,2D} &= \vec{v}_1 \cdot (\vec{q}_2 - \vec{q}_1) + \vec{v}_2 \cdot (\vec{q}_3 - \vec{q}_1) \\ &= \begin{pmatrix} \vec{q}_2 - \vec{q}_1 & \vec{q}_3 - \vec{q}_1 \end{pmatrix} \cdot \begin{pmatrix} \vec{v}_1 \\ \vec{v}_2 \end{pmatrix} \end{aligned} \quad (23)$$

$$\vec{t}_{||} = \frac{\vec{v}_1 \cdot \vec{s}_{12} + \vec{v}_2 \cdot \vec{s}_{13}}{\|\vec{v}_1 \cdot \vec{s}_{12} + \vec{v}_2 \cdot \vec{s}_{13}\|} \quad (24)$$

4. APPLICATION OF THE CRACK WIDTH DETERMINATION IN THE EXPERIMENT

4.1 Computation of the 3D displacements

The system calibration and the computation of the 3D displacements are done with the commercial software ARAMIS developed by GOM GmbH. The 3D coordinates and displacements serve as input for the application of the crack detection and crack width computation.

4.2 Crack detection and crack width analysis

The algorithm from section 3 is applied on the data. δ is set to 0.02 mm (corresponds to 0.2 px in image space) and defines the threshold for crack candidates.

Fig. 10 shows color-coded maps of the norms of the relative translations of the triangles for the first time steps where deformations could be detected. Therefore, the color-code is very sensitive. The widths are changing in the sequence. After 0.19 ms, the first cracks appear in the visualization. On the far left, there is an area where it is not sure if there is a crack. Later, this possible crack closes as other cracks open. The largest crack at time step of 0.20 ms closes in the following time steps too, whereas the neighbor cracks become larger.

Figure 10. Crack detection. Visualization of $\|\vec{t}_{rel,2D}\|$ for each triangle for some selected time steps at the begin of the crack opening.

Triangles with $\|\vec{t}_{rel,2D}\| > \delta$ can be merged to a region if there are neighbors that also fulfill this condition using region growing, see Fig. 11.

Fig. 12 and Fig. 13 show color-coded visualizations of the norms of the relative translation vectors $\|\vec{t}_{rel,2D}\|$ for two later epochs with 2 cracks. In addition, the histograms of the crack widths of the two crack areas are depicted. In these histograms, some statistical values are given: the mean of the crack widths $\bar{r}$, the median r_{median} , the maximum crack width r_{max} , the

Figure 11. Color-labeled regions of triangles with $\|\vec{t}_{rel,2D}\| > \delta$ at 0.22 ms.

standard deviation of the crack widths σ_r and the standard deviation $\sigma_{r,MAD}$ computed using the median absolute deviation (MAD) which is more robust against outliers.

$$\sigma_{r,med} = k \cdot \text{median} \left(\begin{pmatrix} \|r_1 - \text{median}(\vec{r})\| \\ \|r_2 - \text{median}(\vec{r})\| \\ \vdots \end{pmatrix} \right) \quad (25)$$

with

$$k = q_{0.75}^{-1} \approx 1.48$$

where

$\sigma_{r,med}$ = standard deviation computed with MAD

$\vec{r}$ = vector with the measured crack widths

q_p = quantile of order p for $\mathcal{N}(0, 1)$

$\mathcal{N}(0, 1)$ = standard normal distribution

Figure 12. Color-coded visualization of $\|\vec{t}_{rel,2D}\|$ for epoch 25 at 0.24 ms. For the two cracks, histograms of the crack widths are depicted. In addition, the original image of one camera is shown.

In the histograms, some outliers appear due to uncertainties in the normal vector computation at the borders of the mesh. Another reason for outliers are incorrect matching results that are influenced by cracks crossing matching patches. Therefore, in the neighborhood of crack triangles, there are some triangles that are also detected as crack candidates ($\|\vec{t}_{rel,2D}\| > \delta$) but have smaller values of $\|\vec{t}_{rel,2D}\|$.

The diagram in Fig. 14 shows 4 curves: the sum of the mean crack widths of the crack areas ($\sum r_{mean}$), the sum of medians ($\sum r_{median}$) and the sum of the maxima ($\sum r_{max}$). In addition, the total deformation of the sample that is calculated with the wave analysis in the split-Hopkinson tension bar is depicted ($\sum r_{waveanalysis}$) to compare the crack widths with another measurement method. The values of mean and median are strongly depending on the threshold δ which is set to 0.02 mm in this experiment because δ defines which

Figure 13. Color-coded visualization of $||\vec{t}_{rel,2D}||$ for epoch 29 at 0.28 ms. For the two cracks, histograms of the crack widths are depicted. In addition, the original image of one camera is shown.

triangles are considered as crack candidates. Crack widths according to $||\vec{t}_{rel,2D}|| \leq \delta$ are not included in the sums ($\sum r_{mean}$, $\sum r_{median}$ and $\sum r_{max}$). Because of that, the values tends to be smaller than the real value and smaller than $\sum r_{waveanalysis}$, too. In this experiment, there are no further external measurements to compare the results of the single crack width computation because it is very difficult to obtain single crack widths with other measurement techniques in high speed tension tests.

Figure 14. Diagram of the sum of crack widths.

Fig. 15 shows the mean standard deviations $\bar{\sigma}_r$ of the crack widths of each epoch where cracks are detected. Due to outliers, the mean standard deviation computed with the MAD $\bar{\sigma}_{r,MAD}$ is also plotted. $\bar{\sigma}_r$ increases with higher crack widths because the outliers are small (close to δ) and greater values are more influenced by these outliers. In contrast, $\bar{\sigma}_{r,MAD}$ is more or less stable over the time. $\bar{\sigma}_{r,MAD}$ is below 0.015 mm (corresponds to 0.15 px in image space) whereas $\bar{\sigma}_r$ reaches values up to 0.075 mm. Due to the outliers, $\bar{\sigma}_{r,MAD}$ should be preferred as a measure of precision.

Figure 15. Means of the standard deviations of the crack width areas for each epoch.

5. CONCLUSION AND OUTLOOK

This publication presents a strategy for detection of cracks on concrete specimens with non-planar surfaces in tension tests, and the computation of the according widths. A prerequisite is that deformations only appear tangential to the surface. The accuracy of the crack widths depends on the quality of the displacement field and is in the same order of magnitude. In our experiments, accuracies of approximately 0.01 mm were reached. The next step can be the development of an algorithm that can determine crack opening vectors for cracks with significant z-components. Further improvements should also allow to analyze arbitrary 3D surfaces.

ACKNOWLEDGEMENTS

The research work presented in this publication has been performed within the research training group GRK-2250 at TU Dresden funded by the German Research Council (DFG).

REFERENCES

- Barazzetti, L., Scaioni, M., 2009. Crack measurement: Development, testing and applications of an automatic image-based algorithm. *ISPRS Journal of Photogrammetry and Remote Sensing*, 64, 285–296.
- Dare, P., Hanley, H., Fraser, C., Riedel, B., Niemeier, W., 2002. An Operational Application of Automatic Feature Extraction: The Measurement of Cracks in Concrete Structures. *The Photogrammetric Record*, 17(99), 453–464. <http://dx.doi.org/10.1111/0031-868X.00198>.
- Görtz, S., 2004. Zum Schubrissverhalten von Stahlbeton- und Spannbetonbalken aus Normal- und Hochleistungsbeton. PhD thesis, RWTH Aachen.
- Hampel, U., Maas, H.-G., 2009. Cascaded image analysis for dynamic crack detection in material testing. *ISPRS Journal of Photogrammetry and Remote Sensing*, 64(4), 345–350.
- Heravi, A. A., Curosu, I., Mechtcherine, V., 2019. A gravity-driven split Hopkinson tension bar for investigating quasi-ductile and strain-hardening cement-based composites under tensile impact loading. *Cement and Concrete Composites*, n/a–n/a.
- Irwin, G. R., 1958. *Fracture*. Springer Berlin Heidelberg, Berlin, Heidelberg, 551–590.

Koschitzki, R., Schacht, G., Schneider, D., Marx, S., Maas, H.-G., 2011. Integration of photogrammetry and acoustic emission analysis for assessing concrete structures during loading tests. *Proceedings of SPIE Optical Metrology*, 8085, International Society for Optics and Photonics.

Lange, J., Benning, W., 2006. Crack detection using photogrammetry. *Proceedings of 9th European Conference on Non-Destructive Testing, Berlin*, BB 103-CD, NDT, German Society for Non-Destructive Testing, 1–8.

Liebold, F., Maas, H.-G., 2016. Advanced spatio-temporal filtering techniques for photogrammetric image sequence analysis in civil engineering material testing. *ISPRS Journal of Photogrammetry and Remote Sensing*, 111, 13–21.

Liebold, F., Maas, H.-G., 2018. Sub-pixel accuracy crack width determination on concrete beams in load tests by triangle mesh geometry analysis. *ISPRS Annals of Photogrammetry, Remote Sensing and Spatial Information Sciences*, IV-2, 193–200. <https://www.isprs-ann-photogramm-remote-sens-spatial-inf-sci.net/IV-2/193/2018/>.

Maas, H.-G., Hampel, U., 2006. Photogrammetric Techniques in Civil Engineering Material Testing and Structure Monitoring. *Photogrammetric Engineering and Remote Sensing*, 72(1), 39–45.

3.2 Berechnung des dreidimensionalen Rissöffnungsvektors bei gegebenem 3D-Verschiebungsfeld

Kapitel 3.2 (P.V) wurde im ISPRS Journal of Photogrammetry and Remote Sensing, Volume 164, 2020 (ISSN 0924-2716) veröffentlicht als:

Photogrammetric determination of 3D crack opening vectors from 3D displacement fields

Titel in Deutsch:

Photogrammetrische Bestimmung des 3D-Rissöffnungsvektors aus 3D-Verschiebungsfeldern

Autoren:

Liebold, F.¹, Maas, H.-G.¹, Deutsch, J.²

¹ Technische Universität Dresden, Institut für Photogrammetrie und Fernerkundung

² Technische Universität Dresden, Institut für Werkzeugmaschinenentwicklung und adaptive Steuerungen

Publikationsverlauf:

eingereicht Februar 2020, angenommen März 2020, publiziert April 2020

Vollständige Referenz:

Liebold, F., Maas, H.-G., Deutsch, J., 2020. Photogrammetric determination of 3D crack opening vectors from 3D displacement fields. *ISPRS Journal of Photogrammetry and Remote Sensing*, 164, 1-10.

DOI:

<https://doi.org/10.1016/j.isprsjprs.2020.03.019>

Contents lists available at ScienceDirect

ISPRS Journal of Photogrammetry and Remote Sensing

journal homepage: www.elsevier.com/locate/isprsjprs

Photogrammetric determination of 3D crack opening vectors from 3D displacement fields

F. Liebold^{a,*}, H.-G. Maas^a, J. Deutsch^b^a Institute of Photogrammetry and Remote Sensing, Technische Universität Dresden, D-01062, Germany^b Institute of Mechatronic Engineering, Technische Universität Dresden, D-01062, Germany

ARTICLE INFO

Keywords:

Material testing

Image sequence analysis

Deformation measurement

Crack analysis

ABSTRACT

This publication presents a procedure for the determination of all three components of crack opening vectors from stereoscopic image sequences of a specimen under load in civil engineering material testing. The method is based on analyzing stereoscopic image sequences of a concrete specimen with a surface texture, which is suitable for applying image matching techniques. Spatio-temporal correspondences are established by applying sub-pixel accuracy area based image matching techniques to a grid of surface points. Data acquisition starts at zero load. The load is stepwise or continuously increased during the experiment. The surface points are matched between the stereo images and tracked through each camera image sequence. As an intermediate result, we obtain a set of 3D object surface points for each epoch by spatial intersection. These 3D object points are triangulated into a mesh. Then, the mesh triangles are tested for deformations by transforming the triangles into 2D space and computing the norm of the 2D relative translation vector. Connected components of deformed triangles are determined and crack normals are computed. In the next step, the 3D relative translation vector can be derived for each deformed triangle. Defining local crack opening coordinate systems for the deformed triangles, the three components of the crack opening vectors can be computed. The method has been tested and validated in practical experiments. The technique is capable of quantitatively analyzing cracks with a width of less than one pixel in image space.

1. Introduction

In civil engineering material testing, the detection of deformations especially cracks and their widths are very important issues for the civil engineers. Fig. 1 shows 2 example images of a material test with a cylindric specimen under tension load where Fig. 1a depicts the reference image under zero load and Fig. 1b shows a later epoch with 2 cracks.

Classical methods as inductive displacement transducers or strain gauges offer only point-wise measurements whereas photogrammetric methods are able to observe contactless an extensive area with high accuracy. Several photogrammetric crack measurement techniques have been investigated in recent years. If single images should be analyzed, edge detection methods can be used to determine crack widths. The application of the Fly-Fisher algorithm and Routefinder algorithm can be performed to find crack courses and their widths can be computed by the analysis of perpendicular profiles (Dare et al., 2002). Other techniques base on the analysis of image sequences that

allow the comparison of a deformed state to an undeformed state. Benning et al. (2004) used a trinocular camera system to record image sequences during load tests with concrete specimens. First, displacements of a grid of artificial targets on the surface of the specimens were determined. Then, crack widths were computed using a method given by Görtz (2004) that calculates the crack widths in 4-point elements where rotations between the epochs were not considered. Lange and Benning (2006) proposed to use a Helmert transformation before computing the crack widths. Lange and Benning (2006) also described the modes of fracture according to Irwin (1958) and defined the crack opening vector $\vec{t}_c$ as follows:

$$\vec{t}_c = \begin{pmatrix} \text{crack width} \\ \text{crack edge displacement along crack course} \\ \text{vertical crack edge displacement} \end{pmatrix} \quad (1)$$

Maas and Hampel (2006) and Hampel and Maas (2009) used a stereo camera system to compute dense displacement fields. Crack widths were derived from the analysis of profiles through the displacement

* Corresponding author.

E-mail addresses: frank.liebold@tu-dresden.de (F. Liebold), hans-gerd.maas@tu-dresden.de (H.-G. Maas), jessica.deutsch@tu-dresden.de (J. Deutsch).URL: <http://photo.geo.tu-dresden.de> (F. Liebold).<https://doi.org/10.1016/j.isprsjprs.2020.03.019>

Received 18 February 2020; Received in revised form 30 March 2020; Accepted 30 March 2020

0924-2716/ © 2020 International Society for Photogrammetry and Remote Sensing, Inc. (ISPRS). Published by Elsevier B.V. All rights reserved.

Fig. 1. (a) Image under zero load of cylindric specimen; (b) image of a later epoch with 2 cracks. The length of the textured area on the specimen is approximately 4 cm.

Fig. 2. (a) Color-coded visualization of $\|\vec{t}_{rel,2D}\|$; (b) 2 connected components of deformed triangles. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

field. Barazzetti and Scaioni (2009) computed crack widths in monocular image sequences with artificial targets and an orientation frame. Liebold and Maas (2018) also analyzed monocular image sequences of concrete specimens with planar surfaces. The displacements of a random pattern with suitable texture were determined using least-squares matching. The matching points were triangulated into a mesh. 2D crack opening vectors were obtained by a triangle analysis where rotations between the epochs were considered. Liebold et al. (2019) analyzed deformations of cylindric specimens using a stereo camera system and adapted the algorithm of Liebold and Maas (2018) to obtain crack widths on the non-planar surface with triangulated 3D object points. However, the algorithm only works for tangential deformations (no vertical displacements). Fig. 2 shows a color-coded visualization of the deformation quantity $\|\vec{t}_{rel,2D}\|$ (Fig. 2a) as well as the connected components of deformed triangles (Fig. 2b) computed with the algorithm of Liebold et al. (2019) for the cylindric specimen with tangential deformations from Fig. 1.

This publication proposes an extended algorithm that is able to compute crack opening vectors with significant vertical components and continues the work of Koschitzki et al. (2011), Liebold and Maas (2016, 2018) and Liebold et al. (2019).

The next section presents the algorithm for the determination of the 3D crack opening vectors. After this, an application in a torsion experiment is shown. The following section deals with a validation measurement to prove the algorithm and at the end a conclusion is given.

Fig. 3. Matching in the stereo image pair and between epochs as well as triangulation into a mesh. In this example, the specimen is a cylinder with a non-planar surface.

2. 3D crack opening vector

2.1. Image analysis and computation of displacements

First, the inner and relative orientation of the stereo system is determined in a system calibration. Then, a stereo image sequence is recorded of a specimen that is deformed in a load test. The first image pair should be recorded from an undeformed state under zero load. The left image of the first epoch is the master image where a grid of points is defined. The corresponding points in the right image and in the stereo images of each of the following epochs are computed with the sub-pixel accurate least-squares matching method (Ackermann, 1984) such that spatio-temporal correspondences are established. The 3D coordinates of the corresponding points of the stereo pairs are calculated by intersection for each time step. For the proof of consistency between the stereo image pair, the intersection deviation is checked by applying a threshold. Fig. 3 illustrates the image pairs of two time steps and also the intersection.

2.2. Detection of deformed triangles

The 3D coordinates that are obtained in the previous step are triangulated into a mesh as it is also shown in Fig. 3. The triangles are now tested for deformations of their inner geometry. To detect extended triangles for brittle materials, the norm of the relative translation vector in 2D space is computed, as it is done by Liebold et al. (2019). An optimized short overview is given in the following: The first step is the calculation of the edge vectors $\vec{s}_{ref,ij}$ and $\vec{s}_{ij}$ between the triangle vertices $\vec{p}_{ref,i}$ as well as $\vec{p}_i$ for the reference and the deformed state:

$$\begin{aligned}\vec{s}_{ref,ij} &= \vec{p}_{ref,j} - \vec{p}_{ref,i} \\ \vec{s}_{ij} &= \vec{p}_j - \vec{p}_i \\ \forall (i, j) &\in \{(1, 2), (1, 3), (2, 3)\}\end{aligned}\quad (2)$$

It is assumed that one of the triangle edges is stress-free and should have a constant length between the reference and the deformed state because the material is strain-relieved next to the crack opening. Therefore, the edge with the minimal distance change is considered as the constant base line edge with the vertex indices b_1 and b_2 :

$$b_1, b_2 = i_{min}, j_{min} = \underset{i,j}{\operatorname{argmin}} \quad \|\vec{s}_{ij}\| - \|\vec{s}_{ref,ij}\| \quad (3)$$

The remaining index is labeled with up . The vertex coordinates of the deformed state are transformed into the 2D space such that the first

base line vertex defines the origin and the base edge defines the x axis:

$$\begin{aligned}\vec{q}_{b1} &= (0 \ 0) \\ \vec{q}_{b2} &= (\|\vec{s}_{b1,b2}\| \ 0) \\ \vec{q}_{up} &= (dx_{b1,up} \ dy_{b1,up})\end{aligned}\quad (4)$$

$$\text{where } dx_{b1,up} = \left\| \vec{s}_{b1,up} \right\| \cdot \cos(\angle(\vec{s}_{b1,b2}, \vec{s}_{b1,up})) = \frac{\vec{s}_{b1,b2}^T \vec{s}_{b1,up}}{\|\vec{s}_{b1,b2}\|}$$

$$dy_{b1,up} = \sqrt{\|\vec{s}_{b1,up}\|^2 - dx_{b1,up}^2}$$

For the reference state, the vertex coordinates are also transformed to 2D ($\vec{q}_{ref,i,t}$) such that the center points of the base edges coincide to fulfill the rigid transformation between the base edges of the reference and deformed state:

$$\begin{aligned}\vec{q}_{ref,b1,t} &= \left(\frac{1}{2} \cdot \|\vec{s}_{b1,b2}\| - \frac{1}{2} \cdot \|\vec{s}_{ref,b1,b2}\| \ 0 \right) \\ \vec{q}_{ref,b2,t} &= \left(\frac{1}{2} \cdot \|\vec{s}_{b1,b2}\| + \frac{1}{2} \cdot \|\vec{s}_{ref,b1,b2}\| \ 0 \right) \\ \vec{q}_{ref,up,t} &= \vec{q}_{ref,b1,t} + (dx_{ref,b1,up} \ dy_{ref,b1,up})\end{aligned}\quad (5)$$

$$\text{where } dx_{ref,b1,up} = \frac{\vec{s}_{ref,b1,b2}^T \vec{s}_{ref,b1,up}}{\|\vec{s}_{ref,b1,b2}\|}$$

$$dy_{ref,b1,up} = \sqrt{\|\vec{s}_{ref,b1,up}\|^2 - dx_{ref,b1,up}^2}$$

Fig. 4 shows the transformed triangles of the reference and the deformed state with coinciding base lines.

The 2D relative translation vector is computed by the difference of the coordinates of the upper vertex:

$$\vec{t}_{rel,2D} = \vec{q}_{up} - \vec{q}_{ref,up,t} \quad (6)$$

The norm of the relative translation vector $\|\vec{t}_{rel,2D}\|$ is a quantity for the detection of deformed triangles including cracks and is proposed for brittle material. Crack candidates are triangles where $\|\vec{t}_{rel,2D}\| > \delta$ is fulfilled. Fig. 5 illustrates an example of deformed triangles (red). The undeformed triangles have a blue color.

The threshold δ depends on the quality of the displacement field and should be in the order of magnitude of the precision of the 3D object coordinates. As a rule of thumb, the object distance that corresponds to 0.1 px in image space is proposed.

There are also some exceptions, for example in case of crack tips or crack crossings such that the assumption of one stress-free edge is not valid. However, the algorithm should also work for these special cases.

2.3. 3D relative translation vector

The 3D relative translation vector $\vec{t}_{rel}$ is computed as an important interim result for each deformed triangle similar to the 2D case. This allows to measure vertical displacements in contrast to the work of

Fig. 4. Transformed reference as well as deformed triangle. r is the crack width (perpendicular distance). According to Liebold et al. (2019) and Liebold and Maas (2018).

Fig. 5. Deformed triangles where $\|\vec{t}_{rel,2D}\| > \delta$.

Fig. 6. (a) block in the undeformed state with a triangle on the surface. The crack is indicated; (b) broken block with 3D shift of the right part. The triangle is split into two parts. $\vec{t}_{rel}$ is shown for the right vertex. x_c, y_c, z_c : components of the crack opening vector.

Liebold et al. (2019). Then in a later step, the 3D crack opening vector $\vec{t}_c$ can be derived from $\vec{t}_{rel}$ for each deformed triangle. Fig. 6a shows a block with a triangle and its vertices on the surface. A crack is fore-shadowed. In Fig. 6b, the block is broken and the right part is shifted such that the triangle is split into two parts. The 3D relative translation vector $\vec{t}_{rel}$ is drawn.

2.3.1. Model

Due to the crack opening, the points near the crack can be split into two parts (set M_1 and set M_2), see Fig. 7. For both sides of the crack, the model includes a 3D translation $\vec{t}$ and a 3D rotation $\mathbf{R}$ (rigid transformation). The relative movement of the right part is modeled with a 3D relative translation vector $\vec{t}_{rel}$ that is added for the points of set M_2 ,

Fig. 7. Broken block with 2 sets of vertices on each crack side. x_c, y_c, z_c : components of the crack opening vector.

see Eq. (7). A relative rotation is not considered in this approach.

$$\vec{p}_j = \begin{cases} \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j} & \forall j \in M_1 \\ \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j} + \vec{t}_{rel} & \forall j \in M_2 \end{cases} \quad (7)$$

where $\vec{p}_{ref,j}$ = coordinates of the undeformed epoch
 $\vec{p}_j$ = coordinates of the deformed epoch

The rotation matrix is parametrized with quaternions (a, b, c, d):

$$\mathbf{R} = \begin{pmatrix} d^2 + a^2 - b^2 - c^2 & 2 \cdot a \cdot b - 2 \cdot c \cdot d & 2 \cdot a \cdot c + 2 \cdot b \cdot d \\ 2 \cdot a \cdot b + 2 \cdot c \cdot d & d^2 + b^2 - a^2 - c^2 & 2 \cdot b \cdot c - 2 \cdot a \cdot d \\ 2 \cdot a \cdot c - 2 \cdot b \cdot d & 2 \cdot b \cdot c + 2 \cdot a \cdot d & d^2 + c^2 - a^2 - b^2 \end{pmatrix} \quad (8)$$

subject to $a^2 + b^2 + c^2 + d^2 = 1$.

2.3.2. Clustering

Before the computation of the relative translation vector and other further steps can be done, it is necessary to know which point belongs to which set. In contrast to the 2D method, it is not enough to use only the vertices of the deformed triangle (Fig. 6). Due to the 3D rigid transformation, more than 2 points are needed to calculate its parameters. There are different ways for the classification. One possible method is called 'base triangle method' in this publication. First, the triangle edge with minimal distance change between the reference and the deformed epoch is determined. It is already done in the step of detection of the deformed triangles, see Eq. (3). The vertices of the undeformed neighbor triangle with the same edge belong to the set $M_1 = \{b_1, b_2, b_3\}$. The left over vertex of the deformed triangle belongs to set $M_2 = \{up\}$, see Fig. 8. This method contains minimal object information.

The second proposed classification method uses more points in the neighborhood. The neighbor triangles of the deformed triangle, for that $\vec{t}_{rel}$ should be computed, are obtained. Then, connected components of the undeformed neighbor triangles are determined, see Fig. 9. If the deformed triangle is not near the crack tip and is not a node of a union of 2 or more cracks, 2 sets of connected components should be found. The corresponding vertices of the 2 sets of neighbor triangles (green and yellow in Fig. 9) belong to the sets of points M_1 (magenta) and M_2 (cyan).

As already mentioned, there are some exceptions, for instance crack crossings or boundary triangles. For such cases, classification can fail and $\vec{t}_{rel}$ cannot be computed.

2.3.3. Computation using least-squares adjustment

Both presented clustering methods lead to an overdetermination. Because of that, the least-squares method is used to compute the unknowns and residuals $\vec{v}_j$ are added to Eq. (7):

$$\vec{p}_j + \vec{v}_j = \begin{cases} \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j} & \forall j \in M_1 \\ \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j} + \vec{t}_{rel} & \forall j \in M_2 \end{cases} \quad (9)$$

The coordinates of the deformed epoch are considered as observations

Fig. 8. Deformed triangle shown in red and the corresponding undeformed neighbor triangle of the base edge depicted in green. $\vec{p}_{ref,j,t} = \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j}$. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

Fig. 9. Deformed triangle, for which $\vec{t}_{rel}$ should be computed, is shown in strong red. The green triangles are neighbor triangles whose vertices belong to M_1 . The yellow triangles are neighbor triangles whose vertices belong to M_2 . (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

and $\vec{t}$, $\mathbf{R}$ as well as $\vec{t}_{rel}$ are unknowns. Furthermore, there is a constraint for the quaternions:

$$a^2 + b^2 + c^2 + d^2 = 1 \quad (10)$$

The next step is the linearization of the observation equations. Only the quaternions are non-linear in the equations such that Taylor's theorem is only applied on them:

$$\vec{l}_j + \vec{v}_j = \begin{cases} \vec{t} + d\mathbf{R} \cdot \vec{p}_{ref,j} & \forall j \in M_1 \\ \vec{t} + d\mathbf{R} \cdot \vec{p}_{ref,j} + \vec{t}_{rel} & \forall j \in M_2 \end{cases}$$

with $\vec{l}_j = \vec{p}_j - \mathbf{R}_0 \cdot \vec{p}_{ref,j}$ and

$$d\mathbf{R} = \left\{ \frac{\partial \mathbf{R}}{\partial a} da + \frac{\partial \mathbf{R}}{\partial b} db + \frac{\partial \mathbf{R}}{\partial c} dc + \frac{\partial \mathbf{R}}{\partial d} dd \right\} \quad (11)$$

where $\vec{l}_j$ = reduced observation of $\vec{p}_j$
 $\mathbf{R}_0$ = initial rotation matrix

$\mathbf{R}_0$ is computed using the initial values of the quaternions (a_0, b_0, c_0, d_0). The linearized constraint equation is:

$$a_0^2 + b_0^2 + c_0^2 + d_0^2 + 2 \cdot (a_0 \cdot da + b_0 \cdot db + c_0 \cdot dc + d_0 \cdot dd) = 1 \quad (12)$$

The vector of unknowns can be expressed as follows:

$$\mathbf{x} = \left(\vec{t}^T \ a \ b \ c \ d \ \vec{t}_{rel}^T \right)^T \quad (13)$$

It is composed of the initial vector of the unknowns $\mathbf{x}_0$ and the corrections $d\mathbf{x}$:

$$\mathbf{x} = \mathbf{x}_0 + d\mathbf{x}$$

$$\mathbf{x}_0 = (0 \ 0 \ 0 \ a_0 \ b_0 \ c_0 \ d_0 \ 0 \ 0 \ 0)^T$$

$$d\mathbf{x} = \left(\vec{t}^T \ da \ db \ dc \ dd \ \vec{t}_{rel}^T \right)^T \quad (14)$$

The linearized observation equations can be written in matrix notation:

$$\mathbf{A} \cdot d\mathbf{x} = \mathbf{l} + \mathbf{v} \text{ subject to } \mathbf{B} \cdot d\mathbf{x} = \mathbf{w} \quad (15)$$

$\mathbf{l}$ = reduced observation vector

$\mathbf{v}$ = residual vector.

where $\mathbf{A}$ = Jacobian matrix.

$\mathbf{B}$ = condition matrix.

$\mathbf{w}$ = vector of inconsistencies.

The Jacobian matrix is expressed in Eq. (16). The upper submatrix contains the terms for the set M_1 , the lower matrix the terms for the set M_2 . n is the number of the points used for the computation and is also the cardinality of the union of set M_1 and set M_2 . $n_1 = \#M_1$ is the cardinality of the set M_1 .

$$\mathbf{A} = \begin{pmatrix} \mathbf{I}_{3 \times 3} & \frac{\partial \mathbf{R}}{\partial a} \cdot \vec{p}_{ref,1} & \dots & \frac{\partial \mathbf{R}}{\partial d} \cdot \vec{p}_{ref,1} & \mathbf{0}_{3 \times 3} \\ \vdots & \vdots & \vdots & \vdots & \vdots \\ \mathbf{I}_{3 \times 3} & \frac{\partial \mathbf{R}}{\partial a} \cdot \vec{p}_{ref,n_1} & \dots & \frac{\partial \mathbf{R}}{\partial d} \cdot \vec{p}_{ref,n_1} & \mathbf{0}_{3 \times 3} \\ \vdots & \vdots & \vdots & \vdots & \vdots \\ \mathbf{I}_{3 \times 3} & \frac{\partial \mathbf{R}}{\partial a} \cdot \vec{p}_{ref,n_1+1} & \dots & \frac{\partial \mathbf{R}}{\partial d} \cdot \vec{p}_{ref,n_1+1} & \mathbf{I}_{3 \times 3} \\ \vdots & \vdots & \vdots & \vdots & \vdots \\ \mathbf{I}_{3 \times 3} & \frac{\partial \mathbf{R}}{\partial a} \cdot \vec{p}_{ref,n} & \dots & \frac{\partial \mathbf{R}}{\partial d} \cdot \vec{p}_{ref,n} & \mathbf{I}_{3 \times 3} \end{pmatrix} \quad (16)$$

where $\mathbf{I}$ =identity matrix

$\mathbf{0}$ =zero matrix

The reduced observation vector is:

$$\mathbf{l} = \begin{pmatrix} \vec{p}_1 - \mathbf{R}_0 \cdot \vec{p}_{ref,1} \\ \vdots \\ \vec{p}_n - \mathbf{R}_0 \cdot \vec{p}_{ref,n} \end{pmatrix} \quad (17)$$

The condition matrix $\mathbf{B}$ and the vector of inconsistencies $\mathbf{w}$ are expressed in Eq. (18).

$$\mathbf{B} = 2 \cdot (0 \ 0 \ 0 \ a_0 \ b_0 \ c_0 \ d_0 \ 0 \ 0 \ 0) \\ \mathbf{w} = (1 - a_0^2 - b_0^2 - c_0^2 - d_0^2) \quad (18)$$

To minimize the residuals in Eq. (15), the Gauss–Markov model is extended with the method of the Lagrange multipliers $\mathbf{k}$:

$$\Omega = \mathbf{v}^T \cdot \mathbf{v} + 2 \cdot \mathbf{k}^T \cdot (\mathbf{B} \cdot \mathbf{dx} - \mathbf{w}) \rightarrow \min_{\mathbf{dx}} \quad (19)$$

To solve this, the extended normal equations are used (Eq. (20)). The parameters of $\vec{t}$ and $\vec{t}_{rel}$ can be found directly in $\mathbf{dx}$.

$$\begin{pmatrix} \mathbf{A}^T \cdot \mathbf{A} & \mathbf{B}^T \\ \mathbf{B} & \mathbf{0} \end{pmatrix} \cdot \begin{pmatrix} \mathbf{dx} \\ \mathbf{k} \end{pmatrix} = \begin{pmatrix} \mathbf{A}^T \cdot \mathbf{l} \\ \mathbf{w} \end{pmatrix} \quad (20)$$

It is also possible to weight the observations, especially if the second classification method is used. The weight could depend on the distance to the center point $\vec{p}_m$ of the triangle, for that $\vec{t}_{rel}$ is computed:

$$g_j = \exp \left(-\frac{\|\vec{p}_j - \vec{p}_m\|^2}{\alpha^2} \right) \quad (21)$$

where g_j =weight of vertex j

α = distance where the weight gets $\frac{1}{e}$

2.3.4. Orientation of the relative translation vector

Connected components of deformed triangles may have $\vec{t}_{rel}$ with different orientations which means that they have different signs. The direction depends on the side of the crack on which the vertices of the set M_1 are. In Fig. 10, the case of $\vec{t}_{rel}$ vectors with opposite directions is illustrated. For the leftest crack candidate, the base triangle (with the vertices of set M_1) is on left side of the crack and for the adjacent crack candidate, the base triangle is on the other side. This leads to relative

Fig. 10. The direction of the $\vec{t}_{rel}$ vectors of five neighboring deformed triangles is shown. The $\vec{t}_{rel}$ vectors have opposite directions that depend on the side of the crack on which the base triangle (and also the set M_1) is.

translation vectors with opposite directions and so on.

To orient the vectors in a consistent way, an adapted method of Hoppe et al. (1992) is applied. First, a graph is built. The graph contains the triangle center points to the corresponding $\vec{t}_{rel}$ vectors of one connected component of deformed triangles as nodes. The edges of the graph are either edges between neighboring triangles or the edges of a Riemannian graph. For each edge, a cost c_{ij} is defined depending on the cosine between neighboring $\vec{t}_{rel,i}$ and $\vec{t}_{rel,j}$:

$$c_{ij} = 1 - \frac{\left\| \frac{\vec{t}_{rel,i}^T \cdot \vec{t}_{rel,j}}{\|\vec{t}_{rel,i}\| \cdot \|\vec{t}_{rel,j}\|} \right\|}{\|\vec{t}_{rel,i}\| \cdot \|\vec{t}_{rel,j}\|} \quad (22)$$

The orientation of the $\vec{t}_{rel}$ vectors is propagated along the minimum spanning tree connecting the neighboring nodes. $\vec{t}_{rel,j}$ is replaced with $-\vec{t}_{rel,j}$ if $\vec{t}_{rel,j} \cdot \vec{t}_{rel,i} < 0$ where $\vec{t}_{rel,i}$ is an oriented neighbor.

2.3.5. Alternative detection of deformed triangles

Section 2.2 already shows a way to determine deformed triangles analyzing the inner geometry of the triangle using $\|\vec{t}_{rel,2D}\|$. If only (small) vertical displacements appear, the algorithm will possibly not detect the corresponding triangles as deformed (false negatives). Another quantity for the detection is the direct use of $\|\vec{t}_{rel}\|$ computed with the 'base triangle method' for each triangle. However, there also appear errors if the base triangle is deformed such that there are false positives. The combination of both strategies is a possible way to exclude false positives and false negatives. The following algorithm is suggested:

- $\vec{t}_{rel}$ is computed using the 'base triangle method' for each triangle and possibly deformed triangles are detected where $\|\vec{t}_{rel}\| > \delta_1$ (δ_1 : threshold). $\|\vec{t}_{rel,2D}\|$ is also calculated.
- For each deformed triangle, the deformed 2nd order neighboring triangles are determined and the median $\tilde{x}$ of $\|\vec{t}_{rel}\|$ including the candidate itself is computed. In addition, the median absolute deviation MAD is used to calculate the robust standard deviation $\sigma = 1.48 \cdot MAD$.
- For each deformed triangle, if $|\|\vec{t}_{rel}\| - \tilde{x}| > 3 \cdot \sigma$ and if $\|\vec{t}_{rel,2D}\| < \delta_2$, the triangle is filtered out from the potentially deformed triangles (δ_2 : second threshold with $\delta_2 \lesssim \delta_1$).

2.4. Transformation to the crack opening vector

The vector $\vec{t}_{rel}$ is defined in the coordinate system of the deformed state. The crack opening vector $\vec{t}_c$ can be obtained by a rotation of $\vec{t}_{rel}$. The rotation matrix $\mathbf{R}_c$ is composed of the crack normal direction $\vec{n}_{crack}$ (x direction), the direction vector along the crack course $\vec{t}_\parallel$ (y direction) and the vertical direction of the crack edge displacement $\vec{t}_\perp$ (z direction), see Eq. (23). x_c , y_c and z_c are the components of the crack opening vector. x_c is the crack width, y_c is the in-plane shear component and z_c is the out-of-plane shear component (vertical component).

$$\vec{t}_c = \begin{pmatrix} x_c \\ y_c \\ z_c \end{pmatrix} = \mathbf{R}_c^T \cdot \vec{t}_{rel} = \begin{pmatrix} \vec{n}_{crack} & \vec{t}_\parallel & \vec{t}_\perp \end{pmatrix}^T \cdot \vec{t}_{rel} \quad (23)$$

The origin of the crack opening coordinate system is not known. As an approximation, the origin is shifted to the center of the deformed triangle. Fig. 11a illustrates the coordinate system of the crack opening and Fig. 11b shows the decomposition of $\vec{t}_{rel}$ into the components of $\vec{t}_c$ in the crack opening coordinate system.

In the next subsections, some methods will be given to obtain $\vec{n}_{crack}$, $\vec{t}_\parallel$ and $\vec{t}_\perp$.

2.4.1. Crack course direction

The first intermediate step is the estimation of direction of the crack course according to Liebold and Maas (2018) and Liebold et al. (2019).

Fig. 11. (a) crack opening coordinate system. The triangle, for that $\vec{t}_c$ is computed, is depicted in strong red. $\vec{n}_{crack}$ is the x direction of the crack opening, $\vec{t}_\perp$ is the z direction (vertical), $\vec{t}_\parallel$ is perpendicular to $\vec{t}_\perp$ and $\vec{n}_{crack}$. $\vec{t}$ points in the crack course direction; (b) $\vec{t}_{rel}$ decomposed in the components of $\vec{t}_c$. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

Fig. 12. Crack course direction $\vec{t}$ obtained by a line fit through the center points of neighboring deformed triangles.

Fig. 12 shows the principle of the estimation. For each deformed triangle, the deformed triangles of the 2nd order neighborhood (neighbors and neighbors of neighbors) are determined. Then, a line fit through the center points is performed. The direction of line is labeled with $\vec{t}$.

An alternative similar way to estimate the crack course $\vec{t}$ is a line fit through the center points of the edges to neighboring deformed triangles instead of the center points of the triangles itself, see Fig. 13.

At the boundaries of the mesh, $\vec{t}$ is not reliable because there are less deformed neighbors. These triangles should be considered carefully. Border triangles can be determined easily using a half-edge data structure for the triangle mesh. If a deformed triangle has a halfedge where no opposite partner halfedge exists, the triangle is at the boundary of the mesh. Crack crossings can also have a bad influence on the determination of $\vec{t}$ such that they also should be considered carefully. Crossings of deformed triangles can be detected by the analysis of the neighborhood. If there are more than 2 connected components of undeformed neighboring triangles, the triangle can be considered as a crossing. Fig. 14 illustrates a case of a crack crossing where the highlighted blue triangles with the yellow, green and magenta borders are three connected components of undeformed neighbors. The red triangles are the deformed triangles crossed by cracks (black lines).

2.4.2. Crack normal determination

The vertical direction of the crack opening coordinate system is

Fig. 13. Crack course direction $\vec{t}$ obtained by a line fit through the center points of the edges of the neighboring deformed triangles.

Fig. 14. Crack crossing triangle (strong red) with 3 connected components of undeformed neighbor triangles (highlighted blue triangles with yellow, green and magenta boundary). The other red triangles are deformed whereas the blue triangles are undeformed. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

perpendicular to the plane of the points of set M_i , in which the crack normal $\vec{n}_{crack}$ lays. For the 'base triangle method', the vertical direction is obtained by computing the normal of the base triangle:

$$\vec{t}_\perp = \frac{(\vec{p}_{b2} - \vec{p}_{b1}) \times (\vec{p}_{b3} - \vec{p}_{b1})}{\|(\vec{p}_{b2} - \vec{p}_{b1}) \times (\vec{p}_{b3} - \vec{p}_{b1})\|} \quad (24)$$

For the alternative classification method, a plane fit of the vertices of the set M_i is performed to get $\vec{t}_\perp$ as the normal of this plane.

$\vec{t}$ and $\vec{t}_\perp$ are used to determine the crack normal $\vec{n}_{crack}$, see Eq. (25). As shown in Fig. 15, $\vec{t}$, $\vec{t}_\perp$ and $\vec{t}_\parallel$ are in the same plane and $\vec{n}_{crack}$ is perpendicular to this plane. Another application of the cross product leads to the last column vector of the rotation matrix $\mathbf{R}_c$, that defines the y direction $\vec{t}_\parallel$, see Eq. (26).

$$\vec{n}_{crack} = \frac{\vec{t}_\perp \times \vec{t}}{\|\vec{t}_\perp \times \vec{t}\|} \quad (25)$$

$$\vec{t}_\parallel = \vec{t}_\perp \times \vec{n}_{crack} \quad (26)$$

Using Eq. (23), the relative translation vector $\vec{t}_{rel}$ is transformed to the crack opening vector $\vec{t}_c$.

3. Application in an experiment

The algorithm (using the 'base triangle method') is tested in a torsion test that is conducted on a bone-shaped composite specimen with a planar surface (Curosu et al., 2017). The experiment is observed with a stereo camera system. The system calibration of the stereo system and

Fig. 15. Determination of the crack normal $\vec{n}_{crack}$. The triangle, for that $\vec{t}_c$ is computed, is depicted in red. The base triangle is colored green. $\vec{p}_{j,ref,t} = \vec{t} + \mathbf{R}_c \vec{p}_{j,ref}$. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

Fig. 16. (a) color-coded visualization of $\|\vec{t}_{rel,2D}\|$ for each triangle. (b) visualization of $\vec{t}_{rel}$ (magenta, scale factor 5) for the deformed triangles; (c) components of $\vec{t}_c$ (x_c : red, y_c : green, z_c : blue, scale factor 5).

the determination of 3D displacements are performed with the commercial software VIC-3D from the company Correlated Solutions, Inc (version 8, <https://correlatedsolutions.com>). The measuring area is 12 cm $\times$ 4 cm that corresponds to 1200 $\times$ 400 px in image space. The grid size of the matching points is set to 7 px. Systematic errors due to relative rotations caused by the torsion of the specimen are ignored. For the detection of deformed triangles, the algorithm of Section 2.2 is used where δ is set to 0.025 mm.

Fig. 16a depicts a color-coded visualization of the $\|\vec{t}_{rel,2D}\|$ values. A large vertical displacement is visible for the crack with the red triangles. Fig. 16b shows the $\vec{t}_{rel}$ vectors exaggerated with a scale factor of five for the deformed triangles whereas Fig. 16c depicts the components of $\vec{t}_c$ vectors (x : red, y : green, z : blue, scale factor: 5). The $\vec{t}_{rel}$ vectors as well as the z components of the $\vec{t}_c$ vectors show clearly that a torsion is applied on the specimen. Some wrong components are visible at the border of the mesh and at nodes of crack crossings as a consequence of errors in the crack course determination as it is already described in Section 2.4.1.

4. Validation measurement

To validate the algorithm, an experimental setup with two plates (each with 10 cm $\times$ 8 cm) connected with a microscope stage is designed, see Fig. 17.

One of these two plates is connected to a part of the microscope stage that can only be shifted in the vertical direction (z direction). This shift is measured with an inductive displacement transducer (LVDT, Fig. 18a) with a maximum permissible error of $0.4 \mu\text{m} + 0.8 \cdot L \mu\text{m}$ (L in mm). The other plate is fixed with a part of the microscope stage that can be shifted in both horizontal directions (x and y) using two micrometer screw gauges with a resolution of 0.01 mm (Fig. 18b). The maximum permissible error is not known but a typical value is $4 \mu\text{m}$ for micrometer screw gauges of a range of 25 mm.

The tops of both plates are signalized with a random pattern and the relative movements are observed by a stereo camera system consisting of 2 cameras of the type AVT Manta G-125 with CCD sensors that have a resolution of 1292 $\times$ 964 px and a pixel pitch of $3.75 \mu\text{m}$. Thus, 1 px in

Fig. 17. Experimental setup.

Fig. 18. (a) inductive displacement transducer (LVDT) for the measurement of the vertical shift; (b) micrometer screw gauge.

image space corresponds to approximately 0.1 mm in object space. The accuracy of the micrometer screw gauges and the LVDT is thus in the same order of magnitude as the expected accuracy of the measurements from the stereo camera.

$4 \times 4 \times 8$ different relative positions of the plates (in x , y , z) are performed. 4×4 measurements in the x - y -plane at 8 levels of heights. The specified order of the measurements in the x - y -plane is shown in Fig. 19. The first measurement is defined as reference (undeformed) epoch such that $4 \times 4 \times 8 - 1$ relative shifts (also called epochs) could be analyzed.

The x and y shifts are measured with the 2 micrometer screw gauges and the z shifts are measured using the LVDT. These values are considered as expected values. The system calibration of the stereo cameras and the computation of 3D displacements (Section 2.1) is done with the commercial software GOM ARAMIS, a commercial software of the company GOM GmbH (version 2016 hotfix 8, website: www.gom.com/). The grid size of the matching points is set to 20 px.

The deformed triangles of the gap between the plates are determined and the crack opening vectors are computed using the algorithm of Section 2 (using the 'base triangle method'). More than 100 crack triangles are detected that should have the same relative translation vectors (Section 2.3) and also the same crack opening vectors

Fig. 19. Specified order for the measurements in the x - y -plane (one height level).

Fig. 20. Color-coded visualization of the mesh of an example relative shift between the plates. The magenta arrows show the measured $\vec{t}_{rel}$ vectors with a scale factor of 5. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

(Section 2.4, ‘base triangle method’) for each epoch. Fig. 20 shows a color-coded visualization of the deformations ($\|\vec{t}_{rel,2D}\|$) and the 3D $\vec{t}_{rel}$ vectors (for the deformed triangles, magenta arrows) of one of the $4 \times 4 \times 8 - 1$ measurements that are done.

The relative translation vector $\vec{t}_{rel}$ is an important interim result such that the behavior of this vector is analyzed first. Fig. 21 depicts the scattering of the $\vec{t}_{rel}$ vectors for each crack triangle (cluster) and for all epochs (positions) with different random colors. Variations of the measurements between the positions are rarely visible.

To quantify the scattering, some statistical values are determined. The mean vectors ($\vec{t}_{rel,m}$, Eq. (27)) of the clusters and the covariance matrices are computed using Eq. 28 (Appendix A). Outliers are rejected using the Mahalanobis distance (Eq. (29)). Fig. 22 shows the confidence ellipsoids of all positions where similar sizes are visible.

Due to the transformation from $\vec{t}_{rel}$ to $\vec{t}_c$ (Eq. (23)), $\vec{t}_c$ shows another behavior. Fig. 23 depicts the scattering of the $\vec{t}_c$ vectors for all positions. For the estimation of the crack course $\vec{l}$, the first method of Section 2.4.1 is applied.

The statistic values are computed for the $\vec{t}_c$ vectors, too (see Appendix A, $\vec{t}_{c,m}$ is the mean, $\vec{\mu}_{t_c}$ is the expected vector). Outliers are also removed and the confidence ellipsoids are calculated. Fig. 24 shows these ellipsoids (confidence level 95%) of the $\vec{t}_c$ vectors for all epochs (positions). The sizes differ and depend on the height and also on the distance to the origin of the coordinate system. The largest variances of the ellipsoids are in x direction for heights larger than 1.25 mm. Below this, the major axes point in z direction. In addition to

Fig. 21. Scattering of $\vec{t}_{rel}$ for each of the $4 \times 4 \times 8 - 1$ relative shifts of the plates. Each position has a random color.

Fig. 22. Confidence ellipsoids of the $\vec{t}_{rel}$ vectors (confidence level 95%) for each of the $4 \times 4 \times 8 - 1$ relative shifts of the plates.

Fig. 23. Scattering of $\vec{t}_c$ for each of the $4 \times 4 \times 8 - 1$ relative shifts of the plates.

Fig. 24. Confidence ellipsoids of the $\vec{t}_c$ vectors for the $4 \times 4 \times 8 - 1$ relative shifts of the plates and the error vectors (blue, scale factor 10). (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

Fig. 25. Precision shown with the largest principal standard deviations of $\vec{t}_{rel}$ and $\vec{t}_c$. The indices of the positions correspond to the 8 levels of heights (Δz) visualized with different background colors. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

the ellipsoids, the differences to the expected values (from the micrometer screw gauges and the LVDT) are depicted as blue arrows with scale factor 10. Some systematic errors are still visible because there is a preferred direction of the error arrows that mainly points in x direction. The absolute deviations are analyzed in Fig. 26.

The precision is evaluated with the maximum principal standard deviations $s_{max, \vec{t}_{rel}}$ and $s_{max, \vec{t}_c}$ derived from the covariance matrices using Eq. (30) (Appendix A). Fig. 25 show the $s_{max, \vec{t}_{rel}}$ and $s_{max, \vec{t}_c}$ for all epochs where the different background colors correspond to the 8 levels of heights Δz . The maximum principal standard deviations $s_{max, \vec{t}_{rel}}$ of the relative translation vectors $\vec{t}_{rel}$ are on a constant level between 0.014 mm (≈ 0.1 px in image space) and 0.02 mm (≈ 0.2 px), whereas the values for $s_{max, \vec{t}_c}$ depend on the height with values up to 0.037 mm (≈ 0.4 px) for the largest z components but also depend on the length of $\vec{t}_c$ itself. This behavior is also visible in Fig. 22 and Fig. 24. The relation to the height and the length of $\vec{t}_c$ itself is caused by the transformation step from $\vec{t}_{rel}$ to $\vec{t}_c$ (Eq. (23), Section 2.4) and thus to the fluctuation of the crack course direction $\vec{l}$.

For the evaluation of the accuracy, two differences to the expected values are computed: $\|\vec{t}_{rel, m}\| - \|\vec{\mu}_{\vec{t}_{rel}}\|$ and $\|\vec{\mu}_{\vec{t}_c} - \vec{t}_{c, m}\|$. The corresponding graphs are plotted in Fig. 26. For the $\vec{t}_{rel}$ vectors, only the lengths can be compared to the expected values such that $\|\vec{t}_{rel, m}\| - \|\vec{\mu}_{\vec{t}_{rel}}\|$ is computed and visualized. Looking at Fig. 26, the deviation depends on the height. For small heights (< 0.25 mm), the deviations are below 0.004 mm (≈ 0.04 px). The maximum deviation is about 0.017 mm (≈ 0.2 px) for $\Delta z = 1.86$ mm. Reasons could be scaling and alignment errors. Considering the crack opening vectors $\vec{t}_c$, the

Fig. 26. Accuracy is evaluated with $\|\vec{t}_{rel, m}\| - \|\vec{\mu}_{\vec{t}_{rel}}\|$ and $\|\vec{\mu}_{\vec{t}_c} - \vec{t}_{c, m}\|$. The indices of the positions correspond to the 8 levels of heights (Δz) visualized with different background colors. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

Fig. 27. Precision of $\vec{t}_c$ shown with the largest principal standard deviations and accuracy evaluated with $\|\vec{\mu}_{\vec{t}_c} - \vec{t}_{c, m}\|$ for second method of the crack course estimation. The indices of the positions correspond to the 8 levels of heights (Δz) visualized with different background colors. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

components can be compared directly to the expected values. In Fig. 26, the distance between the mean and the expected vector $\|\vec{\mu}_{\vec{t}_c} - \vec{t}_{c, m}\|$ is plotted. It shows a similar behavior as $\|\vec{\mu}_{\vec{t}_{rel}}\| - \|\vec{\mu}_{\vec{t}_c}\|$ due to the error propagation but the deviations are larger with values up to 0.027 mm (≈ 0.3 px).

As mentioned in Section 2.4.1, there is an alternative for the estimation of the crack course $\vec{l}$. Fig. 27 depicts the maximum principle deviations of $\vec{t}_c$ and distance of the mean of $\vec{t}_c$ to the expected vector $\|\vec{\mu}_{\vec{t}_c} - \vec{t}_{c, m}\|$ for application of second method of Section 2.4.1. The behavior is similar to the first method for the crack course estimation ($\vec{l}$).

In conclusion, the $\vec{t}_{rel}$ vectors are more precise than the $\vec{t}_c$ vectors and the algorithm works fine but the small systematic errors leave room for further investigations.

5. Conclusion and outlook

This publication presents an algorithm to compute crack opening vectors for deformed triangles in a triangle mesh based on a displacement field. The developed method is applied on a specimen in a torsion test where vertical displacements appear and are detected. The algorithm is validated in an experiment with two plates having known opening vectors. The precision of $\vec{t}_{rel}$ and $\vec{t}_c$ is evaluated with principal standard deviations where $\vec{t}_{rel}$ is more precise with maximum principle standard deviations up to 0.02 mm. In contrast to $\vec{t}_{rel}$, the maximum principal standard deviations for $\vec{t}_c$ depend on the vertical component of $\vec{t}_c$ and are in the range of 0.013 mm and 0.037 mm. The maximum values appear for a vertical displacement of 1.9 mm. Considering the accuracy, deviations to the comparison measurement up to 0.028 mm for a vertical displacement of 1.9 mm are measured. For smaller vertical displacements, the distances to the expected values are below 0.02 mm.

Future work could concentrate on the improvement of the determination of the crack opening coordinate system in order to be more precisely. In addition, the model can be extended with a relative rotation.

Declaration of competing Interest

None.

Acknowledgements

The presented research work has been performed within the research training group GRK 2250 at Technische Universität Dresden funded by the German Research Foundation (DFG). The practical

experiments have been realized in cooperation with the Institute of Construction Materials at Technische Universität Dresden and with the Civil and Environmental Engineering Department of the Pontificia Universidade Católica de Rio de Janeiro (PUC-Rio).

Appendix A. Appendix

A.1. A statistical analysis of 3D measurements

The statistic analysis of the n measurements (3D vectors $\vec{x}_i$) begins with the computation of the mean $\vec{x}_m$ and the empirical covariance matrix Σ :

$$\vec{x}_m = \frac{1}{n} \cdot \sum_{i=1}^n \vec{x}_i \quad (27)$$

$$\Sigma = \frac{1}{n-1} \cdot \sum_{i=1}^n \left(\vec{x}_i - \vec{x}_m \right) \cdot \left(\vec{x}_i - \vec{x}_m \right)^T \quad (28)$$

Multivariate outliers are detected using the Mahalanobis distance (Eq. (29)) that is distributed according to the χ^2 distribution. The confidence level $1 - \alpha$ is set to 0.9973 according to the 3- σ rule in the 1D case.

$$MD^2(\vec{x}_i) = (\vec{x}_i - \vec{x}_m)^T \cdot \Sigma^{-1} \cdot (\vec{x}_i - \vec{x}_m) \sim \chi_b^2 \quad (29)$$

where b = dimension (here $b = 3$)

$\vec{x}_i$ is considered as an outlier if $MD^2(\vec{x}_i) > \chi_{b,1-\alpha}^2$ where α is the significance level. The outlier rejection is done iteratively. In each iteration, the maximal $MD^2(\vec{x}_i)$ is computed and if it is greater than the threshold ($\chi_{b,1-\alpha}^2$), the observation is rejected. Otherwise, the process stops. Then, the next iteration begins with recomputing the mean and the covariance matrix.

The covariance matrix can be analyzed using the eigenvalue decomposition (Eq. (30)). The principal standard deviations s_1 , s_2 , s_3 are computed taking square roots of the eigenvalues and they are used to evaluate the precision.

$$\Sigma = \mathbf{V} \cdot \mathbf{\Lambda} \cdot \mathbf{V}^T = \mathbf{V} \cdot \begin{pmatrix} s_1^2 & 0 & 0 \\ 0 & s_2^2 & 0 \\ 0 & 0 & s_3^2 \end{pmatrix} \cdot \mathbf{V}^T \quad (30)$$

where $\mathbf{V}$ =eigenvector matrix
 $\mathbf{\Lambda}$ =eigenvalue matrix.

References

- Ackermann, F., 1984. Digital image correlation: performance and potential application in photogrammetry. *Photogramm. Rec.* 11, 429–439. <https://doi.org/10.1111/j.1477-9730.1984.tb00505.x>.
- Barazzetti, L., Scaioni, M., 2009. Crack measurement: development, testing and applications of an automatic image-based algorithm. *ISPRS J. Photogramm. Remote Sens.* 64, 285–296. <https://doi.org/10.1016/j.isprsjprs.2009.02.004>.
- Benning, W., Lange, J., Schwermann, R., Effkemann, C., Görtz, S., 2004. Monitoring crack origin and evolution at concrete elements using photogrammetry. In: *Int. Arch. Photogramm. Remote Sens. Spatial Inf. Sci.*, pp. 678–683. <<https://www.isprs.org/proceedings/XXXV/congress/comm5/papers/638.pdf>>.
- Curosu, I., Liebscher, M., Mechtcherine, V., Bellmann, C., Michel, S., 2017. Tensile behavior of high-strength strain-hardening cement-based composites (hs-shcc) made with high-performance polyethylene, aramid and pbo fibers. *Cem. Concr. Res.* 98, 71–81. <https://doi.org/10.1016/j.cemconres.2017.04.004>.
- Dare, P., Hanley, H., Fraser, C., Riedel, B., Niemeier, W., 2002. An operational application of automatic feature extraction: the measurement of cracks in concrete structures. *Photogramm. Rec.* 17, 453–464. <https://doi.org/10.1111/0031-868X.00198>.
- Görtz, S., 2004. Zum Schubverhalten von Stahlbeton- und Spannbetonbalken aus Normal- und Hochleistungsbeton. Ph.D. thesis. RWTH Aachen.
- Hampel, U., Maas, H.G., 2009. Cascaded image analysis for dynamic crack detection in material testing. *ISPRS J. Photogramm. Remote Sens.* 64, 345–350. <https://doi.org/10.1016/j.isprsjprs.2008.12.006>.
- Hoppe, H., DeRose, T., Duchamp, T., McDonald, J., Stuetzle, W., 1992. Surface reconstruction from unorganized points, in: *Proceedings of the 19th Annual Conference on Computer Graphics and Interactive Techniques*, ACM, New York, NY, USA, pp. 71–78. URL <http://doi.acm.org/10.1145/133994.134011>, doi:10.1145/133994.134011.
- Irwin, G.R., 1958. *Fracture*. Springer Berlin Heidelberg, Berlin, Heidelberg. pp. 551–590. URL https://doi.org/10.1007/978-3-642-45887-3_5, doi:10.1007/978-3-642-45887-3_5.
- Koschitzki, R., Schacht, G., Schneider, D., Marx, S., Maas, H.G., 2011. Integration of photogrammetry and acoustic emission analysis for assessing concrete structures during loading tests. In: *Proceedings of SPIE Optical Metrology, International Society for Optics and Photonics*, <https://doi.org/10.1117/12.889558>.
- Lange, J., Benning, W., 2006. Crack detection using photogrammetry. In: *Proceedings of 9th European Conference on Non-Destructive Testing*. German Society for Non-Destructive Testing, Berlin, NDT, pp. 1–8.
- Liebold, F., Maas, H.G., 2016. Advanced spatio-temporal filtering techniques for photogrammetric image sequence analysis in civil engineering material testing. *ISPRS J. Photogramm. Remote Sens.* 111, 13–21. <https://doi.org/10.1016/j.isprsjprs.2015.10.013>.
- Liebold, F., Maas, H.G., 2018. Sub-pixel accuracy crack width determination on concrete beams in load tests by triangle mesh geometry analysis. *ISPRS Ann. Photogramm. Remote Sens. Spatial Inf. Sci.* IV-2, 193–200. <https://doi.org/10.5194/isprs-annals-IV-2-193-2018>.
- Liebold, F., Maas, H.G., Heravi, A.A., 2019. Crack width measurement for non-planar surfaces by triangle mesh analysis in civil engineering material testing. *Int. Arch. Photogramm. Remote Sens. Spatial Inf. Sci.* XLII-2/W18, 107–113. <https://doi.org/10.5194/isprs-archives-XLII-2-W18-107-2019>.
- Maas, H.G., Hampel, U., 2006. Photogrammetric techniques in civil engineering material testing and structure monitoring. *Photogramm. Eng. Remote Sens.* 72, 39–45. <https://doi.org/10.14358/PERS.72.1.39>.

4 Diskussion

Die vorgestellten Veröffentlichungen sind aufeinander aufbauend. Alle Publikationen haben gemein, dass eine Deformationsanalyse von belasteten Betonproben durch Auswertung von Bildfolgen erfolgt. In einem Bild unter Nulllast (Referenzbild, meistens erstes Bild der Sequenz) wird eine Anordnung von Punkten definiert, deren Verschiebungen in den Folgebildern durch digitale Bildkorrelationsverfahren gemessen werden. Die erfolgreich verfolgten Punkte werden danach zu einem Dreiecksnetz trianguliert. Daran schließt sich eine Untersuchung der Änderungen in den Dreiecken an. Während in Kapitel 2 monokulare Bildsequenzen betrachtet werden, wird in Kapitel 3 auf Stereobildsequenzen eingegangen. Die Übersicht in Abb. 4.1 fasst den Ablauf der Rissdetektionsverfahren zusammen und verdeutlicht den Zusammenhang der Veröffentlichungen. Die Publikationen sind den einzelnen Blöcken zugeordnet.

In Publikation P.I (Kapitel 2.1) werden für jedes Dreieck Hauptdehnungen und die zugehörigen Richtungsvektoren berechnet, um deformierte Bereiche zu detektieren. Um die Sensitivität des Verfahrens zu erhöhen und Rauscheffekte zu vermeiden, werden verschiedene Filterverfahren auf die Hauptdehnungen im Dreiecksnetz angewandt. Die Datengrundlage bietet die Möglichkeit, in der zeitlichen (Zeitreihe für jedes Dreieck) und der räumlichen (räumliche Nachbarschaften der Dreiecke) Ebene zu filtern. Die besten Ergebnisse wurden mit dem bilateralen Filter in der räumlichen und einem gewichteten Mittelwert (Sägezahn) in der zeitlichen Dimension erzielt. Die auf Hauptkomponentenanalyse beruhende raum-zeitliche Filtertechnik lieferte auch gute Ergebnisse, wobei die Festlegung des dazu benötigten Schwellwertes weiterhin eine Herausforderung darstellt. Mit der Veröffentlichung P.I konnte somit die Arbeit von Koschitzki und Maas (2012) fortgeführt und um Hauptdehnungen bzw. Filtermethoden erweitert werden. Durch die Wahl eines Interestoperators haben die Dreiecke nach der Triangulation unterschiedliche Größen, sodass die Hauptdehnungen bzw. Flächendehnungen nicht direkt vergleichbar sind. Somit bleibt ein systematischer Fehler enthalten. Es sollte darauf geachtet werden, dass die Punkte gleichverteilt und damit die Dreiecke in etwa gleich groß sind. Bei Punkten, deren Zuordnung nicht berechnet werden kann, z.B. durch Rissverläufe innerhalb der Bildausschnitte für das Bildkorrelationsverfahren, sollten die Verschiebungen, wie in P.I

geschehen, interpoliert werden, da durch den Verlust von Punkten größere Dreiecke entstünden.

Abbildung 4.1. Flussdiagramm zu den Verfahren mit Einordnung der Publikationen

Hauptdehnungen eignen sich zwar zur Detektion deformierter Bereiche, Rissbreiten können aber nicht direkt abgeleitet werden. Deshalb wendet sich Publikation P.II drei Algorithmen zur Berechnung von Rissbreiten in Dreiecksnetzen zu, nachdem deformierte Dreiecke mit Hauptdehnungen bestimmt wurden. Dabei werden auch Rotationen zwischen den Epochen beachtet. Einer der

Algorithmen bietet auch die Möglichkeit, zusätzlich die Rissuferverschiebung (parallel zum Riss) zu bestimmen und somit den 2D-Rissöffnungsvektor. Damit stellt P.II eine Erweiterung des Algorithmus von Görtz (2004) dar.

Der Fachartikel P.III behandelt eine Strategie der Rissbreitenmessung für dichte Rissmuster. Nach Berechnung eines dichten Verschiebungsfeldes wird ein zunächst grobes Dreiecksnetz in deformierten Bereichen wiederholt verdichtet. Weiterhin wird ein Algorithmus zur Rissbreitenberechnung in einer Ausgleichung vorgestellt, bei dem nicht nur die drei Eckpunkte des Dreiecks, sondern auch nicht triangulierte Punkte des dichten Verschiebungsfeldes innerhalb des Dreiecks einbezogen werden. Das stellt somit eine Verallgemeinerung der in P.II vorgestellten Methode dar. Als wichtiges Zwischenergebnis wird für jedes Dreieck, wie schon bei P.II, der relative Translationsvektor $\vec{t}_{rel}$ berechnet, dessen Betrag $||\vec{t}_{rel}||$ als neues Deformationsmaß für brüchiges Material vorgeschlagen wird. Weiterhin werden die Nachteile der Nutzung von Hauptdehnungen herausgestellt. Diese sind im Gegensatz zu $||\vec{t}_{rel}||$ abhängig von der Größe des Dreiecks und eignen sich daher am ehesten für homogene Dreiecksnetze. Schwellwerte lassen sich für $||\vec{t}_{rel}||$ einfacher, abhängig von der Qualität des Verschiebungsfeldes festlegen. Bei dehnbarem (elastischem) oder kompressiblem Materialverhalten sollte jedoch eine Analyse mit Hauptdehnungen vorgezogen werden.

Die Ermittlung des relativen Translationsvektors $\vec{t}_{rel}$ stellt eine zentrale Neuerung der Arbeit dar, sodass der Algorithmus hier nochmals in leicht veränderter Form zusammengefasst wird. In Abb. 4.2 wird die Ableitung des Vektors dargestellt. Abb. 4.2a zeigt das Dreieck im nicht deformierten Zustand, wobei die Risslinie, an der sich die Rissöffnung vollzieht, gestrichelt eingezeichnet ist. Alle Punkte des Dreiecks werden von der Referenz- zur deformierten Epoche einer Starrkörpertransformation unterzogen. Für einen Punkt wird eine zusätzliche Relativtranslation $\vec{t}_{rel}$ angenommen, siehe Gl. (4.1). Weitere Annahmen sind, dass der obere Teil des Dreiecks keine Relativrotation erfährt und dass in beiden Zuständen die Dreiecksbasisseite spannungsfrei ist, da bei einer Rissöffnung von einer Entlastung der Basisseite auszugehen ist.

$$\begin{aligned}\vec{p}_{b1} &= \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,b1} \\ \vec{p}_{b2} &= \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,b2} \\ \vec{p}_h &= \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,h} + \vec{t}_{rel}\end{aligned}\tag{4.1}$$

mit $\vec{p}_{ref,j}$ = Koordinaten des Dreieckseckpunktes im Referenzzustand
 $\vec{p}_j$ = Koordinaten des Dreieckseckpunktes im deformierten Zustand
 b_1, b_2 = Indizes der Basisseite

h = Index des verbleibenden Punktes
 $\vec{t}$ = globaler Translationsvektor
 $\mathbf{R}$ = globale Rotationsmatrix
 $\vec{t}_{rel}$ = relativer Translationsvektor

Dabei stellt sich die Frage, welche Eckpunkte des Dreiecks zur Basisseite gehören. Eine mögliche Herangehensweise ist die Wahl der Indizes, deren zugehörige Seitenlängen sich am wenigsten ändern:

$$b_1, b_2 = \underset{i,j}{argmin} ||\vec{s}_{ij}|| - ||\vec{s}_{ref,ij}|| \quad \forall (i,j) \in \{(1,2), (1,3), (2,3)\} \quad (4.2)$$

mit $\vec{s}_{ref,ij} = \vec{p}_{ref,j} - \vec{p}_{ref,i}$ Vektoren der Dreiecksseiten im Referenzzustand
 $\vec{s}_{ij} = \vec{p}_j - \vec{p}_i$ Vektoren der Dreiecksseiten im deformierten Zustand

In Abb. 4.2b ist das Referenzdreieck so transformiert, dass die Basisseiten übereinander liegen. Damit unterscheiden sich die Dreiecke nunmehr nur noch um die Relativbewegung des oberen Teils des Dreiecks, die sich in eine Komponente senkrecht zum Riss (Rissbreite r) und eine weitere Komponente parallel zum Riss zerlegen lässt.

Abbildung 4.2. a) Links: Dreieck vor Deformation; rechts: Dreieck nach Deformation, Bewegung des gesamten Dreiecks und Teilung durch Riss in zwei Teile;
 b) Geteiltes deformiertes Dreieck sowie mit $\vec{p}_{ref,j,t} = \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j}$ transformiertes Referenzdreieck; $\vec{n}_{Riss}$: Rissnormale; $\vec{t}_{||}$: Richtung entlang des Rissufers.

Die in den deformierten Zustand transformierten Referenzkoordinaten für die Basislinienpunkte können direkt nach den Gleichungen (4.3) und (4.4) berechnet werden. Die transformierten Koordinaten sind so gewählt, dass die transformierte Basislinie des Referenzzustands und die Basislinie im deformierten

Zustand übereinanderliegen und sich die Restfehler auf beide Eckpunkte gleichmäßig verteilen. Denselben Effekt hätte eine Starrkörpertransformation.

$$\vec{p}_{ref,b1,t} = \frac{1}{2} \cdot (\vec{p}_{b1} + \vec{p}_{b2}) - \frac{1}{2} \cdot \|\vec{s}_{ref,b1,b2}\| \cdot \frac{\vec{s}_{b1,b2}}{\|\vec{s}_{b1,b2}\|} \quad (4.3)$$

$$\vec{p}_{ref,b2,t} = \frac{1}{2} \cdot (\vec{p}_{b1} + \vec{p}_{b2}) + \frac{1}{2} \cdot \|\vec{s}_{ref,b1,b2}\| \cdot \frac{\vec{s}_{b1,b2}}{\|\vec{s}_{b1,b2}\|} \quad (4.4)$$

Der verbleibende Punkt wird so transformiert, dass sich die innere Geometrie des Dreiecks nicht ändert. Dafür werden zwei Hilfsgrößen berechnet: eine Koordinate entlang der Basislinie (Gl. (4.5)) und eine senkrecht dazu (Gl. (4.6)).

$$dx_{ref,b1,h} = \|\vec{s}_{ref,b1,h}\| \cdot \cos(\angle \vec{s}_{ref,b1,b2}, \vec{s}_{ref,b1,h}) = \frac{\vec{s}_{ref,b1,b2}^T \cdot \vec{s}_{ref,b1,h}}{\|\vec{s}_{ref,b1,b2}\|} \quad (4.5)$$

$$dy_{ref,b1,h} = \begin{cases} \sqrt{\|\vec{s}_{ref,b1,h}\|^2 - dx_{ref,b1,h}^2} & \text{für } \det \begin{pmatrix} \vec{s}_{ref,b1,b2} & \vec{s}_{ref,b1,h} \end{pmatrix} \geq 0 \\ -\sqrt{\|\vec{s}_{ref,b1,h}\|^2 - dx_{ref,b1,h}^2} & \text{sonst} \end{cases} \quad (4.6)$$

Für den verbleibenden Punkt mit dem Index h ergeben sich die transformierten Referenzkoordinaten zu:

$$\vec{p}_{ref,h,t} = \vec{p}_{ref,b1,t} + \frac{\vec{s}_{b1,b2}}{\|\vec{s}_{b1,b2}\|} \cdot dx_{ref,b1,h} + \frac{1}{\|\vec{s}_{b1,b2}\|} \cdot \begin{pmatrix} -s_{b1,b2,y} \\ s_{b1,b2,x} \end{pmatrix} \cdot dy_{ref,b1,h} \quad (4.7)$$

Wie aus Abb. 4.2b ersichtlich wird, ergibt sich $\vec{t}_{rel}$ als Differenz der Koordinaten des oberen Punktes im deformierten Zustand $\vec{p}_h$ und der transformierten Koordinaten des Referenzzustands $\vec{p}_{ref,h}$:

$$\vec{t}_{rel} = \vec{p}_h - \vec{t} - \mathbf{R} \cdot \vec{p}_{ref,h} = \vec{p}_h - \vec{p}_{ref,h,t} \quad (4.8)$$

Nun kann der Betrag $\|\vec{t}_{rel}\|$ als Deformationsmaß genutzt werden. Der zweidimensionale Rissöffnungsvektor ergibt durch Rotation von $\vec{t}_{rel}$:

$$\begin{pmatrix} r = x_{Riss} \\ y_{Riss} \end{pmatrix} = \mathbf{R}_{Riss}^T \cdot \vec{t}_{rel} = (\vec{n}_{Riss} \quad \vec{t}_{||})^T \cdot \vec{t}_{rel} \quad (4.9)$$

mit x_{Riss} = Rissbreite (senkrechter Abstand zwischen den Rissufern)
 y_{Riss} = Verschiebung parallel zum Riss

Für die Umrechnung in den Rissöffnungsvektor werden die Rissnormale $\vec{n}_{Riss}$ sowie die Richtung parallel zum Riss $\vec{t}_{||}$ benötigt. In P.II wird ein möglicher Weg

zur Schätzung der Vektoren vorgestellt. Die Präzision der Methode ist durch die Diskretisierung nicht sehr hoch, sodass sich Fehler in Abhängigkeit zur Länge des Relativtranslationsvektors $||\vec{t}_{rel}||$ auswirken, siehe dazu P.III. Während für den relativen Translationsvektor $\vec{t}_{rel}$ Standardabweichungen (Präzision) von 0,06 px erreicht wurden, steigen die Standardabweichungen (Präzision) der Rissbreite auf Werte bis 0,2 px bei einer Rissbreite von 4 px. Für Rissbreiten kleiner 1 px lagen die Standardabweichungen unter 0,05 px im Versuch.

P.III diskutiert auch die Grenzen von monokularen 2D-Auswertungen. Sind die folgenden Annahmen nicht erfüllt, kommt es zu systematischen Fehlern:

- Ebene Messoberfläche
- Rechtwinklige Ausrichtung der optischen Achse zur Oberfläche
- Keine Relativbewegungen zwischen Kamera und betrachteter Oberfläche (nur Bewegungen innerhalb der Ebene erlaubt)

Weiterhin sind Skalierungsfehler durch die Transformation der ermittelten Maße (Rissbreiten, relative Translationsvektoren $\vec{t}_{rel}$) von Pixelwerten in ein metrisches Maß möglich. Dazu kommen mögliche Restfehler der Objektivverzeichnung, die durch eine Kamerakalibrierung minimiert werden können.

In den Publikationen P.IV und P.V werden die Algorithmen aus P.I, P.II und P.III erweitert und auf 3D-Verschiebungsfelder angepasst, die mit einem Stereokamerasystem bestimmt werden, sodass auch nicht ebene Objekte sowie Vertikalbewegungen untersucht und relative Bewegungen zwischen Kamerasystem und Objekt abgefangen werden können. P.IV betrachtet zunächst Algorithmen zu Deformationen, die tangential zur Oberfläche wirken. Mit Hilfe einer Stereokamera werden korrespondierende Punkte zwischen den Bildpaaren wie auch in der zeitlichen Ebene bestimmt, sodass 3D-Verschiebungsfelder für ein Raster von Oberflächenpunkten berechnet werden. Die Oberflächenpunkte werden analog zum 2D-Fall zu einem Dreiecksnetz trianguliert. Durch eine Kongruenzabbildung der 3D-Koordinaten der Dreieckseckpunkte in den 2D-Raum kann der 2D-Algorithmus von P.II genutzt und damit die innere Geometrie der Dreiecke untersucht werden. Der Betrag des relativen Translationsvektors $||\vec{t}_{rel,2D}||$ wird hier ebenfalls als Deformationsmaß zur Rissdetektion verwendet. Die berechnete globale Translation und Rotation werden dabei ignoriert, da sie durch die Kongruenzabbildung keine brauchbaren Aussagen liefern. In P.IV wird der Algorithmus bei einem Dehnungstest mit einer zylindrischen Probe getestet,

wobei die Krafteinwirkung in Richtung der Zylinderachse stattgefunden hat, sodass von tangentialen Deformationen ausgegangen werden kann. Überschreitet $||\vec{t}_{rel,2D}||$ einen vorgegebenen Schwellwert, wird für das zugehörige Dreieck eine Rissnormale mit einem angepassten Verfahren ähnlich dem aus P.II bestimmt und eine Rissbreite berechnet.

Die Methode aus dem Fachartikel P.V erweitert das Verfahren aus P.IV, sodass auch vertikale Komponenten des Rissöffnungsvektors ermittelt werden können. Für die Risskandidaten, die wie in P.IV mit $||\vec{t}_{rel,2D}||$ bestimmt werden, ist es durch Hinzunahme mindestens eines undeformierten Nachbardreiecks möglich, das in P.III aufgestellte Modell (siehe auch Gl. (4.1)) auf den 3D-Fall zu erweitern. Mit Hilfe des Modells kann der dreidimensionale Relativtranslationsvektor $\vec{t}_{rel}$ berechnet werden. Anschließend wird der Vektor $\vec{t}_{rel}$ in die Komponenten des Rissöffnungsvektors zerlegt, dessen Achsrichtungen, also Rissnormale und Vertikalrichtung sowie die dazu rechtwinklige dritte Achse, vorher bestimmt werden. Die Methode aus P.V stellt somit eine Erweiterung des Algorithmus von Lange & Benning (2006) dar. Angewendet wird das Verfahren aus P.V bei einem Betonprobekörper in einem Torsionsversuch, der vertikale Bewegungen aufweist. In einer weiteren Untersuchung wird die relative Verschiebung zweier Platten sowohl mit der photogrammetrischen Methode als auch mit einem induktiven Wegaufnehmer und Mikrometerschrauben gemessen. Die ermittelten Rissöffnungsvektoren können also direkt mit den Messwerten der mechanischen Messgeräte verglichen werden. Die Abweichungen sind abhängig von der Länge des Vektors und wachsen v.a. mit der z-Komponente des Rissöffnungsvektors. Die maximale Abweichung liegt für eine z-Komponente von ca. 1,9 mm bei einem Wert von 0,027 mm, was in etwa 0,3 px im Bildraum entspricht.

5 Ausblick

Im Ausblick werden noch offene Probleme und mögliche Erweiterungen angesprochen. Dazu gehört in Kap. 5.1 die Bestimmung der Rissanzahl, insbesondere bei engen multiplen Rissstrukturen. Kap 5.2 beschäftigt sich mit der Bestimmung von Risspitzen und -geschwindigkeiten. Im folgenden Punkt 5.3 geht es um den Blick ins Innere von Materialproben, den monokulare oder Stereosysteme nicht erlauben. Unter Zuhilfenahme von tomographischen Aufnahmesystemen können dreidimensionale Daten des Innenraums generiert werden. Mögliche Erweiterungen der in dieser Arbeit vorgestellten Algorithmen werden diskutiert. Weiterhin werden in Kap. 5.4 Relativrotationen als Modellerweiterung angesprochen und unter Punkt 5.5 eine genauere Risspositionsbestimmung diskutiert.

5.1 Bestimmung der Anzahl der Risse

Für die Materialforscher ist bei engen Rissstrukturen auch die Anzahl der Risse interessant. Die Zählung der zusammenhängenden Komponenten deformierter Dreiecke kommt schnell an ihre Grenzen, wenn sich Risse kreuzen. Ein Algorithmus zur Skelettierung deformierter Dreiecke könnte genutzt werden, um die Rissanzahl in Dreiecksnetzen zu bestimmen. Ein erster Schritt zur Skelettierung kann die Betrachtung der Fälle in Abb. 5.1 sein. Dort werden vier denkbare Fälle aufgezeigt. Durch Analyse der Nachbarschaften deformierter Dreiecke kann eine Unterscheidung automatisch erfolgen. Das stark hervorgehobene rote Dreieck ist jeweils der Kandidat, dessen Nachbarschaft mit Konnektivitätsanalyse betrachtet wird. Die Anzahl zusammenhängender Komponenten undeformierter Dreiecke in der Nachbarschaft wird durch das Region-Growing-Verfahren ermittelt und kann zur Unterscheidung der Fälle genutzt werden. In Abb. 5.1a gibt es unter den Nachbardreiecken zwei zusammenhängende Komponenten (gelb und grün umrandete Dreiecke). Bei Abb. 5.1c ist es nur eine Komponente (grün umrandet) und damit eine Risspitze dargestellt. In Abb. 5.1d sind es drei Komponenten (gelb, grün bzw. cyan umrandete Dreiecke), was auf eine Kreuzung schließen lässt. In Abb. 5.1b wird ein Randdreieck betrachtet, welches zwei zusammenhängende Komponenten undeformierter Dreiecke aufweist. Die Infor-

mation reicht jedoch noch nicht aus, um festzustellen, ob es am Rand des Netzes liegt. Unter Zuhilfenahme der Halbkantendatenstruktur kann dies ermittelt werden (Botsch et al., 2010). Ein Dreieck ist dann ein Randdreieck im Dreiecksnetz, wenn es eine Dreiecksseite besitzt, die keine Partnerhalbkannte aufweist.

Abbildung 5.1. Analyse der Nachbardreiecke, a) zwei zusammenhängende Komponenten undeformierter Dreiecke (grün bzw. gelb umrandet), b) Randdreieck mit zwei zusammenhängenden Komponenten undeformierter Dreiecke (grün bzw. gelb umrandet), c) Rissspitze mit einer zusammenhängenden Komponente undeformierter Dreiecke (grün umrandet), d) Rissspitze mit drei zusammenhängenden Komponenten undeformierter Dreiecke (grün bzw. gelb bzw. cyan umrandet)

5.2 Rissspitzenbestimmung und -verfolgung

Auch die Rissspitzenverfolgung in Bildsequenzen zur Bestimmung der Rissgeschwindigkeiten stellt eine weitere zukünftige Aufgabe dar. Das in Abb. 5.1 c skizzierte Verfahren kann dazu genutzt werden, um Rissspitzen in Dreiecksnetzen zu erkennen und damit Rissgeschwindigkeiten in Bildsequenzen zu ermitteln.

5.3 Anwendung der entwickelten Algorithmen auf Voxeldaten

Ein weiterer interessanter Punkt für die Materialforschung ist der Blick ins Innere von belasteten Betonproben und damit die Erweiterung der Algorithmen der Deformationsanalyse und Rissbreitenberechnung auf räumliche Voxeldaten, die

z.B. mit Hilfe von Computertomographie aufgenommen werden können. Subvoxel-genaue Verfolgungsmethoden wurden bereits durch Maas et al. (1994) erfolgreich angewendet. Ein dreidimensionales Verschiebungsfeld könnte damit bestimmt werden. Daran könnte sich eine Vernetzung zu einer Tetraederstruktur und die Untersuchung der Tetraeder auf Deformationen anschließen. Analog zur Betrachtung des gespaltenen Dreiecks aus Publikation P.II sind für den Tetraeder bei der Teilung durch einen Riss zwei mögliche Fälle denkbar. Fall 1 wird in Abb. 5.2a skizziert, wo eines der Dreiecke (eine Seitenfläche) undeformiert bleibt und somit drei Eckpunkte keine Relativbewegung untereinander erfahren und sich der übrig bleibende Eckpunkt relativ zu dem undeformierten Dreieck bewegt. In Formeln ausgedrückt gibt es, wie bereits in Publikation P.V aufgeführt, folgende Unterscheidung:

$$\vec{p}_j = \begin{cases} \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j} & \forall j \in M_1 \\ \vec{t} + \mathbf{R} \cdot \vec{p}_{ref,j} + \vec{t}_{rel} & \forall j \in M_2 \end{cases} \quad (5.1)$$

mit $\vec{p}_{ref,j}$ = Punkt im undeformierten (Referenz-)Zustand
 $\vec{p}_j$ = Punkt im deformierten Zustand
 $\vec{t}$ = globaler Translationsvektor
 $\mathbf{R}$ = globale Rotationsmatrix
 $\vec{t}_{rel}$ = relativer Translationsvektor
 M_1 = Menge 1 von Eckpunkten
 M_2 = Menge 2 von Eckpunkten

Im Fall 1 (Abb. 5.2) besteht M_1 aus b_1, b_2, b_3 und M_2 aus dem Punkt mit Index h :

$$M_1 = \{b_1, b_2, b_3\} \text{ und } M_2 = \{h\} \quad (5.2)$$

In Abb. 5.2b ist neben dem geteilten Tetraeder im deformierten Zustand der durch eine Starrkörpertransformation transformierte Referenztetraeder dargestellt, sodass das undeformierte Dreieck des undeformierten Zustands mit dem des deformierten Zustands zusammenfallen. Die Parameter der Starrkörpertransformation lassen sich mit Hilfe der drei Punkte der Menge M_1 ermitteln. Dann ergibt sich der relative Translationsvektor $\vec{t}_{rel}$ durch die Differenz der Koordinaten des Punktes mit Index h im deformierten Zustand und dem transformierten undeformierten Zustand:

$$\vec{t}_{rel} = \vec{p}_h - \vec{t} - \mathbf{R} \cdot \vec{p}_{ref,h} \quad (5.3)$$

Abbildung 5.2. a) Links: Tetraeder vor Deformation; rechts: durch Riss geteilter Tetraeder nach Deformation, zwei Teile mit drei Eckpunkten bzw. mit einem Eckpunkt, die Trennebene ist in grün dargestellt; b) Deformierter Tetraeder und mit $\vec{p}_{\text{ref},j,t} = \vec{t} + \mathbf{R} \cdot \vec{p}_{\text{ref},j}$ transformierter Tetraeder des Referenzzustandes (Fall 1).

Der zweite Fall der Teilung des Tetraeders ist in Abb. 5.3a skizziert. In diesem Fall gibt es zwei Tetraederseiten, die konstant bleiben und zwei, die sich ändern, sodass die Menge M_1 aus b_1 sowie b_2 und M_2 aus h_1 bzw. h_2 bestehen:

$$M_1 = \{b_1, b_2\} \text{ und } M_2 = \{h_1, h_2\} \quad (5.4)$$

Abb. 5.3b zeigt Fall 2. Ähnlich wie in Abb. 5.2b wird der transformierte Referenztetraeder und der deformierte (geteilte) Tetraeder dargestellt. Die Punkte mit den Indizes h_1 und h_2 erfahren eine zusätzliche relative Verschiebung.

Abbildung 5.3. a) Links: Tetraeder vor Deformation; rechts: Tetraeder nach Deformation, Riss teilt Tetraeder in zwei Teile mit jeweils zwei Eckpunkten, die Trennebene ist grün dargestellt; b) Geteilter deformierter Tetraeder und transformierter Tetraeder des Referenzzustandes mit $\vec{p}_{\text{ref},j,t} = \vec{t} + \mathbf{R} \cdot \vec{p}_{\text{ref},j}$ (Fall 2).

Die Parameter des relativen Translationsvektors $\vec{t}_{rel}$ lassen sich in einer Ausgleichung, die bereits in Publikation P.V vorgestellt wurde, berechnen.

Um festzustellen, ob Fall 1 oder Fall 2 angewendet werden sollte und welche Eckpunkte zu welcher Menge zugeordnet werden sollten, wird nun eine mögliche Vorgehensweise vorgeschlagen, siehe Abb. 5.4. Die vier Eckpunkte des Tetraeders haben die Indizes 1, 2, 3 und 4. $\|\vec{t}_{rel,2D,i,j,k}\|$ ist dabei der Betrag des relativen Translationsvektors für die Seitenfläche (Dreieck) mit den Eckpunkten i , j und k im 2D-Raum, also nach der Kongruenzabbildung der Dreieckspunkte in den 2D-Raum nach dem Algorithmus aus Publikation P.IV, und ist als Maß für die Änderung der inneren Geometrie anzusehen. Die Schwellwerte δ_1 und δ_2 sollten in der Größenordnung der Präzision der Punktverfolgung liegen (Daumenregel: 0,1...0,2 Voxel). Nach der Berechnung der Dreiecksdeformationen wird getestet, ob Fall 1 in Frage kommt, indem geprüft wird, ob mindestens ein Dreieck undeformiert ist. Im rechten Zweig wird getestet, welches Paar von gegenüberliegenden Tetraederseitenlängen sich am geringsten ändert. Liegen die Seitenänderungen unter dem Schwellwert δ_2 , wird Fall 2 angenommen, ansonsten ist von einem Sonderfall auszugehen. Ein Sonderfall könnte durch Fehler im Verschiebungsfeld auftreten. Aber auch eine Rissspitze oder mehrere Risse könnten zu einem Sonderfall führen.

Abbildung 5.4. Algorithmus zur Berechnung des relativen Translationsvektors $\vec{t}_{rel}$ für einen Tetraeder mit Fallunterscheidung. δ_1 und δ_2 sind Schwellwerte.

Nachdem der relative Translationsvektor $\vec{t}_{rel}$ für jeden Tetraeder bestimmt wurde, ist es danach möglich, den Rissöffnungsvektor und somit Rissbreiten ähnlich zu den Verfahren aus den Publikationen P.II bis P.V zu bestimmen.

5.4 Modellerweiterung durch Relativrotation

In den vorgestellten Publikationen wurden bisher bei der relativen Bewegung geteilter Dreiecke nur Translationen betrachtet. Die Ergänzung einer Relativrotation wäre eine denkbare Erweiterung. In 2D-Auswertungen könnten Rotationsinformationen, die bei der Bildkorrelation mit gewonnen werden, als Beobachtungen in eine Ausgleichung aufgenommen werden. Außerdem bestünde bei einer Relativrotation das Problem, wie die Rissbreite bzw. der Rissöffnungsvektor zu definieren ist, was auch Bestandteil zukünftiger Arbeiten sein könnte.

5.5 Genauigkeitssteigerungen für die Rissposition

Die vorgestellten Algorithmen erreichen für die Berechnung der Komponenten des Rissöffnungsvektors wie z.B. der Rissbreiten Genauigkeiten im Subpixelbereich. Die Verwendung von Bildkorrelationsverfahren begrenzt allerdings die Genauigkeit der Positionsbestimmung. Eine Kombination der Bildkorrelationstechnik mit Kantendetektionsmethoden bzw. die Analyse von Grauwertprofilen quer zum Riss stellt eine mögliche Erweiterung dar.

5.6 Verbesserung der Rissnormalenschätzung

Die Bestimmung der Rissrichtung erfolgte in den vorgestellten Publikationen für jedes deformierte Dreieck durch Berechnung einer Ausgleichsgeraden durch die Mittelpunkte des Kandidaten selbst sowie benachbarter deformierter Dreiecke. Im zweidimensionalen Fall wurde die Rissnormale dann als Senkrechte auf diese Gerade abgeleitet. Eine Verbesserung der Rissnormalenbestimmung könnte zu einer Genauigkeitserhöhung der Rissbreitenberechnung führen.

Literaturverzeichnis

- Ackermann, F., 1984. Digital Image Correlation: Performance and Potential Application in Photogrammetry. *The Photogrammetric Record*, 11(64), 429–439.
- Albert, J., Maas, H.-G., Schade, A., Schwarz, W., 2002. Pilot Studies on Photogrammetric Bridge Deformation Measurement. *2nd IAG Com. IV Symposium on Geodesy for Geotechnical and Structural Engineering*, 21.-24. Mai, Berlin.
- Arthur, D., Vassilvitskii, S., 2007. K-means++: The Advantages of Careful Seeding. *Proceedings of the Eighteenth Annual ACM-SIAM Symposium on Discrete Algorithms*, SODA '07, Society for Industrial and Applied Mathematics, Philadelphia, PA, USA, 1027–1035.
- Barazzetti, L., Scaioni, M., 2009. Crack Measurement: Development, Testing and Applications of an Automatic Image-based Algorithm. *ISPRS Journal of Photogrammetry and Remote Sensing*, 64, 285–296.
- Barazzetti, L., Scaioni, M., 2010. Development and Implementation of Image-based Algorithms for Measurement of Deformations in Material Testing. *Sensors*, 10, 7469–7495.
- Bay, H., Ess, A., Tuytelaars, T., Van Gool, L., 2008. Speeded-up Robust Features (SURF). *Computer Vision and Image Understanding*, 110(3), 346–359.
- Becker, E., Bürger, W., 1975. *Kontinuumsmechanik*. 20, 1. Auflage, Vieweg + Teubner Verlag.
- Benning, W., 1985. Grundgleichungen der 2D-Deformationsanalyse für ein digitales Deformationsmodell. *Zeitschrift für Vermessungswesen*, 110(3), 67–74.
- Benning, W., Lange, J., Schwermann, R., Effkemann, C., Görtz, S., 2004. Monitoring Crack Origin and Evolution at Concrete Elements using Photogrammetry. *International Archives of Photogrammetry, Remote Sensing and Spatial Information Sciences*, XXXV-B5, 678-683.
- Botsch, M., Kobbelt, L., Pauly, M., Alliez, P., Levy, B., 2010. *Polygon Mesh Processing*. 1. Auflage, A K Peters/CRC Press.
- Brown, Duane, C., 1971. Close-Range Camera Calibration. *Photogrammetric Engineering*, 37(8), 855–866.
- Cooper, A. R., Robson, S., 1990. High Precision Photogrammetric Monitoring of the Deformation of a Steel Bridge. *The Photogrammetric Record*, 13(76), 505–510.

- Cramer, G., 1750. *Introduction à l'analyse des lignes courbes algébriques*. À Genève, chez les frères Cramer et C. Philibert.
- Curosu, I., Liebscher, M., Mechtcherine, V., Bellmann, C., Michel, S., 2017. Tensile Behavior of High-strength Strain-hardening Cement-based Composites (HS-SHCC) Made with High-performance Polyethylene, Aramid and PBO Fibers. *Cement and Concrete Research*, 98, 71–81.
- Curosu, I., Mechtcherine, V., Forni, D., Cadoni, E., 2017. Performance of Various Strain-hardening Cement-based Composites (SHCC) Subject to Uniaxial Impact Tensile Loading. *Cement and Concrete Research*, 102, 16–28.
- Dare, P., Hanley, H., Fraser, C., Riedel, B., Niemeier, W., 2002. An Operational Application of Automatic Feature Extraction: The Measurement of Cracks in Concrete Structures. *The Photogrammetric Record*, 17(99), 453–464.
- Detchev, I., Habib, A., El-Badry, M., 2012. Extraction of Cracks from Concrete Beam Images. *Proceedings of ASPRS 2012 Annual conference Sacramento, CA*.
- Detchev, I., Habib, A., El-Badry, M., 2013. Dynamic beam deformation measurements with off-the-shelf digital cameras. *Journal of Applied Geodesy*, 7(3), 147–157.
- Detchev, I., Habib, A., Lichti, D., El-Badry, M., 2016. Structural 3D Monitoring using a New Sinusoidal Fitting Adjustment. *ISPRS Annals of Photogrammetry, Remote Sensing and Spatial Information Sciences*, III-5, 3–10.
- Fedele, R., Galantucci, L., Ciani, A., 2013. Global 2D Digital Image Correlation for Motion Estimation in a Finite Element Framework: A Variational Formulation and a Regularized, Pyramidal, Multi-grid Implementation. *International Journal for Numerical Methods in Engineering*, 96(12), 739–762.
- Fedele, R., Scaioni, M., Barazzetti, L., Rosati, G., Biolzi, L., 2014. Delamination Tests on CFRP-reinforced Masonry Pillars: Optical Monitoring and Mechanical Modeling. *Cement and Concrete Composites*, 45, 243–254.
- Förstner, W., 1984. Quality Assessment of Object Location and Point Transfer using Digital Image Correlation Techniques. *International Archives of Photogrammetry*, XXV-3A, 197–219.
- Fraser, C. S., Riedel, B., 2000. Monitoring the Thermal Deformation of Steel Beams via Vision Metrology. *ISPRS Journal of Photogrammetry and Remote Sensing*, 55(4), 268–276.
- Ghorbani, R., Matta, F., Sutton, M., 2014. Full-field Deformation Measurement and Crack Mapping on Confined Masonry Walls using Digital Image Correlation. *Experimental Mechanics*, 55(1), 227–243.
- Görtz, S., 2004. Zum Schubrissverhalten von Stahlbeton- und Spannbetonbalken aus Normal- und Hochleistungsbeton. Dissertation, RWTH Aachen.

- Grün, A., 1985. Adaptive Least Squares Correlation: A Powerful Image Matching Technique. *South African Journal of Photogrammetry, Remote Sensing and Cartography*, 14(3), 175–187.
- Grün, A., 2012. Development and Status of Image Matching in Photogrammetry. *The Photogrammetric Record*, 27(137), 36–57.
- Guerrero, N., Martinez, M., Picón, R., Marante, M. E., Hild, F., Roux, S., Florez-Lopez, J., 2014. Experimental Analysis of Masonry Infilled Frames using Digital Image Correlation. *Materials and Structures*, 47(5), 873–884.
- Hampel, U., Maas, H.-G., 2003. Application of Digital Photogrammetry for Measuring Deformation and Cracks During Load Tests in Civil Engineering Material Testing. *Proceedings of Optical 3-D Measurement Techniques VI*, 2, A. Grün, 80–88.
- Hampel, U., Maas, H.-G., 2009. Cascaded Image Analysis for Dynamic Crack Detection in Material Testing. *ISPRS Journal of Photogrammetry and Remote Sensing*, 64(4), 345–350.
- Harris, C., Stephens, M., 1988. A Combined Corner and Edge Detector. *Proceedings of Fourth Alvey Vision Conference*, 147–151.
- Heravi, A. A., Curosu, I., Mechtcherine, V., 2020. A Gravity-driven Split Hopkinson Tension Bar for Investigating Quasi-ductile and Strain-hardening Cement-based Composites under Tensile Impact Loading. *Cement and Concrete Composites*, 105.
- Hoppe, H., DeRose, T., Duchamp, T., McDonald, J., Stuetzle, W., 1992. Surface Reconstruction from Unorganized Points. *Proceedings of the 19th Annual Conference on Computer Graphics and Interactive Techniques*, SIGGRAPH '92, ACM, New York, NY, USA, 71–78.
- Irwin, G. R., 1958. *Fracture*. Springer Berlin Heidelberg, 551–590.
- Keil, S., 2017. *Dehnungsmessstreifen*. 2. Auflage, Springer Vieweg, Wiesbaden.
- Kersten, T., Maas, H.-G., Piezzi, K., Schmassmann, E., 1995. Photogrammetrische Punktbestimmung bei der Überwachung von Staumauern. *Vermessung, Photogrammetrie, Kulturtechnik*, 93(4), 216–220.
- Köppel, S., 2000. Schallemissionsanalyse zur Untersuchung von Stahlbetontragwerken. Dissertation, ETH Zürich.
- Koschitzki, R., Maas, H.-G., 2012. Vergleich photogrammetrischer und akustischer Messverfahren zur Rissdetektion bei Belastungsversuchen im Stahlbetonbau. *Allgemeine Vermessungsnachrichten*, 119(1), 3–10.
- Koschitzki, R., Schacht, G., Schneider, D., Marx, S., Maas, H.-G., 2011. Integration of Photogrammetry and Acoustic Emission Analysis for Assessing Concrete

- Structures during Loading Tests. *Proceedings of SPIE Optical Metrology*, 8085, International Society for Optics and Photonics.
- Lange, J., 2009. Mess- und Auswertungstechnik zur Riss- und Faserdetektion bei Betonbauteilen. Dissertation, RWTH Aachen.
- Lange, J., Benning, W., 2006. Crack Detection using Photogrammetry. *Proceedings of 9th European Conference on Non-Destructive Testing*, Berlin, BB 103-CD, NDT, German Society for Non-Destructive Testing, 1–8.
- Lange, J., Benning, W., Siering, K., 2006. Crack Detection at Concrete Construction Units from Photogrammetric Data using Image Processing Procedures. *International Archives of Photogrammetry, Remote Sensing and Spatial Information Sciences*, XXXVI-7, 493-496.
- Liebold, F., Maas, H.-G., 2016. Advanced Spatio-temporal Filtering Techniques for Photogrammetric Image Sequence Analysis in Civil Engineering Material Testing. *ISPRS Journal of Photogrammetry and Remote Sensing*, 111, 13–21.
- Liebold, F., Maas, H.-G., 2018. Sub-pixel Accuracy Crack Width Determination on Concrete Beams in Load Tests by Triangle Mesh Geometry Analysis. *ISPRS Annals of Photogrammetry, Remote Sensing and Spatial Information Sciences*, IV-2, 193–200.
- Liebold, F., Maas, H.-G., Heravi, A. A., 2019. Crack Width Measurement for Non-planar Surfaces by Triangle Mesh Analysis in Civil Engineering Material Testing. *ISPRS - International Archives of the Photogrammetry, Remote Sensing and Spatial Information Sciences*, XLII-2/W18, 107–113.
- Lloyd, S. P., 1982. Least Squares Quantization in PCM. *IEEE Transactions on Information Theory*, 28(2), 129–137.
- Lowe, D. G., 2004. Distinctive Image Features from Scale-invariant Keypoints. *International Journal of Computer Vision*, 60(2), 91–110.
- Maas, H.-G., 1998. Photogrammetric techniques for deformation measurements on masonry reservoir walls. *IAG SC4 Symposium on Geodesy for Geotechnical and Structural Engineering*, Eisenstadt, Austria, 319–324.
- Maas, H.-G., 2012. Digitale Nahbereichsphotogrammetrie im bautechnischen Versuchswesen. *Bautechnik*, 89(11), 786–793.
- Maas, H.-G., Hampel, U., 2006. Photogrammetric Techniques in Civil Engineering Material Testing and Structure Monitoring. *Photogrammetric Engineering and Remote Sensing*, 72(1), 39–45.
- Maas, H.-G., Stefanidis, A., Grün, A., 1994. From Pixels to Voxels: Tracking Volume Elements in Sequences of 3D Digital Images. *International Archives of Photogrammetry, Remote Sensing and Spatial Information Sciences*, XXX-3/2, 539–546.

- Moes, N., Dolbow, J., Belytschko, T., 1999. A Finite Element Method for Crack Growth without Remeshing. *International Journal for Numerical Methods in Engineering*, 46(1), 131–150.
- Möser, M., Müller, G., Potthoff, H., Schulz, H.-U., Hoffmeister, H., Wanninger, L., Ingensand, H., 2000. *Handbuch Ingenieurgeodäsie: Grundlagen*, 3. Auflage, Herbert Wichmann Verlag.
- Möser, M., Hoffmeister, H., Müller, G., Staiger, R., Wanninger, L., 2012. *Handbuch Ingenieurgeodäsie: Grundlagen*, 4. Auflage, Herbert Wichmann Verlag.
- Niemeier, W., Riedel, B., Fraser, C., Neuss, H., Stratmann, R., Ziem, E., 2008. New Digital Crack Monitoring System for Measuring and Documentation of Width of Cracks in Concrete Structures. *Proceedings of 13th FIG International Symposium on Deformation Measurements and Analysis, Lisbon*, 12–15.
- Niemeier, W., Stratmann, R., Fraser, C., Neuss, H., Riedel, B., Ziem, E., 2007. Rissmonitoring in der modernen Bauwerksunterhaltung. *Der Prüfenieur*, 31, 51–59.
- North, G. R., Bell, T. L., Cahalan, R. F., Moeng, F. J., 1982. Sampling Errors in the Estimation of Empirical Orthogonal Functions. *Monthly Weather Review*, 110(7), 699–706.
- Pearson, K., 1901. LIII. On Lines and Planes of Closest Fit to Systems of Points in Space. *The London, Edinburgh, and Dublin Philosophical Magazine and Journal of Science*, 2(11), 559–572.
- Preisendorfer, R. W., 1988. *Principal component analysis in meteorology and oceanography*. Developments in atmospheric science, Elsevier Amsterdam.
- Qi, X., Lichti, D. D., El-Badry, M., Chan, T. O., El-Halawany, S. I., Lahamy, H., Steward, J., 2014. Structural Dynamic Deflection Measurement with Range Cameras. *The Photogrammetric Record*, 29(145), 89–107.
- Rosten, E., Porter, R., Drummond, T., 2010. Faster and Better: A Machine Learning Approach to Corner Detection. *Pattern Analysis and Machine Intelligence, IEEE Transactions on*, 32(1), 105–119.
- Schacht, G., 2014. Experimentelle Bewertung der Schubtragsicherheit von Stahlbetonbauteilen. Dissertation, Technische Universität Dresden.
- Tomasi, C., Manduchi, R., 1998. Bilateral Filtering for Gray and Color Images. *Proceedings of the Sixth International Conference on Computer Vision*, IEEE, 839–846.
- Weichert, N., Wülker, M., 2000. *Messtechnik und Messdatenerfassung*. Oldenbourg Verlag München Wien.
- Whiteman, T., Lichti, D., Chandler, I., 2002. Measurement of Deflections in Concrete Beams by Close-range Digital Photogrammetry. *International*

Archives of Photogrammetry, Remote Sensing and Spatial Information Sciences, XXXIV-4.

Wouters, B., Schrama, E. J. O., 2007. Improved Accuracy of GRACE Gravity Solutions through Empirical Orthogonal Function Filtering of Spherical Harmonics. *Geophysical Research Letters*, 34(23).

Abkürzungsverzeichnis

2D, 3D	Zweidimensional, Dreidimensional
CCD	Charged Coupled Device
CDF	Cumulative Distribution Function
CT	Computertomographie
DFT	Discrete Fourier Transform
DIC	Digital Image Correlation
DMS	Dehnungsmessstreifen
EOF	Empirical Orthogonal Function/ empirische Orthogonalfunktionen
FAST	Features from Accelerated Segment Test
GRACE	Gravity Recovery And Climate Experiment
IWA	Induktiver Wegaufnehmer
KS	Kolmogorov-Smirnov-Test
KS2	Kolmogorov-Smirnov-Test für weißes Rauschen
LSM	Least Squares Matching
LVDT	Linear Variable Differential Transformer
MAD	Median Absolute Deviation
PCA	Principle Component Analysis
PSD	Power Spectrum Density
RMS	Root Mean Square
SEA	Schallemissionsanalyse
SHCC	Strain-Hardening Cement-based Composites
SIFT	Scale Invariant Feature Transform
SURF	Speeded-Up Robust Features
TIN	Triangulated Irregular Network

Tabellenverzeichnis

Tabellen in P.I

Tabelle 2.1.1 Kolmogorov-Smirnov-Variable für den Schwellwert.....	15
Tabelle 2.1.2 Vergleich der Filtermethoden.....	17

Tabellen in P.II

Tabelle 2.2.1 Nummerierung der Algorithmen.....	25
Tabelle 2.2.2 Statistische Werte der Residuen zwischen Algorithmus 1 und 2.....	25
Tabelle 2.2.3 Statistische Werte der Residuen zur manuellen Messung.....	26
Tabelle 2.2.4 Statistische Werte der Residuen ohne Ausreißer.....	26

Tabellen in P.III

Tabelle 2.3.1 Sollrelativtranslationen im Referenz- und deformierten Zustand...	42
---	----

Abbildungsverzeichnis

Abbildungen in Kapitel 1

Abbildung 1.1 Dehnungsmessstreifen, Wegaufnehmer, Neigungssensor.....	2
Abbildung 1.2 Schallemissionsanalyse.....	3
Abbildung 1.3 Rissbreitenlineal.....	4

Abbildungen in P.I

Abbildung 2.1.1 Versuchsaufbau Biegeversuch.....	12
Abbildung 2.1.2 Farbkodierte Visualisierung der Hauptdehnungen.....	12
Abbildung 2.1.3 Dehnungskarten mit unterschiedlichen Farbkodierungen.....	12
Abbildung 2.1.4 Hauptdehnungsstandardabweichung nach Seitenlängen.....	12
Abbildung 2.1.5 Nachbardreiecke.....	13
Abbildung 2.1.6 Sägezahnfilter kontinuierlich und diskret.....	13
Abbildung 2.1.7 Dehnungskarten, Vergleich EOF-Filtermethoden.....	16
Abbildung 2.1.8 Dehnungskarten mit verschiedenen Filtern.....	16
Abbildung 2.1.9 Dehnungskarten mit verschiedenen Filtern (spätere Epoche).....	17

Abbildungen in P.II

Abbildung 2.2.1 Versuchsaufbau Biegeversuch.....	21
--	----

Abbildung 2.2.2 Dreiecksnetz aus Interestpunkten.....	21
Abbildung 2.2.3 Farbkodierte Visualisierung der Hauptdehnungen.....	21
Abbildung 2.2.4 Zusammenhangskomponenten deformierter Dreiecke.....	22
Abbildung 2.2.5 Teilung eines Dreiecks durch Riss.....	22
Abbildung 2.2.6 Rissbreitenberechnung durch Schnitt Rissnormale-Basis 1.....	22
Abbildung 2.2.7 Rissbreitenberechnung durch Schnitt Rissnormale-Basis 2.....	22
Abbildung 2.2.8 Rissbreitenberechnung mit Höhendifferenz 1.....	23
Abbildung 2.2.9 Rissbreitenberechnung mit Höhendifferenz 2.....	23
Abbildung 2.2.10 Scherkräfte.....	23
Abbildung 2.2.11 Bestimmung der Rissnormale.....	24
Abbildung 2.2.12 Zerlegung der Relativtranslation beim Riss.....	24
Abbildung 2.2.13 Geteiltes Dreieck und transformiertes Referenzdreieck.....	24
Abbildung 2.2.14 Histogramm der Residuen zwischen Algorithmus 1 und 2.....	25
Abbildung 2.2.15 Farbkodierte Visualisierung der Rissbreiten.....	26
Abbildung 2.2.16 Manuelle Rissbreitenmessung.....	26
Abbildung 2.2.17 Histogramme der Residuen der Rissbreiten.....	26

Abbildungen in P.III

Abbildung 2.3.1 Rissbild mit multipler Rissstruktur.....	31
Abbildung 2.3.2 Dreiecksnetz verfolgter Punkte.....	32
Abbildung 2.3.3 Farbkodierte Visualisierung der Hauptdehnungen.....	32
Abbildung 2.3.4 Vergleich Modelle: elastische Deformation bzw. Teilung.....	32
Abbildung 2.3.5 Vergleich der Modelle im Dreiecksnetz.....	33
Abbildung 2.3.6 Abhängigkeit Dreiecksgröße auf Hauptdehnung.....	33
Abbildung 2.3.7 Triangulation erfolgreich verfolgter Punkte.....	33
Abbildung 2.3.8 Fälle für Relativbewegungen bei gleicher Relativtranslation.....	33
Abbildung 2.3.9 Flussdiagramm zur Rissbreitenberechnung.....	34
Abbildung 2.3.10 Erfolg der Bildpunktzuordnung beim Riss.....	34
Abbildung 2.3.11 Ausgedünntes Dreiecksnetz.....	35
Abbildung 2.3.12 Reduzierte Punktauswahl und Vernetzung.....	35
Abbildung 2.3.13 Unterteilung des deformierten Dreiecks.....	36
Abbildung 2.3.14 Verdichtung des Dreiecksnetzes.....	36
Abbildung 2.3.15 Punktmengen auf beiden Risseiten.....	36
Abbildung 2.3.16 Beispiel Punktklassifikation.....	37
Abbildung 2.3.17 K-means-Klassifikation mit Translationen.....	37
Abbildung 2.3.18 K-means-Klassifikation mit Rotationen.....	37
Abbildung 2.3.19 Visualisierung der Relativtranslationen für 4 Epochen.....	39

Abbildung 2.3.20 3D-Visualisierung der Beträge der Relativtranslationen.....	40
Abbildung 2.3.21 Vergleich Hauptdehnungen und Relativtranslationen.....	40
Abbildung 2.3.22 Referenzbild und 3 Fälle von Verschiebungen.....	40
Abbildung 2.3.23 Visualisierung der Beträge der Relativtranslationen.....	41
Abbildung 2.3.24 Streuung der Relativtranslationen (3 Punkte, $v=0,2$ px)	42
Abbildung 2.3.25 Streuung der Relativtranslationen (Ausgleichung, $v=0,2$ px)	43
Abbildung 2.3.26 Streuung der Relativtranslationen (3 Punkte, $v=0,6$ px)	43
Abbildung 2.3.27 Streuung der Relativtranslationen (Ausgleichung, $v=0,6$ px)	44
Abbildung 2.3.28 Äußere und innere Genauigkeiten der Relativtranslationen.....	44
Abbildung 2.3.29 Ausreißeranteil.....	45
Abbildung 2.3.30 Äußere und innere Genauigkeiten der Rissbreiten.....	45
Abbildung 2.3.31 Dreiecksdeformation mit Riss.....	46
Abbildung 2.3.32 Relativer Translationsvektor nach Transformation.....	47
Abbildung 2.3.33 Scherungseffekte beim Riss.....	47
Abbildung 2.3.34 Rissnormalenbestimmung.....	48

Abbildungen in P.IV

Abbildung 3.1.1 Versuchsaufbau.....	53
Abbildung 3.1.2 Stereohochgeschwindigkeitskamera.....	53
Abbildung 3.1.3 Bildpunktzuordnung Stereokamera, Vorwärtsschnitte.....	53
Abbildung 3.1.4 Dreiecksnetz.....	53
Abbildung 3.1.5 Flussdiagramm zur Berechnung der Rissbreite.....	53
Abbildung 3.1.6 Dreiecksdeformation mit Riss.....	54
Abbildung 3.1.7 Relativtranslationsvektor im 2D-Raum nach Transformation.....	54
Abbildung 3.1.8 Bestimmung der Rissrichtung.....	55
Abbildung 3.1.9 Bestimmung der Rissnormalen.....	55
Abbildung 3.1.10 Visualisierung Relativtranslationsvektorbetrag, 5 Epochen.....	56
Abbildung 3.1.11 Zusammenhangskomponenten nach Schwellwertverfahren...56	
Abbildung 3.1.12 Histogramme der Rissbreiten in Epoche 25.....	56
Abbildung 3.1.13 Histogramme der Rissbreiten in Epoche 29.....	57
Abbildung 3.1.14 Vergleich der Rissbreitensummen mit Wellenanalyse.....	57
Abbildung 3.1.15 Standardabweichung der Rissbreiten.....	57

Abbildungen in P.V

Abbildung 3.2.1 Referenz- und Rissbild einer zylindrischen Betonprobe.....	61
Abbildung 3.2.2 Farbkodierte Visualisierung der Rissbreiten.....	61
Abbildung 3.2.3 Bildpunktzuordnung Stereokamera, Vorwärtsschnitte, Netz.....	61

Abbildung 3.2.4 Relativer Translationsvektor nach Kongruenzabbildung.....	62
Abbildung 3.2.5 Deformierte Dreiecke.....	62
Abbildung 3.2.6 Block mit Riss und 3D-Verschiebung, geteiltes Dreieck.....	62
Abbildung 3.2.7 Punktmengen im mathematischen Modell.....	62
Abbildung 3.2.8 Rissdreieck und undeformiertes Nachbardreieck.....	63
Abbildung 3.2.9 Klassifikation zu Punktmengen mit Nachbardreiecken.....	63
Abbildung 3.2.10 Orientierung der relativen Translationsvektoren.....	64
Abbildung 3.2.11 Rissöffnungskoordinatensystem.....	65
Abbildung 3.2.12 Richtung des Rissverlaufs.....	65
Abbildung 3.2.13 Richtung des Rissverlaufs, Alternative.....	65
Abbildung 3.2.14 Risskreuzung.....	65
Abbildung 3.2.15 Bestimmung der Rissnormale.....	65
Abbildung 3.2.16 Relativtranslations- und Rissöffnungsvektoren bei Torsion.....	66
Abbildung 3.2.17 Versuchsaufbau.....	66
Abbildung 3.2.18 Induktiver Wegaufnehmer und Mikrometerschraube.....	66
Abbildung 3.2.19 Reihenfolge der Messungen in der x-y-Ebene.....	66
Abbildung 3.2.20 Farbkodierte Visualisierung und Relativtranslationsvektoren. .	67
Abbildung 3.2.21 Streuung der Relativtranslationsvektoren.....	67
Abbildung 3.2.22 Konfidenzellipsoide der Relativtranslationsvektoren.....	67
Abbildung 3.2.23 Streuung der Rissöffnungsvektoren.....	67
Abbildung 3.2.24 Konfidenzellipsoide der Rissöffnungsvektoren, Restfehler.....	67
Abbildung 3.2.25 Maximale Eigenwerte der Kovarianzmatrizen, Präzision.....	68
Abbildung 3.2.26 Abweichung Soll-Ist.....	68
Abbildung 3.2.27 Abweichung Soll-Ist für Alternativrissrichtung.....	68

Abbildungen in Kapitel 4

Abbildung 4.1 Flussdiagramm zur Einordnung der Publikationen.....	71
Abbildung 4.2 Dreiecksdeformation mit Riss.....	73

Abbildungen in Kapitel 5

Abbildung 5.1 Analyse der Nachbardreiecke.....	78
Abbildung 5.2 Tetraederdeformation Fall 1.....	80
Abbildung 5.3 Tetraederdeformation Fall 2.....	80
Abbildung 5.4 Rissanalysealgorithmus für Tetraeder mit Fallunterscheidung.....	81