TECHNISCHE UNIVERSITÄT DRESDEN

Fakultät Bauingenieurwesen
Institut für Stadtbauwesen und Straßenbau

**Performance-based characterisation of Bitumen and
Mastic using the DSR**

Performance-basierte Charakterisierung von Bitumen und
Mastix unter Verwendung des DSR

Zur Erlangung des akademischen Grades Doktor-Ingenieur (Dr.-Ing.) an der Fakultät
Bauingenieurwesender Technischen Universität Dresden eingereichte

DISSERTATION

von

Mrinali Rajkumar Rochlani, M.Sc.

geb. am 21. Januar 1992 in Thane, Indien

Gutachter:

Prof. Dr.-Ing. habil. Frohmuth Wellner (TU Dresden)

Prof. Dr.-Ing. Martin Radenberg (Ruhr-Universität Bochum)

Prof. Dr.-Ing. habil. Markus Oeser (RWTH Aachen)

Tag der Einreichung: 26. October 2020

Tag der Verteidigung: 23. March 2021

ABSTRACT

This dissertation presents the results of research undertaken for the characterization of bitumen and mastic which are constituents of Hot Mix Asphalt (HMA).

The results of a large number of Dynamic Shear Rheometer (DSR) tests performed in the Laboratory of the Institute for Pavement Engineering at the TU Dresden form the background material for this work. The major objectives of this PhD research work were to gain a fundamental understanding about the mechanical behaviour of bitumen and mastic. The DSR tests undertaken included frequency sweeps for rheological behaviour, single stress creep recovery test (SSCR) for permanent deformation behaviour, Dresden cryogenic test (DDCT) for low temperature performance and fatigue testing with column cylindrical specimen. Selected tests were carried out on bitumen and mastic also to investigate the sensitivity of the materials to ageing. The frequency sweep data was also modelled using an appropriate rheological model to derive rheological data over a large frequency and temperature range. Based on the tests conducted, particular chosen parameters calculated were synthesized into a performance diagram which was developed within the framework of the dissertation. This was the main outcome of the PhD research work, which allows for optimum bitumen and mastic selection and ranking in terms of overall performance and specific desired criteria.

Since this dissertation is a cumulative dissertation, it has been divided into three distinct parts.

The first part forms a framework of the research undertaken and justifies the need and use of the dissertation in the future, along with explaining the test procedures in detail and resulting performance diagram developed using the data of three bitumen of the same penetration grade.

The main part involves the published research – four journal papers and one chapter published in conference proceedings. The first paper uses the method developed to study one base bitumen and corresponding mastics with Limestone, Dolomite, Rhyolite and Granodiorite fillers. Other than understanding how fillers influence different mechanical properties, a main finding was that the specific surface area of the filler was the most sensitive parameter affecting the mechanical response of the mastics. Also, it was observed that the mastic prepared with Granodiorite filler showed the best fatigue and rutting resistance for this particular bitumen.

Hence, the procedure could help identifying optimum filler-bitumen relations in advance. The second paper was about crumb rubber modified bitumen. This involved the study of four materials – one base bitumen and two different types of crumb rubber added different proportions. The results indicated an improvement in all performance-related properties by crumb rubber addition in bitumen and further allowing the ranking of materials. The third paper studied the feasibility of recycling a waste Ceramic powder as a filler alternative and it was found to have more superior performance than the commonly used Limestone filler. The fourth paper considers how addition of one filler, Limestone, to three differently-sourced bitumen of the same grade affects the properties of mastics. This study further emphasises the need to study mastics and predetermine the optimum filler-bitumen combinations that could avoid long-term maintenance costs. The fifth paper emphasises the need to move from current empirical testing to more specialised testing for bitumen by presenting different performance based results for three commonly used bitumen of penetration grade 50/70 that showed significant differences in the performance parameters.

The third part of the dissertation is an additional section that includes the paper that was submitted to a journal and is currently in the second round of reviews under review. This paper studies fatigue behaviour of bitumen at different temperatures and frequencies using the Dissipated Energy (DE) approach. Fatigue functions were determined based on the relation between DE and the load cycle at failure. Based on these, a temperature was found to be a ‘frequency-free transition temperature’ for this bitumen as the failure lines at this temperature were overlapping at both frequencies tested.

KURZFASSUNG

Diese Dissertation präsentiert die Ergebnisse einer Forschungsarbeit zur Charakterisierung von Bitumen und Mastix, die als Bestandteil von Asphaltgemischen verwendet werden.

Die Ergebnisse einer großen Anzahl von Dynamisches Scherrheometer (DSR) Versuche, die im Labor des Instituts für Stadtbauwesen und Straßenbau der TU Dresden durchgeführt wurden, bilden die Grundlage für diese Arbeit. Das Hauptziel dieser Dissertation bestanden darin, ein grundlegendes Verständnis über das mechanische Verhalten von Bitumen und Mastix zu gewinnen. Die durchgeführten DSR Versuche umfassten Frequenzsweeps für die Erfassung des rheologischen Verhaltens, Single Stress Creep Recovery Versuche (SSCR) für die Charakterisierung des permanenten Verformungsverhaltens, Dresden Cryogenic (DDCT) Versuche zur Erfassung des Verhaltes bei niedrigen Temperaturen und Ermüdungsversuche. Des Weiteren wurden ausgewählte Versuche am Bitumen und Mastix durchgeführt, um die Alterungsempfindlichkeit der Materialien zu untersuchen. Die Ergebnisse der Frequenzsweeps wurden ebenfalls mit einem geeigneten rheologischen Ansatz modelliert, um rheologische Charakteristiken über einen großen Frequenz- und Temperaturbereich abzuleiten. Schließlich wurde im Rahmen der Dissertation ein Performancediagramm für Bitumen und Mastix entwickelt. Auf der Grundlage der durchgeführten DSR-Versuche konnten Parameter für dieses Performancediagramm synthetisiert werden.

Da es sich bei dieser Arbeit um eine kumulative Dissertation handelt, wurde erfolgte eine Aufgliederung in drei Teile.

Der erste Teil der Arbeit umfasst eine Zusammenfassung der durchgeführten Forschungsarbeiten. Insbesondere werden die durchgeführten DSR Versuche detailliert erläutert und das entwickelte Performancediagramm am Beispiel von drei verschiedenen Bitumen 50/70 dargestellt.

Der Hauptteil der Arbeit umfasst vier Veröffentlichungen in Fachzeitschriften sowie ein Konferenzbeitrag. Die erste Beitrag widmet sich der Untersuchung des Einflusses von verschiedenen Füllern (Kalkstein-, Dolomit-, Rhyolith- und Granodioritfüller) auf das Verhalten von Mastix unter Verwendung desselben Bitumens 50/70. Dabei hat sich gezeigt,

dass die spezifische Oberfläche des Füllers der entscheidende Parameter ist, der das Verhalten von Mastix beeinflusst. Es wurde auch beobachtet, dass der mit Granodiorit-Füller hergestellte Mastix die beste Ermüdungs- und Spurrinnenbeständigkeit für dieses spezielle Bitumen zeigt. Daher könnte das in der Veröffentlichung vorgestellte Verfahren dazu beitragen, das optimale Verhältnis zwischen Füller und Bitumen im Voraus zu ermitteln. Die zweite Veröffentlichung befasst sich mit gummimodifiziertem Bitumen. Dabei wurden vier Materialien untersucht - ein Grundbitumen und zwei verschiedene Arten von Gummigranulaten mit unterschiedlichen Anteilen. Die Ergebnisse zeigten eine Verbesserung aller leistungsbezogenen Eigenschaften durch den Zusatz von Gummigranulat im Bitumen. Die dritte Veröffentlichung untersuchte die Eignung von Keramikmehl als Füller für Asphaltgemische. Dabei konnte festgestellt werden, dass dieser Keramikfüller zu besseren Eigenschaften des Mastix für das verwendete Bitumen im Vergleich zu einem Kalksteinfüller führt. Die vierte Veröffentlichung befasst sich hier mit der Frage, wie sich die Zugabe eines Füllers (Kalkstein-Füller) zu drei Bitumen unterschiedlicher Provenienz, jedoch derselben Sorte auf die Eigenschaften von Mastix auswirkt. Diese Studie unterstreicht weiter die Notwendigkeit, Mastix zu untersuchen um die optimalen Füller-Bitumen-Kombinationen zu bestimmen. Die fünfte Veröffentlichung betont die Notwendigkeit, von den derzeitigen empirischen Versuchen an Bitumen, wie z.B. Ring und Kugel Versuch zu performance-orientierten Versuchen für Bitumen überzugehen. Am Beispiel der Ergebnisse von DSR Versuchen an drei verschiedenen Bitumen 50/70 wird gezeigt, dass diese Bitumen sehr unterschiedliches mechanisches Verhalten aufweisen. Verdeutlicht wird dieser Sachverhalt in einem Performance-Diagramm, welches ausführlich in der Veröffentlichung diskutiert wird.

Der dritte Teil der Dissertation beinhaltet eine Veröffentlichung, die bei Fachzeitschriften eingereicht wurde und sich derzeit im Review befindet. Zusätzlich wurde in dieser Arbeit das Ermüdungsverhalten von Bitumen bei verschiedenen Temperaturen und Frequenzen mit Hilfe des Dissipated Energy (DE)-Ansatzes untersucht. Die Versagenslinien wurden auf der Grundlage der Beziehung zwischen DE und der Lastwechselzahl beim Versagen entwickelt. Auf dieser Grundlage wurde eine Temperatur als "frequenzfreie Übergangstemperatur" für dieses Bitumen ermittelt, da sich die Ermüdungsfunktionen bei dieser Temperatur bei beiden getesteten Frequenzen überlappen.

ACKNOWLEDGMENTS

I express sincere gratitude to my Doktorvater, Prof. Dr.-Ing. habil. Frohmut Wellner of Technische Universität Dresden for giving me the opportunity to do my PhD under his supervision and present my work at multiple conferences. I am eternally grateful to him for providing guidance at every step of the way and for always being immensely kind, patient, supportive & encouraging throughout the process. I have grown as a person and learnt a lot from him. I would also like to thank Prof. Dr.-Ing. Martin Radenberg of Ruhr-Universität Bochum and Dr.-Ing. habil. Markus Oeser of RWTH Aachen Universität for taking time out of their busy schedules for me and for providing me with valuable feedback and guidance for improving my dissertation.

I heartily thank Dr.-Ing. habil. Sabine Leischner for her continuous guidance and encouragement along this PhD journey and for always being patient with me. It would be impossible to complete my PhD without her constant direction and optimism. My sincere gratitude to Gustavo Canon Falla M.Sc. for his guidance and support through each step of the scientific tasks. His goodwill and kindness have enabled me to complete my work efficiently. I would also like extend my thanks to Andreas Otto, René Schubert and Jacqueline Radtke for helping and providing guidance with laboratory procedures.

My hearty gratitude to the Graduate Academy and TU Dresden for providing the funding for my PhD under the scholarship program of ‘Promotion of Early-Career Female Scientists at TU Dresden.’ A sincere thanks to Ms. Vivien Lippmann for her patience and guidance throughout the scholarship program. I would also like to thank DFG (Deutsche Forschungsgemeinschaft) and FOR 2089 for providing part of the funding, equipment and materials.

I am eternally grateful to Prof. Dr. Silvia Caro Spinel of Universidad de Los Andes, Colombia for her constant guidance, advice and collaboration throughout my PhD process. I am forever indebted to her for the time and effort she has taken to help me every time. It would be impossible to have finished my PhD without her constant motivation and humour. I would also like to thank Prof. Dr. David Wareham of University of Canterbury, New Zealand for teaching me about not only life but also key research paper writing skills. They both have not only made paper writing truly a fun process but have contributed in my development as a researcher and an individual!

Last but not the least, I would like to wholeheartedly thank my family - Dadashri, Ambalal M. Patel, my parents, Geeta and Rajkumar Rochlani and my siblings, Toshina and Alcide. Because of their unconditional love, support and encouragement, I am where I am and could complete my PhD in due time.

Dresden, 21th October 2020

Mrinali Rochlani

DECLARATION OF INDEPENDENT WORK

I confirm that this assignment is my own work and that I have not sought or used inadmissible help of third parties to produce this work. I have fully referenced and used inverted commas for all text directly quoted from a source. Any indirect quotations have been duly marked as such.

This work has not yet been submitted to another examination institution – neither in Germany nor outside Germany – neither in the same nor in a similar way and has not yet been published.

Papers published and submitted manuscript specific declarations are presented for each paper in Part II and Part III respectively, that confirm that most of the work was done by me and is co-signed by all co-authors.

Dresden, 21th October 2020

Mrinali Rochlani

Dedicated to my family.

Table of Contents

Part I - Introduction & Summary Part III - Submitted Manuscripts

1	Introduction	1
1.1	Background.....	1
1.2	Current Challenges	2
1.3	Aim of the Thesis	5
1.4	Scope of the Thesis	5
2	Summary of Research	6
2.1	Asphalt and its Constituents.....	6
2.1.1	Asphalt	6
2.1.2	Bitumen	7
2.1.3	Fillers.....	9
2.1.4	Aggregates.....	10
2.1.5	Voids	10
2.2	Mechanical Properties of Asphalt.....	10
2.3	Existing Test Methods for Bitumen and Mastics	12
2.3.1	Bitumen Testing	12
2.3.1.1	Traditional Testing Methods	12
2.3.1.2	Advanced Testing Methods.....	14
2.3.1.3	Bitumen Standardisation	15
2.3.2	Mastic Testing	17
2.4	Dynamic Shear Rheometer.....	18
2.5	DSR Laboratory Procedure	19
2.5.1	Shear Strain & Frequency Sweep Tests	20
2.5.2	Single Stress Creep Recovery (SSCR).....	24
2.5.3	Cryogenic Tests (Dresden Cryogenic Tests (DDRT))	25
2.5.4	Fatigue Tests	27
2.6	Performance Diagram.....	32
3	Recommendation for Further research.....	33
4	Bibliography	34

Part II - Core Publications

Papers Published and Declaration of work done	43
--	-----------

Part III - Submitted Manuscripts

Papers Submitted to Journals and Declaration of work done	96
--	-----------

Table of Figures

Figure 1 a) Schematic DSR testing arrangement b) DSR at TU Dresden.....	19
Figure 2 Specimens for the strain frequency sweep (left), MSCR and cooling tests (middle), specimens for the fatigue tests (right) [21].....	20
Figure 3 Strain Sweep Test Results for a bitumen	21
Figure 4 Curve Shifting of the LVE Limit for a bitumen	21
Figure 5 Typical Frequency Sweep Test Results: (a) Isothermal Plots for $ G^* $ (b) Isothermal Plots for δ (c) Cole-Cole Plots (d) Black Diagram for a bitumen	22
Figure 6 Master curves of dynamic shear modulus for 3 bitumen (B1, B2, B3) in 3 aging conditions (unaged, RTFOT aged and PAV aged) [13].....	23
Figure 7 Ageing Index for dynamic shear modulus [70]	24
Figure 8 SSCR Test Results [13]	25
Figure 9 Full cryogenic cycle for the bitumen	26
Figure 10 Cooling Cycle of Bitumen [70]	27
Figure 11 Fatigue sample dimensions (left) and Silicone Mould (right) [89]	28
Figure 12 a) Typical Stress-Strain Cycle b) Resulting Hysteresis Loop [93].....	30
Figure 13 Stress fatigue curves for the bitumen tested	31
Figure 14 Performance Diagram [13]	33

Table of Tables

Table 1 - Paving Grade Bitumen Requirements [39]	16
Table 2 - Polymer Modified Bitumen Requirements[39]	17
Table 3 Results of the SSCR tests	25
Table 4 Cryogenic Stress parameters [70]	27
Table 5 Fatigue performance parameter.....	31

PART I

INTRODUCTION AND SUMMARY

1 INTRODUCTION

1.1 Background

Transportation is one of the most vital factors that affect the economic and social development of any nation. Any inadequacies in the transport system would hinder the socio-economic development and prosperity of any country. An efficient transportation system, therefore, is extremely critical for any country's success.

There are mainly four types of transportation - road transportation, rail transportation, water transportation, and air transportation. Road transportation is the most common mode of transport due to its flexibility, availability and relatively lower costs. Roads are like the intrinsic nerves that connect anything to everything. They are of utmost importance as they contribute to the overall performance and functioning of the community by providing connections between the rural and urban areas, as well as, the industrial and residential areas. Roads allow the movement of not only men and materials, but also utilities such as water, electrical wires and phone cables, among others.

Therefore, pavement design is a critical aspect of every urban community. The standard requirements of roads include safety and comfort for all its users – from the vehicle drivers to cyclists to pedestrians to the people using public transport. Furthermore, pavements should be economical, smooth, durable and have reduced noise pollution along with providing sufficient drainage facilities. In particular, it should be able to bear the subjected loads and distribute them onto a wider area of the soil subgrade below it. Based on their structural performances, pavements have been classified as rigid pavements and flexible pavements. Rigid pavements are made using Portland cement and aggregates while flexible pavements are made using bitumen and aggregates. The focus of this work is on flexible pavements.

Flexible pavements or asphalt pavements can be used for the construction of the upper layers of a pavement. While the main contents of an asphalt pavement are bitumen and aggregates, bitumen can also be combined with polymers, epoxies, recycled products like tyre rubbers and other additives to enhance the performance of the whole asphalt mix. The behaviour of the asphalt mainly depends on the performance and interaction between its constituents. Therefore,

for the design of pavements, understanding the material properties at different scales (i.e. microscale to macroscale) is imperative.

Furthermore, in recent years, due to the increase in population, the traffic volumes have also escalated at an exponential rate. This escalation in traffic volumes has led to pavements being subjected to higher loads at greater frequencies, which in turn causes greater damage in a reduced time. Therefore, the goal of pavement engineers is to continuously find solutions for more economical and durable pavements that require little to no maintenance and are also environmentally sustainable. One of the ways to improve pavements is by use and choice of optimum and advanced materials based on desired performance requirements. The material properties used in the pavement should, therefore, be evaluated more realistically and rationally, specifically in terms of dynamic stress-strain response which a pavement would be normally subjected to. While aggregates are available naturally and relatively abundantly, other materials like bitumen need industrial processing which makes them expensive and environmentally unfriendly. Therefore, the use of such materials should be minimised without affecting the structural requirement of the pavement. As engineers and researchers, it is imperative that we design futuristic pavements that are economical, durable and sustainable.

1.2 Current Challenges

Road transport infrastructure is an essential component of a competitive and successful industrial society. They also represent a very high economic value. The Federal Transport Infrastructure Plan 2030 of the German government takes this fact into account by planning total investments of approximately €130 billion for the maintenance and construction of the federal road network [1]. While the development of new vehicles and intelligent transport concepts in Germany is primarily driven by industry, relatively fewer major innovations have been made in the field of road transport infrastructure in recent decades. This deficit is due on the one hand to a lack of research funds, which, unlike the marketable products of the automotive industry, are not provided by industry but mainly from public resources, and on the other hand to relatively rigid regulations which are hardly suitable for stimulating the creativity and innovation of German industry, engineers and scientists. As a result, most of the bitumen testing done still includes the decades' old tests like penetration and ring and ball softening point tests. These tests are too empirical and do not provide sufficient performance-related properties but are still in use today.

These circumstances have contributed to the fact that an increasing number of cases of damage and cracking in asphalt layers of pavements from the building industry as well as from the road construction administration are increasingly being reported within the warranty period before the designed lifespan. This damage can be attributed to insufficient bitumen quality and aging processes. Age hardening of bitumen is a major problem that remarkably affects the durability of the pavement. Once the bitumen hardens, the overall mixture becomes brittle, and its ability to undertake stresses and strains due to traffic considerably reduce. As a result, deterioration due to easily induced cracking can occur. Along with this, the adhesion bond between the aggregates and bitumen weakens due to excessive hardening, which leads to a loss in materials, further weakening the whole mix. Therefore, aging mechanisms and effects need to be analysed in detail as it is of the utmost importance for durability.

Another important aspect to take into consideration is that even though the properties of bitumen greatly influence the characteristics of the mix, the filler-bitumen interaction and the effect of filler properties on the mix performance are not completely understood. The physical and chemical properties of fillers have shown to influence the rheological and mechanical properties of the pure binder. The mastic may therefore provide a better correlation to the final mix as it also considers the physiochemical aspects of the bitumen-filler interaction. Hence, mastic testing could in the future be an addition to existing binder tests.

Furthermore, owing to the rapid growth of traffic volumes and an increment in heavy good vehicles, the existing pavement structures are subjected to larger stresses induced due to the ever growing heavy traffic. In most of the cases, the structures are not designed to withstand these severe loads. This, thereby, leads to degradation at a faster rate. Additionally, a significant percentage of the road infrastructure in Europe was constructed between the 1960s to the 1980s, post-World War II, during the economic recovery phase [2,3]. These roads are old and have already reached their critical lifespan. With the expected increase in population, comes a greater demand for methods to efficiently rejuvenate existing infrastructure and extend pavement lifespans.

On the other side of the spectrum, there is a growing need for sustainability in construction. Bitumen is a natural resource and a non-renewable substance. The European Union in the past years has emphasized more on the dire need for the recycling of resources. Additionally, due to

global warming and climate change, the weather has become inconsistent and does not follow the same trends anymore. For example, some regions now experience flooding due to increased precipitation, while others may experience elevated daily temperatures. The climate changes directly affect the pavements and therefore make one question, whether the desired durability and structure stability could be acquired by the typical traditional design methods currently used.

From these challenges, comes the necessity to deepen our understanding of the constituents that make up a pavement and how their properties could be improved with little or no impact on the environment. There is also a need to rethink the pavement design methods, construction practices and maintenance of pavements to produce more durable, economical and sustainable pavement structures. It is critical to also consider the existing road infrastructure and question, how can they be adequately rehabilitated or reused and recycled. Furthermore, due to the limited finances in global budgets devoted to research and infrastructure, there is an urgency to develop dexterous economic solutions for road maintenance as well.

To overcome these problems and to prepare the road infrastructure for the demands of the future, new testing approaches are required for the assessment of the constituents of a pavement. There is an immediate need for an in-depth understanding of how the constituents in a typical pavement interact with one another in the inhomogeneous mix, how they behave when subjected to loading and how their properties change and evolve as time goes on. Since current test methods for bitumen are too basic, they fail to provide useful information about the rheological properties of bitumen, and hence, there is a necessity to modify and develop new, appropriate testing methods and procedures to obtain a comprehensive binder characterisation.

Therefore, in the last decades, there has been a shift in pavement research from focusing not only on a macro-scale but also on the micro-scale. In recent decades, there grew a need for not only asphalt testing but also bitumen performance testing, initiating in the US under the Strategic Highway Research Program [4,5]. Even though there has been significant growth in the study of bitumen behaviour in the last few years, the current literature is still relatively empirical and in a research and development phase instead of providing a definite understanding of complex fundamental bitumen phenomenon.

1.3 Aim of the Thesis

The purpose of this dissertation is to close the existing knowledge gaps and to add to the existing understanding of bitumen and mastics. The chief aim of the doctorate work was to develop a comprehensive testing methodology using the state-of-the-art DSR device, at TU Dresden's laboratory for Pavement Engineering, which could be used to derive the mechanical behaviour of bitumen and mastics. This procedure would include testing to acquire information about the rheological behaviour, fatigue resistance, permanent deformation and low temperature behaviour of the materials, along with aging susceptibility. Furthermore, these results would be summarised and synthesized for providing a means for efficiently ranking materials based on specific and overall mechanical performance.

The usage of the method would be then verified by testing a multitude of materials that include unmodified and modified bitumen, as well as mastics in unaged and aged conditions. For bitumen, it would enable in not only excluding qualitatively unsuitable bitumen during the production process but also control and manage the quality fluctuations that often occur, especially in bitumen. Moreover, for modified bitumen, conventional tests are not enough to understand their behaviour and provide efficient comparisons among materials, hence, the DSR tests would provide an alternative medium for detailed mechanical testing and comparisons. This would therefore allow for efficient comparing among multiple bitumen allowing for the choice of the best-suited material for the design road. For mastic studies, these results could help understand how the binder properties change once filler is added to bitumen at a certain proportions, which filler has the optimum characteristics in terms of rheology, fatigue, rutting, creep and low-temperature performance, and, lastly, how the properties change after simulation of long-term aging using a pressure aging vessel. This method, therefore, could open up new ways of assessing the quality of bitumen and mastics in order to not only act as quality control for mixtures but also guide in choosing the appropriate material based on chosen purposes and optimum bitumen-filler combinations in order to avoid long-term maintenance costs.

1.4 Scope of the Thesis

The scope of the thesis consists of three parts. The first part (Section 2) gives a brief overview of bitumen and asphalt mixtures and the research undertaken during the Ph.D. It shortly explains the mechanical properties of mixtures, the existing test methods, and the challenges faced in Germany. Additionally, the summary includes the DSR tests and the performance ranking

diagram that were developed. These are presented in a way of presenting results of three bitumen of similar penetration grades. Lastly, recommendations are mentioned for future research ideas.

The second part of the thesis includes the core research publications already published in reputed first quartile journals. This includes four publications – three journal paper published in first quartile journals and one published in a conference proceedings books.

The third part incorporates research manuscripts that are already submitted to reputed journals and are currently under review. Two manuscripts are presented here that present a part of the studies conducted within the scope of the doctorate work.

2 SUMMARY OF RESEARCH

2.1 Asphalt and its Constituents

2.1.1 Asphalt

Asphalt or asphalt mixtures are the final pavement mixtures that consist of a combination of aggregates, filler, bitumen, and additives which are mixed together at an elevated temperature of 150° to 170°C. Asphalt is also referred to as asphalt concrete, Hot Mix Asphalt (HMA), simply asphalt, blacktop or bituminous mixture and is generally used as a surface layer of flexible pavements. This material is placed on a prepared unbound granular layer (UGL) and compacted using mechanical means. Once the asphalt cools down, it forms a hard surface with a higher stiffness than the underlying layers. Asphalt layers can carry both compressive as well as tensile stresses effectively. It is an inhomogeneous material with a complex temperature and frequency dependency [6]. It portrays elastic, viscous, and plastic deformation behaviour. The performance of a mixture is determined by its grain skeleton, which includes the coarse grain aggregates and the asphalt mastic - the bitumen and filler and how they interact with each other and with other constituents that make up the mixture. The mixture not only influences the quality but also the lifetime of the pavement [7,8].

Asphalt mixtures can be looked at from a multi-scale point of view - starting from a micro to a macro level, i.e. from the bitumen to the asphalt mixture level, including the levels in between. The different levels include bitumen, mastic, mortar, and finally asphalt. Bitumen is the binder.

Mastics are mixtures of bitumen and fillers (less than 0.075mm). Mortars are a mixture of bitumen, fillers, and fine aggregates (smaller than 2.36mm). While asphalt mixes include bitumen, fillers, fine and coarse aggregates. Each of these mixtures has a great influence on the final asphalt mixture after construction [9]. While the coarse aggregates are primarily responsible for the load-bearing capacity of the structure, the bitumen and mastic phases deal with aging, cracking, fatigue, and moisture-related damage [10]. Overall, asphalt is composite and heterogeneous which makes it anisotropic. From there, comes a need to deepen the understanding at different scales of observation. This study of various scales would lead to a high design accuracy of the final mixture, thereby minimising the unnecessary overdesigning costs. Macroscale and mesoscale studies are also significant in today's world as the focus of recent researchers lies in the prediction of the mixture using finite element models that require proper material properties and parameters to function accurately.

2.1.2 Bitumen

Bitumen is a dark viscous mixture made of hydrocarbons that is found naturally and can also be distilled as a by-product of the petroleum industry. The term 'Bitumen' has been believed to originate from the ancient Indian language, Sanskrit, where 'jatu' means pitch and 'jatu-krit' signifies pitch creating, which is related to the pitch of some resinous trees. The Latin synonym for this was suggested to be 'pictu-men' or 'gwitu-men' which was later shortened to 'bitumen' in English [3].

The use of bitumen dates as early as 3800 B.C. when natural bitumen was used as mortar in the Indus Valley and the Euphrates for masonry as well as for waterproofing purposes [11]. There are also multiple references found in the Bible for bitumen usage in the waterproofing of Noah's arch and the cradle of Moses [3]. Additionally, bitumen was also used as an adhesive, disinfectant, and insecticide, while also having medicinal purposes [12]. The first applications of bitumen usage for road construction date as back as 600 B.C. in Babylon [2]. However, it was only in the mid-nineteenth century, when Europe rediscovered bitumen and used began utilizing natural bitumen for road construction. Natural bitumen use was reduced in the early 1900s and was soon replaced by tar, which was further superseded by bitumen acquired by the distillation of crude oil [3].

Bitumen is a complex organic material made up of hydrocarbons with minor amounts of functional groups that contain sulphur, nitrogen, oxygen, and other heteroatoms. These heteroatoms can significantly affect the polarity and functionality of the molecules, leading to major differences in the rheological properties of bitumen derived from different sources [5]. Due to its complex chemical composition and its property to readily age as a result of oxidation and thermal changes, the mechanical and chemical properties of bitumen change overtime. Furthermore, the bitumen properties severely depend upon the crude oil source and distillation processes. Hence, there are differences in mechanical performances observed among similar penetration graded bitumen [13]. Therefore, an interdisciplinary approach is required in order to garner a comprehensive understanding of bitumen and its mechanical behaviour, as well as its consecutive effect on the resulting bituminous mixtures.

Bitumen is a thermoplastic material which exhibits viscoelastic behaviour. It behaves like an elastic solid at low temperatures (like glass), while it exhibits a fluid-like behaviour at higher temperatures, which flows readily when subjected to load. At intermediate temperatures (i.e. normal pavement temperatures), it has properties within the viscoelastic range, i.e. having both elastic as well as viscous characteristics [14]. Additionally, bitumen and bituminous mixtures are highly dependent on time and temperature conditions. Therefore, they exhibit mechanical behaviour that is difficult to comprehend, and which cannot be described using simple elastic models. However, it is this rheological behaviour of bitumen that makes them flexible and versatile materials for being used as paving binders in any habitable climate of the world [15]. Therefore, due to its complex behaviour, there is a requirement for wide-ranging test methods that consider specific mechanical behaviour.

Since conventional bitumen is considered to have hit a performance ceiling, modified binders are being readily introduced. For the past decades, many additives have become available for bitumen modifications. These include Styrene Butadiene Styrene (SBS), Ethylene Vinyl Acetate (EVA), and Styrene–Butadiene Rubber (SBR) [16], among several others; which though effective, are very expensive [17]. A promising additive due to its ready availability is Crumb Rubber (CR), which is derived from discarded tyres. The addition of CR to bitumen binder has shown to enhance the physical properties of bitumen; while at the same time providing notable improvements in the rutting and fatigue resistance of the pavements [16,18,19].

In addition, the quality of asphalt is currently defined in Germany using empirical requirements for each of its constituents. These include, in particular, requirements regarding bitumen properties (e.g. needle penetration, and ring and ball softening point) as well as volumetric specifications and degree of compaction [20]. Macro-mechanical testing of asphalt in the service conditions is not carried out due to the expenses associated with one to one testing facilities such as circular tracking test. To increase the durability of asphalt pavements, it is necessary to characterise individually the properties of both asphalt mixture and its constituents like bitumen and mastics [21].

Furthermore, while the bitumen acquired may fulfil the existing standards (softening point, ring and ball, etc.), it fails to perform under heavy traffic conditions and changing weather conditions, thereby indicating the insufficiency of the conventional test methods. Also, bitumen ageing causes physical (hardening and rheological changes) and chemical changes (oxidation, evaporation, polarity changes, etc.) that occur within the structure [3,22,23]. Ageing can be simulated in the lab using a Rolling Thin Film Oven Test (RTFOT) for short-term and Pressure Ageing Vessel (PAV) for long-term aging. Hence, ageing is a critical aspect required to be considered when designing a road.

While Bitumen has been utilized for a wide range of applications owing to its waterproofing and thermoplastic characteristics in recent years, it is primarily used for pavement construction and partly for airfield pavements. Together with making up for 85% of the worldwide bitumen consumption. Another 10% of bitumen is used for roofing purposes and the last 5% is utilized as sealants and insulants for other building materials, among other uses [24]. The bitumen used for road construction is called paving grade bitumen while the bitumen used for other purposes is known as industrial grade bitumen. Furthermore, in 2018, 297.9 million metric tonnes of asphalt were produced in Europe, out of which 41 million metric tonnes were produced in Germany [25].

2.1.3 Fillers

Any granular material used in the production of hot mix asphalt with a grain diameter of less than $75\mu\text{m}$ is considered a filler. When combined with bitumen, a bituminous mixture called asphalt mastic is produced. The influence of filler in the performance of the mastic and asphalt depends on the bitumen to filler ratio. When the filler content in the mastic exceeds 30% of the

volume of 50% of the mass the effect of the filler to the performance starts to become relevant [26]. Recent studies have shown that fillers are more than just ‘void fillers’ and actively interact with bitumen [26–29]. The filler has demonstrated to affect the mechanical properties of mastics and asphalt mixtures [22,30,31]. Many researchers have concluded that the chemical, geometrical and mechanical properties of the fillers have a great influence on the performance of the mastics and the overall asphalt mixture [30,32,33]. Furthermore, the fillers also affect the ageing characteristics of the mastics [7]. They not only act as a ‘void filler’ but also act as an active material that affects the bitumen-filler interaction [27]. The fillers have a physical stiffening effect of the bitumen and have also shown to affect the moisture resistance, workability, and the compaction of the final mix [29,30,32].

2.1.4 Aggregates

Aggregates make up 80 to 95% of asphalt by mass. Aggregates include coarse aggregates (particles greater than 2.36mm), fine aggregates (particles less than 2.36mm) as well as fillers. The main purpose of aggregates is to provide resistance to wear and deterioration of pavement surfaces. They also provide stability and strength to the asphalt by aggregate interlocking action and friction. Additionally, they provide a rough, skid-resistant pavement surface and impart durability to the structure against weathering and high wheel loads. Course aggregates usually consist of crushed natural rock or gravel, acquired from the quarry or river bed. Fine aggregates usually are acquired from sands or can also be manufactured by crushing rocks in the quarry. The aggregates and their proportions for a pavement are chosen based on the mix design and desired gradation.

2.1.5 Voids

Air voids are necessary in asphalt for additional compaction under traffic loading and for allowing the expansion of asphalt when there is an increase in temperatures without loss of stability or bleeding. The higher the void content, the higher is the permeability of a mix. Typically, a void content is between 2 to 4% depending on the mix design.

2.2 *Mechanical Properties of Asphalt*

Essentially, two major aspects of material properties in the M-E design of asphalt pavements are considered: (1) the stress-strain behaviour of the mixtures used to analyse critical stresses and strains in the pavement structure which include stiffness and Poisson’s ratio considerations;

(2) the specific performance behaviours of materials that dictate the probable mode of pavement failure [34,35]. The chief distresses or modes of failure in pavements include permanent deformation (or rutting), fatigue damage, and thermal cracking.

The key parameters used in a pavement mix design involves the analysis and determination of the respective proportions of binder, aggregates and voids. However, to comprehend the complete performance of asphalt, including the determination of specific characteristic behaviour and prediction of the mode of failure, it is important to calculate the mechanical properties of a mixture. These main properties include stiffness (rheology), permanent deformation performance, resistance to thermal cracking, and fatigue.

The stiffness modulus of an asphalt layer is an indicator of how a material can withstand and spread the loading, thereby protecting the layers underneath. The stiffness varies as a function of temperature and frequency (i.e. corresponding to vehicular speed). The strain-stress response that occurs at low temperatures or short loading times is generally elastic and is characterised by high stiffness, whereas at high temperatures and low frequencies, viscous behaviour is evident with low stiffness moduli and with rutting problems.

Fatigue cracking is a phenomenon of fracture under repeated or fluctuating loading that results in an accumulation of damage over time. The fatigue resistance of a material indicates the property of a material to endure repeated loading without fracture. In asphalt pavements, fatigue cracking happens to be one of the primary distresses and includes three chief phases- crack initiation, crack propagation, and eventual final failure [36]. The progressive damage causes the initiation of cracks at the bottom of the bituminous layers which then propagate upwards to the pavement surface in thinner asphalt pavements. On the other hand, in thicker asphalt pavements, cracks start at the pavement surface and then propagate towards the bottom of bituminous layers [37,38]. The parameter used to describe fatigue resistance is usually in terms of fatigue life, i.e. the number of cycles required to cause failure. Fatigue testing of asphalt is effort- and time-consuming. In addition, fatigue in asphalt pavements is a subject that is still not completely understood and hence, needs to be rigorously researched.

Permanent deformation is another primary distress found inbound as well as UGL of the asphalt pavements caused because of repeated heavy-vehicular loading. This accumulative or

irrecoverable deformation usually forms ruts at the pavement surface. Non-structural rutting problems exhibit distinctive shoulders on the road surfacing caused by accumulated permanent vertical strain confined to the bituminous layers, which can be solved by the overlap of wearing courses [39]. Structural rutting problems caused by accumulated vertical strain can be due to incorrect pavement design and occurs in the entire structure, including the bound and unbound layers. Rutting is one of the major reasons for pavements to require premature replacement as it severely affects the smoothness and serviceability of pavements. To counteract this problem, stiffer and leaner asphalt mixes were utilised but this leads to higher failures due to fatigue [40].

Thermal cracking distress in asphalt pavements are due to tensile cracks induced by low temperatures. These cracks occur due to tensile stresses that result in the contraction of pavements as temperatures reduce. The micro-cracking generally being at the pavement edges and surfaces, and with repeated thermal loading, transverse cracks develop that run down through the complete depth of a pavement. A major factor that influences the thermal cracking in pavements is the rheology of bitumen [41].

Furthermore, while all these mechanical properties are very crucial, it is imperative to also consider the durability of the mix. While durability is not a measurable property, it represents the inherent characteristic of a mix to maintain its mechanical properties throughout the designated lifespan of the pavement. While many factors influence the durability of a mixture, ageing and moisture susceptibility are two of the most critical points of analysis [42,43].

2.3 Existing Test Methods for Bitumen and Mastics

2.3.1 Bitumen Testing

This section has been divided into three sections: the first includes the traditional tests that have been and are still in use for decades and the second is the relatively advanced testing methods and third includes the German specifications for bitumen.

2.3.1.1 Traditional Testing Methods

The European Classification Method focuses on the penetrability of bitumen, found by the Needle Penetration Test (EN 1426) [44]. As a result, penetration tests are used widely to classify bitumen into different grades. These tests while simple and easy, are not based on any mechanical properties and do not consider the thermal susceptibility of the bitumen. Other

empirical tests commonly used include the Fraass Method Breaking Point (EN 12593) [45], and Ring and Ball Softening Point (EN 1427) [46]. Moreover, the specifications for road bitumen in Europe are based on the hardness classification by penetration values while in the USA the bitumen used to be specified by the viscosity grading system (ASTM D 3381)[47]. The European equivalent for the dynamic and kinematic viscosity test are presented in EN 12596 [48] and EN 12595 [49] respectively.

The Needle Penetration test is the chief test according to European standards used to determine the consistency of bitumen in order to grade them by measuring the depth a standard needle would penetrate vertically under specific conditions of standard load, duration and temperature. In this, the measurement of the penetration (in units of one tenth of a mm) of a standard needle in bitumen sample maintained at 25°C is done at five seconds interval. Softer the bitumen, the higher is the penetration. B50/70 indicates a penetration value of the binder ranges between 50 to 70 (1/10mm) of the standard needle. This test is most commonly adopted to classify the bitumen in terms of its hardness and simplicity. However, the disadvantages include that it is an empirical test and has no relation with the fundamental properties of the binder.

The (Fraass Method) Breaking Point test is used to determine the breaking point of solid and semisolid bitumen. The Fraass Breaking Point is the temperature at which bitumen first becomes brittle, as indicated by the appearance of cracks when a thin film of the bitumen on a metal plaque is cooled and flexed in accordance with specified conditions. The temperature is decreased at a rate of 1°K/min. The test gives a rough estimation of the transition between ductility and brittleness of the bitumen. The apparatus consists of stainless steel plaque, cooling and bending apparatus, thermometer (-38°C/+30°C), plate and stand.

The Ring and Ball Softening Point test is used to find the softening point which is the temperature at which the bitumen attains a particular degree of softening under specific conditions of the ring and ball test. Here, a brass ring containing the test sample of bitumen is suspended in a beaker in a liquid bath. A steel ball is placed on the bitumen sample and the liquid medium is heated at a rate of 5K/minute. The temperature at which the bitumen touches the metal plate placed at a specified distance (25.4mm) below the ring is the softening point. Harder grades of bitumen possess higher softening points than softer bitumen.

Another common test is the viscosity test that measures viscosity which is the property of a liquid that retards its flow due to internal friction and represents a measure of resistance to flow and hence. The dynamic viscosity is generally calculated by measuring the time required for a certain volume of bitumen to flow at 60°C in a glass capillary viscometer using the vacuum method. This method is considered to be a suitable indicator of the permanent deformation behaviour of bitumen. Kinematic viscosity on the other hand is measured at 135°C and is calculated by measuring the time taken for a certain bitumen volume to pass through a glass capillary viscometer under the influence of gravity.

The penetration grading and viscosity grading are limited in their ability to fully grade binders. In addition, these test methods do not give an indication of the viscoelastic nature of bitumen at any particular test temperature and do not have the flexibility to be undertaken at different loading modes[5]. Hence, in the late 80s through early 90s, the Strategic Highway Research Program in the U.S.A. considered closely all aspects of highway engineering and created new methods of testing and specifying asphalt binders. As a result, a new US binder specification called Superpave (Superior Performing Pavements) was developed.

2.3.1.2 Advanced Testing Methods

The primary purpose of the Superpave specification is to facilitate the construction of a superior quality bitumen product. The Superpave performance grading relates all the asphalt binder properties and the conditions under which it is used to its performance. The most crucial advancement is the move from empirical testing of bitumen to advanced functional testing, where the binder can be graded at a controlled rate and temperature so as to obtain the engineering properties of the binder. The Dynamic Shear Rheometer (DSR) (AASHTO T315) [50] and Bending Beam Rheometer (AASHTO T313) [51] replace the normal viscosity and penetration tests, respectively. European standards have adopted some of these tests and are briefly explained below.

Using the DSR, rheological testing and permanent deformation testing have been developed in the recent decades. The dynamic shear modulus and phase angle can be calculated as an indication of the rheological behaviour of bitumen and its mixtures using a DSR within a temperature between 10°C to 90°C and frequency between 0.1 to 10Hz as specified in the EN 14770 [52]. The shear modulus and phase angle are calculated in terms of oscillatory stress and

resulting strains. The creep recovery test mentioned under the EN 16659 standard [53] is used to predict the permanent deformation behaviour of bituminous mixtures and is done using the DSR at 60°C with the 25 mm parallel plate. In this, usually two parameters are calculated – the percent recovery and the non-recoverable compliance values. Here, the specimen is subjected to stress (usually 3.2 kPa) for one second, and nine seconds are allowed for relaxation. These steps are repeated ten times and the resulting strains are measured for each cycle.

The flexural creep stiffness determination test is done using a bending beam rheometer at low temperatures. It involves a beam shaped specimen in placed in a liquid bath and is subjected to a three-point bending loading for a certain time duration at lower temperatures. The resulting deflection is measured with time and the stiffness is calculated from the stress applied and the resulting strain values. This test is designed to determine the creep stiffness at low service temperatures [54].

While these tests now exist, there is no compulsion to use them in Germany. They are simply an additional component that are gradually gaining popularity [20]. These tests have however long in use in the US and Europe is slightly lagging behind in terms of accurate bituminous testing. There is, therefore, a strong need to develop newer and more efficient testing and classification methods.

2.3.1.3 Bitumen Standardisation

The DSR is a state-of-the-art equipment that has been in use only in the last few decades. It was started under the Strategic Highway Research Program [4,5] in the USA and was eventually included in the Superpave binder specifications of AASHTO T 315 [55]. While there have been development in the field of Bitumen testing especially in the USA, Germany is still lagging a little behind. The requirements in Europe for bitumen have been described in the standards EN 12591[56] and EN 14023 [57] by European Committee for Standardization (CEN). The committee allowed every country to choose sections and implement them into their standards. Germany also implemented the parts of this into their TL Bitumen standards for unmodified and polymer modified bitumen [58]. Furthermore, German authorities now require additional details from the bitumen supplier and its user. While on paper the changes with additional testing for bitumen were included in standards like TL Bitumen-StB 07, 2013 [58], the German testing laboratories are still developing the required competency to adapt to the changes [20].

The authorities want to ensure consistent material properties throughout the supply chain. The table below show the requirements for paving grade bitumen (Table 1) and polymer modified bitumen (Table 2) as specified in the German standard TL Bitumen-StB.

From Table 1 and 2 it can be seen that in Germany, it is required to simple do empirical testing on bitumen. Testing using the DSR or BBR are not compulsory here. The MSCR test was recently added in 2016 into the German Standards [59]. While tests done using these devices are well-known world-wide and already in use for decades in the US and other countries, there is still a reluctance to employ these methods.

Table 1 - Paving Grade Bitumen Requirements [20]

Property	Unit	Method	Bitumen				
			20/30	30/45	50/70	70/100	160/220
Needle penetration at 25°C	1/10 mm	DIN EN 1426	20 to 30	30 to 45	50 to 70	70 to 100	160 to 220
Softening point ring and ball	°C	DIN EN 1427	55 bis 63	52 bis 60	46 bis 54	43 bis 51	35 bis 43
Flash point	°C	DIN EN ISO 2592	≥ 240	≥ 240	≥ 230	≥ 230	≥ 220
Solubility	M.-%	DIN EN 12592	≥ 99,0	≥ 99,0	≥ 99,0	≥ 99,0	≥ 99,0
Fraass breaking point	°C	DIN EN 12593	-	≤ -5	≤ -8	≤ -10	≤ -15
Resistance against hardening (RTFOT)		DIN EN 12607-1					
Retained penetration after RTFOT	%		≥ 55	≥ 53	≥ 50	≥ 46	≥ 37
Change of softening point after RTFOT	°C		≤ 8	≤ 8	≤ 9	≤ 9	≤ 11
Change of mass after RTFOT	M.-%		≤ 0,5	≤ 0,5	≤ 0,5	≤ 0,8	≤ 1,0
Additional methods for gathering of experience							
DSR Temperature sweep 30°C to 90°C	-	TL Bitumen Chapter 5.3	No requirement but value has to be documented				
BBR – Flexural creep stiffness	-	TL Bitumen Chapter 5.4					

Table 2 - Polymer Modified Bitumen Requirements [20]

Property	Unit	Method	PmB				
			120/200-40 A	45/80-50 A	25/55-55 A	10/40-65 A	40/100-65 A
Needle penetration at 25°C		DIN EN 1426	120 bis 200	45 bis 80	25 bis 55	10 bis 40	40 bis 100
Softening point ring and ball	°C	DIN EN 1427	≥ 40	≥ 50	≥ 55	≥ 65	≥ 65
Force ductility	J/cm²	DIN EN 13589	≥ 2	≥ 2	≥ 3	≥ 2	≥ 3
Temperature for force ductility		DIN EN 13703	at 0°C	at 5°C	at 5°C	at 10°C	at 5°C
Flash point	°C	DIN EN ISO 2592	≥ 220	≥ 235	≥ 235	≥ 235	≥ 235
Fraass breaking point	°C	DIN EN 12593	≤ -20	≤ -15	≤ -10	≤ -5	≤ -15
Elastic recovery at 25°C	%	DIN EN 13398	≥ 50	≥ 50	≥ 50	≥ 50	≥ 70
Storage stability		DIN EN 13399					
Difference in softening point	°C	DIN EN 1427	≤ 5	≤ 5	≤ 5	≤ 5	≤ 5
Stability against hardening (RTFOT)							
Change of mass after RTFOT	M.-%	DIN EN 12607-1	≤ 0,5	≤ 0,5	≤ 0,5	≤ 0,5	≤ 0,3
Retained penetration after RTFOT	%	DIN EN 1426	≥ 60	≥ 60	≥ 60	≥ 60	≥ 60
Maximum increase in softening point after RTFOT	°C	DIN EN 1427	≤ 8	≤ 8	≤ 8	≤ 8	≤ 8
Minimum increase in Softening point after RTFOT	°C	DIN EN 1427	≤ 2	≤ 2	≤ 2	≤ 2	≤ 5
Elastic recovery at 25°C after RTFOT	%	DIN EN 13398	≥ 50	≥ 50	≥ 50	≥ 50	≥ 50
Additional methods for gathering of experience							
Force ductility	-	TL Bitumen Chapter 5.2	No requirement but value has to be documented				
DSR Temperature sweep 30°C to 90°C	-	TL Bitumen Chapter 5.3					
BBR – Flexural creep stiffness	-	TL Bitumen Chapter 5.4					

2.3.2 Mastic Testing

While bitumen testing has made some strides, mastic testing is a completely advanced field of study that is slowly gaining popularity. However, the effect of the physical and chemical composition of fillers on the asphalt mixture is contradictory [60]. It is therefore advantageous to have detailed specifications for bitumen and mastics that take into consideration the intrinsic phenomenological behaviour of the materials to help in bitumen and filler selection based on desired performance criteria. Accurate mechanical performance for bitumen and mastics could be derived using just one single machine - the DSR.

Studies on mastics are focused on studying the choice of suitable fillers, alternative fillers, optimum filler proportions, bitumen-filler interactions, effect of its chemical properties on mechanical performance and ageing characteristics of bituminous mixtures. Furthermore, at the moment, there exist no standards or specifications regarding mastics, which makes it a state-of-the-art and interesting field of study that could help us deepen our understanding of the

asphalt pavement performance and the interaction of the constituents with one another. However, mastics are a state-of-the-art study area that are slowly gaining popularity. There is a lack of clear understanding as to what the role of the filler truly is and how it interacts with bitumen [22,23].

Additionally, it is also important to note that not only the binder, but also the bitumen-aggregate interaction affects the ageing process. Based on the aggregate and filler type, the ageing performance of the same binder will differ due to the mineral composition of an aggregate surface, the chemical and physical properties of the aggregate and fillers along with the orientation of the polar molecules in the binder present in the vicinity of the binder-mineral surface interface [61]. They also concluded that the aggregates affect binder ageing via two mechanisms - adsorption and absorption. The adsorption signifies the adhesion of fractions or polar groups of bitumen onto the aggregate surface while absorption deals with exudation of the lighter molecules of bitumen within the pores of aggregates and fillers [62]. These surface phenomena break the proportional fractional balance that exists within the binder and lead to a poorly dispersed binder, affecting the bitumen-ageing rate [61]. Moreover, the mineral and chemical components present on the aggregate surface could act as catalysts or retarders for the ageing reaction, hence present various contradictions [63].

2.4 Dynamic Shear Rheometer

The Dynamic Shear Rheometer (DSR) is an appropriate equipment that could be used to test the mechanical performances of bitumen and mastics. This dynamic oscillatory test apparatus that can be used to describe the linear viscoelastic properties of bitumen and mastics over a range of temperatures and frequencies. It applies a sinusoidal shear strain or shear stress to a sample sandwiched between two parallel disks and measures the corresponding stiffness and viscosity at a magnitude of temperatures. A schematic diagram of the typical testing geometry and the DSR at TU Dresden is presented in Figure 1. The upper plate applies an oscillatory torsional load on the specimen while the lower plate remains fixed thus imposing shear on the specimen. The DSR equipment is connected externally to a computer in which a software is used to control the equipment and the applied load, concurrently measure the material response and thus, display the results via a graphical user interface or via an external text file.

As the DSR only takes two measurements, namely torque (τ) and angular rotation (θ), the remaining mechanical properties are calculated in response to these two parameters. The software automatically calculates the dynamic shear moduli and phase angles by measuring the applied stress, the resulting strain in the specimen along with the time lag between the stress and the strain. The amplitude of the stress is measured by determining the torque transmitted through the sample in response to the applied strain or vice versa.

Slowly further tests like the Multiple Stress Creep Recovery (MSCR) for rutting [64] and Linear Amplitude Sweep (LAS) for fatigue [65] were added to the American Standards. These tests are all done using the parallel plate geometry. While the most commonly used configuration worldwide is the parallel plate geometry, the DSR companies are developing more and more configurations to assist in different parameter testing and calculations. The DSR at TU Dresden has four different configurations. Further details about the DSR are provided in the next section.

Figure 1 a) Schematic DSR testing arrangement b) DSR at TU Dresden

2.5 DSR Laboratory Procedure

The informative value of the tests currently used in Germany to determine bitumen properties is very limited, inaccurate and outdated when it comes to assessing the performance properties of bitumen [21]. Meaningful information about relevant rheological properties of bitumen and specialised rutting, fatigue and low temperature behaviours is required. Therefore, new, suitable and more meaningful methods have to be developed which allow a comprehensive

performance-oriented characterisation of bitumen and mastic mixtures. This section therefore shows exemplary DSR procedure developed to characterise bitumen and mastic characteristics.

The DSR is currently the most commonly used test instrument for the determination of the rheological properties of bitumen, and thus, it was the chief instrument used for the study of various materials including mastics. These tests are explained briefly in the sub-sections that follow by presenting results of three bitumen of penetration grade 50/70. This whole procedure has then been transferred to mastics and modified bitumen in the core and submitted publications presented in Part I and Part III with detailed topic specific literature review.

Figure 2 Specimens for the strain frequency sweep (left), MSCR and cooling tests (middle), specimens for the fatigue tests (right) [22]

2.5.1 Shear Strain & Frequency Sweep Tests

These tests were conducted for materials at temperatures of -10°C, 10°C, 30°C, 50°C and 70°C in order to determine the linear viscoelastic (LVE) limit strains. The LVE limit is generally defined as the strain value where the dynamic shear modulus gets reduced by 5% of its initial value. These strain limits found were further reduced by 20 %, to ensure that the LVE region was maintained during the temperature and frequency sweep tests that followed (Figures 3 and 4).

Figure 3 Strain Sweep Test Results for a bitumen

Figure 4 Curve Shifting of the LVE Limit for a bitumen

Using these strain limits as inputs, two frequency sweep tests were then conducted; (a) at temperatures from -10°C to 30°C using an 8 mm diameter plate with specimen thickness of 2 mm and (b) at 30°C to 70°C using a 25 mm diameter plate and 1 mm thick specimen in the frequency range of 0.0159 to 79.6 Hz. The difference in the diameter plate was due to the range of stiffness of the materials at the selected temperature ranges (i.e., lower temperatures required smaller plates due to the high stiffness of the materials). Typical frequency sweep results are presented in Figure 5.

Figure 5 Typical Frequency Sweep Test Results: (a) Isothermal Plots for $|G^*|$ (b) Isothermal Plots for δ (c) Cole-Cole Plots (d) Black Diagram for a bitumen

From these tests, rheological data (i.e. dynamic shear modulus and phase angle) was acquired and using the Time-Temperature-Superposition Principle (TTSP) and the mechanical 2 Spring-2 Parabolic-1 Dashpot (2S2P1D) model [66,67], master curves were constructed. The TTSP was done using the Williams Landel Ferry (WLF) equation along with the 2S2P1D model [6], which can be used in analysis of rheological responses for viscoelastic bituminous material. The TTSP allows the construction of master curves at a reference temperature by applying a shift factor. The master curves can be used to predict the rheological behavior of viscoelastic

materials at various temperatures assuming that the material behaves thermo-rheologically simple [68]. Typical master curves for three bitumen in different ageing conditions are presented as follows in Figure 6.

Figure 6 Master curves of dynamic shear modulus for 3 bitumen (B1, B2, B3) in 3 ageing conditions (unaged, RTFOT aged and PAV aged) [13]

Using the rheological data, the stiffness and phase angle values can be compared at chosen conditions, commonly being at 20°C and 60°C as they are representative of the fatigue and permanent deformation behaviours. Additionally, it is common practise to find the ageing index, which is a ratio of any aged property to the unaged property at the same conditions for a material. For the three bitumen, the following ageing indexes were found as presented by Figure 7 for two ageing and two temperature conditions. The lower the ageing index, the lower is the ageing susceptibility.

Figure 7 Ageing Index for dynamic shear modulus [69]

2.5.2 Single Stress Creep Recovery (SSCR)

SSCR tests were conducted to assess the rutting resistance of the admixtures on RTFOT aged materials. SSCR tests were conducted on three replicates per specimen at 60°C for the 25 mm plate, and at 10°C for the 8 mm plate. In these tests, a stress of 3.2 kPa was applied for 1 sec, while allowing the material to recover for the next 9 sec. This procedure was repeated for 10 cycles. The percentage recovery (%Rec) and the non-recoverable compliance (J_{nr}) were obtained for each cycle and then averaged for every sample [70]. The two parameters, J_{nr} and %Rec were obtained using the following equations:

$$\%Rec = \frac{\varepsilon_1 - \varepsilon_{10}}{\varepsilon_1} * 100 \quad [\%] \quad (1)$$

$$J_{nr} = \frac{\varepsilon_{10}}{100 * 3.2} \quad [kPa^{-1}] \quad (2)$$

where ε_1 is the strain increment at the end of the creep phase of the first cycle, and ε_{10} is the strain increment at the end of the relaxation phase of the tenth cycle.

The results of the SSCR tests for the different bitumen (unaged and RTFOT aged) can be compared using the parameters J_{nr} , R and the resulting terminus damage are shown in Table 3 and graphically with the help of the recorded deformation curves in Figure 8. The lower the J_{nr} value is, the lower is the expected depth, and hence the material has better rutting resistance.

Table 3 Results of the SSCR tests

<i>Material</i>	<i>J_{nr} [kPa⁻¹]</i>	<i>R [%]</i>	<i>Cumulative Strain after 10 cycles [%]</i>
B1	3.22	1.45	102.99
B2	1.68	6.31	55.10
B3	2.44	3.76	68.56
B1 RTFOT	0.45	22.13	14.48
B2 RTFOT	0.66	15.23	21.25
B3 RTFOT	0.45	21.47	14.25

Bitumen B1 shows the largest permanent deformation, followed by bitumen B3 and lastly, bitumen B2 in unaged conditions. However, after ageing, bitumen B2 RTFOT had the highest J_{nr} value and the lowest resistance to plastic deformation. While bitumen B1 RTFOT and B3 RTFOT had identical values of J_{nr} and identical deformation curves.

Figure 8 SSCR Test Results [13]

2.5.3 Cryogenic Tests (Dresden Cryogenic Tests (DDRT))

Cooling in winter temperatures lead to cryogenic tensile stresses in the asphalt. These stresses can be compensated to a certain extent by the tensile strength of the asphalt, which also increase with decreasing temperature. The tensile strength, however, only increases on cooling up to a limit value depending on the bitumen used. After falling below this limit, the increasing embrittlement leads to a decrease in tensile strength. As a result, on further cooling, the temperature (breaking temperature) is reached at which the cryogenic tensile stresses exceed the tensile strength of the asphalt and thus lead to cracking (cold crack) in the asphalt. In conjunction with the tensile stresses induced by traffic loads, the crack can also occur at temperatures that are more positive than the breaking temperature [71]. Colder cracks in asphalt

can start at the interface between mastic mixture and rock or within the bitumen film [72]. Therefore, the cryogenic behaviour of the binder and the adhesion to the rock have a decisive influence on crack formation in asphalt [73].

As a result, the Dresden Cryogenic Test (DDCT) was developed to test cryogenic performance of bituminous mixtures [22]. This recently developed test procedure corresponds to a scaled-down version adapted for the DSR from the German standard DIN EN 12697-46 [74]. The tests were carried out on prismatic samples (Figure 2). The dimensions of the prismatic samples were 50 mm x 4 mm x 9 mm (length x width x height). The specimens were attached to the upper spindle and the lower base plate of the DSR and cooled down from 20°C to -15 °C with a cooling rate of -10 K per hour. The specimens were then left for 2 hours at -15 °C and kept at a constant specimen length (relaxation phase) [22]. Throughout the entire experiment, the axial stress resulting from the temperature change was measured while keeping the sample length constant. The lower the exerted stress is, the better the material is expected to perform under the low temperatures. After the cooling and recovery cycle, the material is once again heated from -15°C to 20°C at the same rate, and this denotes the heating cycle. Figure 9 shows the typical cryogenic test.

Figure 9 Full cryogenic cycle for the bitumen [22]

The results of a typical cryogenic cycle are presented in Figure 10, however without the recovery period. The cryogenic stresses at -15°C is taken as the key parameter for low temperature behaviour determination. The lower the thermal stress exerted by the specimen, the better it would be expected to behave during colder weather.

Figure 10 Cooling Cycle of Bitumen [69]

Furthermore, the recovery of stress took place by leaving the material at -15°C . These values, along with the recovery percent are presented in Table 4. It can be observed that the bitumen showed a recovery of the range 62-73% while Bitumen B3 had the highest recovery values.

Table 4 Cryogenic Stress parameters [69]

Material	Cryogenic stress at -15°C [N/mm^2]	Cryogenic stress after 2 h Relaxation at -15°C [N/mm^2]	Cryogenic Recovery Percent [%]
B1	0.04	0.0151	62.25%
B2	0.13	0.0391	68.15%
B3	0.09	0.0244	72.89%

2.5.4 Fatigue Tests

Fatigue cracking is a major distress in asphalt pavements and is a result of repeated cyclic loading that leads to an accumulation of damage and cracking [36]. The fatigue failure for asphalt mixtures has been characterised using different approaches that include phenomenological techniques, continuum damage mechanics, fracture mechanics and lastly, energy dissipation methods [36,38,75]. In the past decade, multiple fatigue tests have been developed and implemented on asphalt mixtures [76]. In Germany, however, the Indirect Tensile Test (IDTT) and the flexural four-point bending test are most commonly used. However, most fatigue tests are time and effort consuming and can be comparatively expensive. Owing to these shortcomings and considerable research showing a strong relationship between fatigue properties of the asphalt mixture to that of the corresponding bitumen and mastics, the

focus on experimentally characterising fatigue in asphalt binders and mastics is a state-of-art field of study and has significant research potential [22,77–80].

Furthermore, there are protocols to estimate the fatigue resistance of bitumen using rheometers, like the time-sweeps and the Linear Amplitude Sweep (LAS) [81]. However, due to the frequent debonding problems associated with the plate-plate configuration and therefore, sometimes the binder-steel plate bond is tested rather than the actual fatigue of the bitumen[78]. Furthermore, the gap between the plates have to be increased for modified bitumen and mastics [82]. In addition, while the LAS test is relatively fast and can be easily performed, it is based on complicated theory and assumptions which may not be necessarily true [83,84].

Stress-controlled fatigue tests were conducted using cylindrical bitumen column specimens at 10 Hz and at an intermediate temperature of 20°C [22,85,86]. The cylindrical columns were 20 mm high, with the effective testing section being 11 mm in height and 6 mm in diameter (Figure 11). Steel rings (outer diameter 8 mm, wall thickness 1 mm, and 4.5 mm in height) were fixed at both ends of the column to install the sample on the rheometer. The sample was fixed at the bottom and subjected to torsional load at the top. Nine fatigue tests were conducted for each admixture, using three replicates at three different stress levels. The results were analysed using the energy ratio [38] method based on the Dissipated Energy Ratio theory [87].

Figure 11 Fatigue sample dimensions (left) and Silicone Mould (right) [88]

In addition, the fatigue tests were done in a stress controlled mode as it is commonly done for asphalt fatigue tests [89] in Germany. The geometrical configuration herein proposed, on the contrary, overcomes this issue, at the time that it provides the full fatigue curve of the material

and not just an index that provides information on the expected fatigue resistance of the material [90].

Furthermore, fatigue data can also be presented in terms of hysteresis loops and as dissipated energy. The dissipated energy per cycle represents the difference between the applied and recovered energy and equals the area within the hysteresis loop [91]. It can be easily calculated by numerical integration from time t_0 to t_6 , which presents one complete loading-unloading cycle as seen in Figure 12. Figure 12a shows the typical sinusoidal curve for applied stress and resulting strain, which is delayed by a phase lag. The whole cycle can be broken into two parts, as in a DSR the loading once takes place in the one direction, and then in the other direction. Here, from t_0 to t_3 is T_R (right direction) and t_3 to t_6 are T_L (left direction). Figure 12b shows the resulting hysteresis loop due to the above cycle and with the use of integration via various limits between t_0 to t_6 , the area covered within the hysteresis loop can be found. The applied energy is equal to the sum of the areas covered under firstly $t_0t_1t_2$ and secondly under $t_3t_4t_5$. The recovered area is presented under t_2-t_3 and t_5-t_6 using the black lines. The subtraction of the above integrated areas gives the area of the loop.

(a)

(b)

Figure 12 a) Typical Stress-Strain Cycle b) Resulting Hysteresis Loop [92]

Further details about the test can be found in the third part of the dissertation, which holds a whole paper on fatigue test at different temperatures and frequencies titled, '*Dissipated Energy Based Approach to Assess the Influence of Temperature and Frequency on the Fatigue Response of Bitumen.*' [92]

The fatigue test results throughout were analysed using the energy ratio method which states that the dissipated energy of bitumen at failure can be calculated at the point where the product of number of load cycles and the corresponding dynamic shear modulus is a maximum [38]. For the fatigue tests results presented here, the stress levels were chosen in a way, so as to maintain an initial strain level at 100 load cycles within the range of 0.5 to 2.0%. Due to this, the unaged bitumen were tested usually in a stress range of 100-200 kPa, RTFOT at 150-250 kPa and PAV at 250-400 kPa [13]. This is expected due to an increase in stiffness with an increase of ageing, therefore, resulting in a higher elastic behaviour and a lower strain at the same stress. The fatigue curves at three different ageing conditions are presented as an example in Figure 13.

Figure 13 Stress fatigue curves for the bitumen tested

From the figure, it can be observed that while there are clear distinctions between the unaged, RTFOT and PAV-aged curves, the ranking among the materials becomes clearer with ageing. At unaged condition, the curves tend to overlap, while for RTFOT and PAV, the bitumen B2 has clearly the best performance with yielding the highest fatigue life at any given stress level.

For the synthesis of results diagram presented in the next section, the stress level required to cause failure at a load cycle value of 100,000 in PAV aged conditions was used as a characteristic parameter for estimating the fatigue behaviour of the materials (Table 5). The previously used characteristic parameter in the form of the number of load cycles until the macro-crack criterion is reached at a stress level of 450 kPa [78] was adapted.

Table 5 Fatigue performance parameter	
Material	Stress [kPa] @ 1E+5 LC
B1	123
B2	118
B3	105
B1 RTFOT	222
B2 RTFOT	320
B3 RTFOT	212
B1 PAV	325
B2 PAV	350
B3 PAV	290

2.6 Performance Diagram

For a summarizing and comparative evaluation of the behavior of bitumen, a network diagram was developed for the ranking of bitumen. The following six performance-oriented material criteria were considered:

- Shear stiffness (complex shear modulus) at 20°C and 60°C and 10 Hz - unaged
- Fatigue behaviour (stress at a fatigue load change rate of 100,000) - PAV aged
- Low temperature behaviour (cryogenic stress reached at -15°C) - unaged
- Ageing sensitivity with regard to stiffening (ageing index at 60°C, 10 Hz)
- Resistance to plastic deformation (J_{nr} value)

Figure 14 shows the performance diagrams in which the bitumen can be directly compared, evaluated and ranked according to their performance-relevant properties. The axes are presented in such a way that, the larger the area inside, the better is the overall performance. From the figure, the ageing indexes, cryogenic stress and J_{nr} value axes are reversed, as performance relates inversely to these parameters. Therefore, for Figure 14, bitumen B1 is the best overall performing material based on the selected criteria as it has the highest overall area. Furthermore, using the diagram, materials can be chosen based on specific required performances. For example, if permanent deformation is more critical for the road one is constructing, then if the J_{nr} axis is observed, instantly, B1 or B3 could be chosen. However, if fatigue is more critical, the axis for fatigue can be observed and instantly, choice of B2 would be optimum. If low temperature behaviour is crucial, then bitumen B1 would be a better alternative. It is to be noted that these diagrams can be modified to incorporate other relevant parameters when necessary; and if properties are considered to be more relevant than others for a specific project, it could be possible to add scalar weights to each axis, which will impact the computation of the overall area. An example of this diagram has been presented in Figure 14.

Figure 14 Performance Diagram [13]

3 RECOMMENDATIONS FOR FURTHER RESEARCH

Considerable amount of materials were tested and are presented in the Core Publications and Submitted Manuscripts sections which include testing on multiple unmodified and modified bitumen and mastics made using different fillers and proportions. However, there is still need to test more materials in order to acquire accurate threshold values for performance diagram and tests that were developed. This would involve testing of more types of bitumen and fillers and various mastic combinations among them including varying ageing conditions. Moreover, more parameters such as chemical analysis could be integrated into the diagram to have a more complete overall behaviour. In addition, additional testing of asphalt mortars and mixtures needs to be conducted to verify the bitumen-mastic-mortar-asphalt correlation.

4 BIBLIOGRAPHY

- [1] C. Walther, A. Dahl, V. Waßmuth, Contribution to the Discussion of Infrastructure Project Appraisal: The German FTIP 2030 Case, *J. Appl. Bus. Econ.* 20 (2018). <https://doi.org/10.33423/jabe.v20i8.216>.
- [2] B. Hofko, Characterization of bituminous bound material, TU Wien, 2019.
- [3] R.N. Hunter, The Shell Bitumen Handbook, 6th edition, 2015. <https://doi.org/10.1680/tsbh.58378>.
- [4] D.A. Anderson, D.W. Christensen, H.U. Bahia, R. Dongre, M.G. Sharma, C.E. Antle, J. Button, Binder characterization and evaluation. Volume 3: Physical characterization. Strategic Highway Research Program, *Strateg. Highw. Res. Progr.* (1994). <https://doi.org/10.1520/stp18191s>.
- [5] J.C. Petersen, R.E. Robertson, J.F. Branthaver, P.M. Harnsberger, J.J. Duvall, S.S. Kim, D. a Anderson, D.W. Christiansen, H.U. Bahia, Binder Characterization and Evaluation. Volume 1. No SHRP-A-367, 1994.
- [6] H. Di Benedetto, B. Delaporte, C. Sauzéat, Three-Dimensional Linear Behavior of Bituminous Materials: Experiments and Modeling, *Int. J. Geomech.* 7 (2007). [https://doi.org/10.1061/\(asce\)1532-3641\(2007\)7:2\(149\)](https://doi.org/10.1061/(asce)1532-3641(2007)7:2(149)).
- [7] D. Anderson, H. Bahia, R. Dongre, Rheological Properties of Mineral Filler-Asphalt Mastics and Its Importance to Pavement Performance, in: *Eff. Aggregates Miner. Fill. Asph. Mix. Perform.*, 2009. <https://doi.org/10.1520/stp24215s>.
- [8] F.L. Roberts, S. Prithvi, E. Kandhal, R. Brown, L. Dah-Yinn, T.W. Kennedy, Hot Mix Asphalt Materials, Mixture Design, and Constrution, 1996.
- [9] B.S. Underwood, Y.R. Kim, Microstructural investigation of asphalt concrete for performing multiscale experimental studies, *Int. J. Pavement Eng.* (2013). <https://doi.org/10.1080/10298436.2012.746689>.
- [10] M. Chen, B. Javilla, W. Hong, C. Pan, M. Riara, L. Mo, M. Guo, Rheological and interaction analysis of asphalt binder, mastic and mortar, *Materials (Basel)*. (2019). <https://doi.org/10.3390/ma12010128>.
- [11] H. Abraham, Asphalts and allied substances: Their ocourrence, modes of production, uses in the arts and methods of testing., Fifth, D von Nostrand Comnpny, London, 1945.
- [12] J. Connan, Use and trade of bitumen in antiquity and prehistory: Molecular archaeology reveals secrets of past civilizations, *Philos. Trans. R. Soc. B Biol. Sci.* (1999).

- <https://doi.org/10.1098/rstb.1999.0358>.
- [13] M. Rochlani, S. Leischner, G.C. Falla, P. Goudar, F. Wellner, Influence of Source and Ageing on the Rheological Properties and Fatigue and Rutting Resistance of Bitumen Using a DSR, in: *Lect. Notes Civ. Eng.*, 2020. https://doi.org/10.1007/978-3-030-48679-2_46.
 - [14] G.D. Airey, Use of Black Diagrams to Identify Inconsistencies in Rheological Data, *Road Mater. Pavement Des.* (2002). <https://doi.org/10.1080/14680629.2002.9689933>.
 - [15] G.D. Airey, State of the Art Report on Ageing Test Methods for Bituminous Pavement Materials, *Int. J. Pavement Eng.* (2003). <https://doi.org/10.1080/1029843042000198568>.
 - [16] D. Lo Presti, G. Airey, Tyre rubber-modified bitumens development: the effect of varying processing conditions, *Road Mater. Pavement Des.* 14 (2013) 888–900. <https://doi.org/10.1080/14680629.2013.837837>.
 - [17] Nuha S. Mashaan, An overview of crumb rubber modified asphalt, *Int. J. Phys. Sci.* 7 (2012) 166–170. <https://doi.org/10.5897/ijpsx11.007>.
 - [18] R. Hicks, J. Lundy, J. Epps, Life cycle costs for asphalt-rubber paving materials, in: *Proc. First Int. Conf. World Asph. Pavements*, 2000.
 - [19] T. Chen, T. Ma, X. Huang, Y. Guan, Z. Zhang, F. Tang, The performance of hot-recycling asphalt binder containing crumb rubber modified asphalt based on physiochemical and rheological measurements, *Constr. Build. Mater.* 226 (2019) 83–93. <https://doi.org/10.1016/j.conbuildmat.2019.07.253>.
 - [20] M. Wegmann, L. Vienenkötter, M. Pfitzmann, Bitumen quality recording - A German approach, in: *Proc. 6th Eurasphalt Eurobitume Congr.*, Czech Technical University in Prague, Prague, Czech Republic, 2016. <https://doi.org/10.14311/EE.2016.339>.
 - [21] F. Wellner, G.C. Falla, S. Leischner, Betrachtungen zur Einschätzung der Bitumenqualitäten unter besonderer Berücksichtigung der Alterung, in: *Proc. Asph.* 2019, 2019.
 - [22] M. Rochlani, S. Leischner, G.C. Falla, D. Wang, S. Caro, F. Wellner, Influence of filler properties on the rheological, cryogenic, fatigue and rutting performance of mastics, *Constr. Build. Mater.* 227 (2019) 116974. <https://doi.org/10.1016/j.conbuildmat.2019.116974>.
 - [23] R. Alfaqawi, G.D. Airey, J.R.A. Grenfell, Effects of mineral fillers and bitumen on ageing of asphalt mastics properties, in: *Bear. Capacit. Roads, Railw. Airfields - Proc. 10th Int. Conf. Bear. Capacit. Roads, Railw. Airfields*, BCRRA 2017, 2018.

- <https://doi.org/10.1201/9781315100333-41>.
- [24] Eurobitume, Asphalt Institute, The Bitumen Industry - A Global Perspective, Second Edi, Asphalt Industry and Eurobitume, 2011. http://www.aapaq.org/q/2012st/doc/REF/B01_AI-Eurobitume_The_Bitumen_Industry-A_Global_Perspective_2011.pdf.
- [25] E.A.P.A. EAPA, Asphalt in Figures 2018, 2018. https://eapa.org/wp-content/uploads/2020/02/Asphalt-in-figures_2018.pdf.
- [26] A.E. Alvarez, E. Ovalles, S. Caro, Assessment of the effect of mineral filler on asphalt-aggregate interfaces based on thermodynamic properties, *Constr. Build. Mater.* (2012). <https://doi.org/10.1016/j.conbuildmat.2011.08.089>.
- [27] Y.-R. Kim, D.N. Little, Linear Viscoelastic Analysis of Asphalt Mastics, *J. Mater. Civ. Eng.* 16 (2004). [https://doi.org/10.1061/\(asce\)0899-1561\(2004\)16:2\(122\)](https://doi.org/10.1061/(asce)0899-1561(2004)16:2(122)).
- [28] P. Dehdezi, C.C. Thodesen, Effects of Fillers on the Rheological / Mechanical Performance of Mastics / Asphalt Mixes, (n.d.).
- [29] B. Huang, X. Shu, X. Chen, Effects of mineral fillers on hot-mix asphalt laboratory-measured properties, *Int. J. Pavement Eng.* 8 (2007) 1–9. <https://doi.org/10.1080/10298430600819170>.
- [30] K. Rieksts, M. Pettinari, V. Haritonovs, The influence of filler type and gradation on the rheological performance of mastics, *Road Mater. Pavement Des.* (2019). <https://doi.org/10.1080/14680629.2018.1428216>.
- [31] R. Moraes, H. Bahia, Effect of Mineral Fillers on the Oxidative Aging of Asphalt Binders, *Transp. Res. Rec. J. Transp. Res. Board.* (2015). <https://doi.org/10.3141/2506-03>.
- [32] V. Antunes, A.C. Freire, L. Quaresma, R. Micaelo, Influence of the geometrical and physical properties of filler in the filler-bitumen interaction, *Constr. Build. Mater.* (2015). <https://doi.org/10.1016/j.conbuildmat.2014.12.008>.
- [33] R. Moraes, H. Bahia, Effect of Mineral Fillers on the Oxidative Aging of Asphalt Binders Laboratory Study with Mastics, *Transp. Res. Rec. J. Transp. Res. Board.* (2015) 19–31. <https://doi.org/10.3141/2506-03>.
- [34] J. Read, D. Whiteoak, The Shell bitumen handbook, Read, J., Whiteoak, D. (2003). *Shell Bitum. Handbook*. Thomas Telford. (2003). <https://doi.org/10.1680/sbh.32200>.
- [35] G.D. Airey, *Rheological Characteristics of Polymer Modified and Aged Bitumens*, 1997.
- [36] K.A. Ghuzlan, S.H. Carpenter, Energy-derived, damage-based failure criterion for

- fatigue testing, *Transp. Res. Rec.* (2000). <https://doi.org/10.3141/1723-18>.
- [37] R. Kim, H.J. Lee, D. Little, Fatigue Characterization of Asphalt Concrete Using Viscoelasticity and Continuum Damage Theory, *J. Assoc. Asph. Paving Technol.* (1997).
- [38] G.M. Rowe, M.G. Bouldin, Improved Techniques to Evaluate the Fatigue Resistance of Asphaltic Mixtures, 2nd Eurasphalt Eurobitume Congr. Barcelona 2000. (2000).
- [39] S. Tayfur, H. Ozen, A. Aksoy, Investigation of rutting performance of asphalt mixtures containing polymer modifiers, *Constr. Build. Mater.* (2007). <https://doi.org/10.1016/j.conbuildmat.2005.08.014>.
- [40] N.S. Mashaan, A.H. Ali, M.R. Karim, M. Abdelaziz, Effect of crumb rubber concentration on the physical and rheological properties of rubberised bitumen binders, *Int. J. Phys. Sci.* (2011). <https://doi.org/10.5897/IJPS11.113>.
- [41] U. Isacson, H. Zeng, Relationships between bitumen chemistry and low temperature behaviour of asphalt, *Constr. Build. Mater.* (1997). [https://doi.org/10.1016/S0950-0618\(97\)00008-1](https://doi.org/10.1016/S0950-0618(97)00008-1).
- [42] D. Mastrofini, M. Scarsella, Application of rheology to the evaluation of bitumen ageing, *Fuel*. (2000). [https://doi.org/10.1016/S0016-2361\(99\)00244-6](https://doi.org/10.1016/S0016-2361(99)00244-6).
- [43] A.E. Alvarez, E. Ovalles, S. Caro, Assessment of the effect of mineral filler on asphalt-aggregate interfaces based on thermodynamic properties, *Constr. Build. Mater.* 28 (2012) 599–606. <https://doi.org/10.1016/j.conbuildmat.2011.08.089>.
- [44] CEN, EN 1426, Bitumen and bituminous binders. Determination of needle penetration, 2015.
- [45] CEN, EN 12593: Bitumen and bituminous binders - Determination of the Fraass breaking point, 2015. <https://doi.org/https://dx.doi.org/10.31030/2292068>.
- [46] German Institute for Standardisation (Deutsches Institut für Normung), DIN EN 1427: Bitumen and bituminous binders - Determination of the softening point - Ring and Ball method, 2015.
- [47] ASTM D 3381., Standard Specification for Viscosity-Graded Asphalt Cement for Use in Pavement, *Am. Soc. Test. Mater. Stand.* (2016). <https://doi.org/10.1520/D3381>.
- [48] CEN, EN 12596: Bitumen and bituminous binders. Determination of dynamic viscosity by vacuum capillary, 2014.
- [49] CEN, EN 12595: Bitumen and bituminous binders - Determination of kinematic viscosity, 2014. <https://doi.org/https://dx.doi.org/10.31030/2143330>.

- [50] AASHTO, Standard Method of Test for Determining the Rheological Properties of Asphalt Binder Using a Dynamic Shear Rheometer (DSR), Stand. T315. (2012).
- [51] AASHTO T313, Standard Test Method for Determining the Flexural Creep Stiffness of Asphalt Binder Using the Bending Beam Rheometer (BBR), Annu. B. Am. Soc. Test. Mater. ASTM Stand. (2012). <https://doi.org/10.1520/D6648-08.2>.
- [52] CEN, EN 14770: Determination of complex shear modulus and phase angle — Dynamic Shear Rheometer (DSR), 2012.
- [53] Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), DIN EN 16659: Bitumen und bitumenhaltige Bindemittel - MSCR-Prüfung (Multiple Stress Creep and Recovery Test), 2016.
- [54] Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), DIN EN 14771: Bitumen und bitumenhaltige Bindemittel - Bestimmung der Biegekriechsteifigkeit - Biegebalkenrheometer (BBR), 2012.
- [55] American Association of State Highway and Transportation Officials, AASHTO T315 - Determining the Rheological Properties of Asphalt Binder Using a Dynamic Shear Rheometer (DSR), 2010.
- [56] EN 12591 - Bitumen und bitumenhaltige Bindemittel - Anforderungen an Straßenbaubitumen, Beuth Verlag, 2009.
- [57] CEN, EN 14023, Bitumen und bitumenhaltige Bindemittel - Rahmenwerk für die Spezifikation von polymermodifizierten Bitumen, Beuth Verlag, 2013.
- [58] FGSV, TL Bitumen-StB, Technische Lieferbedingungen für Straßenbaubitumen und gebrauchsfertige Polymermodifizierte Bitumen, 2013.
- [59] FGSV 723, AL MSCR-Test (DSR) FGSV 723: Arbeitsanleitung zur Bestimmung des Verformungsverhaltens von Bitumen und bitumenhaltigen Bindemitteln im Dynamischen Scherrheometer (DSR), (FGSV), Forschungsgesellschaft für Straßen- und Verkehrswesen, 2016.
- [60] V. Antunes, A.C. Freire, L. Quaresma, R. Micaelo, Effect of the chemical composition of fillers in the filler-bitumen interaction, Constr. Build. Mater. 104 (2016) 85–91. <https://doi.org/10.1016/j.conbuildmat.2015.12.042>.
- [61] J. Wu, G. Airey, The Influence of Mineral Fillers on Mastic Aging Properties, in: 2011. [https://doi.org/10.1061/41186\(421\)342](https://doi.org/10.1061/41186(421)342).
- [62] S.A. Osman, The Role of Bitumen and Bitumen/filler Mortar in Bituminous Mixture Fatigue, University of Nottingham, 2004.

- [63] M. Makowska, T. Pellinen, The “false positive” on the antiaging properties of asphalt fines investigated by RTFO laboratory aging of mastics, in: 2017. <https://doi.org/10.1201/9781315643274-53>.
- [64] AASHTO T 350-19, Standard Method of Test for Multiple Stress Creep Recovery (MSCR) Test of Asphalt Binder Using a Dynamic Shear Rheometer (DSR), Am. Assoc. State Highw. Transp. Off. (2019).
- [65] AASHTO TP8-94, Method for Determining the Fatigue Life of Compacted Hot-Mix Asphalt (HMA) Subjected to Repeated Flexural Bending. AASHTO Provisional Standards ., 2002.
- [66] A. Pedraza, H. Di Benedetto, C. Sauzéat, S. Pouget, 3D Linear viscoelastic behaviour of bituminous mixtures containing high content of multi-recycled RAP, Road Mater. Pavement Des. (2019). <https://doi.org/10.1080/14680629.2019.1594054>.
- [67] F. Olard, H. Di Benedetto, General “2S2P1D” Model and Relation Between the Linear Viscoelastic Behaviours of Bituminous Binders and Mixes, Road Mater. Pavement Des. (2003). <https://doi.org/10.1080/14680629.2003.9689946>.
- [68] N.I. Nur, E. Chailleux, G.D. Airey, A comparative study of the influence of shift factor equations on master curve construction, Int. J. Pavement Res. Technol. 4 (2011) 324–336. [https://doi.org/10.6135/ijprt.org.tw/2011.4\(6\).324](https://doi.org/10.6135/ijprt.org.tw/2011.4(6).324).
- [69] M. Rochlani, S. Leischner, F. Canon Falla, Gustavo Wellner, Towards a unified performance based characterisation of Bitumen and Mastic using the DSR, Road Mater. Pavement Des. (n.d.).
- [70] American Association of State Highway and Transportation Officials, AASHTO TP 70 - Standard Method of Test for Multiple Stress Creep Recovery (MSCR) Test of Asphalt Binder Using a Dynamic Shear Rheometer (DSR), 2013.
- [71] M. (2017) Gehrke, Komplexe Charakterisierung bitumenhaltiger Bindemittel anhand temperatur-, frequenz- und belastungsabhängiger Kennwerte, Ruhr Universität Bochum, 2017.
- [72] J. (2003); Vonk, W.; Korenstra, J.; van Hek, Rissbildung in Asphaltbelägen: leicht zu verstehen, Zeitschrift Bitum. (2003) 4/03; 166 – 169.
- [73] P.E. Sebaaly, E. Hitti, D. Weitzel, Effectiveness of Lime in Hot-Mix Asphalt Pavements, in: Transp. Res. Rec., 2003. <https://doi.org/10.3141/1832-05>.
- [74] Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), DIN EN 12697-46: 2012-07., Asphalt - Prüfverfahren für Heißasphalt - Teil 46: Widerstand gegen Kälterisse

- und Tieftemperaturverhalten bei einachsigen Zugversuchen, Beuth Verlag, Berlin, 2012.
- [75] C. Maggiore, J. Grenfell, G. Airey, A.C. Collop, Evaluation of fatigue life using dissipated energy methods, RILEM Bookseries. (2012). https://doi.org/10.1007/978-94-007-4566-7_63.
 - [76] A. Braham, B.S. Underwood, State of the Art and Practice in Fatigue Cracking Evaluation of Asphalt Concrete Pavements, 2016.
 - [77] R. Botella, F.E. Pérez-Jiménez, R. Miró, Application of a strain sweep test to assess fatigue behavior of asphalt binders, Constr. Build. Mater. (2012). <https://doi.org/10.1016/j.conbuildmat.2012.06.059>.
 - [78] M. Hospodka, B. Hofko, R. Blab, Introducing a new specimen shape to assess the fatigue performance of asphalt mastic by dynamic shear rheometer testing, Mater. Struct. Constr. (2018). <https://doi.org/10.1617/s11527-018-1171-6>.
 - [79] A. Pereira, R. Micaelo, L. Quaresma, M.T. Cidade, Evaluation of different methods for the estimation of the bitumen fatigue life with DSR testing, in: RILEM Bookseries, 2016. https://doi.org/10.1007/978-94-017-7342-3_81.
 - [80] M. Partl, H. Bahia, F. Canestrari, C. Roche, H. Benedetto, D. H. Piber, Advances in Interlaboratory Testing and Evaluation of Bituminous Materials. State-of-the-Art Report of the RILEM Technical Committee 206-ATB, 2013. <https://doi.org/10.1007/978-94-007-5104-0>.
 - [81] C. Riccardi, A. Cannone Falchetto, M. Losa, M. Wistuba, Back-calculation method for determining the maximum RAP content in Stone Matrix Asphalt mixtures with good fatigue performance based on asphalt mortar tests, Constr. Build. Mater. 118 (2016) 364–372. <https://doi.org/10.1016/j.conbuildmat.2016.05.086>.
 - [82] P. Teymourpour, A.J. Hanz, T. Mandal, H.U. Bahia, S.J. Rizzutto, Effect of parallel plate gap height on repeatability in DSR measurements of crumb-rubber modified binders, J. Mater. Civ. Eng. 28 (2016). [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0001542](https://doi.org/10.1061/(ASCE)MT.1943-5533.0001542).
 - [83] F. Zhou, P. Karki, S. Im, Development of a Simple Fatigue Cracking Test for Asphalt Binders, Transp. Res. Rec. (2017). <https://doi.org/10.3141/2632-09>.
 - [84] R. van Rooijen, L. Planque, M. Wegmann, H. Di Benedetto, S. Mangiafico, C. Sauzeat, F. Olard, S. Pouget, Bitumen fatigue performance evaluation - with or without RAP - a real challenge, in: 2017. <https://doi.org/10.14311/ee.2016.055>.
 - [85] M.R. Mitchell, R.E. Link, L.T. Mo, M. Huurman, S.P. Wu, A.A.A. Molenaar, Research of Bituminous Mortar Fatigue Test Method Based on Dynamic Shear Rheometer, J. Test.

- Eval. 40 (2012) 84–90. <https://doi.org/10.1520/jte103738>.
- [86] P. Cong, N. Liu, H. Shang, H. Zhao, Rheological and fatigue properties of epoxy asphalt binder, *Int. J. Pavement Res. Technol.* 8 (2015) 370–376. [https://doi.org/10.6135/ijprt.org.tw/2015.8\(5\).370](https://doi.org/10.6135/ijprt.org.tw/2015.8(5).370).
- [87] S. Shen, G.D. Airey, S.H. Carpenter, H. Huang, A Dissipated Energy Approach to Fatigue Evaluation, *Road Mater. Pavement Des.* 7 (2007) 47–69. <https://doi.org/10.3166/rmpd.7.47-69>.
- [88] M. Rochlani, G. Canon Falla, F. Wellner, D. Wang, Z. Fan, S. Leischner, Feasibility study of waste ceramic powder as a filler alternative for asphalt mastics using the DSR, *Road Mater. Pavement Des.* (2020). <https://doi.org/10.1080/14680629.2020.1778508>.
- [89] Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), Technische Prüfvorschriften für Asphalt (TP Asphalt-StB), Teil 24: Spaltzug-Schwellversuch – Beständigkeit gegen Ermüdung (2018), Köln, 2018.
- [90] M. Rochlani, S. Leischner, D. Wareham, S. Caro, G.C. Falla, F. Wellner, Investigating the performance-related properties of crumb rubber modified bitumen using rheology-based tests, *Int. J. Pavement Eng.* (2020). <https://doi.org/10.1080/10298436.2020.1776868>.
- [91] T.M. Ahmed, H.A. Khalid, A new approach in fatigue testing and evaluation of hot mix asphalt using a dynamic shear rheometer, in: *Bitum. Mix. Pavements VI - Proc. 6th Int. Conf. Bitum. Mix. Pavements, ICONFBMP 2015*, 2015. <https://doi.org/10.1201/b18538-51>.
- [92] M. Rochlani, S. Leischner, S. Caro, G.C. Falla, F. Wellner, Dissipated Energy Based Approach to Assess the Influence of Temperature and Frequency on the Fatigue Resistance of Bitumen, *Mater. Struct.* (n.d.).

PART II

CORE PUBLICATIONS

Note: This part includes published scientific papers. Copyright and all rights of these papers are retained by respective copyright holders.

PAPERS PUBLISHED AND DECLARATION OF WORK DONE

- a) **Influence of filler properties on the rheological, cryogenic, fatigue and rutting performance of mastics.** Mrinali Rochlani, Sabine Leischner, Gustavo Canon Falla, Dawei Wang, Silvia Caro, Frohmut Wellner. Published in Construction and Building Materials in September 2019. Journal Impact Factor – 4.419.
- The preparation of the materials, DSR testing, data analysis, diagrams along with writing of the manuscripts and further revisions were done by Ms. Rochlani independently under the supervision of Prof. Wellner and Dr. Leischner. Only the chemical tests of the fillers were done at Harbin University and raw data was acquired, which was analysed by Ms. Rochlani. The other authors provided valuable comments and feedback based on which the paper was edited by Ms. Rochlani.

Mrinali
Rochlani

Digital unterschrieben von
Mrinali Rochlani
Datum: 2020.10.07
10:06:35 +02'00'

.....

Mrinali Rochlani

Sabine
Leischner

Digital unterschrieben von
Sabine Leischner
Datum: 2020.10.07
14:17:47 +02'00'

.....

Sabine Leischner

Gustavo
Canon Falla

Digitally signed by Gustavo Canon Falla
DN: cn=Gustavo Canon Falla, o=TUD,
ou=ISS,
email=gustavo_adolfo.canon_falla@tu-
dresden.de, c=US
Date: 2020.10.07 16:52:47 +01'00'

.....

Gustavo Canon Falla

Dawei Wang

数字签名者: Dawei Wang
日期: 2020.10.09
07:40:37 +08'00'

.....

Dawei Wang

Silvia Caro

Digitally signed by Silvia
Caro
Date: 2020.10.09
09:19:30 -05'00'

.....

Silvia Caro

Frohmut
Wellner

Digital unterschrieben von
Frohmut Wellner
Datum: 2020.10.08
13:47:15 +02'00'

.....

Frohmut Wellner

- b) Investigating the performance-related properties of crumb rubber modified bitumen using rheology-based tests.** Mrinali Rochlani, Sabine Leischner, David Wareham, Silvia Caro, Gustavo Canon Falla & Frohmut Wellner. Published in International Journal of Pavement Engineering in June 2020. Journal Impact Factor – 2.464.
- The preparation of the materials, DSR testing, data analysis, diagrams along with writing of the manuscripts and further revisions were done by Ms. Rochlani independently under the supervision of Prof. Wellner and Dr. Leischner. The other authors provided valuable comments and feedback based on which the manuscript was edited by Ms. Rochlani.

Mrinali
Rochlani

.....

Mrinali Rochlani

Digital unterschrieben von
Mrinali Rochlani
Datum: 2020.10.07
10:19:12 +02'00'

Sabine
Leischner

.....

Sabine Leischner

Digital unterschrieben von
Sabine Leischner
Datum: 2020.10.07
14:30:03 +02'00'

David G.
Wareham

.....

David Wareham

Digitally signed by David
G. Wareham
Date: 2020.10.12
09:16:27 +13'00'

Silvia Caro

.....

Silvia Caro

Digitally signed by Silvia
Caro
Date: 2020.10.09
09:31:21 -05'00'

Gustavo
Canon Falla

.....

Gustavo Canon Falla

Digitally signed by Gustavo Canon Falla
DN: cn=Gustavo Canon Falla, o=TUD,
ou=ISS,
email=gustavo_adolfo.canon_falla@tu-
dresden.de, c=US
Date: 2020.10.08 15:23:24 -01'00'

Frohmut
Wellner

.....

Frohmut Wellner

Digital unterschrieben von
Frohmut Wellner
Datum: 2020.10.08
13:47:43 +02'00'

- c) **Feasibility study of waste ceramic powder as a filler alternative for asphalt mastics using the DSR.** Mrinali Rochlani, Gustavo Canon Falla, Frohmut Wellner, Dawei Wang, Zepeng Fan & Sabine Leischner. Published in Road Materials and Pavement Design in June 2020. Impact factor – 2.582.
- The preparation of the materials, DSR testing, data analysis, diagrams along with writing of the manuscripts and further revisions were done by Ms. Rochlani independently under the supervision of Prof. Wellner and Dr. Leischner. The material of ceramic filler was provided by RWTH Aachen. The other authors provided valuable comments and feedback based on which the manuscript was edited by Ms. Rochlani.

Mrinali
Rochlani

Digital unterschrieben von
Mrinali Rochlani
Datum: 2020.10.07
10:19:37 +02'00'

.....

Mrinali Rochlani

Sabine
Leischner

Digital unterschrieben von
Sabine Leischner
Datum: 2020.10.07
14:30:30 +02'00'

.....

Sabine Leischner

Gustavo
Canon Falla

Digitally signed by Gustavo Canon Falla
DN: cn=Gustavo Canon Falla, o=TUD,
ou=ISS,
email=gustavo_adolfo.canon_falla@tu-
dresden.de, c=US
Date: 2020.10.07 16:56:19 +01'00'

.....

Gustavo Canon Falla

Dawei Wang

数字签名者: Dawei Wang
日期: 2020.10.09
07:41:46 +08'00'

.....

Dawei Wang

Zepeng Fan

数字签名者: Zepeng Fan
日期: 2020.10.11
16:08:08 +02'00'

.....

Zepeng Fan

Frohmut
Wellner

Digital unterschrieben von
Frohmut Wellner
Datum: 2020.10.08
13:48:15 +02'00'

.....

Frohmut Wellner

d) Towards a unified performance based characterisation of Bitumen and Mastic using the DSR. Mrinali Rochlani, Sabine Leischner, Gustavo Canon Falla, Frohmut Wellner. Published in Road Materials and Pavement Design in April 2021. Journal Impact factor – 2.582.

- The preparation of the materials, DSR testing, data analysis, diagrams along with writing of the manuscripts and further revisions were done by Ms. Rochlani independently under the supervision of Prof. Wellner and Dr. Leischner. The other authors provided valuable comments and feedback based on which the paper was edited by Ms. Rochlani.

Mrinali
Rochlani

Digital unterschrieben von
Mrinali Rochlani
Datum: 2020.10.07
10:20:38 +02'00'

.....

Mrinali Rochlani

Sabine
Leischner

Digital unterschrieben von
Sabine Leischner
Datum: 2020.10.07
14:31:17 +02'00'

.....

Sabine Leischner

Gustavo
Canon Falla

Digitally signed by Gustavo Canon Falla
DN: cn=Gustavo Canon Falla, o=TUD,
ou=ISS,
email=gustavo_adolfo.canon_falla@tu-
dresden.de, c=US
Date: 2020.10.07 16:57:22 +01'00'

.....

Gustavo Canon Falla

Frohmut
Wellner

Digital unterschrieben von
Frohmut Wellner
Datum: 2020.10.08
13:48:57 +02'00'

.....

Frohmut Wellner

e) **Influence of Source and Ageing on the Rheological Properties and Fatigue and Rutting Resistance of Bitumen Using a DSR.** Mrinali Rochlani, Sabine Leischner Gustavo Canon Falla, Puneet Goudar, Frohmut Wellner. Published in Proceedings of the 9th International Conference on Maintenance and Habitation of Pavements-Mairepav9 in July 2020. Series Title, 'Lecture Notes in Civil Engineering.'

- The preparation of the materials, DSR testing, data analysis, diagrams along with writing of the manuscripts and further revisions were done by Ms. Rochlani independently under the supervision of Prof. Wellner and Dr. Leischner. The other authors provided valuable comments and feedback based on which the manuscript was edited by Ms. Rochlani.

Mrinali
Rochlani

Digital unterschrieben von
Mrinali Rochlani
Datum: 2020.10.07
10:20:01 +02'00'

Mrinali Rochlani

Sabine
Leischner

Digital unterschrieben von
Sabine Leischner
Datum: 2020.10.07
14:30:55 +02'00'

Sabine Leischner

Gustavo
Canon Falla

Digitally signed by Gustavo Canon Falla
DN: cn=Gustavo Canon Falla, o=TUD,
ou=ISS,
email=gustavo_adolfo.canon_falla@tu-
dresden.de, c=US
Date: 2020.10.07 16:56:54 +01'00'

Gustavo Canon Falla

Puneet Shivakumar
Goudar

Digitally signed by Puneet
Shivakumar Goudar
Date: 2020.10.09
18:14:27 +02'00'

Puneet Goudar

Frohmut
Wellner

Digital unterschrieben von
Frohmut Wellner
Datum: 2020.10.08
13:48:39 +02'00'

Frohmut Wellner

Influence of filler properties on the rheological, cryogenic, fatigue and rutting performance of mastics

Mrinali Rochlani^{a,*}, Sabine Leischner^a, Gustavo Canon Falla^a, Dawei Wang^{b,c}, Silvia Caro^d, Frohmut Wellner^a

^a Institute of Urban and Pavement Engineering, Technische Universität Dresden, Germany

^b School of Transportation Science and Engineering, Harbin Institute of Technology, Harbin, China

^c Institute of Highway Engineering, RWTH Aachen University, Aachen, Germany

^d Department of Civil and Environmental Engineering, Universidad de los Andes, Bogotá, Colombia

HIGHLIGHTS

- We evaluated four mastics prepared with a single base bitumen and different fillers.
- The physical and chemical properties of the fillers were characterized.
- We assessed the linear viscoelastic and mechanical performance of the mastics.
- Several correlations between filler and mastic properties were identified.
- Performance diagrams are proposed to rank the overall quality of different mastics.

ARTICLE INFO

Article history:

Received 7 June 2019

Received in revised form 11 September 2019

Accepted 14 September 2019

Available online 28 September 2019

Keywords:

Mineral filler

Mastics

Rheological properties

Fatigue resistance

Low temperature performance

Rutting resistance

DSR

ABSTRACT

This paper compares the rheology properties and mechanical performance of four mastics fabricated with the same base bitumen and four different fillers (dolomite, granodiorite, limestone and rhyolite). The main objective of the investigation was to measure the impact that the filler exerts on the mechanical response of the bitumen. An experimental campaign using the dynamic shear rheometer was performed to quantify rheological properties of the different mastics under both, unaged and aged conditions, as well as their fatigue, rutting and low-temperature cracking susceptibility. A main finding is that the specific surface area of the filler was the most sensitive parameter affecting the mechanical response of the mastics. Also, it was observed that the mastic prepared with granodiorite filler showed the best fatigue and rutting resistance. The results of the investigation were synthesized through a 'performance diagram' that can be used for ranking and characterising bituminous mastics.

© 2019 Elsevier Ltd. All rights reserved.

1. Introduction

In recent years, pavement structures have been deteriorating at an elevated rate due to the increase in service traffic densities, axle loading, changes in weather conditions and, in some cases, a reduction in maintenance activities. Although public agencies continue investing large amounts of funds to attain high-quality and long-lasting pavements, many of these structures show early signs of distresses [1]. As part of the actions to minimize the degradation of pavement surfaces and increase the durability of the asphalt

layers, it is a common practice to improve conventional bitumen in order to enhance performance-related properties, such as resistance to fatigue and low temperature cracking, along with adequate protection against permanent deformation or rutting [2]. Within this context, mastic testing and optimum bitumen-filler combination studies are topics that are slowly gaining popularity and have shown to have more potential than conventional bitumen testing [3–7].

The role of the filler within an asphalt mixture can be divided into two different actions: i) as an inert material, acting as a void 'filler' between coarse aggregates, and ii) as an active material, when interacting with the bitumen at the interface [8]. Multiple researchers have demonstrated that the geometrical, chemical

* Corresponding author at: Georg-Schumann-Straße 7, 01187 Dresden, Germany.
E-mail address: mrinali_rajakumar.rochlani@tu-dresden.de (M. Rochlani).

and mechanical properties of fillers considerably influence the response and performance of the mastic, as well as those of the final asphalt mixtures [4,9,10]. In fact, it has been concluded that the mineral filler may affect asphalt mixes in multiple ways by stiffening the bitumen, and by altering the moisture resistance, workability and compaction characteristics of asphalt mixtures [4,5,7]. Further studies have also confirmed that fillers with a large specific surface area (SSA) and density would lead to a higher stiffening effect, as these fillers would have superior bitumen adsorption properties [11].

In general, a filler is said to affect the mastic and asphalt performance based on the type of material used, its nature (i.e., acidic or basic, physio-chemical properties), and its concentration in the mixture [12–15]. A recent study complemented these findings by demonstrating that it is possible to use surface free energy measurements (i.e., a thermodynamic property) to optimise the type and amount of filler added to a mastic, with the objective of assuring high-quality adhesion properties within a mixture [16].

On the other hand, another important cause for asphalt pavement deterioration is ageing, which leads to hardening effects and that could result in an increased cracking susceptibility of the pavement [17,18]. In the European Union (EU), standard specifications, as well as in several existing published studies on ageing, only the bitumen is individually aged and tested [19]. However, the bitumen cannot be isolated from the mixture, as the physiochemical interactions between bitumen-filler and bitumen-aggregate could catalyse or mitigate the aging process [3,18,20]. Some studies have reported that the filler type and properties could be disregarded altogether when considering ageing, as the filler properties showed no effect on ageing [21,22]. However, contradicting studies have demonstrated that fillers adsorb heavier fractions of bitumen, mainly asphaltenes, which lead to a reduction in the stiffness or an 'age softening' process when compared to plain bitumen [3,18]. These studies have also demonstrated that the adsorption processes are influenced by the filler physical and chemical properties. This situation suggests that there is still a lack of understanding regarding the actual role of mineral fillers in the overall ageing phenomena occurring in asphalt mixtures, and that the characteristics of the mineral fillers and bitumen used along with their interaction should be considered when assessing these processes [18].

Within this context, the objectives of this work are to gain understanding about the influence of different fillers on the rheological properties of mastics, and to develop a suitable plan for testing mastics that could support filler-type selection processes. To achieve these goals, a comprehensive laboratory study was conducted using the Dynamic Shear Rheometer (DSR) in order to investigate the effect of four types of fillers on the rheological properties of the mastics, as well as on the fatigue, rutting and low temperature performance of these materials. Moreover, the rheological tests were conducted on unaged and aged mastic specimens in order to assess the role of the type of filler in the ageing susceptibility of the materials.

This work uses the 2 Spring-2 Parabolic-1 Dashpot (2S2P1D) model [23] to analyse the rheological response of the different mastics. Although this model has been used in several studies for modelling bitumen performance, there are limited applications for mastic materials [23]. Thus, a contribution of this research is the further use of the 2S2P1D model for analysing rheological mastics data. Along with this, a cryogenic test procedure was especially developed for the DSR with the goal of quantifying the low-temperature cracking susceptibility of the mastics through the magnitude of the thermal stresses induced in the material at low temperatures. Moreover, specialized fatigue tests were conducted using a newly developed method for the DSR that includes mastic cylindrical specimens. An analysis was also undertaken to correlate the frequency sweep test data with the cryogenic, rutting and

fatigue test results. Lastly, statistical tools were used to determine the extent at which the physical and chemical properties of the fillers correlate to the rheological and mechanical properties of the mastics, shedding some light to the contradictions found in existing works. Lastly, the paper proposes a new methodology to compare and rank mastics based on performance diagrams, which are constructed using the rheological and mechanical properties collected during the study.

2. Materials and methodology

2.1. Materials and sample preparation

To prepare the mastic specimens, a bitumen classified as 50/70 (1/10 mm) penetration grade, which is widely used in pavement engineering applications in Germany, was selected as the base bitumen. The actual penetration of this base bitumen was 52 (1/10 mm) and the softening point was 51.4 °C. Four mineral fillers (Dolomite, Granodiorite, Limestone and Rhyolite) were used in this research. According to the German guidelines [24], the maximum particle size of mineral fillers is 0.063 mm; however, it was found that the selected fillers were slightly oversized. Nevertheless, it was decided to conduct the tests without further sieving, in order to resemble in-situ conditions. The Limestone filler is the most commonly used filler in Germany, while Dolomite, Granodiorite and Rhyolite fillers find their applications in some local cases.

The bitumen and the filler were blended in the laboratory at 150 °C and at mixing speed of 60 RPM to prepare mastics with a binder-filler mass ratio of 1:1.6. This value was chosen to mimic the bitumen-filler ratio of a stone mastic asphalt, SMA 11S, which is the most popular asphalt mixture used in Germany [25]. According to the TL Asphalt-StB, the recommended bitumen-filler ratio in terms of mass is in the range of 1:1.2 to 1:1.8 [25]. This ratio translates to a volumetric concentration range of 0.36 to 0.38, as the same bitumen was used and the density of the mineral fillers is similar.

The following abbreviations are used throughout the paper to refer to the different mastics:

- mastic with Dolomite filler: Dolomite,
- mastic with Granodiorite filler: Granodiorite,
- mastic with Limestone filler: Limestone, and
- mastic with Rhyolite filler: Rhyolite.

To gain a better understanding of the properties of the different fillers, a detailed study of the physical and chemical properties of the four fillers was conducted as part of this study. This characterisation included specific gravity tests, particle size tests, Brunauer–Emmett–Teller (BET) tests for SSA, Scanning Electron Microscopy (SEM) imaging, and X-ray fluorescence spectrometry tests. The corresponding results are presented in a later section.

2.2. Aging procedure

In order to investigate the filler effect on the long-term performance of the mastics, the mastics were artificially aged in the laboratory. Traditionally, a combination of the Rolling Thin Film Oven Tests (RTFOT) at 163 °C for 75 min and the Pressure Ageing Vessel (PAV) at 100 °C for 20 h at 3.2 MPa is used to simulate the effect of short term and long-term ageing on bitumen/mastic, respectively. Since RTFOT is a time consuming and impractical method for mastics, the method of RTFOT + PAV was replaced by a PAV ageing procedure of 25 h at 100 °C and 2.07 MPa. This ageing method was selected based on the work by Migliori and Corte [26], in which

Fig. 1. a) DSR test device, b) specimen for strain and frequency sweep and for Single Stress Creep Recovery (SSCR) tests, c) specimen for cryogenic stress tests, and d) specimen for fatigue tests.

it was found that 5 h of PAV are equivalent to the standard RTOFT ageing procedure.

2.3. DSR testing

All the rheological and mechanical tests on bitumen and mastics, which included strain, temperature and frequency sweep tests, as well as cryogenic, fatigue and rutting tests, were performed using an Anton Paar MCR 502 Modular Compact Rheometer. Fig. 1 presents the rheometer, as well as the different experimental configurations used for each test.

3. Laboratory tests results

3.1. Properties of the filler materials

This section presents the physical and chemical characterisation of the selected fillers. Firstly, particle size distribution study (using the Horiba LA-920 Particle Size Analyzer) and SEM analysis (using the FEI HELIOS NanoLab 600i dual beam system) of the fillers were undertaken in order to gain a closer look into the microstructure/micromorphology of the filler materials (Figs. 2 and 3). The scale of observation for SEM analysis extended from 8 μm to 300 μm . Fig. 3 shows images at a scale of observation of 30 μm . From the particle size distribution and the microscopic images, it can be observed that Dolomite and Limestone fillers showed a majority of the particles having a smaller grain size, with the Dolomite having the highest proportion of particles with similar diameter. Rhyolite showed an overall well-graded distribution of particle sizes with a significant portion of particles larger than 20 μm . This filler also had a rougher texture than the rest of the fillers. Granodiorite filler showed a variation between particle sizes, ranging from very

small (order of less than 5 μm) to large (more than 20 μm). The geometry of its particles was very angular, while that of the other fillers was more rounded.

Table 1 lists the results of the physical properties of the fillers like density, SSA and pore volume. These tests were done using a 3H-2000PS1 Surface and Pore Size Analyzer in static measurement mode.

Results from these tests permit to conclude that the Rhyolite filler had the lowest density, while Dolomite filler had the highest density (Table 1). In terms of the SSA, it can be observed that the Granodiorite filler had the largest SSA, which is up to 4.4 times higher than in all other fillers, whilst the Limestone filler presented the smallest SSA value. Rhyolite had the highest pore volume and highest average pore size. The Granodiorite filler had the smallest average pore size, whilst the Limestone had the lowest pore volume.

In terms of the chemical analysis, Table 2 presents the results of the various oxide profiles acquired from X-Ray Fluorescence (XRF) tests using PAN Analytical PW4400 spectrometer. It can be observed that the oxide compositions of Granodiorite filler were similar to those of the Rhyolite filler, with the highest percentage of SiO_2 (more than 60%), followed by Al_2O_3 (18–19%). On the contrary, CaO dominated the composition of Dolomite and Limestone fillers, with 61.97% and 92.97% respectively. Additionally, the Dolomite filler also contained a significant portion of MgO, in the order of 26%, which was almost negligible in the other fillers.

3.2. Strain, temperature and frequency sweep test

Strain, temperature and frequency sweeps were conducted on unaged and PAV aged bitumen and mastics. In order to determine the Linear Viscoelastic (LVE) limit for each material, strain sweep tests were performed separately at temperatures -10°C , 10°C , 30°C , 50°C and 70°C at a frequency of 10 Hz and shear strain values in a range of 0.02 and 1.5%. The LVE limit was denoted by the strain value where the dynamic shear modulus equates to 95% of the initial value [27]. These LVE limit strains were further reduced by 20% to ensure that the frequency sweeps were within the LVE region.

Two frequency sweep tests were carried out on every unaged and aged material. One frequency sweep test was conducted at low and intermediate temperatures in the range of -10°C to 30°C using an 8 mm diameter parallel plate with a 2 mm specimen thickness using an angular strain value of 0.4 to 0.8% for unaged materials and 0.03 to 0.1% for aged materials. The second sweep test was performed at higher temperatures, ranging between 30°C and 70°C , using a 25 mm diameter parallel plate and a 1 mm thick specimen using an angular strain of 0.75 to 1.5% for unaged materials and 0.15 to 0.7% for aged materials. The testing

Fig. 2. Particle size distributions of the fillers.

Fig. 3. SEM images of a) Dolomite, b) Limestone, c) Rhyolite, and d) Granodiorite at a 30 μm scale.

Table 1
Physical properties of the fillers.

Filler name	Specific surface area [m^2/g]	Pore volume [ml/g]	Average pore size [nm]	Density [g/cm^3]
Limestone	4.1904	0.0168	16.04	2.72
Dolomite	6.4282	0.0202	12.57	2.85
Rhyolite	6.6294	0.0603	36.38	2.62
Granodiorite	18.4665	0.0411	8.9	2.74

Table 2
Oxide composition of the fillers investigated in [%].

Filler Name	Na_2O	MgO	Al_2O_3	SiO_2	K_2O	CaO	TiO_2	Fe_2O_3	others
Limestone	0.18	2.02	1.29	1.94	0.19	92.97	0.12	0.82	0.46
Dolomite	0.27	26.02	2.26	5.23	0.61	61.97	0.07	1.91	1.60
Rhyolite	1.42	0.41	19.65	65.69	8.98	0.26	0.26	3.04	0.24
Granodiorite	3.22	2.44	18.09	61.70	3.42	2.73	1.04	6.35	0.58

geometry (diameter /gap) was selected in order to keep the torque of the spindle within manufactures recommended limits.

The widely known 2S2P1D model [28], in conjunction with the time-temperature superposition principle, was used in this research to numerically model the LVE response of bituminous materials. This model is valid for any rheological bituminous material and for relevant pavement conditions in terms of frequency and temperature [29]. The model describes the performance of the material through seven parameters [28], as follows:

$$G_{2S2P1D}^*(i\omega\tau) = G_\infty + \frac{G_\infty - G_0}{1 + \alpha(i\omega\tau)^{-k} + (i\omega\tau)^{-h} + (i\omega\beta\tau)^{-1}} \quad (1)$$

where G^* is the predicted dynamic shear modulus, G_∞ is the glassy modulus, G_0 is the static modulus, i is the complex number, ω is the angular frequency, equal to $2\pi f$ (with f being the loading frequency), k and h are dimensionless parameters, β is a parameter related to Newtonian viscosity, α is a shape factor and τ is the characteristic time, which depends on temperature. This later parameter is presented as a function of the shift factor a_T , $\tau(T) = a_T(T)^* \tau_0$, where τ_0 is determined at the reference temperature T_r .

The rheological data were then fitted to the 2S2P1D model at a reference temperature of 20 $^\circ\text{C}$. The black diagram curves presented in Fig. 4 depict the variation of the phase angle with the dynamic shear modulus of the unaged materials tested. Fig. 4a shows the black diagrams from the actual test data, while Fig. 4b shows the smoother, easier to compare diagrams generated using the 2S2P1D model. As observed, the addition of mineral fillers shifted the bitumen curve slightly to the up-right zone of the black diagram, thus leading to a stiffer or more solid-like response. From Fig. 4 it can also be observed that within the low dynamic shear modulus region, the phase angle of the plain bitumen and mastics gradually tended to converge to around 88 $^\circ$. As the phase angle approaches closer to 90 $^\circ$, it indicates that the tested materials approach to the full viscous (liquid) state. Granodiorite had the highest phase angle with a close overlap with both the Dolomite and Rhyolite, while Limestone tracked a slightly lower curve, with 3 $^\circ$ to 5 $^\circ$ lower phase angle values for any given dynamic shear modulus than the other mastics. Overall, the phase angle values were similar among all mastics, with differences of less than 10% in all cases, which means that this property is not strongly influenced by the filler properties.

Fig. 4. Black diagram a) test results, and b) 2S2P1D model data for the unaged bitumen and mastics tested.

To complement the black diagrams, the fitted shear modulus and phase angle master curves are presented in Fig. 5 and the model parameters are listed in Table 3.

Fig. 5a shows that the shear modulus ($|G^*|$) master curves of the mastics were above the master curve of the base bitumen throughout the full frequency range, which is an expected result that could be attributed to the stiffening effect of fillers. It was also found that the dynamic shear modulus of the Limestone was close to that of the base bitumen, ranging from 1.15 to 1.85 times that of the bitumen as the frequency increases. Granodiorite and the Rhyolite mastics presented the highest moduli. A reason explaining the lowest shear stiffness of the Limestone and the highest stiffness of the Granodiorite amongst the mastics is the SSA of the fillers, since the Limestone filler had the lowest SSA while the Granodiorite the highest. A lower SSA would lead to less adsorption of the bitumen film layer, thereby forming a poorer bond that results in a lower stiffness, and vice versa.

At low temperatures (i.e., high frequency), the Granodiorite showed the highest shear stiffness and the Limestone the lowest. At higher temperatures (i.e., low frequency), all mastics were close to one another, with the Granodiorite having the highest stiffness, which is 18% higher than the Limestone at a reduced frequency of 10 Hz and at 20 °C.

The phase angle (δ) master curve, presented in Fig. 5b, confirms that the filler does not significantly influence the phase angle, since all master curves overlapped and were relatively close to one

another within the range of $\pm 3^\circ$. The different stiffening effect of different fillers on mastic was also investigated by Alfaquawi et al. [18] where similar observations were found compared to the results herein obtained. Cole-Cole plots were used to verify the fit quality of the 2S2P1D model with the actual test data (Fig. 6). It can be clearly seen that the model provided a good fit for the bitumen as well as for the mastic. Hence, it can be concluded that the 2S2P1D model is successful for fitting mastic materials, as already observed by Di Benedetto [28].

To better visualize the effect of the fillers in the base bitumen, frequency sweep test data are presented in Fig. 7 in terms of the ratio of the dynamic shear modulus and phase angle between the mastic and the bitumen, at different temperatures and at 10 Hz. Thus, Fig. 7a presents the stiffening effect of the mastics by comparing the change in the dynamic shear modulus, while 7b shows the data for the phase angle. The results from Fig. 7a prelude that the Rhyolite and the Granodiorite were the mastics with the highest increase in stiffness compared to that of the bitumen (i.e., their dynamic shear modulus was up to 5.0 and 5.5 times that of the bitumen at 40 °C, respectively), while the Limestone filler produced the lowest stiffening effect (i.e., a maximum increase in the dynamic shear modulus of 3.0 times with respect to the bitumen at 40 °C). While the results from Fig. 7b confirmed that adding fillers had no significant effect on the phase angle values for temperatures of 10 °C and above, a slight reduction of around 5 to 20% was observed for temperatures ranging from 5 °C to −10 °C.

Fig. 5. Master curves of a) dynamic shear modulus and b) phase angle of the unaged bitumen and mastics (lines – model, points – measured data).

Table 3

 Parameters of WLF equation and 2S2P1D model for the bitumen and mastics with $G_0 = 0$ MPa and $T_i = 20$ °C.

	WLF Equation Parameters			2S2P1D Model Parameters				
	C_1 [–]	C_2 [–]	$/G_0$ [MPa]	k [–]	h [–]	α [–]	τ [s]	β [–]
Bitumen	14.85	122.46	0.67E3	0.314	0.709	5.88	7.6E-05	41.5
Limestone	30.11	210.21	1.26E3	0.310	0.704	5.11	5.4E-05	69.4
Dolomite	15.23	126.31	1.75E3	0.302	0.701	4.08	8.2E-05	59.8
Rhyolite	15.71	125.31	1.92E3	0.319	0.905	5.10	7.2E-05	62.8
Granodiorite	27.21	186.00	2.15E3	0.263	0.741	4.98	7.02E-05	50.8

Fig. 6. Experimental data obtained from DSR tests fitted with the 2S2P1D model for unaged materials.

3.3. Aging index (A.I.)

As explained before, frequency sweep tests were conducted on the bitumen and mastics after being aged using a modified PAV procedure. Ageing of bituminous materials is usually denoted using an ageing index (A.I.):

$$A.I. = \frac{P_{aged}}{P_{unaged}} \quad (2)$$

where P_{unaged} = any physical property (e.g., viscosity, Softening Point of the binder or dynamic shear modulus, among others) measured on the unaged bituminous materials, and P_{aged} = the same physical property measured under aged conditions.

In this study, the dynamic shear modulus values at 20 °C and 10 Hz, and at 60 °C and 10 Hz were used to evaluate the ageing effects of the materials (Fig. 8). Thus, the selected ageing index parameter in herein called A.I. $_{stiffness}$.

Data in Fig. 8 show that all mastics were more and differently affected by ageing than the bitumen in terms of their increase in

Fig. 8. Stiffness ageing index (A.I.) at 20 °C & 60 °C at 10 Hz.

stiffness. At both temperatures, the A.I. $_{stiffness}$ suggested that the Granodiorite was the least susceptible to ageing while the Limestone was the most susceptible, as the A.I. $_{stiffness}$ of the Limestone was 1.72 and 2.65 larger than for the Granodiorite at 20 °C and 60 °C, respectively. In fact, the aging of the Granodiorite was almost the same as that of bitumen at both temperatures with A.I. $_{stiffness}$ differences of 7.5 and 2.5% at 20 and 60 °C. The results obtained in this research are in good agreement with some previous findings reported by Alfaqawi et al [18], who reported A.I. $_{stiffness}$ values ranging between 3 and 4.5 for some mastics tested at 20 °C. The results also showed that the impact of ageing on the shear stiffness of the materials was highly dependent on temperature, and that the differences were larger at higher temperatures; this was observed, for example, on the fact that the values of A.I. $_{stiffness}$ for all mastics were between 2.8 and 4.3 times larger at 60 °C than at 20 °C. The reason for the different aging performance was probably due to the contact area properties developed between the filler particles and the bitumen, which depends on the mineralogical properties and the chemical properties of the filler (aggregate) along with chemical reaction between both components [30].

3.4. Cryogenic stress tests

Cryogenic stress tests were performed in order to determine the thermal stresses induced in the bitumen and mastics when

Fig. 7. a) Stiffening effect, and b) phase angle changes due to adding fillers into the bitumen at 10 Hz and different temperatures.

subjected to low temperatures. This test procedure was designed and implemented as part of this work using the DSR. The idea was derived from the German standard DIN EN 12697-46, which entails testing prismatic asphalt mixture specimens subjected to low temperatures without being subjected to any forces [31].

These tests were performed only on the unaged bitumen and mastics. The specimens had a rectangular prismatic size with 50 mm in length, 4 mm in thickness and 9 mm in width (see Fig. 3) and were fixed between the upper spindle and lower base plate, respectively, and subjected to a constant temperature rate of 10 °C per hour. The temperature range of the test was from 20 °C to −15 °C. More specifically, the specimen was first subjected to 20 °C for 10 min, after which a cooling cycle began that consisted of gradually reducing the temperature from 20 °C to −15 °C. The unloaded specimens were kept for 2 h at −15 °C to observe relaxation effects, and this was followed by a heating cycle where the temperature was increased back to the original 20 °C. There was no loading applied to the specimen; instead, the axial force generated on the specimen by the change in temperature was measured during the experiment. This axial force was converted to thermal stresses by dividing the force by the area of the specimen. Fig. 9(a) shows a typical result of this test for the unmodified bitumen. The three distinct cycles are presented in this figure, where the relaxation is displayed in the form of the black line between the heating and cooling cycles. It was observed that the heating cycles displayed a full recovery of the initial stresses when the testing temperature returned to its initial value of 20 °C. However, the slope of the heating cycle was different than the slope of the cooling cycle. At temperatures around −10 °C, a change in curvature was observed in the heating cycle curves. The reason for this change in curvature could be attributed to the expansion of the material due to the increasing temperatures.

The overall results of the bitumen and mastics are presented in Fig. 9(b). From these results, it can be seen that all the specimens exhibited a slight relaxation in the normal force by the end of the two hours period. It was also observed that the bitumen 50/70 exerted the lowest initial axial force, while showing the smallest relaxation, of approximately 0.25 N.

Based on the results, the normal stress recorded after the two-hour relaxation period at −15 °C and the percentage of recovery after that period were defined as the cryogenic stress parameters for mastic characterisation (Table 4).

The value of percent recovery (reduction in the axial force exerted by the specimen) in Table 4 shows that the plain bitumen had the highest recovery of 64.64% and produced a much lower thermal stress than the mastics (i.e., approximately 20% of the stress applied by the mastics). Among the mastics, the Rhyolite presented the highest stress relaxation (57.23%), closely followed by the Limestone (55.23%). However, Limestone had the lowest

Table 4
Cryogenic stress parameters.

Material	Normal stress after 2 h at −15 °C [MPa]	Recovery (%)
Bitumen 50/70	−0.0171	64.64
Limestone	−0.0634	55.23
Dolomite	−0.0819	47.11
Rhyolite	−0.0795	57.23
Granodiorite	−0.104	36.65

thermal stress among all mastics (−0.0634 MPa), followed by the Rhyolite, which generated 23% higher stress than the Limestone. On the other hand, the Granodiorite showed the smallest recovery with a value of 36.65%, and exerted the highest thermal stress of all the mastics (−0.104 MPa). Using these results, it is possible to conclude that the Limestone mastic had better low temperature performance, while the Granodiorite was the mastic with the least favourable performance under these temperature conditions.

A comparison between the cryogenic stress generated after the two hours recovery period and the dynamic shear modulus for all materials, shows the existence of a proportional relationship between these two parameters at various temperatures (Fig. 10). Hence, the low-temperature performance of the mastics was directly affected by their stiffness. As the dynamic shear modulus increased, the cryogenic stress also increased. Higher values of modulus produced stiffer and more brittle mixes at lower temperatures, thereby generating higher thermal stresses. However, further validation of this trend is required by testing various types of bitumen and mastics.

Fig. 10. Correlation between the cryogenic stress parameter and the dynamic shear modulus at 10 Hz.

Fig. 9. a) Full cryogenic cycle for the bitumen, and b) results of the cryogenic stress tests for all materials tested.

3.5. Fatigue tests

Shear stress-controlled fatigue tests were carried out using cylindrical specimens at a frequency of 10 Hz and a constant temperature of 20 °C. The specimens had a height of 20 mm, a top and bottom diameter with rings of 7 mm and without rings of 6 mm, while the actual dimension of the tested part had a height of 11 mm and a 5 mm diameter (Fig. 11). Each material was tested using nine specimens that were subjected to three different stress levels, with three specimens being tested at each stress level. The analysis of the results of the fatigue tests allows identifying three different phases: 1) the no-damage phase, 2) the crack initiation phase, and 3) the crack propagation phase. The number of load cycles at failure was determined at the transition point between the crack initiation and crack propagation phase; i.e., the peak of the energy ratio $[G'] \cdot N_f$ (i.e., the number of applied cycles), as it represents the rapid increase in damage accumulation and, after this point, the dynamic shear modulus and dissipated energy drastically drop, indicating the failure of the specimen (Fig. 12) [9,32,33]. The traditional Wöhler curve [33,34] was used to present the results of the fatigue tests in terms of the stress versus fatigue life.

Fig. 12 shows the results of the fatigue tests. It can be observed that the fatigue functions of the mastic specimens were above the fatigue function of the base bitumen 50/70. It can be also seen that at low and intermediate stress levels in the centre region of the diagram, the Granodiorite presented the highest fatigue resistance throughout, followed by the Rhyolite, the Limestone and then the Dolomite. However, at high stress levels (i.e., right hand side of the figure); the Dolomite performed as the second best after the Granodiorite, followed by the Rhyolite and the Limestone, respectively. Rhyolite and Limestone mastics had nearly the same fatigue curves at high stress levels.

Fig. 11. Fatigue sample dimensions.

Fig. 12. Fatigue curves for the unaged bitumen and mastics tested.

Table 5

Number of cycles to failure, N_f , at a stress level of 450 kPa.

	N_f @ 450 kPa [–]
Bitumen	10
Granodiorite	95,000
Dolomite	31,000
Rhyolite	46,000
Limestone	32,500

Table 5 lists the number of average loading cycles to failure (N_f) at a stress level of 450 kPa, which was as the selected fatigue performance parameter, following the approach used by Hospodka [35]. These data show that the stress dependant fatigue lives of all mastics were between 31.5 and 95.0 times larger than that of the base bitumen, and that the fatigue resistance of the Granodiorite was between 2.0 and 3.0 times larger than the other mastics, showing the superiority of this mastic to resist damage under cycling loading.

3.6. Permanent deformation tests

To evaluate the rutting resistance of the specimens, Single Stress Creep Recovery (SSCR) tests were conducted on the bitumen and mastics at 60 °C with the 25 mm plate. Since rutting is likely to occur at an earlier life of an asphalt pavement, only unaged materials were tested. For the SSCR test, a single stress level of 3.2 kPa was applied for one second, while allowing the material to recover for the next nine seconds according to the guidelines from the German code established by FGSV [36]. This step was repeated for 10 cycles. The percentage recovery, Rec , and the non-recoverable creep compliance, J_{nr} , were obtained for each cycle and averaged for every specimen. The J_{nr} and Rec parameters were obtained using the following equations:

$$Rec = \frac{\varepsilon_1 - \varepsilon_{10}}{\varepsilon_1} \cdot 100 \quad [\%] \quad (3)$$

$$J_{nr} = \frac{\varepsilon_{10}}{100 \cdot 3.2} \quad [kPa^{-1}] \quad (4)$$

where, ε_1 is the strain increment after the first cycle (at the end of the creep phase), and ε_{10} is the strain increment after the 10 s cycle (at the end of the relaxation phase).

The test results of the bitumen can be compared numerically using the values of the obtained values of J_{nr} and Rec [36] and graphically using the creep cycles plotted. The results are given in Table 6, while the SSCR test results at 60 °C are depicted in Fig. 13. The lower the J_{nr} value, the better the rutting resistance of the material.

Table 6 shows that the Granodiorite displayed the highest recovery percent of 15.85%, which was between 1.6 and 7.1 times larger than for the other mastics. Based on the tests results, the Granodiorite is expected to have the best rutting performance as it had a significantly lower J_{nr} value of 0.1 kPa⁻¹, while all the other materials were 3 times this value and significantly similar,

Table 6

Results of the SSCR tests.

Material	J_{nr} (kPa ⁻¹)	Rec (%)	Cumulative Damage after 10 cycles (%)
Bitumen	0.33	10.02	94.4
Granodiorite	0.10	15.85	3.06
Dolomite	0.33	10.05	10.6
Rhyolite	0.29	2.53	9.16
Limestone	0.30	2.22	9.72

Fig. 13. Creep curves at 3.2 kPa at 60 °C for unaged mastics.

including the base bitumen. When the actual deformation was observed during the 10 load cycles, as depicted in Fig. 13 it was seen that the bitumen had the highest deformation among all the materials, to the extent of presenting a 95% accumulated deformation after 10 load cycles, which is an expected result due to its softer nature compared to the stiffer mastics, all of which had an accumulated deformation of less than 11%.

4. Correlation analysis between filler properties and mastics behaviour

In order to investigate the influence of the filler properties on the rheological and mechanical properties of the mastics, correlation analyses were conducted using the filler properties and their chemical composition. These analyses are useful to reveal mathematical correlations between different sets of parameters.

Data in the Table 7 presents the Person's correlation matrix results between the filler properties and the mastic response. Values in this table show the correlation in terms of R , the correlation coefficient, and Sig , the level of significance. The value of R represents the linear relation between any two variables and is in the range of -1.0 to 1.0 , whereby a value of -1.0 denotes a perfect negative correlation, and 1.0 a perfect positive correlation. The negative sign denotes an inverse relation, (i.e., when one variable increases, the other variable decreases). As the values approach 0.0 from either side, the correlation gets weaker and a value of absolute zero denotes no relation between variables. The level of significance or Sig denotes the probability of rejecting the correlation. R and Sig sum up to 1.0 , and if Sig is higher than R , the correlation can be deemed as improbable. In order to easily identify the

parameters presenting a correlation, R values higher than $+0.7$ and less than -0.7 are highlighted in the matrix below.

The results showed that some rheological and mechanical response of the mastics could be indeed correlated with some fillers properties. For example, it is observed that the dynamic shear modulus at 20 °C and 60 °C of the mastics was highly correlated with three chemical compositions of the fillers (Al_2O_3 , SiO_2 , and CaO), while fatigue performance was highly correlated to Al_2O_3 , SiO_2 and MgO content and to SSA. Additionally, the ageing performance of the mastics, expressed by the $A.I_{stiffness}$, which was generally believed to be mostly dependent on the bitumen, showed a strong correlation with the SSA of the fillers (R value of 0.943). The cryogenic stresses also presented a correlation to the pore volume, particle size and, with R values greater than 0.9 , with some oxides concentrations (Al_2O_3 , SiO_2 , and CaO). The three rutting parameters (i.e., the R_{ec} value, cumulative damage after 10 cycles and the J_{nr} value), highly correlated to the SAA (R values in the range of 0.865 – 0.983). Out of all the filler properties, the SSA correlated the most with the rheological and mechanical behaviour of the mastics in a way such that as the SSA increased, the stiffness along with the fatigue and rutting performance also increased. It seems that larger values of SSA increase the possibility of the bitumen to chemically react with the filler particles and to be more readily adsorbed onto the filler particle surface. This would also affect the properties of the adhesive bond formed between the bitumen and filler, therefore affecting the overall performance of the mastic.

On the other hand, several parameters did not correlate to each other, as shown in Table 7. The density, pore volume, pore size and average particle size of the fillers in Table 7 showed hardly any significant correlation with the rheological and mechanical test results. It was concluded that these were inherent properties of the material with a small influence on the rheological or mechanical behaviour of the mastics. It is noteworthy that other oxides of the fillers were ignored in this study as they made up a very small percent of the material and also were observed to have to no significant relations.

5. Mastic performance diagrams

In order to summarize the behaviour of the mastics, a mesh graph – herein called performance diagram – was developed for the evaluation of bitumen/mastics properties. The evaluation was based on mastic stiffness (dynamic shear modulus at 20 °C and 10 Hz), fatigue behaviour (number of load cycles until the macro

Table 7
Correlation coefficient matrix between mechanical properties and filler properties.

		SSA [m ² /g]	PV [ml/g]	POS [nm]	PAS [μm]	Density [g/cm ³]	Al ₂ O ₃ [%]	SiO ₂ [%]	CaO [%]	MgO [%]
Ageing index stiffness at 20 °C & 10 Hz	R	0.943	−0.173	0.531	0.032	−0.396	−0.418	−0.430	0.564	0.149
	Sig	0.110	0.827	0.469	0.968	0.604	0.582	0.570	0.436	0.851
Dynamic Shear Modulus @ 20 °C & 10 Hz	R	0.782	0.766	0.117	0.615	−0.231	0.888	0.891	−0.963	−0.285
	Sig	0.292	0.234	0.883	0.385	0.769	0.112	0.109	0.037	0.715
Dynamic Shear Modulus @ 60 °C & 10 Hz	R	0.423	0.495	0.895	0.236	−0.385	0.866	0.869	−0.959	−0.115
	Sig	0.577	0.505	0.105	0.764	0.615	0.134	0.131	0.041	0.885
No. of Load Cycles at 450 kPa (Fatigue Test)	R	0.976	0.595	0.078	0.598	−0.623	0.777	0.785	−0.650	−0.835
	Sig	0.024	0.405	0.922	0.402	0.377	0.223	0.215	0.350	0.165
Cryogenic Stress	R	0.551	0.887	0.397	0.764	−0.371	0.906	0.905	−0.977	−0.177
	Sig	0.449	0.113	0.603	0.236	0.629	0.094	0.095	0.023	0.823
Recovery Percent (SSCR)	R	0.865	−0.041	−0.723	0.170	0.533	0.235	0.245	−0.342	0.289
	Sig	0.135	0.959	0.277	0.830	0.467	0.765	0.255	0.658	0.710
Cumulative Damage (SSCR)	R	−0.969	−0.041	−0.379	0.386	0.120	0.628	−0.629	0.562	0.439
	Sig	0.031	0.959	0.621	0.614	0.880	0.372	0.371	0.438	0.561
J _{nr} value (SSCR)	R	−0.983	−0.313	0.404	−0.215	0.106	−0.607	−0.621	0.587	0.439
	Sig	0.034	0.687	0.596	0.785	0.894	0.393	0.379	0.413	0.561

SA: Surface Area, PV: Pore Volume, POS: Average Pore Size, PAS: Average Particle Size, R: Correlation to Pearson, Sig: Significance (2-sided).

Fig. 14. Performance diagrams for the bitumen and the mastics evaluated.

crack criterion is reached at a stress level of 450 kPa, or N_f), low temperature behaviour (cryogenic stress remaining after the relaxation phase, calculated from the axial force produced by the material to prevent expansion), ageing sensitivity to stiffening (ageing index or $A.I._{stiffness}$ at 60 °C, 1.59 Hz) and, finally, the resistance to plastic deformation (J_{nr} value of the unaged mastics).

Fig. 14 shows the performance diagram for all mastics tested. The performance diagrams were structured in such a way that an improvement in a material property can be expected with an increasing distance from the axis cross or origin. Thus, mastics that covered a large area in these diagrams would be expected to have a superior performance. As a result, performance diagrams permit to easily assess, compare, and rank the mastics based on their performance-relevant properties. Based on this ranking, it is possible to select an optimal filler for a specific bitumen.

For the case of the four mastics evaluated, it was clear that the Granodiorite mastic had the largest area within the performance diagram and, hence, that it seems to be the most suitable filler to provide a high-performance behaviour in asphalt mixtures, followed by the Rhyolite, the Dolomite and the Limestone, for the specific tested base bitumen.

6. Conclusions

This paper investigated the effect of four different fillers on the rheological properties and mechanical performance of mastics fabricated with the same common base bitumen. Four different tests were conducted using a DSR equipment – strain, temperature and frequency sweep, cryogenic, fatigue and SSCR tests. Also, the effect of the fillers on the ageing hardening processes of the

mastics was investigated. All the results were presented in a simplified performance diagram to visualize how the mastic properties differ depending on the filler used, and to propose a performance ranking system for selecting the most appropriate filler that could enhance the properties of the material. Overall, the performance diagram showed that the mastics behaved quite differently, with the Granodiorite being the most suitable filler for the base bitumen investigated, because it had the highest stiffening effect on the bitumen, while the ageing susceptibility was the lowest. Furthermore, the Granodiorite mastic also exhibited the best fatigue and rutting resistance performance among all the materials.

Correlation analyses showed that the SSA of the fillers is a dominant property that affect the rheological and mechanical performance of the mastics. For the materials tested, it was found that higher SSA was related to better performance of the mastic in terms of stiffness, and ageing, fatigue and rutting resistance. Based on the tests undertaken in this study, it is recommended to select a filler with a high SSA to achieve good performance and durability (i.e., fatigue, rutting and ageing) of the mastic. However, further studies are required to better investigate how fillers with high SSA might affect the performance of asphalt mixtures. In terms of the chemical composition of the fillers, Al_2O_3 , SiO_2 , and CaO contents also showed positive correlations with stiffness, fatigue and cryogenic performance.

It is important to emphasize that only four mastics, which were fabricated with four different mineral fillers commonly used in Germany and one base bitumen, were investigated in this research. Thus, even though the results herein obtained are promising, further investigations are required to confirm the broad validity of these findings.

Acknowledgements

We hereby acknowledge the financial support provided by TU Dresden as part of the Scholarship Program for the Promotion of Early-Career Female Scientists for Ms. Rochlani. This paper is also partly based on the research project carried out at the request of the German Research Foundation (DFG), under research project No. WE 1642/1-2 and LE 3649/1-2 (FOR2089). The authors are solely responsible for the content.

References

- [1] ITF Transport Outlook 2017, OECD; doi: 10.1787/9789282108000-en, 2017.
- [2] F. Wellner, G.C. Falla, S. Leischner, Betrachtungen zur Einschätzung der Bitumenqualitäten unter besonderer Berücksichtigung der Alterung. In: Proceedings of the Asphaltstraßentagung 2019, 2019.
- [3] R. Moraes, H. Bahia, Effect of mineral fillers on the oxidative aging of asphalt binders, *Transp. Res. Rec. J. Transp. Res. Board* (2015), <https://doi.org/10.3141/2506-03>.
- [4] K. Rieksts, M. Pettinari, V. Haritonovs, The influence of filler type and gradation on the rheological performance of mastics, *Road Mater Pavement Des.* 20 (4) (2019) 964–978, <https://doi.org/10.1080/14680629.2018.1428216>.
- [5] B. Huang, X. Shu, X. Chen, Effects of mineral fillers on hot-mix asphalt laboratory-measured properties, *Int. J. Pavement Eng.* 8 (1) (2007) 1–9, <https://doi.org/10.1080/10298430600819170>.
- [6] N. Shashidhar, A. Shenoy, On using micromechanical models to describe dynamic mechanical behavior of asphalt mastics, *Mech. Mater.* (2002), [https://doi.org/10.1016/S0167-6636\(02\)00166-7](https://doi.org/10.1016/S0167-6636(02)00166-7).
- [7] Y. Tan, M. Guo, Interfacial thickness and interaction between asphalt and mineral fillers, *Mater Struct Constr.* (2014), <https://doi.org/10.1617/s11527-013-0083-8>.
- [8] Y.-R. Kim, D.N. Little, Linear viscoelastic analysis of asphalt mastics, *J. Mater. Civ. Eng.* 16 (2) (2004) 122, [https://doi.org/10.1061/\(asce\)0899-1561](https://doi.org/10.1061/(asce)0899-1561).
- [9] V. Antunes, A.C. Freire, L. Quaresma, R. Micaelo, Influence of the geometrical and physical properties of filler in the filler-bitumen interaction, *Constr. Build. Mater.* 76 (2015) 322–329, <https://doi.org/10.1016/j.conbuildmat.2014.12.008>.
- [10] H. Wang, I.L. Al-Qadi, A.F. Faheem, H.U. Bahia, S.-H. Yang, G.H. Reinke, Effect of mineral filler characteristics on asphalt mastic and mixture rutting potential, *Transp. Res. Rec. J. Transp. Res. Board* (2011), <https://doi.org/10.3141/2208-05>.
- [11] P. Kandhal, S. Chakraborty, Effect of asphalt film thickness on short- and long-term aging of asphalt paving mixtures, *Transp. Res. Rec. J. Transp. Res. Board* (2007), <https://doi.org/10.3141/1535-11>.
- [12] A. Kavussi, R.G. Hicks, Properties of bituminous mixtures containing different fillers, *Asphalt Pav. Technol.* (1997) 153–186.
- [13] M. Guo, A. Bhasin, Y. Tan, Effect of mineral fillers adsorption on rheological and chemical properties of asphalt binder, *Constr. Build. Mater.* 141 (2017) 152–159, <https://doi.org/10.1016/j.conbuildmat.2017.02.051>.
- [14] A. Simone, F. Mazzotta, S. Eskandarsefat, et al., Experimental application of waste glass powder filler in recycled dense-graded asphalt mixtures, *Road Mater Pavement Des.* (2019), <https://doi.org/10.1080/14680629.2017.1407818>.
- [15] V. Vignali, F. Mazzotta, C. Sangiorgi, A. Simone, C. Lantieri, G. Dondi, Incorporation of rubber powder as filler in a new dry-hybrid technology: rheological and 3D DEM mastic performances evaluation, *Materials* (Basel) (2016), <https://doi.org/10.3390/ma9100842>.
- [16] A.E. Alvarez, K.L. Gomez, D.C. Gomez, O.J. Reyes-Ortiz, Optimising the effect of natural filler on asphalt-aggregate interfaces based on surface free energy measurements, *Road Mater. Pavement Design* (2018).
- [17] J.C. Petersen, A review of the fundamentals of asphalt oxidation: chemical, physicochemical, physical property, and durability relationships, *Transp. Res. E-Circular (E-C140) Natl. Acad. Washingt DC.* (2009).
- [18] R. Alfaqawi, G.D. Airey, J.R.A. Grenfell, Effects of mineral fillers and bitumen on ageing of asphalt mastics properties. In: Bearing Capacity of Roads, Railways and Airfields - Proceedings of the 10th International Conference on the Bearing Capacity of Roads, Railways and Airfields, BCRRA 2017, 2018. doi: 10.1201/9781315100333-41.
- [19] DIN EN 14769: Bitumen Und Bitumenhaltige Bindemittel – Beschleunigte Langzeit-Alterung Mit Einem Druckalterungsbehälter (PAV). Deutsches Institut für Normung, Beuth Verlag, Berlin, 2012.
- [20] D. Anderson, H. Bahia, R. Dongre Rheological Properties of Mineral Filler-Asphalt Mastics and Its Importance to Pavement Performance. In: Effects of Aggregates and Mineral Fillers on Asphalt Mixture Performance, 2009. doi:10.1520/stp24215s.
- [21] J. Wu, G. Airey, The influence of mineral fillers on mastic aging properties 2011 doi: 10.1061/41186(421)342.
- [22] S.C. Huang, M. Zeng, Characterization of aging effect on rheological properties of asphalt-filler systems, *Int. J. Pavement Eng.* (2007), <https://doi.org/10.1080/10298430601135477>.
- [23] A. Pedraza, H. Di Benedetto, C. Sauzéat, S. Pouget, 3D Linear viscoelastic behaviour of bituminous mixtures containing high content of multi-recycled RAP, *Road Mater Pavement Des.* (2019), <https://doi.org/10.1080/14680629.2019.1594054>.
- [24] Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), TL Gestein StB – Technische Lieferbedingungen Für Gesteinskörnungen Im Straßenbau, 2011.
- [25] Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), TL Asphalt-StB 07, Technische Lieferbedingungen Für Asphaltmischgut Für Den Bau von Verkehrsflächenbefestigungen, 2007.
- [26] F. Migliori, J.-F. Corté, Comparative study of RTFOT and PAV aging simulation laboratory tests, *Transp Res Rec J Transp Res Board* (2007), <https://doi.org/10.3141/1638-07>.
- [27] G.D. Airey, B. Rahimzadeh, A.C. Collop, Viscoelastic linearity limits for bituminous materials, *Mater Struct Constr.* (2003), <https://doi.org/10.1617/14081>.
- [28] Benedetto H Di, B. Delaporte, C. Sauzéat, Three-dimensional linear behavior of bituminous materials: experiments and Modeling, *Int. J. Geomech.* 7 (2) (2007) 149, [https://doi.org/10.1061/\(asce\)1532-3641](https://doi.org/10.1061/(asce)1532-3641).
- [29] C. Riccardi, Mechanistic Modelling of Bituminous Mortars to predict Performance of Asphalt Mixtures containing RAP, (2017).
- [30] A. Cala, S. Caro, M. Lleras, Y. Rojas-Agramonte, Impact of the chemical composition of aggregates on the adhesion quality and durability of asphalt-aggregate systems, *Constr. Build Mater.* 216 (2019) 661–672, <https://doi.org/10.1016/j.conbuildmat.2019.05.030>.
- [31] Deutsches Institut für Normung, DIN EN 12697-46: 2012-07., Asphalt – Prüfverfahren Für Heiasphalt – Teil 46: Widerstand Gegen Klterisse Und Tieftemperaturverhalten Bei Einachsigen Zugversuchen. Beuth Verlag, Berlin, 2012.
- [32] D.A. Anderson, Y.M. Le Hir, M.O. Marasteanu, J.-P. Planche, D. Martin, G. Gauthier, Evaluation of fatigue criteria for asphalt binders, *Transp. Res. Rec. J. Transp Res Board* (2001), <https://doi.org/10.3141/1766-07>.
- [33] A. Wöhler, Versuche über die Festigkeit der Eisenbahnwagenachsen, *English summary, J. Eng.* 4 (1867) 160–161.
- [34] S. Shen, G.D. Airey, S.H. Carpenter, H. Huang, A dissipated energy approach to fatigue evaluation, *Road Mater Pavement Des.* (2007), <https://doi.org/10.3166/rmpd.7.47-69>.
- [35] M. Hospodka, B. Hofko, R. Blab Zur Ermüdungsbeständigkeit von Asphaltmastic Prüfmethodik und Einflussparameter. In: Fifth Dresdener Asphalttage. TU Dresden; 2017.
- [36] AL MSCR-Test (DSR) FGSV, 723: Arbeitsanleitung Zur Bestimmung Des Verformungsverhaltens von Bitumen Und Bitumenhaltigen Bindemitteln Im Dynamischen Scherrheometer (DSR). (FGSV), Forschungsgesellschaft für Straßen- und Verkehrswesen, 2016.

International Journal of Pavement Engineering

ISSN: (Print) (Online) Journal homepage: <https://www.tandfonline.com/loi/gpav20>

Investigating the performance-related properties of crumb rubber modified bitumen using rheology-based tests

Mrinali Rochlani , Sabine Leischner , David Wareham , Silvia Caro , Gustavo Canon Falla & Frohmut Wellner

To cite this article: Mrinali Rochlani , Sabine Leischner , David Wareham , Silvia Caro , Gustavo Canon Falla & Frohmut Wellner (2020): Investigating the performance-related properties of crumb rubber modified bitumen using rheology-based tests, International Journal of Pavement Engineering, DOI: [10.1080/10298436.2020.1776868](https://doi.org/10.1080/10298436.2020.1776868)

To link to this article: <https://doi.org/10.1080/10298436.2020.1776868>

Published online: 13 Jun 2020.

Submit your article to this journal [↗](#)

Article views: 14

View related articles [↗](#)

View Crossmark data [↗](#)

Full Terms & Conditions of access and use can be found at
<https://www.tandfonline.com/action/journalInformation?journalCode=gpav20>

Investigating the performance-related properties of crumb rubber modified bitumen using rheology-based tests

Mrinali Rochlani^a, Sabine Leischner^a, David Wareham^b, Silvia Caro^c, Gustavo Canon Falla^a and Frohmut Wellner^a

^aInstitute of Urban and Pavement Engineering, Technische Universität Dresden, Dresden, Germany; ^bDepartment of Civil and Natural Resources Engineering, University of Canterbury, Christchurch, New Zealand; ^cDepartment of Civil and Environmental Engineering, Universidad de los Andes, Bogotá, Colombia

ABSTRACT

In recent years, crumb rubber (CR) has become an attractive option to modify bitumen. In this research, a set of Dynamic Shear Rheometer (DSR) tests were used to gauge the effect of two types of CR on different rheological and mechanical properties of CR bitumen (CRB). To achieve this goal, temperature and frequency sweep tests were conducted on three CRB and one penetration 50/70 reference bitumen, and Single Stress Creep Recovery (SSCR) tests were used to quantify the susceptibility of the bitumen to permanent deformation. Moreover, a new specialised cryogenic test and a recently developed fatigue test conducted on prismatic and cylindrical column bitumen samples, respectively, were implemented using the rheometer, and used to assess the low-temperature cracking and fatigue behaviour of the materials. The results indicate that the improvement in all performance-related properties by adding CR into bitumen can be evaluated by using one single device. A performance diagram developed by the authors was used to visualise and compare the effects of adding CR to the bitumen in regards to their rheological, low temperature, permanent deformation and fatigue performance properties.

ARTICLE HISTORY

Received 14 November 2019
Accepted 26 May 2020

KEYWORDS

Crumb rubber bitumen;
rheology; fatigue; rutting;
cryogenic stresses; DSR

Introduction

In recent times, road structures have deteriorated at an elevated rate due to the continuous growth in service traffic densities, axle loading, changes in weather conditions and reduced maintenance services (Lo Presti 2013). As a result, many governments have been doing significant investments to attain exceptional, long-lasting pavements; however, these structures are still showing early signs of distress (Mashaan 2012, *ITF Transport Outlook* 2017 2017). In order to reduce the degradation of pavement surfaces, as well as to improve the durability of the asphalt layer, there is a direct need to enhance conventional bitumen so as to achieve high-quality performance-related properties; including resistance to fatigue and low-temperature cracking, along with adequate protection against permanent deformation or rutting (Mashaan 2012).

One way to improve bitumen properties is through the use of additives, with many commercial ones commonly available for bitumen modification. These include SBS-Styrene Butadiene Styrene, EVA-Ethylene Vinyl Acetate, and SBR-Styrene-Butadiene Rubber (Airey 2003), among several others; which though effective, are very expensive (Mashaan 2012). A promising additive due to its ready availability is Crumb Rubber (CR), which is derived from discarded tyres. CR in asphalt mixes has been used worldwide since the early 1960s, and its use is consistent with the European Union's growing desire to recycle and reuse. The addition of CR to bitumen binder has shown to enhance the physical properties of bitumen; while at the same time providing notable improvements in the properties of the bitumen (Hicks *et al.* 2000, Lo Presti

and Airey 2013, Zhou *et al.* 2014, Chen *et al.* 2019). Multiple researchers have attested that pavements constructed with CR modified asphalt also provide better protection against fatigue and permanent deformation, along with noise reduction (Epps 1994, Fager 2001, Airey *et al.* 2002, Zhou *et al.* 2014). It has also been shown that crumb rubber can improve the low temperature properties and overall improves the performance of reclaimed asphalt (Ding *et al.* 2019). To arrive to these conclusions, most tests have been conducted on crumb rubber modified asphalt mix instead of crumb rubber bitumen; while the ones on bitumen typically included semi-empirical tests (ring and ball, needle penetration tests, viscosity, etc.), along with basic Dynamic Shear Rheometer (DSR) rheology tests (temperature and frequency sweep tests) and complementary tests, such as the Beam Bending Rheometer (BBR) (Lo Presti 2013). The outdated semi-empirical tests currently in use for quality assessment of bitumen in several countries have a limited ability to specifically evaluate the binder characteristics in a comprehensive mesoscale (Kim and Little 2004). On the other hand, while the DSR test has been extensively used in the past to characterise rheological properties of asphalt rubber (Kök and Çolak 2011, Cong *et al.* 2013, Lo Presti 2013, Kraft *et al.* 2018) and to assess fatigue resistance, moisture damage resistance and storage conditions of CR bitumen (Ding *et al.* 2017), the use of the rheometer equipment to comprehensively characterise specific mechanical performance properties, such as a fatigue, permanent deformation and low-temperature cracking susceptibility, has not been explored in detail (Chen *et al.* 2019).

CONTACT Mrinali Rochlani mrinali_rajkumar.rochlani@tu-dresden.de

© 2020 Informa UK Limited, trading as Taylor & Francis Group

Table 1. Characteristics of the CR source used.

Crumb Rubber Type	Composition	Max. Grain Size	CR Source	
			Tyre Type	Manufacturing Process
Source A	Crumb Rubber – 100%	≤ 0.4 mm	Truck Tyre	Cryogenic Process
Source B	Crumb Rubber – 62%	< 1 mm	Automobile and Truck Tyres Mix	Ambient Process
	Bitumen – 22%	–		
	Activated Mineral Binder Stabiliser – 16%	≤ 40 µm		

This leads to the need for development and utilisation of improved testing methods to attain a comprehensive binder characterisation. Using a single machine to accomplish this task would be an improvement over current bitumen characterisation methods, which typically require different equipment to assess specific performance-related properties. Since the rheometer is the most common technique for studying bitumen rheology, it was selected as the chief instrument for the study of the different CR modified bitumen or admixtures in this research.

Therefore, the objective of the present research is to complement existing works that have evaluated the benefits of CR bitumen through existing rheometer-based protocols along with recently developed methodologies that make use of this device. All tests were performed using an Anton Paar MCR 502 Modular Compact Rheometer. Temperature and frequency sweep tests were done to quantify the rheological properties of the different bitumen samples and the 2 Springs – 2 Parabolic elements – 1 Dashpot (2S2P1D) model was utilised to fit the data (Benedetto *et al.* 2007, Nur *et al.* 2013). It is noteworthy that this model has been applied for plain bitumen and polymer modified bitumen in the past (Nur *et al.* 2013, Cardone *et al.* 2015) but no significant literature was found in which it had been used to model CR modified bitumen. Along with rheology, Single Stress Creep Recovery (SSCR) tests, which follow the German standard AL-DSR MSCR – FGSV 723 (FGSV 2016 2016), and share equivalent objectives as the commonly used Multi Stress Creep Recovery (MSCR) test, were conducted to assess permanent deformation resistance. Furthermore, a recently proposed cryogenic test was used to measure low-temperature cracking susceptibility in the DSR equipment, and stress-controlled fatigue tests were performed in the same device using small cylindrical column samples to obtain the fatigue curves of the binders evaluated. To comprehensively assess the acquired results (i.e. rheological, cryogenic, fatigue and rutting response), performance diagrams were used to compare the response of the different CRBs. In summary, a wide-ranging laboratory study was conducted to investigate the effect of two sources of CRB, with one chosen in a proportion as suggested by Kraft *et al.* (2018) and other tested in two different proportions on different rheological and mechanical properties using one single device, and the results were analysed and compared using performance diagrams.

Materials and methods

Materials

In this study, a Russian penetration grade 50/70 bitumen provided by Total, with a penetration value of 53 (1/10 mm) and a

softening point of 53.5°C, was selected as the reference bitumen, and three crumb rubber modified bitumen admixtures (CRB I, CRB II and CRB III) were manufactured using the reference bitumen. Two types of CR (from two sources; A and B) were utilised as additives. The first CR (Source A) was acquired from a European manufacturer who grind truck tyres using a cryogenic grinding method. The other CR source was a commercial rubber product acquired from Portugal, termed RAR-X. This latter one (Source B) was a reacted and activated rubber which consisted of a binder composed of an Activated Mineral Binder Stabiliser (AMBS), plain soft bitumen and fine crumb rubber at optimised proportions (Sousa *et al.* 2013, Kraft *et al.* 2018). Table 1 summarises the details of the two CR sources used. There are two manufacturing methods mentioned in this table: i) cryogenic grinding (Source A), which is a process involving the use of liquid nitrogen to freeze the rubber and then grinding it in a hammer mill; and ii) ambient grinding (Source B), which is a mechanical process that involves producing large, irregular sized crumb rubber at or above room temperature (Lo Presti 2013).

The CRB I admixture was fabricated using 85% reference bitumen and 15% by weight of Source A CR, as previously determined by Kraft *et al.* (2018), while CRB II and CRB III were 85% reference bitumen and 15% Source B CR, and 75% reference bitumen and 25% Source B CR by weight, respectively (Table 2). Two different percentages of CR Source B or RAR-X were considered, as the optimum percentage for the selected base bitumen was unknown. CR from source A was an unreacted rubber powder and CR Source B was a pre-swollen rubber mix. While for the pre-swollen CR (Source B) only relatively low mixing times were needed to reach stable conditions in terms of shear stiffness determined using the DSR of the CR-bitumen mix, source A rubber required longer mixing times to achieve the same goal. These structures within the bitumen are generated as the matrix bitumen transforms from a homogenous material into a two-phase continuous structure which incorporates a rubber powder-bitumen system (Blazewski *et al.* 2018).

CRB I was a more viscous and a non-readily-flowable material than the other two admixtures. Thus, it was more challenging to produce testing samples of this admixture, particularly the required cylindrical fatigue samples.

Table 2. Composition of the admixtures.

Admixture Name	Bitumen Percent	CR Percent	CR Source Used
Bitumen 50/70	100	0	–
CRB I	85	15	Source A
CRB II	85	15	Source B
CRB III	75	25	Source B

Preparation of the CRB admixtures

There are two methodologies for adding CR to the asphalt mix: wet and dry processes (Sousa *et al.* 2013). In the wet process, the CR is added to the hot bitumen. The interaction process between the CR and bitumen has not been fully understood yet; however, there are indications that the interaction between CR and bitumen is not chemical in nature but it is represented by a diffusion process with no chemical interaction (Frantzis 2004, Artamendi *et al.* 2006, Ragab *et al.* 2013). In the dry process, on the contrary, the CR replaces a small portion of aggregate and, hence, is blended in with the aggregate in a hot mix plant. The CR bitumen admixtures for this research were produced using the wet process. While for the pre-swollen CR (Source B) only relatively low mixing times were needed to reach stable conditions in terms of shear stiffness determined using the DSR of the CR-bitumen mix, source A rubber required longer mixing times to achieve the same goal.

Unlike the structured networks commonly generated during certain bitumen modification using thermoplastic elastomers polymers, such as SBS and others, after the CR and bitumen are mixed, it is expected that the CR particles would remain as dispersed particles (Lo Presti *et al.* 2012, Blazejowski *et al.* 2018). Nevertheless, one of the well-known consequences of this is the lack of storage stability that was observed for CR modified bitumen.

To prepare the admixtures, the reference bitumen was first heated for one hour in the oven at a temperature of 180°C, after which CR was added to the hot bitumen in a mixing bowl. The mixing temperature (180°C) and the mixer rotation speed (200 RPM) were kept constant during the mixing process (Kraft *et al.* 2018). The material was mixed in the special chamber with a special heating plate and vacuum, so as to significantly reduce ageing due to oxidation. The CRB admixtures were mixed for a total of 150 min, with samples taken at 15-minute intervals to track the optimum mixing time. This was identified by measuring the stiffness at 60°C at 30 Hz in a DSR test of each 15-min period sample derived from the mixing process. Figure 1 shows the stiffness profile as a function of mixing time, which allows concluding that the optimum mixing time was 90 min for the CRB I (Kraft *et al.* 2018) and 30 min for CRB II and III.

Testing procedures

As explained previously, all performance tests were done using a rheometer. Compared to most common test procedures (Multi-stress creep recovery test (MSCR), DSR tests, BBR tests etc.) used in the past to evaluate the CRB performance that require the use of multiple equipment (Lo Presti 2013), only the DSR test device was herein used to evaluate the CRB performance in terms of plastic deformation performance, stiffness, low temperature performance and fatigue performance. These tests are explained next.

Shear strain and frequency sweep tests

These tests were conducted for all admixtures at temperatures of −10°C, 10°C, 30°C, 50°C and 70°C in order to determine the linear viscoelastic (LVE) limit strains. The LVE limit was defined as the strain value where the dynamic shear modulus gets reduced by 5% of its initial value. These strain limits were further reduced by 20%, to ensure that the LVE region was maintained during the temperature and frequency sweep tests that followed. The resulting strain ranges values (temperature range −10–70°C) were 0.55–8.50%, 0.45–4.44%, 0.42–6.18% and 0.52–4.96% for bitumen 50/70, CRB I, CRB II and CRB III, respectively. Thus, two temperature and frequency sweep tests were then conducted, one from −10°C to 30°C using an 8 mm diameter plate with specimen thickness of 2 mm, and the second from 30°C to 70°C using a 25 mm diameter plate and 1 mm thick specimen, all of them within the frequency range of 0.0159–79.6 Hz. The difference in the diameter plate was due to the range of stiffness of the materials at the selected temperature ranges (i.e. lower temperatures required smaller plates due to the high stiffness of the materials).

From the frequency tests, rheological data (i.e. dynamic shear modulus and phase angle) was acquired and analysed by applying the TTSP to construct the master curve of the dynamic shear modulus at a reference temperature of 20°C. The experimental data was analysed using the mechanical 2 Spring-2 Parabolic-1 Dashpot (2S2P1D) model (Di Benedetto *et al.* 2007). The advantage of numerical modelling is that it gives analytical expressions that can be used to extrapolate data outside of the range provided by the experimental measures. Furthermore, numerical models give quantitative

Figure 1. Dynamic shear modulus of the CRB at 60°C versus mixing time for the three CR modified bitumen.

parameters that provide a rational basis for comparison criteria between different materials.

Master curves are used to present the extended data (mechanical properties) over a wide range of loading times and frequencies in one graph provided that the material behaves thermo-rheologically simple. Black Diagrams present raw data in form of a complex moduli versus phase angles plot, without requiring any time-temperature superposition. The continuous trend in Black diagrams make it evident that a material behaves thermo-rheologically simple, thereby the TTSP is applicable to the materials. Furthermore, Black diagrams are helpful in evaluating any data discontinuities which make it an essential for studying CRB. Cole-Cole plots present the relation of loss moduli and storage moduli (Lesueur *et al.* 1996). In this study, the shift factors were fitted to the Williams-Landel-Ferry, or WLF, function, as follows (Nur *et al.* 2011):

$$\log \alpha_T = \log \frac{\eta_0(T)}{\eta_0(T_r)} = -\frac{c_1(T - T_r)}{c_2 + (T - T_r)} \quad (1)$$

where α_T is the shifting factor, η is the Newtonian viscosity, T is the initial temperature, T_r is the arbitrarily chosen reference temperature, and C_1 and C_2 are fitting constants. On the other hand, the 2S2P1D model describes the performance of the material through seven parameters (Di Benedetto *et al.* 2007), as follows:

$$G_{2S2P1D}^*(i\omega\tau) = G_\infty + \frac{G_\infty - G_0}{1 + \alpha(i\omega\tau)^{-k} + (i\omega\tau)^{-h} + (i\omega\beta\tau)^{-1}} \quad (2)$$

here, G^* represents the predicted dynamic shear modulus, G_∞ the glassy modulus, G_0 the static modulus, i is the complex number, ω is the angular frequency equal to $2\pi f$ (with f being the loading frequency), k and h are dimensionless parameters, β is a parameter related to Newtonian viscosity, α is a shape factor, and τ is the characteristic time, which depends on temperature. This later parameter is presented as a function of the shift factor a_T , $\tau(T) = a_T(T)^* \tau_0$, where τ_0 is determined at the reference temperature T_r (Di Benedetto *et al.* 2007).

Error minimisation procedures of least absolute relative error (LARE) and mean normalised error (MNE) were used to determine the model variables providing the best fit of the experimental data. The quality of fit of the model to the test data can be observed in the Results and Discussion section.

Cryogenic tests

These tests were performed to determine the thermal stresses and the response of bitumen when subjected to changes in temperature (Rochlani *et al.* 2019). This recently developed test procedure corresponds to a scaled-down version adapted for the DSR from the German standard DIN EN 12697-46, which entails testing of prismatic bitumen specimens (50 mm length, 4 mm thickness and 9 mm width) subjected to low temperatures without being subjected to any forces (Deutsches Institut für Normung 2012). The prismatic bitumen specimen was fixed on the upper spindle and lower base plate, while being subjected to a constant change of temperature at a rate of 10°C per hour. The temperature range of the test was from

20°C to −15°C. The axial force exerted on the specimen due to an imposed change in temperature was measured. The obtained axial force divided by the cross-sectional area of the specimen results in the normal stress, which corresponds to the thermal stress generated within the specimen. This test was repeated twice for each material with the results being very similar (less than 10% difference) and, hence, only one result per bitumen is presented and analysed in later sections.

Fatigue tests

Due to the repeated heavy traffic load, tensile stresses occur at the bottom of the asphalt base layer, causing micro-cracks which accumulate. With repeated loading, these cracks spread upwards and are linked to macro-cracks that can be seen on the pavement surface. When these cracks finally propagate to the surface, a crack pattern typical of fatigue damage develops. It can be assumed that one reason for the insufficient fatigue performance of asphalt mixes and hence the premature pavement damage can be the addressed to the insufficient quality of the bitumen. As a result, stress-controlled fatigue tests were conducted using cylindrical bitumen column specimens at 10 Hz and at an intermediate temperature of 20°C (Mitchell *et al.* 2012, Cong *et al.* 2015, Rochlani *et al.* 2019). The cylindrical columns were 20 mm high, with the effective testing section being 11 mm in height and 6 mm in diameter. Steel rings (outer diameter 8 mm, wall thickness 1, and 4.5 mm in height) were fixed at both ends of the column to install the sample on the rheometer. The sample was fixed at the bottom and subjected to torsional load at the top. Nine fatigue tests were conducted for each admixture, using three replicates at three different stress levels and three parallel tests were run. The results were analysed using the Dissipated Energy Ratio theory (Shen *et al.* 2007) in order to construct the fatigue curve of each CRB. It is important to note that the fabrication of these specimens under aged polymer modified and CRB is cumbersome, but a smoother, improved approach is currently being developed. For this reason, testing was done on unaged materials to provide an initial insight of the relative response among the materials that are tested in terms of ranking and expected performance.

It should also be stressed that there are protocols to estimate the fatigue resistance of bitumen using rheometers, being the Linear Amplitude Sweep (LAS) (Riccardi *et al.* 2016) Test the most common one. However, due to the heterogeneous nature of the CRB samples, conducting LAS or equivalent procedures that use the plate-plate configuration is challenging and could provide unreliable results. Although Teymourpour reported (Teymourpour *et al.* 2016) that reliable LAS test results can be achieved by increasing the gap between the plates for CRB samples, the authors decided to undertake stress-controlled fatigue tests on column samples to have a same sample shape for both CRB mixes, independently of the maximum particle size of each mix. Indeed, the geometrical configuration herein proposed, overcomes this issue, at the time that provides the full fatigue curve of the material and not just testing data to estimate the expected fatigue resistance of the material. It is noteworthy that the selection of a stress-controlled mode for this test follows current practices for asphalt fatigue tests in Germany.

Figure 2. a) rheometer device, b) specimen for strain and frequency sweep and for Single Stress Creep Recovery (SSCR) tests, c) specimen for cryogenic stress tests, and d) fatigue tests specimen.

Single stress creep recovery (SSCR)

SSCR tests were conducted to assess the rutting resistance of the admixtures on RTFOT aged materials. SSCR tests were conducted on three replicates per specimen at 60°C for the 25 mm plate, and at 10°C for the 8 mm plate. In these tests, a stress of 3.2 kPa was applied for 1 sec, while allowing the material to recover for the next 9 sec. This procedure was repeated for 10 cycles. The percentage recovery (%Rec) and the non-recoverable compliance (J_{nr}) were obtained for each cycle and then averaged for every sample (American Association of State Highway and Transportation Officials 2013). The two parameters, J_{nr} and %Rec were obtained using the following equations:

$$\%Rec = \frac{\epsilon_1 - \epsilon_{10}}{\epsilon_1} * 100 \quad [\%] \quad (3)$$

$$J_{nr} = \frac{\epsilon_{10}}{100 * 3.2} \quad [kPa^{-1}] \quad (4)$$

where ϵ_1 is the strain increment at the end of the creep phase of the first cycle, and ϵ_{10} is the strain increment at the end of the relaxation phase of the tenth cycle.

The rheometer machine used in this study, was well as the test specimens used for each test are presented in Figure 2.

Results and discussion

Temperatures and frequency sweep test results

Figure 3a presents the Black diagrams obtained for all admixtures, Figure 3b the Cole–Cole plots obtained using both the experimental and the 2S2P1D model fitted data, and Figure 3c and 3d the phase angle and dynamic modulus master curves obtained using the model data at a reference temperature of 20°C, respectively.

The Black diagrams (Figure 3a) show a smooth fit from one temperature to another, and the transition from the big plate (25 mm) geometry for higher temperatures to the small plate (8 mm) geometry for lower temperatures. It is noted that all CR-modified bitumen specimens had a lower phase angle for any given shear modulus value in comparison to the reference bitumen, thereby implying a more elastic behaviour. CRB I had the lowest phase angle values, with a plateau at around 60°, which were consistently lower than all other admixtures for equivalent values of shear modulus. This shape of the curve

in the Black diagram is typically observed for polymer modified bitumen (Burger *et al.* 2001). CRB III lies somewhere in between the reference bitumen and the CRM I admixture with a slight plateau at 60° and an increase up till 80°, while CRB II had the closest profile to the bitumen 50/70. The slight deviation of the CRBs from the reference bitumen could be a result of the interaction between the bitumen and the CR particles. Since CRB I was made using rubber from source A (100% rubber), it would naturally form a direct bitumen–CR interaction than the rest. In contrast, there are less visible changes in the CRB II and CRB III admixtures, as the source used to fabricate these was a pre-reacted rubber contained a portion of a non-reactive filler.

The Cole–Cole plots (Figure 3b) show the actual data and the 2S2P1D model predicted values over a wide range of frequency and temperature combinations. These data show that the CRB I Cole–Cole plot had the lowest storage and loss modulus, while those for the plain, CRB II and CRB III bitumen resulted in similar plots. From a visual perspective, the small separation between the actual and predicted data means that the 2S2P1D model provides a good fit for all materials. Therefore, it can also be concluded that the 2S2P1D model can adequately model CR modified bitumen rheological behaviour.

Similar to the Black diagrams, from the phase angle master curves (Figure 3c), it is observed that the CRB I had the lowest phase angle for any given frequency and temperature combination and, hence, would more readily relax stresses and recover strains. The CRB III admixture follows closely behind CRB I, while the reference bitumen presented the highest phase angle values. The differences in the curve shapes are again attributed to the amount of crumb rubber present in each rubber type.

Lastly, in terms of the master curves for the shear modulus (Figure 3d), it can be clearly seen that the curves for the bitumen 50/70, the CRB II and the CRB III are close to one another, while the terminal dynamic shear moduli for CRB II and CRB III are also similar. The CRB I presented a significantly lower shear moduli when compared to the reference bitumen, and this could be a result of the interaction processes between the CR and bitumen, which is related to a diffusion process. While the other three materials, including the unmodified bitumen, exhibited much higher moduli at higher frequencies and lower temperatures, making the influence of the rubber diffusion process more visible. Alternatively, the higher modulus

for the CRB II and CRB III could be just a result of the stiffening effect due to the mineral filler present in the CR Source B. In any case, considering that CRB I showed more flexibility (greater ability to recover from strains) or that CRB II and CRB III showed a similar rheological behaviour as the plain bitumen, either explanation could provide an impetus for further utilisation of crumb rubber from waste tyres as a bitumen modifier, thereby reducing bitumen requirements.

In order to determine the characteristic stiffness values for the admixtures, the dynamic shear modulus at 20°C and 60°C at 10 Hz was compared (Table 3). At 60°C, it was evident that the reference bitumen had a much lower modulus than all the modified bitumen admixtures, meaning that at high temperatures this bitumen has more potential to deform than any other admixture. Table 3 also shows that the reference bitumen, CRB II and CRB III all have similar moduli at 20°C and 10 Hz (less than 1.1% difference); while CRB I's modulus is 10% lower than the others. At 60°C and 10 Hz, CRB II's modulus was around 22kPa lower than that of CRB III, which implies

Table 3. Comparison of the dynamic shear moduli at 20 and 60°C and 10 Hz.

Sample	Absolute shear modulus at 20°C and 10 Hz [kPa]	Absolute shear modulus at 60°C and 10 Hz [kPa]
Bitumen 50/70	10221.21	30.11
CRB I	9032.34	67.22
CRB II	10747.87	45.15
CRB III	10868.91	67.90

that the selected amount of the CR Source B used in the admixtures has a more pronounced effect at higher temperatures. The moduli for CRB I and CRB III were very similar at this higher temperature, with a difference of less than 1 kPa, and they both were substantially higher than for the other two bitumen. This difference could be a result of the dissimilar diffusion processes between the rubber and bitumen. Therefore, it seems that the CRBs deforms less and recovers more readily from strains at higher temperatures. Table 4 presents the rheological data modelling parameters using the time-temperature superposition principle (WLF equation) and the 2S2P1D model.

Figure 3. a) black diagrams (experimental data), b) Cole-Cole plots (experimental and fitted data), c) phase angle master curves (fitted data) at a reference temperature of 20°C and d) dynamic shear modulus master curves (fitted data) at a reference temperature of 20°C.

Table 4. Parameters of TTSP equation and 2S2P1D model for all the bitumen, with $G_0 = 0$ MPa and $T_r = 20^\circ\text{C}$.

	WLF Equation Parameters		2S2P1D Model Parameters					
	C_1 [-]	C_2 [$^\circ\text{C}$]	$ G_{\infty} $ [MPa]	k [-]	h [-]	a [-]	τ [s]	β [-]
Bitumen 50/70	14.61	125.30	0.73E3	0.29	0.70	5.98	8.22E-5	52.8
CRB I	15.65	134.33	0.49E3	0.30	0.67	7.02	2.38E-4	1012
CRB II	15.11	128.17	0.79E3	0.26	0.68	6.37	5.77E-5	202.1
CRB III	15.81	132.83	0.76E3	0.24	0.63	5.98	3.56E-5	1003

Cryogenic stress test results

Based on the method described earlier, Figure 4 presents the results of the cryogenic stress tests in terms of the thermal stresses produced on the testing specimen during the cooling and heating cycle. The three cycles (cooling, recovery and heating) are clearly differentiated in Figure 4a, where the recovery period is displayed in the form of the green-continuous line between the cooling and heating cycles. The heating cycle displays a full recovery of the initial stresses when the testing temperature returns to its initial value of 20°C . The slope of the heating cycle is steeper than the slope of the cooling cycle, especially at temperatures around -10°C , where a change of curvature in the heating cycle curves becomes more pronounced. This sudden step-change could be attributed to reaching some limiting

value in the ability in the material to expand as the temperature increases.

Figure 4b shows the obtained cooling cycles, while Figure 4c shows the heating and recovery cycle results for all the admixtures. It is evident that the bitumen 50/70 experienced the lowest initial normal stress at the end of the cooling cycle, while CRB I had a slightly higher stress (-2 kPa) and CRB II and CRB III exerted the highest stresses (as high as -2.5 kPa). All admixtures exhibited a slight recovery in the normal stress by the end of the two-hour period. From Figure 4c, it is evident that the base bitumen showed the least relaxation, of approximately 0.25 kPa. The recovery for the CRB I was much larger, being close to 1 kPa; while for CRB II and CRB III admixtures, the values were approximately 1.5 kPa. All CRB admixtures ended up with a final normal stress of around 1 kPa (at the

Figure 4. a) Full cryogenic cycle for one material (CRB I), and recorded normal stress during b) the cooling cycles, and c) the heating and recovery cycles for the CRBs and the base 50/70 bitumen.

Table 5. Cryogenic stress parameter.

Material	Normal stress after 2 h at -15°C [kPa]	Recovery [%]
Bitumen 50/70	-1.50	16.56
CRB I	-0.94	53.39
CRB II	-1.05	58.52
CRB III	-1.05	58.51

Table 6. Fatigue performance parameter.

Material	Stress level @ fatigue life of 150,000 load cycles [kPa]
Bitumen 50/70	102
CRB I	118
CRB II	110
CRB III	135

end of the recovery period and consecutive to the beginning of the heating cycle, denoted by the diamond in the right diagram of Figure 4c). The base bitumen was close to 1.5 kPa (denoted by the 'x' symbol in the right diagram of Figure 4c).

Table 5 lists the normal stress after relaxation at -15°C , and the correlated recovery percentage data, which are the two parameters selected to assess the susceptibility to low-temperature cracking of the four binders. Results from Figure 4 and Table 5 show that even though the base 50/70 bitumen was subjected to smaller thermal stresses compared to the other CRBs tested, it had the lowest ability to recover. In contrast, all crumb rubber modified materials had a higher ability to recover, with CRB II and CRB III displayed the highest recovery percentages (Table 5). CRB I had the lowest normal stress after the two hours period at -15°C , while the stresses for CRB II and CRB III were near 12% larger than for CRB I. Moreover, the reference bitumen had a 0.5 kPa higher normal stress and a significantly lower recovery than the three rubber modified mixtures (more than 3 times lower), all of which were greater than 50%. The results from Table 5 support the frequency sweep test results, in the sense that the addition of rubber adds to the flexibility response of the bitumen, thereby improving its stress recovering properties. The results obtained with this newly developed test could be an effective alternative to conventional tests, like the asphalt pavement thermal testing system (TSRST) and the BBR test, so as to underline the benefits of using CRB in terms of low temperature performance (Lee *et al.* 2008, Kök *et al.* 2013, Wang *et al.* 2017).

Fatigue test results

Figure 5 shows the fatigue test results, expressed as the fatigue curves of the materials (i.e. number of loading cycles (LC) until

macro-crack formation as a function of the applied stress level). The LC where macro-crack forms is considered as the point of failure. Results from this figure show that the CRB II and CRB III admixtures outperformed the reference 50/70 bitumen at all stress levels, with CRB III failing at the greatest number of load cycles for any given stress level. Therefore, it can be concluded that CRB III has better fatigue resistance properties than the other three admixtures. On the other hand, CRB I showed better fatigue characteristics for stress levels lower than 125 kPa (i.e. takes longer to fail for any applied stress) than the reference bitumen. However, at higher stress levels, it was observed that this CR bitumen fail significantly quicker than all others materials. It is suspected that the bitumen-rubber interaction is stronger at lower stresses, and is therefore able to recover strains more rapidly, thereby failing at longer loading periods. The fatigue behaviour of CRB II (slightly better than the reference bitumen) and CRB III (significantly better at lower stresses, and relatively better at higher stresses) could be a result of the filler present in Source B CR or of differences in the chemical and physical properties between both CR sources (A and B).

A mid-range value of 150,000 load cycles (testing range) was chosen in order to compare the different admixtures. Table 6 lists the stress levels that should be applied to the materials to fail at that number of loading cycles. The results indicate that CRB III requires the largest stress level to fail at these load cycles, while the reference bitumen requires the smallest stress level (33 kPa smaller than for the CRB III). Regardless, all the CRB admixtures require larger stresses than the reference bitumen to achieve a similar number of load cycles to failure, then showing a superior fatigue resistance, as already demonstrated in previous works for different types of CRB (Lo Presti 2013, Kraft *et al.* 2018, Yu *et al.* 2018). It is noteworthy that the

Figure 5. Fatigue curves for the bitumen tested (LC: life cycles).

Figure 6. Creep curves at 3.2 kPa at a) 60°C, and b) 10°C.

Table 7. Parameters of the SSCR tests.

Material	60°C		10°C	
	J_{nr} [kPa ⁻¹]	%Rec [%]	J_{nr} [kPa ⁻¹]	%Rec [%]
Bitumen 50/70	1.02	3.11	3.09E-04	80.79
CRB I	0.17	64.33	2.28E-04	89.88
CRB II	0.73	8.57	2.91E-05	84.15
CRB III	0.37	20.34	2.47E-05	87.53

150,000 load cycles value was arbitrarily selected and, as Figure 5 reveals, the actual number of load cycles to failure is actually contingent upon the applied stress, with the associated conclusion for CRB I a function of the stress level (particularly at the higher stress levels).

Single-stress creep recovery (SSCR) test results

As previously mentioned, SSCR tests were conducted at two temperatures (60°C, standard (American Association of State Highway and Transportation Officials 2010, 2013), and 10°C for low temperature response) at a stress level of 3.2 kPa. The SSCR test results can be contrasted using the creep cycles plotted (Figure 6) and the average J_{nr} and %Rec values for 10 cycles (Table 7).

Results at 60°C in Figure 6 show that the reference 50/70 bitumen had the largest deformations (32.5), followed by CRB II, CRB III and CRB I, respectively, with CRB I having a strain value smaller than 5.0 during the totality of the experiment (Figure 6a). In Table 7, low J_{nr} and high %Rec values indicate a greater resistance of the bitumen to rutting, since the J_{nr} number is proportional to the permanent deformation of the material. Correspondingly, higher values of %Rec means an enhanced capacity of the admixture to recover after the creep period. An examination of the J_{nr} values reveals that CRB I had the lowest value, while the reference bitumen presented the largest (a difference of 90% between both bitumen); while for %Rec, the base 50/70 bitumen showed the smallest recovery (3.11%, Table 7), with CRB I showing a substantially higher recovery of 64.33% (almost 21 times larger than the reference bitumen). The results for CRB II and III admixtures indicate that as the rubber content increased from

15% to 25%, the recovery significantly increased from 8.57% to 20.34% (Table 7), as expected. This implies that the rubber content increases the flexibility of the admixture, which means that it would deform less, while at the same time it would easily recover from any deformation. This would translate into longer lasting pavement, with lower associated maintenance costs.

As observed in Figure 6b and Table 7, at 10°C all the admixtures had very low deformations, less than 0.014, coupled with much lower J_{nr} values (magnitude of e^{-6} to e^{-7}) and very high %Rec (higher than 80%) (Table 7). These similarities point to very similar elastic behaviour of all admixtures at lower temperatures. The reference bitumen and CRB I were seen to deform more and recovered less than the other admixtures with some clearly-defined peaks. These peaks may be a result of the visco-elastic behaviour, indicating formation and recovery of thermal stresses and cracks and a release of energy.

The fact that the CRB admixtures present superior rutting behaviour than the reference bitumen at high and low temperatures reinforces the results presented in previous works regarding the advantages of modifying bitumen with waste rubber (Lee *et al.* 2008, Lo Presti 2013, Kaloush 2014, Wang *et al.* 2017).

Synthesis of results

Experimental results were used to construct Figure 7 which includes performance diagrams to pictorially rank the admixtures based on their stiffness ($\pm G^*$ at 20 and 60°C and 10 Hz), cryogenic (stress recovery), fatigue (stress level to fail at 150,000 loading cycles), and rutting behaviour (J_{nr} and %Rec at 60°C). (Tables 3, 5, 6 and 7)

This diagram, which was originally introduced by the authors in a previous work (Rochlani *et al.* 2019), provides the possibility of ranking different bitumen admixtures on the basis of any of the specific parameters studied in this research and obtained via the rheometer instrument. For example, it can be seen that CRB III has the highest fatigue resistance compared to the other admixtures and, therefore,

Figure 7. Ranking diagram for the base bitumen and the three CRB materials.

displays the best performance as evaluated by this particular parameter. In contrast, CRB I performs the best when considering rutting resistance (J_{nr} at 60°C). In addition, CRB I shows the lowest stiffness at 20°C and 10 Hz compared to the plain bitumen 50/70, CRB II and CRB III. When comparing all these results together, it is possible to assert that the admixture CRB III present the best overall performance, since it has the greatest numerical enclosed area, followed by CRB I, CRB II and the base 50/70 binder. It is to be noted that these diagrams can be modified to incorporate other relevant parameters when necessary; and if properties are considered to be more relevant than others for a specific project, it could be possible to add scalar weights to each axle, which will impact the computation of the overall area.

Conclusions

In this study, results from relevant advanced characterisation tests were used to gain a deeper understanding of the effect of two types of CR on the rheological and mechanical properties of three CRB (CRB I, CRB II and CRB III) using only a rheometer device. A ranking diagram that summarises these results allows to clearly visualise the effect of bitumen modification on the overall response and performance of bitumen.

Based on the results, it is concluded that the rheometer has a good ability to characterise the admixtures in regard to their rheological, low temperature, permanent deformation and fatigue performance properties. Furthermore, the results of the temperature and frequency sweep, cryogenic, fatigue and SSCR tests showed that CR substantially enhances the performance of the reference bitumen. While the CR addition in

bitumen present several advantages, it should be noted that mixing times are high to allow for appropriate swelling and reactions to take place. The mixing time and energy are not a concern for a pre-reacted rubber, such as that derived from Source B.

Acknowledgements

We would like to acknowledge the help of Juliane Kraft for providing guidance for preparing the rubber modified bitumen. We hereby acknowledge the financial support of TU Dresden within the Scholarship Program for the Promotion of Early-Career Female Scientists for Ms. Rochlani. This paper is also based on the research project carried out at the request of the German Research Foundation (DFG), under research project No. WE 1642/1-2 and LE 3649/1-2 (FOR 2089). The authors are solely responsible for the content.

Disclosure statement

No potential conflict of interest was reported by the author(s).

Funding

This work was supported by Deutsche Forschungsgemeinschaft: [Grant Number WE 1642/1-2 and LE 3649/1-2 (FOR 2089)] and by Technische Universität Dresden under the Scholarship Program for the Promotion of Early-Career Female Scientists of TU Dresden for Ms. Rochlani.

References

- Airey, G.D., 2003. Rheological properties of styrene butadiene styrene polymer modified road bitumens. *Fuel*, 82 (14), 1709–1719.

- Airey, G.D., Singleton, T.M., and Collop, A.C., 2002. Properties of polymer modified bitumen after rubber-bitumen interaction. *Journal of Materials in Civil Engineering*, 14 (4), 344–354.
- American Association of State Highway and Transportation Officials, 2010. AASHTO T315 - Determining the Rheological Properties of Asphalt Binder Using a Dynamic Shear Rheometer (DSR).
- American Association of State Highway and Transportation Officials, 2013. AASHTO TP 70 - Standard Method of Test for Multiple Stress Creep Recovery (MSCR) Test of Asphalt Binder Using a Dynamic Shear Rheometer (DSR).
- Artamendi, I., et al., 2006. Diffusion kinetics of bitumen into waste tyre rubber. In: *Asphalt Paving Technology: Association of Asphalt Paving Technologists-Proceedings of the Technical Sessions*. 75, 135.
- Blaziejowski, K., Gawdzik, B., and Matynia, T., 2018. Effect of Recycled rubber on the properties of road bitumen. *Journal of Chemistry*, 2018, 1–6.
- Burger, A.F., et al., 2001. Rheology of polymer modified bitumen: comparative study of three binder/filler systems. *20th South African Transport Conference*.
- Cardone, F., et al., 2015. Influence of mineral fillers on the rheological response of polymer-modified bitumens and mastics. *Journal of Traffic and Transportation Engineering (English Edition)*, 2 (6), 373–381.
- Chen, T., et al., 2019. The performance of hot-recycling asphalt binder containing crumb rubber modified asphalt based on physiochemical and rheological measurements. *Construction and Building Materials*, 226, 83–93.
- Cong, P., et al., 2013. Investigation of asphalt binder containing various crumb rubbers and asphalts. *Construction and Building Materials*, 40, 632–641.
- Cong, P., et al., 2015. Rheological and fatigue properties of epoxy asphalt binder. *International Journal of Pavement Research and Technology*, 8 (5), 370–376.
- Deutsches Institut für Normung, 2012. DIN EN 12697-46: 2012-07., *Asphalt - Prüfverfahren für Heißasphalt - Teil 46: Widerstand gegen Kälterisse und Tieftemperaturverhalten bei einachsigen Zugversuchen*. Berlin: Beuth Verlag.
- Di Benedetto, H., Delaporte, B., and Sauzéat, C., 2007. Three-dimensional linear behavior of bituminous materials: experiments and modeling. *International Journal of Geomechanics*, 7 (2), 149–157.
- Ding, X., et al., 2017. Experimental study of stable crumb rubber asphalt and asphalt mixture. *Construction and Building Materials*, 157, 975–981.
- Ding, X., et al., 2019. Laboratory investigation of the recycled asphalt concrete with stable crumb rubber asphalt binder. *Construction and Building Materials*, 203, 552–557.
- Epps, J.A., 1994. Uses of recycled rubber tires in highways, NCHRP synthesis of highway practice 198; Transportation Research Board, National Research Council.
- Fager, G.A., 2001. *Asphalt rubber: a summary of the use of crumb rubber in the hot mixes: Kansas experience 1990–2000*. Kansas: Kansas Department of Transportation.
- FGSV 723, 2016. AL MSCR-Test (DSR) FGSV 723: *Arbeitsanleitung zur Bestimmung des Verformungsverhaltens von Bitumen und bitumenhaltigen Bindemitteln im Dynamischen Scherrheometer (DSR)*. Cologne: (FGSV), Forschungsgesellschaft für Straßen- und Verkehrswesen.
- Frantzis, P., 2004. Crumb rubber-bitumen interactions: diffusion of bitumen into rubber. *Journal of Materials in Civil Engineering*, 16 (4), 387–390.
- Hicks, R., Lundy, J., and Epps, J., 2000. Life cycle costs for asphalt-rubber paving materials. In: *Proceedings of the First International Conference on the World of Asphalt Pavements*.
- ITF/OECD, 2017. ITF Transport Outlook 2017. *Organisation for Economic Cooperation and Development (OECD)*, 1–180. Transport Outlook. <https://doi.org/10.1787/9789282108000-en>.
- Kaloush, K.E., 2014. Asphalt rubber: performance tests and pavement design issues. *Construction and Building Materials*, 67, 258–264.
- Kim, Y.-R. and Little, D.N., 2004. Linear viscoelastic analysis of asphalt mastics. *Journal of Materials in Civil Engineering*, 16 (2), 122–132.
- Kök, B.V., and Çolak, H., 2011. Laboratory comparison of the crumb-rubber and SBS modified bitumen and hot mix asphalt. *Construction and Building Materials*, 25 (8), 3203–3212.
- Kök, B.V., Yilmaz, M., and Geçkil, A., 2013. Evaluation of low-temperature and elastic properties of crumb rubber- and SBS-modified bitumen and mixtures. *Journal of Materials in Civil Engineering*, 25 (2), 257–265.
- Kraft, J., Blasl, A., and Wellner, F., 2018. Performance Related properties of rubber-modified bitumen. *Proceedings of 7th Transport Research Arena TRA 2018*, April 16–19, 2018, Vienna, Austria.
- Lee, S.J., Akisetty, C.K., and Amirkhanian, S.N., 2008. The effect of crumb rubber modifier (CRM) on the performance properties of rubberized binders in HMA pavements. *Construction and Building Materials*, 22 (7), 1368–1376.
- Lesueur, D., et al., 1996. A structure-related model to describe asphalt linear viscoelasticity. *Journal of Rheology*, 40, 813–836.
- Lo Presti, D., 2013. Recycled Tyre rubber modified Bitumens for road asphalt mixtures: A literature review. *Construction and Building Materials*, 49, 863–881.
- Lo Presti, D., and Airey, G., 2013. Tyre rubber-modified bitumens development: the effect of varying processing conditions. *Road Materials and Pavement Design*, 14 (4), 888–900.
- ashaan, Nuha S., 2012. An overview of crumb rubber modified asphalt. *International Journal of the Physical Sciences*, 7 (2), 166–170.
- Mitchell, M.R., et al., 2012. Research of bituminous mortar fatigue test method based on dynamic shear rheometer. *Journal of Testing and Evaluation*, 40 (1), 84–90.
- Nur, N.I., et al., 2013. Modelling the rheological properties of bituminous binders using the 2S2P1D model. *Construction and Building Materials*, 38, 395–406.
- Nur, N.I., Chailleux, E., and Airey, G.D., 2011. A comparative study of the influence of shift factor equations on master curve construction. *International Journal of Pavement Research and Technology*, 4 (6), 324–336.
- Ragab, M., Abdelrahman, M., and Ghavibazoo, A., 2013. Performance enhancement of crumb rubber-modified Asphalts through control of the developed internal network structure. *Transportation Research Record*, 2371, 96–104.
- Riccardi, C., et al., 2016. Back-calculation method for determining the maximum RAP content in Stone matrix asphalt mixtures with good fatigue performance based on asphalt mortar tests. *Construction and Building Materials*, 118, 364–372.
- Rochlani, M., et al., 2019. Influence of filler properties on the rheological, cryogenic, fatigue and rutting performance of mastics. *Construction and Building Materials*, 227, 116974.
- Shen, S., et al., 2007. A dissipated energy approach to fatigue evaluation. *Road Materials and Pavement Design*, 7 (1), 47–69.
- Sousa, J.B., et al., 2013. Reacted and activated rubber. *Transportation Research Record: Journal of the Transportation Research Board*, 2371 (1), 32–40.
- Teymourpour, P., et al., 2016. Effect of parallel plate gap height on repeatability in DSR measurements of crumb-rubber modified binders. *Journal of Materials in Civil Engineering*, 28 (8), 04016047.
- Wang, T., et al., 2017. A review on low temperature performances of rubberized asphalt materials. *Construction and Building Materials*, 145, 483–505.
- Yu, J., et al., 2018. Fatigue resistance characterization of warm asphalt rubber by multiple approaches. *Applied Sciences (Switzerland)*, 8 (9), 1495–1506.
- Zhou, H., Holikatti, S., and Vacura, P., 2014. Caltrans use of scrap tires in asphalt rubber products: a comprehensive review. *Journal of Traffic and Transportation Engineering (English Edition)*, 1 (1), 39–48.

Road Materials and Pavement Design

ISSN: (Print) (Online) Journal homepage: <https://www.tandfonline.com/loi/trmp20>

Feasibility study of waste ceramic powder as a filler alternative for asphalt mastics using the DSR

Mrinali Rochlani , Gustavo Canon Falla , Frohmut Wellner , Dawei Wang , Zepeng Fan & Sabine Leischner

To cite this article: Mrinali Rochlani , Gustavo Canon Falla , Frohmut Wellner , Dawei Wang , Zepeng Fan & Sabine Leischner (2020): Feasibility study of waste ceramic powder as a filler alternative for asphalt mastics using the DSR, Road Materials and Pavement Design, DOI: [10.1080/14680629.2020.1778508](https://doi.org/10.1080/14680629.2020.1778508)

To link to this article: <https://doi.org/10.1080/14680629.2020.1778508>

Published online: 22 Jun 2020.

Submit your article to this journal [↗](#)

Article views: 15

View related articles [↗](#)

View Crossmark data [↗](#)

Full Terms & Conditions of access and use can be found at
<https://www.tandfonline.com/action/journalInformation?journalCode=trmp20>

Feasibility study of waste ceramic powder as a filler alternative for asphalt mastics using the DSR

Mrinali Rochlani^a, Gustavo Canon Falla^a, Frohmut Wellner^a, Dawei Wang^{b,c}, Zepeng Fan^b and Sabine Leischner^a

^aInstitute of Urban and Pavement Engineering, Technische Universität Dresden, Dresden, Germany; ^bInstitute of Highway Engineering, RWTH Aachen University, Aachen, Germany; ^cSchool of Transportation Science and Engineering, Harbin Institute of Technology, Harbin, People's Republic of China

ABSTRACT

Utilisation of recycled construction and demolition waste (CDW) within pavements is a beneficial substitution technique towards sustainability. Following this approach, this research investigates the feasibility of using waste ceramic powder as an alternative filler in mastics. To evaluate the performance of the alternative ceramic filler, its physical and chemical properties were compared to a commonly used mineral filler – limestone. Mastics were made using both fillers and the same reference bitumen. These unaged and Pressure Aging Vessel (PAV) aged materials were tested using the Dynamic Shear Rheometer (DSR) to measure the rheological properties and evaluate them using the 2 Springs-2 Parabolic Elements-1 Damper (2S2P1D) model. Furthermore, fatigue and rutting resistance tests the unaged bitumen and mastics were also done using the same machine. The aging index and bitumen–filler interaction values were also calculated. The results were synthesised in a single performance diagram for visual comparison of various parameters for different materials. Overall, after comparison of various parameters, it was observed that the ceramic powder can be effectively used as a filler alternative in asphalt, having higher stiffness, better aging characteristics, higher bitumen–filler interaction and rutting resistance and similar fatigue performance to that of the limestone mastic.

ARTICLE HISTORY

Received 26 September 2019
Accepted 12 May 2020

KEYWORDS

Sustainable pavement; recycling ceramic; mineral filler; mastic; rheological property; DSR

1. Introduction

In recent years, the damage has increasingly occurred in the case of bituminous surface layers, such as the loss of aggregates and decreased fatigue life of the base layers in various parts of Europe. These damages cannot be attributed either to a severe weather phenomenon or a dramatically increased traffic load. Most likely this damage is due to a lack of performance of the asphalt mastic (bitumen + mineral fine fraction), like poor adhesion to the aggregates or overall lack in strength. This can be due to low quality of one of the two components, bitumen and added filler or the poor interaction between them. Recent research on this topic (Babadopulos et al., 2019; Rieksts et al., 2019; Rochlani et al., 2019) on this topic suggests that the mineralogical composition of the added filler affects the performance of the mastic. It can be assumed that besides low performing bitumen also an inappropriate filler for a specific bitumen can lead to poor performing asphalt mixes. Hence, it is important to investigate the effect of the filler properties on the performance of mastic. This study aims to develop

a suitable and comprehensive test procedure using the DSR device to assess the quality of asphalt mastic with regard to rheology, aging, rutting and fatigue performance.

In addition, the concept of sustainability has gained extensive attention and acceptance in the past decades. In the context of pavement engineering, a sustainable structure is one that minimises its environmental impacts through the reduction of energy consumption, natural resources and associated emissions while simultaneously adhering to the required performance conditions (van de Ven et al., 2011). Leaning towards a less energy-intensive approach, lead to the creation cold-mix asphalt (CMA) and cold-in place recycling (CIR) mixes which not only save energy and money but also mitigate the emissions formed. Other promising recycling alternatives developed include the reclaimed asphalt pavement (RAP), reclaimed asphalt shingles (RAS) and rubber modified pavements (RMP) which provide additional benefits of waste management and disposal along with curtailing the need for natural resources (Giani et al., 2015; Shu & Huang, 2014). Another extension towards sustainability could be the use of ceramic powder, derived from construction and demolition waste (CDW). This powder could replace natural fillers while also improve the overall performance of an asphalt mix.

Ceramic has high mechanical strength, abrasion and chemical resistance; these properties have led to its extensive use and mass production, thereby leading to more waste (Muniandy et al., 2018; Pacheco-Torgal & Jalali, 2010). In Europe alone, it has been estimated that 1.4 million tons of ceramic waste is produced yearly (Ibáñez-Forés et al., 2011). Owing to the desirable properties and to counteract disposal problems, ceramic has been tested as a coarse aggregate substitute in concrete (Senthamarai & Devadas Manoharan, 2005). One study involved comparison of conventional concrete with one made with ceramic aggregates and found that the ceramic concrete was workable and had slightly lower compressive and tensile strengths (Senthamarai & Devadas Manoharan, 2005). Another study concluded that a 20% replacement of cement with ceramic powder increased the durability however decreased the strength of the concrete (Pacheco-Torgal & Jalali, 2011). Additionally, it was found that concrete with ceramic aggregates performed better in terms of capillary water absorption, oxygen permeability and chloride diffusion than the conventional mix (Pacheco-Torgal & Jalali, 2011).

Along with its use in concrete, some studies were done for waste ceramic use in asphalt. Silvestre et al. (2013) investigated the feasibility of recycled ceramic aggregates (RCA) usage as a partial replacement for natural aggregates in hot mix asphalt. It was found that 30% replacement with RCA led to a lighter mix with improved rutting resistance and tensile strength however the amount of bitumen required increased due to ceramic's porous nature. Feng et al. (2013) evaluated the mechanical and thermal performance of asphalt mixture containing crushed ceramic waste aggregates (CWAs) for the surface layer. Based on their experiment and simulation results, the substitution percentage of CWAs was recommended to be less than 40% to balance both mechanical and thermal performance. Another study showed that asphalt mixtures with 20% ceramic waste replacement performed the best in terms of Marshall Stability and resilient modulus (Muniandy et al., 2018). However, the use of coarse aggregates in asphalt was found to have poor interface adhesion problems due to the glaze present in ceramic; while the recycling process of coarser CWAs fails to eliminate this glaze (Silvestre et al., 2013). The recycling of coarse CWA inevitably produces large amounts of ceramic powder which is generally disposed of (Ibáñez-Forés et al., 2011); this powder could be used as a filler in mastics (mix of bitumen and filler). The choice of filler is important as it affects the final asphalt mixes in multiple ways including stiffening the bitumen along with altering the moisture resistance, workability and compaction characteristics of asphalt mixtures (Rochlani et al., 2019).

Taking into consideration the environmental benefits of recycling ceramic waste, the adhesive deficiencies that already exist with CWA, and filler effects on a mix, the main objective of this study was to conduct a feasibility study of using waste ceramic powder as a filler alternative. In order to validate its practicability, ceramic filler was compared with a commonly used mineral filler, limestone. A chemical and physical study was done on the fillers. To study the filler effects on mastics, rheological, rutting and fatigue testing of the mastics made with both fillers was tested using the Dynamic Shear Rheometer (DSR). Rheological behaviour was tested using frequency sweeps, rutting resistance with Single Stress Creep Recovery (SSCR) test and fatigue performance using the stress-controlled test with cylindrical

column samples. Based on the filler and mastic test results, the potential use of waste ceramic powder as an alternative filler in mastic.

2. Materials and methods

2.1. Fillers

There were two fillers used in this research – waste ceramic and limestone. The waste ceramic powder used in this research was produced by crushing a waste sink obtained from an abandoned building. The waste ceramic was crushed using a jaw crusher and then sieved. On the other hand, limestone filler is a commonly used filler and was acquired from a local quarry in Germany. The fillers were used as obtained, without sieving so as to simulate field conditions.

2.2. Bitumen and mastics

Bitumen of penetration grade 50/70 was selected in this research as bitumen to prepare mastics as it is predominately used in Europe. The basic technical properties of the bitumen were shown in Table 1. The base bitumen and two kinds of fillers were blended to prepare mastics respectively and the binder-filler mass ratio is 1:1.6. This is a mid-range value as suggested in the German code (Forschungsgesellschaft für Straßen- und Verkehrswesen [FGSV], 2007). In this research, mastics composed of ceramic and limestone are named ceramic and limestone, respectively.

2.3. Mastic production

Mastics were produced using 35 g of bitumen and the corresponding weight of each filler based on their density in a mass ratio of bitumen: filler of 1:1.6. First, the bitumen was heated to 160°C for 10 min to make it flowable. Then the required amount of bitumen was poured inside a container placed over a scale to weigh the amount of material. After which the required amount of filler was placed on top of the bitumen inside the container. The bitumen–filler mix was stored in the oven at 160°C for 20 min and mixed a total of times- before, during and after the storage inside the oven. The materials were mixed consistently using a metallic tool to ensure a homogenous mix. These materials were aged in the pressure-aging vessel by spreading the sample in trays and placing them at 100° for 25 h to simulate long term aging.

2.4. Filler physical and chemical property test

To comprehensively compare the physical and chemical properties of fillers and identify their effects on mastic, the basic characterisation on fillers were carried out. The adopted tests include specific gravity test, particle size test, BET-specific surface area (SSA) test, scanning electron microscopy (SEM) imaging and X-ray fluorescence spectrometry test.

2.5. Dynamic shear rheometer test

The dynamic shear rheometer (DSR) was used to study the rheology, fatigue and rutting performance of the base bitumen and mastics. For the rheological study, frequency sweep tests were conducted at frequencies from 0.0159 to 47.7 Hz at various temperatures. The adopted test temperatures were

Table 1. Basic technical properties of Bitumen used.

Indexes	Test Value
Penetration@25°C/0.1mm	52
Softening point (R&B)/°C	51.4

–10°C, 0°C, 10°C, 20°C, 30°C, 40°C, 50°C, 60°C and 70°C, respectively. To evaluate this tested results and further approximate data over a wider frequency-temperature range with the use of master curves, the 2 spring – 2 parabolic elements – 1 dashpot (2S2P1D) rheological model was used. This model, in combination with the time-temperature superposition principle, was used to numerically model the linear viscoelastic (LVE) response of bitumen and mastics. This formulation is valid for any rheological simple bituminous material and for relevant pavement conditions in terms of frequency and temperature. The model describes the performance of the material through seven parameters as follows (Di Benedetto et al., 2007):

$$G_{2S2P1D}^*(i\omega\tau) = G_\infty + \frac{G_\infty - G_0}{1 + \alpha(i\omega\tau)^{-k} + (i\omega\tau)^{-h} + (i\omega\beta\tau)^{-1}} \quad (1)$$

where G^* is the predicted dynamic shear modulus, G_∞ is the glassy modulus, G_0 is the static modulus, i is the complex number, ω is the angular frequency, k , h dimensionless parameters, β is a parameter related to Newtonian viscosity, α is a shape factor and τ is the characteristic time, which depends on temperature.

For fatigue testing, stress-controlled tests were conducted on column cylindrical samples for each material. A total of nine samples were tested at three different stress levels, three samples at each stress level for each material. The stress levels were determined using pre-tests so as to attempt to keep the initial strain level of each material within the same range between 0.5 and 2.0. This was done to remain within the LVE region.

In addition, single stress creep recovery (SSCR) tests were conducted for determining the rutting performance of the bituminous materials. SSCR is similar to the multiple stress creep recovery (MSCR) (AL MSCR-Test (DSR) FGSV 723, 2016) tests, with the difference that in the SSCR only one stress level of 3.2 kPa was utilised while MSCR comes with a combination of two to three stresses. In this study, SSCR tests were conducted at 60°C with the 25 mm plate. Stress of 3.2 kPa was applied for 1 s, while allowing the material to recover for the next 9 s. This step was repeated for 10 cycles. The percentage recovery ($R\%$) and the non-recoverable compliance (J_{nr}) were obtained for each cycle and then averaged for every sample. The $R\%$ and J_{nr} values were obtained using the following equations:

$$R\% = \frac{\varepsilon_1 - \varepsilon_{10}}{\varepsilon_1} \cdot 100 \quad (\%) \quad (2)$$

$$J_{nr} = \frac{\varepsilon_{10}}{100 \cdot 3.2} \quad (\text{kPa}^{-1}) \quad (3)$$

where ε_1 is the strain increment after the first cycle (at the end of the phase of creep), ε_{10} is the strain increment after the 10 s cycle (at the end of the relaxation phase).

2.6. Bitumen–filler interaction parameter

The overall properties of mastic depend not only on the properties and proportion of its constituents (bitumen and filler), but also on the physicochemical interaction between them. The physicochemical interaction involves the selective adsorption of polar groups (asphaltene and resins) of bitumen onto the filler surface through electrostatic, dipole–dipole or Van der Waals forces (Clopotel et al., 2012; Fritschy & Papirer, 1978).

Owing to the great importance of physicochemical interaction between bitumen and aggregate/filler, many researches have been conducted to develop a practical method to quantitatively evaluate this effect; these efforts include surface physical and chemical methods, micro/nano characterisation techniques and dynamic mechanical analysis (Antunes et al., 2016; Clopotel et al., 2012; Rochlani et al., 2019). The last method, dynamic mechanical analysis is one of the most promising approaches; it studies the interfacial behaviour indirectly and is based on the rheology property of mastic. Guo et al. (2017) proposed an interface interaction parameter based on the classical LVE theory model and the modified Palierne emulsion model. It was found that the proposed indicator can

represent the interaction between bitumen and filler exactly. Guo et al. (2017) evaluated Luis Ibrarra-A, K. Ziegel-B and C interaction parameters and found that the C parameter was the least sensitive to volume fraction. The C interaction parameter was also employed in this research to evaluate the interaction between bitumen and different fillers. The C parameter characterises the selective adsorption of bitumen on mineral fillers using Equation (4) (Guo et al., 2017)

$$C = \frac{G_c^*/G_m^* - 1}{(1.5 + G_c^*/G_m^*) \cdot \varphi} \quad (4)$$

where G_c^* is the complex modulus of mastic, G_m^* is the complex modulus of bitumen, φ is the volume fraction of filler. A larger C value indicates a larger bitumen–filler interaction.

3. Results and discussions

3.1. Physical and chemical properties of fillers

The SEM images in Figure 1 present filler micromorphology. The images are at a scale of $10 \mu\text{m}$ and show ceramic filler having more rounded and porous particles, while limestone filler has no clearly visible pores. The physical properties of different fillers including density, specific surface area and particle size distribution were shown in Figure 2(a, b), respectively. It could be seen in Figure 2(a) that ceramic filler has a lower density and a higher specific surface area than the limestone filler. This is likely to be attributed to the porous structure of ceramic filler as shown in Figure 1(a). It can be observed from Figure 2(b) that the average particle sizes of ceramic and limestone fillers were approximately 26 and $32 \mu\text{m}$, respectively. The graphs show limestone filler having a more uniform grading, while ceramic illustrates a more gap-graded profile.

The oxide composition profile of the fillers obtained from X-Ray Fluorescence (XRF) tests using the PAN Analytical PW4400 spectrometer are shown in Table 2. The ceramic filler is mainly composed of SiO_2 and Al_2O_3 while CaO dominates the limestone filler. The chemical composition of aggregates can affect the cohesion and adhesion performance between bitumen and aggregates. This chemical difference between the fillers could also affect the interaction behaviour between the filler and bitumen.

Figure 1. SEM images of (a) ceramic and (b) limestone fillers at a scale of $10 \mu\text{m}$.

Figure 2. (a) Density and specific surface area and (b) particle size distribution of ceramic and limestone filler.

Table 2. Oxide composition of the fillers in percent.

Filler Name	Na ₂ O	MgO	Al ₂ O ₃	SiO ₂	K ₂ O	CaO	TiO ₂	Fe ₂ O ₃	others
Ceramic	3.26	2.46	18.25	62.37	3.46	2.75	1.05	6.31	0.14
Limestone	0.18	2.02	1.29	1.94	0.19	92.97	0.12	0.82	0.46

3.2. Frequency sweep tests results

Frequency sweeps were done for the unaged and PAV bitumen and mastics. The rheological data derived from these can be presented using the Black diagram, Cole–Cole plots and Master curves. These diagrams provide a convenient approach to identifying the difference in rheological property of different materials. The DSR tests were conducted in a particular range, however, in order to predict beyond the tested range as well as to acquire smoother curves, the 2S2P1D model was used. Figure 3(a, b) shows the master curves for stiffness and phase angle respectively, while Figure 3(c, d) shows the Cole–Cole plots and Black diagrams, respectively. The reference temperature selected for the master curve construction was 20°C. Table 2 shows the 2S2P1D model parameters.

Figure 3(a) shows the master curves using the measured and model data for unaged and aged materials. As expected, the bitumen has a lower stiffness than the mastics. Limestone has 1.9 times the terminal stiffness of bitumen, while ceramic is 3.4 times larger. With aging, the stiffness of all three materials increased, with Limestone showing the highest visual difference between the unaged and aged curves; numerical analysis of aging is done in the next section titled aging index. Figure 3(b) displays the phase angle master curves, and instantly it can be seen that the three unaged materials overlap; therefore, fillers have no effect on bitumen in unaged condition. While for aged materials, ceramic had the lowest phase angles at reduced frequencies and high temperatures which signify a more elastic behaviour. On the other hand, limestone, showed the highest phase angles at higher temperatures, leaning towards a viscous behaviour. Elastic behaviour is desirable at higher temperatures, so as to recover strains developed due to the lower stiffness.

Figure 3(c) shows the Cole–Cole plots for the unaged and aged materials using test and model data. It can be visually observed that the fit of the model data is relatively good. As expected, ceramic mastic has the largest loss and storage moduli values for aged and unaged, owing to its largest stiffness. Figure 3(d) shows the Black diagrams for the materials constructed using the rheological model. The unaged materials have curves relatively close to one another, however, in aged, the shape of bitumen and limestone remains the same as that of unaged but ceramic mastic shows a significant shape difference, with reaching a full viscous state at a much higher stiffness value than the other two materials.

Table 3 displays the fitted model parameters of bitumen and mastics for the 2S2P1D model where, k and h are constants from the parabolic creep elements with $0 \leq k \leq h \leq 1$, β is a constant from the

Figure 3. (a) Dynamic shear modulus master curve with measured & model data, (b) phase angle Master curve, (c) Cole–Cole plots with measured & model data, (d) black diagrams of unaged and PAV aged bitumen and mastics constructed with 2S2P1D model.

Table 3. 2S2P1D model parameters of bitumen and mastics.

Material	k	h	δ	τ_0 (s)	β	$ G_\infty $ (MPa)
Bitumen	0.314	0.709	5.88	7.6E-5	41.5	665
Bitumen Aged	0.239	0.617	7.03	4.8E-4	926	1040
Ceramic	0.271	0.740	4.91	7.0E-5	52.8	2152
Ceramic Aged	0.289	0.691	17.9	8.5E-2	180.8	2350
Limestone	0.310	0.701	5.11	5.4E-5	69.4	1261
Limestone Aged	0.218	0.451	2.41	2.0E-4	1090	2060

dashpot of the model, α is a shape factor, and τ_0 is the characteristic time, which depends on the shift factors and the temperature.

3.3. Aging index

The aging index parameter A.I. can be used to evaluate the aging performance of any material. It can be found using the formula given below, where P is any property of the material (Equation 4). The aging index A.I._{Stiffness} was determined using the absolute shear modulus values at 20°C and 60°C for 10 Hz and PAV aged bitumen and mastics (Equation (4)).

$$A.I. = \frac{P_{aged}}{P_{unaged}} \quad (5)$$

Figure 4. A.I._{Stiffness} at 20°C and 60°C at 10 Hz.

The lower the aging index, the less susceptible to aging a material is, and therefore fewer changes can be observed with respect to unaged materials. Figure 4 represents the A.I._{Stiffness} for all the three materials. It can be seen that the ceramic mastic is the least affected by aging in terms of stiffness.

3.4. Rutting performance

SSCR tests were undertaken in order to determine the rutting performance of the bitumen and mastics. The results are presented in Figure 5 where it can be initially observed that ceramic had a must lower deformation than limestone at the end of the ten load cycles. Table 4 elaborates the results numerically for all three material with the non-recoverable compliance, the recovery per cent and the cumulative damage at the end of the test. It can be seen that the percent recovery %R value of ceramic mastic is greater than that of limestone mastic while the J_{nr} value of ceramic mastic is smaller than limestone mastic. This indicates that ceramic mastic exhibits better rutting resistance with lower J_{nr} value and higher %R.

3.5. Fatigue performance

Fatigue cracking is primary distress that occurs in flexible pavement. Customarily, fatigue tests have been limited to asphalt mixtures, however, with the development of the DSR, arises the opportunity for testing bituminous mixtures for fatigue behaviour.

Figure 5. SSCR test results.

Table 4. MSCR test results at 60°C and 3.2 kPa.

Material	J_{nr} (kPa ⁻¹)	%R (%)	Cumulative Deformation at end of 10 cycles (-)
Bitumen	0.33	10.0	94.3
Ceramic	0.05	12.18	1.64
Limestone	0.3	2.22	9.70

Figure 6. Fatigue sample with dimensions. **Figure 7.** $|G^*| \cdot N_f$ versus number of load cycles for different initial strain levels.

The fatigue tests in this research were carried out at one single temperature only which was 20°C using cylindrical samples of plain bitumen and both mastics at a frequency of 10 Hz. The sample with dimensions is provided in Figure 6. The results were analysed using the Dissipated Energy Ratio method which states that the energy dissipated by a material can be expressed using the product of the number of load cycles and the complex shear modulus. While the number of cycles at failure is denoted by the value of N corresponding to the highest value of $N^*|G^*|$. It can be graphically seen as the peak of the N versus the $N^*|G^*|$ graph. This can be further clarified by Figure 7, which shows the number of load cycles at failure for three tests at different stress levels with distinct initial strains.

The number of load cycles at failure found were plotted with respect to initial strains and applied stresses, shown in Figure 8(a, b) respectively. An exponential trendline function was plotted along all the points. High accuracy was observed with values of R^2 for the strain fatigue curves being higher than 0.95. Overall, it can be observed that the mastic due to their stiffer nature performed better than the bitumen and was tested at much higher stress levels of 400–600 kPa, compared to the 120–200 kPa of plain bitumen to attain the same initial strains between 0.5 and 2.

Figure 8. Fatigue curves for (a) strain and (b) stress.

Table 5. Fatigue criterions for the materials tested.

Material	Strain level @ fatigue life of 100,000 LC (%)	Stress level @ fatigue life of 100,000 LC (kPa)
Bitumen	0.72	103
Limestone	0.66	380
Ceramic	0.56	372

At present, there exists no standardised criteria/parameter that could be considered to compare the DSR results of bituminous mixtures for fatigue. In order to compare and evaluate the results of the fatigue tests, the fatigue stress and strain level at 100,000 load cycles at failure ($N_{\max}$) were chosen (Table 5). This criterion was selected as at this number of load cycles the initial strain was low enough to be within the LVE range for these materials. Figure 8 represents the results of fatigue tests. Based on the results of the fatigue tests, limestone mastic performed slightly better than the ceramic one in terms of fatigue as for the chosen standard, ceramic had a higher stress level for the same number of load cycles.

Tests are required to have good repeatability and comparability to guarantee a widespread application. All three curves are fitted to the mean values of nine single fatigue tests at three different shear stress levels, respectively. All stress versus number of load cycles curves show an excellent coefficient of determination of $R^2 = 0.99$.

3.6. Bitumen–filler interaction evaluation

Three temperatures 20°C, 40°C and 60°C were selected to compare the C interaction parameter at a frequency of 1.59 Hz, and the calculated results were shown in Figure 9. Conclusions can be drawn that the parameter C values of ceramic are greater than that of limestone at all the three temperatures considered.

This indicates that the physicochemical interaction between bitumen and ceramic filler is stronger than limestone filler, and could be a result of the higher specific surface area provided by the ceramic filler for better adsorption of the bitumen, thereby forming a stronger bond.

3.7. Synthesis of results

Figure 10 illustrates a classification diagram to compare three bituminous materials (bitumen and two mastics) using seven representative performance criteria. The diagram shows seven performance criteria which include the absolute shear modulus $|G^*|$ at 20°C and 60°C to represent the stiffness at

Figure 9. Calculated C parameters at different temperatures.

Figure 10. Classification of the mastics.

normal and high-temperature conditions, the aging index $A.I_{Stiffness}$ to represent the sensitivity to aging related to the absolute shear modulus, fatigue (stress for fatigue failure at 100,000 LC) and rutting performance (J_{nr} value and %R) along with the C-interaction parameter to represent the interaction between the filler and the bitumen. The measured values from the DSR tests along with the calculated values, like aging index and C-interaction parameter are shown here. The higher the area in the performance diagram, the better the material performs overall.

These diagrams give the possibility to undertake a ranking of fillers for a specific bitumen in order to pre-select a specific filler based on the performance criteria required. As of now, due to limited results, only limited materials are presented here, however, the testing program is being continued in at TU Dresden taking into account more bitumen and filler types.

4. Conclusions

The research investigated the feasibility of using waste ceramic powder as fillers in mastic for asphalt pavements. To validate the utility of ceramic as a filler, its properties were compared with that of limestone filler. For this, various tests were conducted, starting from a physical and chemical study on the fillers to conducting various tests using the DSR on mastics that evaluated the rheological, rutting and fatigue characteristics.

Ceramic had a porous structure and a higher percentage of lower diameter particles, therefore having a higher specific surface area. This in turn led to higher adsorption of bitumen onto its surface. Owing to this, a higher interaction between the bitumen–filler was calculated (C-parameter). Ceramic mastic had a much higher stiffness than limestone mastic throughout the temperature-frequency range, however with lower phase angle values, signifying a desired elastic behaviour throughout. This waste material filler also had the lowest susceptibility to long-term aging. Along with improved rheological properties, it was observed to have much better rutting performance with the lowest J_{nr} values than the other materials and comparable fatigue characteristics. Additionally, further experimental tests are needed to quantitatively evaluate the effect of waste ceramic powder on the low-temperature performance and to investigate if ceramic fillers from different sources show the same chemical composition and hence, the same effect on the performance of mastic. Further testing on asphalt mixes with ceramic fillers are recommended to evaluate the effect of ceramic fillers on asphalt performance.

The synthesis of the results in one diagram shows the vast improvement potential that could be achieved with the use of waste ceramic powder as a filler. With the improvement in rheology, rutting and fatigue performance of mastics and most probably also of asphalt mixes, the use of ceramic filler would also reduce the waste that ends up in landfill sites and would be a step towards sustainable pavements.

Acknowledgments

This paper is based on a part of the research project carried out at the request of the German Research Foundation (DFG), under research project number OE 514/1-2, WE 1642/1-2 and LE 3649/1-2 (FOR 2089). In addition, the financial support of the TU Dresden within the Scholarship Program for the Promotion of Early-Career Female Scientists for Ms. Mrinali Rochlani is acknowledged. The authors are solely responsible for the content.

Disclosure statement

No potential conflict of interest was reported by the author(s).

Funding

This paper is based on a part of the research project carried out at the request of the German Research Foundation (DFG), under research project Number OE 514/1-2, WE 1642/1-2 and LE 3649/1-2 (FOR 2089). In addition, the financial support of the TU Dresden within the Scholarship Program for the Promotion of Early-Career Female Scientists for Ms. Mrinali Rochlani is acknowledged.

References

- AL MSCR-Test (DSR) FGSV 723. (2016). *Arbeitsanleitung zur Bestimmung des Verformungsverhaltens von Bitumen und bitumenhaltigen Bindemitteln im Dynamischen Scherrheometer (DSR)*. Forschungsgesellschaft für Straßen- und Verkehrswesen.
- Antunes, V., Freire, A. C., Quaresma, L., & Micaelo, R. (2016). Effect of the chemical composition of fillers in the filler-bitumen interaction. *Construction and Building Materials*, 104, 85–91. <https://doi.org/10.1016/j.conbuildmat.2015.12.042>
- Babadopulos, L., Orozco, G., Mangiafico, S., Sauzéat, C., & Di Benedetto, H. (2019). Influence of loading amplitude on viscoelastic properties of bitumen, mastic and bituminous mixtures. *Road Materials and Pavement Design*, 20(Suppl 2), 780–796. <https://doi.org/10.1080/14680629.2019.1628428>
- Clopotel, C., Velasquez, R., & Bahia, H. (2012). Measuring physico-chemical interaction in mastics using glass transition. *Road Materials and Pavement Design*, 13(Suppl 1), 304–320. <https://doi.org/10.1080/14680629.2012.657095>
- Di Benedetto, H., Delaporte, B., & Sauzéat, C. (2007). Three-dimensional linear behavior of bituminous materials: Experiments and modeling. *International Journal of Geomechanics*, 7, 149–157. <https://doi.org/10.1061/>
- Feng, D., Yi, J., & Wang, D. (2013). Performance and thermal evaluation of incorporating waste ceramic aggregates in wearing layer of asphalt pavement. *Journal of Materials in Civil Engineering*, 25(7). <https://doi.org/10.1061/>
- Forschungsgesellschaft für Straßen- und Verkehrswesen. (2007). *TL Asphalt-StB 07, Technische Lieferbedingungen für Asphaltmischgut für den Bau von Verkehrsflächenbefestigungen*.
- Fritschy, G., & Papirer, E. (1978). Interactions between a bitumen, its components and model fillers. *Fuel*, 57(11), 701–704. [https://doi.org/10.1016/0016-2361\(78\)90025-X](https://doi.org/10.1016/0016-2361(78)90025-X).

- Giani, M. I., Dotelli, G., Brandini, N., & Zampori, L. (2015). Comparative life cycle assessment of asphalt pavements using reclaimed asphalt, warm mix technology and cold in-place recycling. *Resources, Conservation and Recycling*, 104(PA), 224–238. <https://doi.org/10.1016/j.resconrec.2015.08.006>
- Guo, M., Tan, Y., Wang, L., & Wang, Y. (2017). Improvement of evaluation indicator of interfacial interaction between asphalt binder and mineral fillers. *Construction and Building Materials*, 151, 236–245. <https://doi.org/10.1016/j.conbuildmat.2017.05.003>
- Ibáñez-Forés, V., Bovea, M. D., & Simó, A. (2011). Life cycle assessment of ceramic tiles. Environmental and statistical analysis. *International Journal of Life Cycle Assessment*, 16(9). <https://doi.org/10.1007/s11367-011-0322-6>.
- Muniandy, R., Ismail, D. H., & Hassim, S. (2018). Performance of recycled ceramic waste as aggregates in hot mix asphalt (HMA). *Journal of Material Cycles and Waste Management*, 20, 844–849. <https://doi.org/10.1007/s10163-017-0645-x>.
- Pacheco-Torgal, F., & Jalali, S. (2010). Reusing ceramic wastes in concrete. *Construction and Building Materials*, 24(5), 832–838. <https://doi.org/10.1016/j.conbuildmat.2009.10.023>
- Pacheco-Torgal, F., & Jalali, S. (2011). Compressive strength and durability properties of ceramic wastes based concrete. *Materials and Structures*, 44(1), 155–167. <https://doi.org/10.1617/s11527-010-9616-6>.
- Rieksts, K., Pettinari, M., & Haritonovs, V. (2019). The influence of filler type and gradation on the rheological performance of mastics. *Road Materials and Pavement Design*, 20(4), 964–978. <https://doi.org/10.1080/14680629.2018.1428216>
- Rochlani, M., Leischner, S., Falla, G. C., Wang, D., Caro, S., & Wellner, F. (2019). Influence of filler properties on the rheological properties and performance of mastics. *Construction and Building Materials*, 227, <https://doi.org/10.1016/j.conbuildmat.2019.116974>
- Senthamarai, R. M., & Devadas Manoharan, P. (2005). Concrete with ceramic waste aggregate. *Cement and Concrete Composites*, 27(9–10), 910–913. <https://doi.org/10.1016/j.cemconcomp.2005.04.003>
- Shu, X., & Huang, B. (2014). Recycling of waste tire rubber in asphalt and portland cement concrete: An overview. *Construction and Building Materials*, 67(PB), 217–224. <https://doi.org/10.1016/j.conbuildmat.2013.11.027>
- Silvestre, R., Medel, E., García, A., & Navas, J. (2013). Using ceramic wastes from tile industry as a partial substitute of natural aggregates in hot mix asphalt binder courses. *Construction and Building Materials*, 45, 115–122. <https://doi.org/10.1016/j.conbuildmat.2013.03.058>.
- van de Ven, M. F. C., Molenaar, A. A. A., & Poot, M. R. (2011). *Asphalt mixtures with waste materials: possibilities and constraints*. 10th Conference on Asphalt Pavements in Southern Africa. 11-14. September, KwaZulu Natal, South Africa.

Road Materials and Pavement Design

ISSN: (Print) (Online) Journal homepage: <https://www.tandfonline.com/loi/trmp20>

Towards a unified performance based characterisation of bitumen and mastic using the DSR

Mrinali Rochlani, Gustavo Canon Falla, Sabine Leischner & Frohmut Wellner

To cite this article: Mrinali Rochlani, Gustavo Canon Falla, Sabine Leischner & Frohmut Wellner (2021): Towards a unified performance based characterisation of bitumen and mastic using the DSR, Road Materials and Pavement Design, DOI: [10.1080/14680629.2021.1906736](https://doi.org/10.1080/14680629.2021.1906736)

To link to this article: <https://doi.org/10.1080/14680629.2021.1906736>

Published online: 05 Apr 2021.

Submit your article to this journal [↗](#)

View related articles [↗](#)

View Crossmark data [↗](#)

Full Terms & Conditions of access and use can be found at
<https://www.tandfonline.com/action/journalInformation?journalCode=trmp20>

Towards a unified performance based characterisation of bitumen and mastic using the DSR

Mrinali Rochlani , Gustavo Canon Falla, Sabine Leischner and Frohmut Wellner

Institute of Urban Planning and Pavement Engineering, Department of Civil Engineering, TU Dresden, Dresden, Germany

ABSTRACT

A laboratory study was done on three bitumen of penetration grade 50/70 from three sources and three corresponding mastics made using these three base bitumen and one filler – Limestone. The tests were all done using the Dynamic Shear Rheometer (DSR), including frequency sweeps for rheology, single stress creep recovery test (SSCR) for permanent deformation behaviour, Dresden cryogenic test (DDCT) for low temperature performance, and fatigue testing using column specimen. The frequency sweep data was modelled using the 2 Spring-2 Parabolic-1 Dashpot (2S2P1D) rheological model. Selected tests were carried out on unaged and aged bitumen and mastic samples to investigate the sensitivity of the materials to ageing. Performance diagrams were made which could enable in bitumen and mastic selection based on specified desired criteria. It was found that bitumen from different bitumen producers and provenances had different performance behaviours. Furthermore, the addition of the limestone filler also affect the ranking based on specified behaviours.

ARTICLE HISTORY

Received 30 July 2020
Accepted 13 March 2021

KEYWORDS

Bitumen and mastics; low temperature performance; rheology; fatigue performance; permanent deformation; new DSR testing and ranking

Introduction

With the increase in population, there has been an increase in the traffic loading and densities as well. Due to these reasons combined with the climate change, pavements have been degrading at a higher rate and therefore, more thought needs to be given to the design methods. As a result, large sums of money are invested every year in the construction, maintenance and repairs of the roads all over the world (ITF Transport Outlook 2017, 2017). The quality of bitumen is currently defined in Germany using empirical requirements for each of its constituents. These include, in particular, requirements regarding bitumen properties, mechanical tests like needle penetration, ring and ball softening point and Fraass breaking point test (Wegmann et al., 2016). While these tests are easy to comprehend, they fail to accurately present actual stress-strain material behaviour at different temperatures and frequencies. Furthermore, while there are multiple standards for asphalt testing, no standards exist in Europe for mastics or mortars. Additionally, macro-mechanical testing of asphalt under service conditions is not carried out due to the expenses associated with one to one testing facilities such as circular tracking test. In order to increase the durability of asphalt pavements, it is necessary to characterise the properties of both asphalt mixture and asphalt constituents (Wellner et al., 2019). Based on the results of these tests, the choice of materials and components can then be optimised for the respective application in road pavements.

Bitumen quality is seen to vary based on the source of the crude oil and the refining procedure used (Oner et al., 2017). Furthermore, the bitumen acquired may fulfil the existing standards (softening point, ring and ball, etc.) however fail to perform under heavy traffic conditions and changing weather conditions, thereby indicating the insufficiency of the conventional test methods. Furthermore, bitumen ageing causes physical (hardening and rheological changes) and chemical changes (oxidation, evaporation, polarity changes, etc.) that occur within the structure (Alfaqawi et al., 2017; Hunter, 2015). Ageing can be simulated in the lab using a Rolling Thin Film Oven Test (RTFOT) for short-term and Pressure Ageing Vessel (PAV) for long-term ageing. Hence, ageing is a critical aspect required to be considered when designing a road.

Additionally, it is also important to note that not only the binder, but also the bitumen-aggregate interaction affects the ageing process. Based on the aggregate and filler type, the ageing performance of the same binder will differ due to the mineral composition of an aggregate surface, the chemical and physical properties of the aggregate and fillers along with the orientation of the polar molecules in the binder present in the vicinity of the binder-mineral surface interface (Wu & Airey, 2011). They also concluded that the aggregates affect binder ageing via two mechanisms – adsorption and absorption. The adsorption signifies the adhesion of fractions or polar groups of bitumen onto the aggregate surface while absorption deals with exudation of the lighter molecules of bitumen within the pores of aggregates and fillers (Osman, 2004). These surface phenomena break the proportional fractional balance that exists within the binder and lead to a poorly dispersed binder, affecting the bitumen-ageing rate (Wu & Airey, 2011). Moreover, the mineral and chemical components present on the aggregate surface could act as catalysts or retarders for the ageing reaction, hence present various contradictions (Makowska & Pellinen, 2017).

Additionally, in multiple studies, the granulometric, chemical, and mechanical properties of fillers have shown to significantly affect the response and performance of both the mastic and the overall mix (Kim & Little, 2004; Rieksts et al., 2019; Wang et al., 2011). They not only act as a ‘void filler’ but also act as an active material that affects the bitumen-filler interaction (Kim & Little, 2004). The fillers have a physical stiffening effect of the bitumen, and have also shown to affect the moisture resistance, workability and the compaction of the final mix (Antunes et al., 2015; Huang et al., 2007; Rieksts et al., 2019). However, the effect of the physical and chemical composition of fillers on the asphalt mixture is contradictory (Antunes et al., 2016).

It is therefore advantageous to have detailed specifications for bitumen and mastics that take into consideration the intrinsic phenomenological behaviour of the materials to help in bitumen selection based on desired performance criteria. Accurate specifications for bitumen and mastics could include tests using just one single test device – the Dynamic shear Rheometer (DSR). Each batch of bitumen could be tested easily for the rheology, ageing, rutting and fatigue performance within a reasonable time and cost frame at point of origin, i.e. as soon as it is derived from the source (Hunter, 2015; Rochlani, Leischner, et al., 2020). This would help in differentiating between batches of superior and inferior quality and saving maintenance costs in the long run. Furthermore, the compatibility of the bitumen-filler can also be studied beforehand in order to enable in the selection of the optimum filler for the bitumen at hand (Antunes et al., 2016; Rieksts et al., 2019; Rochlani, Canon Falla, et al., 2020).

Objective

The aim of the investigations was twofold: (a) gain an understanding of the performance behaviour of bitumen 50/70 of different bitumen producers or provenances but same penetration grade and (b) to determine the influence of bitumen provenances on the properties of mastic mixtures with the same limestone filler on the other hand. For this reason, a comprehensive laboratory study was carried out, in particular to determine the rheological properties along with permanent deformation, fatigue and low-temperature behaviour by means of tests conducted with only one test device – the Dynamic shear Rheometer (DSR) under consideration of ageing (RTFOT and PAV). Based on the experimental

results, the influence of bitumen source, ageing and filler used, on the change of performance of bitumen and corresponding mastic mixtures could be evaluated. Another contribution of this research is the application of 2 Spring-2 Parabolic-1 Dashpot (2S2P1D) model for rheological data modelling and analysis, for which as of now, limited literature and documentation exist using this model for constructing master curves for unaged and aged mastics but expresses the merit of the model (Biligiri et al., 2010; Yusoff et al., 2014).

Materials

A total of three bitumen of different provenances (B1, B2 and B3) and a limestone filler were selected for the production of the mastic mixtures (M1, M2 and M3). The bitumen-filler ratio by weight of the laboratory mixtures was 1:1.6 (mass fractions). This ratio was adopted in order to mimic the ratio of a stone mastic asphalt, (i.e. SMA 11S), which is the most popular asphalt mixture used in Germany (Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), 2007). According to the TL Asphalt-StB, the recommended bitumen-filler ratio in terms of mass is in the range of 1:1.2–1:1.8 (Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), 2007). This ratio is equivalent to a volumetric concentration range of approximately 0.36 as calculated by the density of the filler. Furthermore, Limestone filler was used in the study as it is frequently used in Germany especially for asphalt mixtures. The limestone filler had a specific surface area of 4.19 m²/g and a density of 2.72 g/cm³. Further it had a pore volume of 0.0168 ml/g and an average pore size of 16.04 nm. Additionally, a filler was defined based on the German guidelines (Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), 2011), the maximum particle size of fillers was 0.063 mm.

To determine the effect of bitumen provenance on the long-term behaviour of the materials, the ageing of the mastic mixtures was carried out in the laboratory. Within the scope of this laboratory study, ageing was carried out in the short term and the long-term methods. For the short term ageing, only Rolling Thin Film Oven Tests (RTFOT) at 163°C for 75 min was used. For long-term ageing, only the Pressure Ageing Vessel (PAV) was used for 25 h at 100°C and 2.07 MPa without any prior RTFOT. The choice of PAV laboratory ageing without RTFOT was based on the investigations on Migliori and Corte (Migliori & Corté, 1998), which showed that the short-term and long-term ageing of bitumen and mastic mixtures can be realistically simulated only using the PAV ageing method, as an extra 5 h is equivalent to the RTFOT ageing procedure. All the materials tested are presented in Table 1 with their source and ageing conditions.

Mastics were made using around 50 g of bitumen and the corresponding mass of Limestone filler using the mass ratio of bitumen: filler of 1:1.6. Firstly, bitumen was heated to 160°C for 10–15 min, so that it was flowable. Then the chosen amount of bitumen was poured into a separate container

Table 1. Details about materials tested.

Material ID	Material type	Bitumen source	Ageing
B1	Bitumen	1	Unaged
B2	Bitumen	2	Unaged
B3	Bitumen	3	Unaged
B1 RTFOT	Bitumen	1	RTFOT aged
B2 RTFOT	Bitumen	2	RTFOT aged
B3 RTFOT	Bitumen	3	RTFOT aged
B1 PAV	Bitumen	1	PAV aged
B2 PAV	Bitumen	2	PAV aged
B3 PAV	Bitumen	3	PAV aged
M1	Mastic	1	Unaged
M2	Mastic	2	Unaged
M3	Mastic	3	Unaged
M1 PAV	Mastic	1	PAV aged
M2 PAV	Mastic	2	PAV aged
M3 PAV	Mastic	3	PAV aged

Figure 1. DSR instrument (left), specimens for the strain frequency sweep, SSCR test (plate-plate) (middle), specimens for the cryogenic test (Prismatic rectangular) (middle), fatigue tests (column cylindrical) (right).

placed over a scale and already tared to 0. After that, the required amount of filler was added into the bitumen and the mixture was stirred with a glass rod. The bitumen and filler mixture was then placed in the oven at 160°C for 10 min and all in all, the mix was mixed a total of three times – before, during and after the storage inside the oven. The materials were mixed consistently using a glass rod to ensure a homogenous mix before sample pouring and preparation.

DSR tests conducted

The informative value of the tests currently used in Germany to determine bitumen characteristics, such as the determination of the ring and ball softening point and needle penetration, is very limited, empirical and outdated when it comes to assessing the performance properties of bitumen (Wellner et al., 2019). The penetration values for the three bitumen were 53.0, 55.2 and 54.7 dmm while the ring and ball softening point was found to be 49, 52 and 46°C for B1, B2 and B3 respectively. While the empirical test results are similar for the three bitumen, their companies and manufacturers were different. While these bitumen had very similar penetration and softening points, more meaningful information about relevant rheological properties of bitumen and specialised rutting and fatigue behaviours cannot be derived. Therefore, new, suitable and more meaningful methods have to be developed which allow a comprehensive performance-oriented characterisation of bitumen and mastic mixtures. The DSR is currently the most promising technology that can be used for the determination of the rheological properties of bitumen and mastic mixtures. For this reason, the DSR was used in this laboratory study. All DSR tests were carried out in the laboratory of the Institute for Urban planning and Road Construction at the Technical University of Dresden with an Anton Paar MCR 502 Modular Compact Rheometer (Figure 1).

Laboratory test results

The laboratory procedure thus explained includes the study of materials over a broad range of testing temperatures and includes the study of the critical distresses and causes of pavement failure at different temperature conditions, from low to intermediate to high, but in terms of bitumen and mastics. Firstly, rheology and its parameters were studied to evaluate the rheological behaviour of the materials to a range of temperatures and frequencies using the amplitude and frequency sweep tests. To evaluate rutting behaviour, creep tests are presented. For intermediate tests, fatigue tests using cylindrical specimens were done, which ensure failure in the middle of specimen and offer the advantage of

Figure 2. (a) Absolute shear modulus versus shear strain including LVE limits for bitumen (b) Curve shifting of the LVE limit.

using the specimens later for mortar studies as well. Then, low temperature behaviours using a simple to understand, cryogenic test were used.

Strain & frequency sweep tests for rheology study

Initially, preliminary strain sweeps were required to determine the linear viscoelastic (LVE) strain limits of the respective samples. The strain or amplitude sweeps were performed for each material at the temperatures of -10 , 0 , 10 , 30 , 50 and 70°C . A curve of the LVE was plotted and the LVE limits (Figure 2(a)) for the other temperatures were interpolated. These limits were further reduced by 20% and then used as inputs in the frequency sweep tests (Figure 2(b)).

The figure below presents an example of the strain sweep results and shifting of the curve.

For each material, two frequency sweep tests were then performed. One, in the temperature range of -10°C to 30°C using a plate with a diameter of 8 mm and sample thickness of 2 mm and the other, in the range of 30°C to 70°C using a plate with a diameter of 25 mm and a 1 mm thick sample. In terms of repeatability, two repetitions were done. Both represented nearly overlapping results, hence one of the results is represented here. Moreover, the testing was done within a range of frequencies from 0.01 Hz to 75 Hz. For each frequency sweep, the tests were done at intervals of 10°C by allowing the material to remain at the temperature for 10 min within the tolerance of 0.1°C . Therefore, a sweep was done at -10 , 0 , 10 , 20 , 30 , 40 , 50 , 60 and 70°C . Using the tested results and rheological modelling, master curves were constructed. Furthermore, the effect of the filler and ageing indexes were also numerically calculated.

2S2P1D model & master curves

The results were modelled using the popularly used 2 Spring-2 Parabolic-1 Dashpot (2S2P1D) model by Di Benedetto (Di Benedetto et al., 2007) and the time-temperature superposition principle (TTSP) to model the linear viscoelastic response of the materials tested. This model uses seven parameters as presented in the equation below (Di Benedetto et al., 2007):

$$G_{2S2P1D}^*(i\omega\tau) = G_\infty + \frac{G_\infty - G_0}{1 + \alpha(i\omega\tau)^{-k} + (i\omega\tau)^{-h} + (i\omega\beta\tau)^{-1}} \quad (1)$$

where $|G^*|$ – the predicted dynamic shear modulus; G_∞ – the glassy modulus; G_0 – the static modulus; i – the complex number; ω – the angular frequency, equal to $2\pi f$ (with f being the loading frequency);

Figure 3. Master curves for (a) the dynamic shear modulus and (b) phase angle at 20°C for the unaged bitumen and mastics.

Figure 4. Master curves for (a) the dynamic shear modulus and (b) phase angle at 20°C for the PAV aged bitumen and mastics.

k and h – dimensionless parameters; β – a parameter related to Newtonian viscosity; α – a shape factor and τ – the characteristic time, which depends on temperature.

The rheological test data was fitted using the TTSP and the 2S2P1D model to form master curves for stiffness and phase angles at a reference temperature of 20°C. The master functions for the investigated materials unaged and PAV aged are shown in Figures 3 and 4 respectively. The master curves show the effect of filler modification on the dynamic shear modulus and the phase angles for different ageing conditions. The 2S2P1D parameters are mentioned in Table 2.

Table 2. 2S2P1D model parameters.

Material	k [-]	h [-]	α [-]	τ_0 [s]	β [-]	G_∞ [MPa]
B1	0.32	0.711	8.50	5.5E-5	35.03	800
B1 RTFOT	0.25	0.61	5.07	1.0E-4	150.15	849
B1 PAV	0.21	0.56	6.02	3.0E-4	650	902
B2	0.30	0.67	4.04	4.8E-5	20	799
B2 RTFOT	0.24	0.63	3.23	4.7E-5	52.80	810
B2 PAV	0.23	0.62	5.01	2.0E-4	350	852
B3	0.31	0.71	5.88	7.6 E-5	41.51	665
B3 RTFOT	0.29	0.70	5.98	7.2E-5	52.84	735
B3 PAV	0.24	0.62	7.02	4.9E-4	92.68	1040
M1	0.21	0.63	3.71	2.6E-4	80.2	1500
M1 PAV	0.19	0.55	4.01	1.3E-4	200.92	1594
M2	0.30	0.67	4.04	4.8E-5	64.1	1632
M2 PAV	0.23	0.62	5.06	2.0E-4	346.2	1698
M3	0.25	0.64	3.73	4.1E-4	80.8	1578
M3 PAV	0.21	0.56	5.98	3.0E-4	451.2	1654

The addition of mineral filler (here: limestone filler) to the bitumen leads, as expected, to a stiffening of the mastic mixtures, recognisable by the upward shift of the functions in Figure 3(a), leading to a stiffer or more solid-like response. If the three bitumen are compared, bitumen B2 has the lowest dynamic shear modulus while B1 and B3 have the higher values of moduli and are almost overlapping. Furthermore, if only the mastics are compared, the three mastics are very close to each other, almost overlapping at higher frequencies, however overall, mastic M1 has a higher modulus than the other two, followed by M2 and M3 respectively, a different ranking pattern to that of the bitumen. Additionally, the master curves for the phase angles are presented in Figure 3(b). Due to filler addition, there is a reduction in the phase angles, and hence the curves shift downwards. As the phase angle approaches closer to 90°, it indicates that the tested materials approaches a full viscous (liquid) state while 0°, indicates a full elastic state. For the unaged bitumen, B2 had the highest phase angle, while once again bitumen B1 and B3 are almost overlapping. Here, the mastics of B2 and B3 are very close to one another, while M1 has the most elastic (lower phase angles) behaviour. Overall, the phase angle values were similar among all bitumen and mastics when compared amongst each other in the same ageing conditions i.e. differences of less than 10% in all cases (for example between unaged B1, B2, and B3 or amongst M1 PAV, M2 PAV and M3 PAV and so on including the both unaged and aged conditions), which means that this property of phase angle is not strongly influenced by the source of the bitumen and the corresponding influence on the mastic for this particular filler.

If the long-term aged conditioned materials are observed in Figure 4, it can be seen that with ageing, there is a stiffening effect due to oxidation, and hence all stiffness master curves shift upwards and the phase angle master curve shift downwards. The master curves of the stiffness were presented in a non-log axis to better visualise the differences between the materials. If the bitumen are considered, B1 PAV and B2 PAV are overlapping, while B3 has a much higher stiffness than the other two. On the other hand, if mastics are observed, there are clear distinctions in terms of ranking, with M3 PAV having the highest stiffness, followed by M1 PAV and M2 PAV respectively. This was a different trend and ranking than that was observed for unaged mastics. The reason for these changes in ranking could be attributed to the bitumen-filler interaction and the filler compatibility with the bitumen chosen. Additionally, if the master curves for the phase angles are observed, all the curves for bitumen and mastics are almost overlapping with each other, with a difference of $\pm 5^\circ$, thereby showing there is not much influence on the phase angles due to ageing. In summary, even the bitumen are of the same penetration grade, their rheology is far from identical, making it imperative to use specialised rheological testing such as this. Furthermore, addition of fillers affects the bitumen and mastic rheology as well, and therefore need to be taken into consideration as well.

Figure 5. (a) Stiffening effect, and (b) phase angle changes due to adding fillers into the respective bitumen at different temperatures and 10 Hz.

Effect of the filler on bitumen

To graphically and numerically present the filler modification effects on the base bitumen, the filler index (FI) was calculated for the dynamic shear modulus and phase angles at different temperatures at a frequency of 10 Hz. This has been presented in Figure 5. The formula is as follows:

$$FI = \frac{M}{B} \quad (2)$$

where, FI – Filler Index; M – any mastic property; B – the corresponding bitumen property.

Figure 5(a) presents the stiffening effect, while Figure 4(b) shows the phase angle effect. From Figure 5(a), it can be observed that Mastic M2 has the highest modification index for the bitumen, especially at temperatures higher than 20°C. The filler has a different effect on the bitumen B2, thereby having a distinctively different behaviour than the other mastics. On the other hand, for aged conditions, mastic M3 has the highest stiffening effect, while for temperatures higher than 40°C, all the mastics curves are relatively closer to one another. Figure 4(b) shows the phase angles changes. The unaged mastics/bitumen values result in a higher reduction in phase angle than the aged material values. However, it can be noted that the mastics have a lower phase angle than the bitumen, which indicates that addition of fillers, moves the mixture towards a more elastic region. Furthermore, in unaged state, for lower temperatures of -15°C, we observe significantly different behaviours between the bitumen and mastics, where mastic M2 has the least change in its degree of elasticity with filler addition (as very close to 1.0), while B1 and B3, showed a much more reduction in the phase angles (25–30% reduction). If PAV aged materials are considered, while mastic M2 PAV and M3 PAV are very close (ranging from 0.9 to 1.0 as temperature increase from -15°C to 60°C), mastic M1 PAV showed a rather different behaviour, especially at 40°C, where this mastic has a much lower phase angle than its counterpart B1 PAV. This further enforces the need for extensive testing of not only bitumen but also mastics and to try to understand what role fillers actually play in the mix and how they chemically and physically alter behaviours. The bitumen B1 and B3 tend to be less affected by filler addition, as compared to B2.

Figure 6. Ageing index A.I. (a) Dynamic shear modulus (b) Phase angle at 20°C and 10 Hz and at 60°C and 10 Hz.

Ageing index for stiffness & phase angles

An assessment of the change in relevant properties of bituminous materials due to ageing can be made using an ageing index AI:

$$AI = \frac{P_{aged}}{P_{unaged}} \quad (3)$$

where P_{unaged} – any physical property (e.g. viscosity, Softening Point of the binder or dynamic shear modulus, among others) measured on the unaged bituminous materials, and P_{aged} – the same physical property measured under aged conditions.

The dynamic shear modulus and phase angles at 20°C and 60°C at a frequency of 10 Hz were used to determine the ageing index AI stiffness. The bar charts have been presented in Figure 6.

It can be seen that for the bitumen and mastic mixtures examined, the ageing index at 20°C is at a relatively constant level independent of the material (range of 2.1–2.9 for bitumen of penetration 50/70, and 1.0–1.7 for mastics) (Rochlani, Leischner, et al., 2020). At a temperature of 60°C, however, significant differences in ageing behaviour can be observed. The bitumen B2 showed the highest sensitivity to ageing, with an index as high as 18.5 (i.e. higher the A.I., more aged is the material), while the other bitumen B1 and B3 had A.I. of 11.2 and 11.8 respectively, relatively close to one another and far lower than B2. While for mastics, the highest A.I., or most ageing behaviour was observed for mastic M3 with a value of 10.35. At the same temperature, the mastic M2 had a significantly lower index of 4.28, thereby being the least susceptible to ageing. The stiffening of bitumen and mastic mixtures due to ageing is much more pronounced at higher temperatures than at lower temperatures. The difference in behaviours could be related to the chemical and mineralogical properties of the filler and the chemical reactions that might take place bitumen and filler. On the other hand, if the A.I. for phase angles (Figure 6(b)) are observed, we notice not much difference in the indexes between the bitumen and the mastics at both the temperatures. All indexes are lower than 1.0, as expected, as the materials move to more elastic behaviour than viscous, leading to a reduction in the phase angle values at aged condition. However, the source does not seem to influence the phase angle behaviour in terms of ageing.

Figure 7. Creep curves at 3.2 kPa and 60°C, bitumen – unaged and RTFOT aged and mastics – unaged.

Single stress creep recovery test (SSCR) for permanent deformation performance

In order to characterise the resistance to plastic deformation of the mastic mixtures, SSCR tests were carried out at a temperature of 60°C with the 25 mm plate. A stress of 3.2 kPa was applied for one second, and consecutive nine seconds were allowed for recovery. A total of 10 load cycles took place. This procedure is as mentioned in the German standard by FGSV (FGSV 723, 2016). Three repetitions were done for each material and good reproducibility was visible, as expected. The deformation R and compliance J_{nr} were calculated for each load cycle using the following equations:

$$R = \frac{\varepsilon_1 - \varepsilon_{10}}{\varepsilon_1} * 100[\%] \quad (4)$$

where R – Recovery Percent.

$$J_{nr} = \frac{\varepsilon_{10}}{100 * 3.2} [\text{kPa}^{-1}] \quad (5)$$

where J_{nr} – Non-Recoverable Compliance, ε_1 – Strain increment after the first cycle (at the end of the creep phase), and ε_{10} – Strain increment after the 10 second cycle (at the end of the relaxation phase).

The results of the SSCR tests for the different bitumen (unaged and RTFOT aged) mastic mixtures (unaged) can be compared using the parameters J_{nr} , R and the resulting terminus damage are shown in Table 3 and graphically with the help of the recorded deformation curves in Figure 7. The lower the J_{nr} value is, the lower is the expected depth, and hence the material has better rutting resistance.

Bitumen B1 shows the largest permanent deformation, followed by bitumen B3 and lastly, bitumen B2 in unaged conditions. On the other hand, if mastics are observed, the rutting is reduced as compared to the bitumen, as the deformation curves move downwards, while the J_{nr} values reduce. However, the mastic M3 has the lowest permanent deformation and J_{nr} value, while mastic M1 and M3 are close to one another with J_{nr} values of 1.40 and 1.46 respectively. However, after ageing, bitumen B2 RTFOT had the highest J_{nr} value and the lowest resistance to plastic deformation. While bitumen B1 RTFOT and B3 RTFOT had identical values of J_{nr} and identical deformation curves. The permanent

Table 3. Results of the SSCR tests.

Material	J_{nr} [kPa ⁻¹]	R [%]	Cumulative strain after 10 cycles [%]
B1	3.22	1.45	102.99
B2	1.68	6.31	55.10
B3	2.44	3.76	68.56
M1	1.40	13.21	44.89
M2	1.46	14.92	46.79
M3	0.91	16.37	27.85
B1 RTFOT	0.45	22.13	14.48
B2 RTFOT	0.66	15.23	21.25
B3 RTFOT	0.45	21.47	14.25

deformation ranking for bitumen and mastics is different, thereby further enforcing that the same filler affects different bitumen in different ways.

Dresden cryogenic (DDC) test for low temperature performance

Cooling in winter temperatures with simultaneous obstruction of contraction (no joints, frictional base) lead to cryogenic tensile stresses in the asphalt. These stresses can be compensated to a certain extent by the tensile strength of the asphalt, which also increases with decreasing temperature. The tensile strength, however, only increases on cooling up to a limit value depending on the bitumen used. After falling below this limit, the increasing embrittlement leads to a decrease in tensile strength. As a result, on further cooling, the temperature (breaking temperature) is reached at which the cryogenic tensile stresses exceed the tensile strength of the asphalt and thus lead to cracking (cold crack) in the asphalt. In conjunction with the tensile stresses induced by traffic loads, the crack can also occur at temperatures that are more positive (i.e. higher) on temperature scale, than the breaking temperature (Gehrke, 2017).

Colder cracks in asphalt can start at the interface between mastic mixture and rock or within the bitumen film (Vonk et al., 2003). Therefore, the cryogenic behaviour of the binder and the adhesion to the rock have a decisive influence on crack formation in asphalt (Sebaaly et al., 2003).

Cooling tests were carried out to test the effect of bitumen provenance and the addition of limestone filler to bitumen with regard to low temperature behaviour. The tests were carried out on prismatic samples (Figure 1). Two repetitions of this test were done. This test is based on the principle of the asphalt test of Thermal Stress Restrained Specimen Test (TSRST) which typically uses a prismatic asphalt specimen for determining the low temperature susceptibility to cracking of asphalt and is explained in greater detail in the EN 12697-46:2012 (European Committee for Standardization (CEN), 2012). The dimensions of the prismatic samples for the DSR test were 50 mm × 4 mm × 9 mm (length × width × height). The specimens were easily attached to the upper spindle and the lower base plate of the DSR and cooled down from 20°C to –15 °C with a cooling rate of –10 K per hour. The specimens were then left for 2 h at –15°C and kept at a constant specimen length (recovery phase). Throughout the entire experiment, the axial stress resulting from the temperature change was measured while keeping the sample length constant. The lower the exerted stress is, the better the material is expected to perform under the low temperatures.

Figure 8(a) show the cryogenic curves for bitumen and mastics till –15°C while Figure 8(b) shows the numerical values of the forces exerted at –15°C. It can be seen that the bitumen exert different levels of cryogenic stress, with B1 having the lowest stress, while B3 has almost two times of that of B1, and B2 is three times that of B1. While if mastics are considered, M1, like B1, exerts the lowest force, followed by M3 (18% increase from M1) and lastly by M2 (230% higher than M1). The reason for the differences in the low temperature performances could be attributed to the stiffness of the materials. The higher the stiffness of a material is, the higher is the expected cryogenic stress regardless of bitumen and mastics as shown by Rochlani et al. (2019).

Figure 8. (a) Cryogenic curves for bitumen and mastics (b) Bar chart of the resulting cryogenic stress at -15°C .

Table 4. Cryogenic stress parameters.

Material	Cryogenic stress at -15°C [N/mm ²]	Cryogenic stress after 2 h relaxation at -15°C [N/mm ²]	Cryogenic recovery percent [%]
B1	0.04	0.0151	62.25%
B2	0.13	0.0391	68.15%
B3	0.09	0.0244	72.89%
M1	0.16	0.0735	54.13%
M2	0.37	0.1988	49.19%
M3	0.19	0.0858	54.84%

Furthermore, the recovery of stress took place by leaving the material at -15°C . These values, along with the recovery percent are presented in Table 4. It can be observed that the bitumen show a recovery of the range 62–73% while the mastics have a lower recovery in the range of 49–55%. Bitumen B3 and mastic M3 had the highest recovery values.

Fatigue performance tests

The bitumen used in asphalt and thus, also the mastic have a decisive influence on the fatigue behaviour of asphalt mixtures. As the adhesion between bitumen and rock $|G^*|$ also contributes significantly to the formation of fatigue cracks, it is to be assumed that the fatigue behaviour of mastic mixture is more indicative of the fatigue behaviour of asphalt than of bitumen. In addition, fatigue tests on mastic mixes are much easier and quicker to carry out than on asphalt, as the costly production of asphalt mixes and test specimens is no longer necessary.

To prepare these samples, it was important that they were fluid and homogenous. For this, the PAV aged bitumen was heated at a temperature of 160°C for at least 30 min, to ensure good fluidity. Then the samples were poured and they were allowed to cool at room temperature for around 5–7 min, after which they were placed in the refrigerator (at a temperature of $1-3^{\circ}\text{C}$) for at least 20 min to ensure shape formation. The samples were then removed from the moulds and stored in the fridge again. The same steps were repeated for mastics, only that before the mastics were poured, they were stirred for around 10–20 s with a glass rod to ensure a homogenous mix and that the filler particles do not settle.

A more common fatigue test to determine damage in bitumen is the Linear Amplitude Sweep (LAS) test (as described in AASHTO TP 101-14). In short, it uses the results of frequency and strain sweep tests in combination with a viscoelastic continuum damage mechanics (VECD) model to determine

Figure 9. 3D-view (left) fatigue sample with dimensions (middle) specimens with moulds (right).

the fatigue life of bitumen (Hintz et al., 2011; van Rooijen et al., 2017). Although there is not a specific temperature to conduct this test, it is of utmost important to choose the correct test temperature as it greatly influences the damage mechanism (Safaei & Castorena, 2020). One recognised challenge of the LAS test is the use of the 8 mm plate, which has commonly reported to lead to failure occurring due to de-bonding of specimen from the plates (Hintz & Bahia, 2013; Hospodka et al., 2018; Safaei & Castorena, 2020). As a result, sometimes the binder-steel plate bond is tested rather than fatigue damage processes in the bitumen. Furthermore, the gap between the plates have to be increased for modified bitumen and mastics. In addition, while the LAS test is relatively fast and can be easily performed, the use of the VECD model to determine the characteristic damage behaviour of the material seems insufficient to properly capture changes in the material properties of the bitumen, such as ageing, when estimating its fatigue life (Pravat & Zhou, 2018; van Rooijen et al., 2017; Zhou et al., 2017). Due to these limitations with using the plate-plate combination for fatigue testing in the DSR, fatigue testing using a modified sample geometry, such as a ‘cylindrical column’, is innovative alternative for bitumen, mastic and mortar testing characterisation. These specimens were initially produced by TU Delft and have since then gained popularity (Woldekidan, 2011). A common problem recognised with these specimens is that they fail at the edges of the steel rings, however, with slight modifications to the shape at the edges and with experience, efficient mould and sample preparation, the probability of breakage was reduced to 10%. The negative specimens used to make the mould were 3D to ensure high accuracy, and using that silicone mould were made. The breaks occurring at the edges were disregarded and only the results of the specimens that failed in the middle were considered.

Hence, fatigue tests can be carried out with the DSR using cylindrical test specimens (Figure 1). The 3D shape, dimensions of the specimen and mould for sample preparation are presented in Figure 9. Based on the test conditions according to TP Asphalt, part 24 (Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), 2007), the tests were carried out at 20°C and a frequency of 10 Hz. For these stress controlled tests, the stress levels were chosen in a way to maintain an initial strain level at 100 load cycles within the range of 0.5–2.2%. Nine individual tests were carried out and evaluated to determine the fatigue function for each material. Based on the approach to the dissipated energy ratio according to Rowe & Bouldin (2000), the number of load cycles up to the macro-crack criterion was determined.

Figure 10 shows the fatigue functions of the tested bitumen and mastics- unaged and PAV aged. From the figure, it can be observed that there is a clear distinction between the unaged and PAV aged curves; the curves shift to the right as since the stiffness increases, a higher stress is required to obtain the same initial strain values. Furthermore, the curve slopes for all the materials are relatively similar and this could be an indicator of the fatigue performance of the mastics is inherited from the bitumen, and hence the bitumen quality is very critical in determining the fatigue behaviour of an asphalt mixture. Also, all materials showed high R^2 values of at least 0.94, indicating a high accuracy of the test.

If the ranking are considered, for unaged bitumen and mastics, the curves are very close to one another. For the mastics, the curves are almost overlapping. However, if the PAV aged materials are seen, the distinctions between the materials are more apparent. The fatigue function of PAV aged

Figure 10. Fatigue functions of the investigated bitumen and mastics at unaged & PAV aged conditions.

Table 5. Fatigue test parameter.

Material ID	Stress level required for failure at LC number of 100,000 [-]
B1 PAV	325
B2 PAV	350
B3 PAV	290
M1 PAV	430
M2 PAV	385
M3 PAV	353

bitumen B2 shows the highest number of load cycles up to macro-crack failure at the same stress, followed by PAV aged bitumen B1 and PAV aged bitumen B3. However, this ranking sequence was not observed with the mastic mixtures. Here, the PAV aged mastic mixture M1 PAV made with the bitumen B1 required the higher numbers of load cycles to reach the macro-crack followed by M2 PAV mastic mixture and followed by the M3 PAV mixture for the same stresses. The differences could be as a result of the binder-filler bond formed that is affected due to ageing perhaps due to the chemical changes taking place.

For the synthesis of results diagram presented in the next section, the stress level required to cause failure at a load cycle value of 100,000 was used as a characteristic parameter for estimating the fatigue behaviour of the materials (Table 5). The parameter chosen is an alternative to the parameter defined by Hospodka et al. (2017) who chose a characteristic fatigue parameter in the form of the number of load cycles until the macro-crack criterion is reached at a stress level of 450 kPa was adapted in order to define a uniform criterion for the assessment of bitumen and mastic with regard to fatigue behaviour.

Synthesis of DSR test results for bitumen & mastics

For a summarising and comparative evaluation of the behaviour of bitumen and mastic mixtures, a radar diagram is presented for the ranking of bitumen and mastic properties. The choice of these parameters comes from the idea to have an overall bitumen behaviour presentation that considers all temperature behaviours (low, intermediate and high) and rheology at critical temperatures such as 20°C and 60°C, but also that fatigue at intermediate temperatures and rutting behaviours at higher temperatures and lastly the low temperature behaviours. While these parameters were chosen based

Figure 11. Performance diagrams for the evaluation of the behaviour of the examined bitumen 50/70.

on the authors' point of view of what parameters are relevant, the diagram can be naturally adapted based on properties that other researchers would like to present.

The following six performance-oriented material criteria were considered:

- Shear stiffness (dynamic shear modulus) at 20°C and 60°C and 10 Hz – unaged
- Fatigue behaviour (stress at a fatigue load change rate of 100,000) – PAV aged
- Low temperature behaviour (cryogenic stress reached at -15°C) – unaged
- Ageing sensitivity with regard to stiffening (ageing index at 60°C, 10 Hz)
- Resistance to plastic deformation (J_{nr} value)

Figures 11 and 12 show the performance diagrams in which the bitumen and mastic mixtures can be directly compared, evaluated and ranked according to their performance-relevant properties. The axis are presented in such a way that, the larger the area inside, the better is the overall performance. Thereby, for Figure 11, bitumen B1 is best overall performing material; while from Figure 12, mastic M1 and M2 are the better performing mastics. Furthermore, on the basis of this ranking, it is possible, to select an optimum bitumen for a particular filler or vice versa. For example, if permanent deformation is more critical for the road one is constructing, then if the J_{nr} axis is observed, instantly, B1 or B3 could be chosen. However, if fatigue is more critical, the axis for fatigue can be seen and instantly, choice of B2 would be optimum. If low temperature behaviour is crucial, then bitumen B1 would be a better alternative.

Furthermore, if the bitumen and mastic diagrams are compared, bitumen B1 has the best overall performance followed by B3, and lastly by B2. However, for mastics, M1 and M2 are now almost equally good with similar enclosed areas, however M3 has a significant reduction in performance behaviours. Therefore, adding the same filler to different bitumen, results in different ranking, where M2 has an improved performance to B2, while M3 has a worse performance than B3.

In future, it would be beneficial and is planned to add further chemical analysis and viscosity results for bitumen and mastics and to further compare the results with that for mortar and the resulting asphalt mixture.

Figure 12. Performance diagrams for evaluation of the behaviour of the mastic mixtures investigated.

Conclusion

This paper presented the results of a laboratory study in which significant performance-related properties of three different bitumen 50/70 and corresponding mastic mixtures were measured with the same filler (limestone filler) using only one laboratory instrument – the DSR. These properties were determined using results of the frequency sweep tests, fatigue tests, Dresden cryogenic test (DDCT) for low temperature performance and SSCR tests to evaluate the resistance to plastic deformation. Selected tests were carried out on unaged and aged bitumen and mastic samples to investigate the sensitivity of the materials to ageing. Based on the test results it is possible, for example, to specifically select a bitumen for a filler based on the properties of the mastic mixture relevant for the dimensioning of asphalt pavements.

The following conclusions can be drawn:

- Based on the results of the DSR tests it is possible to characterise bitumen and mastic with regard to all relevant properties (e.g. fatigue and low-temperature behaviour, plastic deformation behaviour, ageing). In this context a new method for the evaluation of bitumen and mastic properties was developed. Each batch of bitumen could be tested easily for the properties of rheology, ageing, rutting and fatigue performance within a reasonable time and cost frame at point of origin, i.e. as soon as it is acquired from the source.
- The provenance of the bitumen had a clear influence on their behaviour, resulting in different performance behaviours. The addition of limestone filler to bitumen of different provenances also affected the performance behaviour of mastic to varying degrees.
- The choice of suitable fillers for bitumen should be made in accordance with the bitumen to be used, also taking into account the provenance.

It is therefore advantageous to have detailed specifications and standards that consider more than just the penetration and softening point for bitumen and mastics, as these existing empirical procedures fail to help in optimum bitumen selection based on desired performance criteria. This would help in differentiating between batches of superior and inferior quality at point of origin and saving maintenance costs at the end of the day.

In this study, the DSR tests could only be carried out on selected unmodified bitumen 50/70 and mastic mixtures in order to develop a general procedure for the evaluation of the performance relevant properties of bitumen and mastic mixtures. Further investigations using other bitumen and fillers are required and already planned in order to extend the knowledge gained here and to confirm the universality of these results.

Acknowledgements

We hereby acknowledge the financial support provided by TU Dresden as part of the Scholarship Program for the Promotion of Early-Career Female Scientists for Ms. Rochlani. This paper is also partly based on the research project carried out at the request of the German Research Foundation (DFG), under research project No. WE 1642/11 and LE 3649/2 (FOR2089). The authors are solely responsible for the content.

Disclosure statement

No potential conflict of interest was reported by the author(s).

Funding

This work was supported by German Research Foundation [grant numbers WE 1642/11, LE 3649/2] and TU Dresden.

ORCID

Mrinali Rochlani <http://orcid.org/0000-0003-4323-2242>

References

- Alfaqawi, R., Airey, G. D., & Grenfell, J. R. A. (2017, June 28–30). *Effects of mineral fillers and bitumen on ageing of asphalt mastics properties*. Proceedings of the 10th International Conference on the Bearing Capacity of Roads, Railways and Airfields, BCRRA June 2017. <https://doi.org/10.1201/9781315100333-41>
- Antunes, V., Freire, A. C., Quaresma, L., & Micaelo, R. (2015). Influence of the geometrical and physical properties of filler in the filler-bitumen interaction. *Construction and Building Materials*, 76(2), 322–329. <https://doi.org/10.1016/j.conbuildmat.2014.12.008>
- Antunes, V., Freire, A. C., Quaresma, L., & Micaelo, R. (2016). Effect of the chemical composition of fillers in the filler-bitumen interaction. *Construction and Building Materials*, 104, 85–91. <https://doi.org/10.1016/j.conbuildmat.2015.12.042>
- Biligiri, K. P., Kaloush, K., & Uzan, J. (2010). Evaluation of asphalt mixtures' viscoelastic properties using phase angle relationships. *International Journal of Pavement Engineering*, 11(2), 143–152. <https://doi.org/10.1080/10298430903033354>
- Di Benedetto, H., Delaporte, B., & Sauzéat, C. (2007). Three-dimensional linear behavior of bituminous materials: Experiments and modeling. *International Journal of Geomechanics*, 7(2). [https://doi.org/10.1061/\(asce\)1532-3641\(2007\)7:2\(149\)](https://doi.org/10.1061/(asce)1532-3641(2007)7:2(149))
- European Committee for Standardization (CEN). (2012). *EN 12697-46:2012 – Test methods for hot mix asphalt – Part 46: Low temperature cracking and properties by uniaxial tension tests*.
- FGSV 723. (2016). *AL MSCR-Test (DSR) FGSV 723: Arbeitsanleitung zur Bestimmung des Verformungsverhaltens von Bitumen und bitumenhaltigen Bindemitteln im Dynamischen Scherrheometer (DSR)*. (FGSV), Forschungsgesellschaft für Straßen- und Verkehrswesen.
- Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV). (2007). *TL Asphalt-StB 07, Technische Lieferbedingungen für Asphaltmischgut für den Bau von Verkehrsflächenbefestigungen*.
- Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV). (2011). *TL Gestein StB – Technische Lieferbedingungen für Gesteinskörnungen im Straßenbau*.
- Gehrke, M. (2017). *Komplexe charakterisierung bitumenhaltiger Bindemittel anhand temperatur-, frequenz- und belastungsabhängiger kennwerte*. Ruhr Universität Bochum.
- Hintz, C., & Bahia, H. (2013). Understanding mechanisms leading to asphalt binder fatigue in the dynamic shear rheometer. *Road Materials and Pavement Design*, 14(2), 231–251. <https://doi.org/10.1080/14680629.2013.818818>
- Hintz, C., Velasquez, R., Johnson, C., & Bahia, H. (2011). Modification and validation of linear amplitude sweep test for binder fatigue specification. *Transportation Research Record*, 2207(1), 99–106. <https://doi.org/10.3141/2207-13>
- Hospodka, M., Hofko, B., & Blab, R. (2017). Zur Ermüdungsbeständigkeit von Asphaltmastix Prüfmethodik und Einflussparameter. *Fifth Dresdener Asphalttage*.
- Hospodka, M., Hofko, B., & Blab, R. (2018). Introducing a new specimen shape to assess the fatigue performance of asphalt mastic by dynamic shear rheometer testing. *Materials and Structures/Materiaux et Constructions*, 51(46). <https://doi.org/10.1617/s11527-018-1171-6>

- Huang, B., Shu, X., & Chen, X. (2007). Effects of mineral fillers on hot-mix asphalt laboratory-measured properties. *International Journal of Pavement Engineering*, 8(1), 1–9. <https://doi.org/10.1080/10298430600819170>
- Hunter, R. N. (2015). The shell Bitumen handbook. In *The shell Bitumen handbook*. <https://doi.org/10.1680/tsbh.58378>
- ITF Transport Outlook 2017. (2017). OECD. <https://doi.org/10.1787/9789282108000-en>
- Kim, Y.-R., & Little, D. N. (2004). Linear viscoelastic analysis of asphalt mastics. *Journal of Materials in Civil Engineering*, 16(2). [https://doi.org/10.1061/\(asce\)0899-1561\(2004\)16:2\(122\)](https://doi.org/10.1061/(asce)0899-1561(2004)16:2(122))
- Makowska, M., & Pellinen, T. (2017). The “false positive” on the antiaging properties of asphalt fines investigated by RTFO laboratory aging of mastics. <https://doi.org/10.1201/9781315643274-53>
- Migliori, F., & Corté, J.-F. (1998). Comparative study of RTFOT and PAV aging simulation laboratory tests. *Transportation Research Record: Journal of the Transportation Research Board*, 1638(1), 56–63. <https://doi.org/10.3141/1638-07>
- Oner, J., Sengoz, B., Maidanova, N., Topal, A., & Malkoc, G. (2017). Evaluation of rheological effects of waxes on bitumen from different sources. <https://doi.org/10.14311/ee.2016.086>
- Osman, S. A. (2004). *The role of bitumen and bitumen/filler mortar in bituminous mixture fatigue*. University of Nottingham.
- Pravat, K., & Zhou, F. (2018). *Evaluation of asphalt binder performance with laboratory and field test sections*. Report No. FHWA/TX-18/0-6674-01-R1. <https://static.tti.tamu.edu/tti.tamu.edu/documents/0-6674-01-R1.pdf>
- Rieksts, K., Pettinari, M., & Haritonovs, V. (2019). The influence of filler type and gradation on the rheological performance of mastics. *Road Materials and Pavement Design*, 20(4), 964–978. <https://doi.org/10.1080/14680629.2018.1428216>
- Rochlani, M., Canon Falla, G., Wellner, F., Wang, D., Fan, Z., & Leischner, S. (2020). Feasibility study of waste ceramic powder as a filler alternative for asphalt mastics using the DSR. *Road Materials and Pavement Design*, 1–13. <https://doi.org/10.1080/14680629.2020.1778508>
- Rochlani, M., Leischner, S., Falla, G. C., Goudar, P., & Wellner, F. (2020). Influence of source and ageing on the rheological properties and fatigue and rutting resistance of Bitumen using a DSR. In *Lecture Notes in Civil Engineering*. https://doi.org/10.1007/978-3-030-48679-2_46
- Rochlani, M., Leischner, S., Falla, G. C., Wang, D., Caro, S., & Wellner, F. (2019). Influence of filler properties on the rheological, cryogenic, fatigue and rutting performance of mastics. *Construction and Building Materials*, 227, 116974. <https://doi.org/10.1016/j.conbuildmat.2019.116974>
- Rowe, G. M., & Bouldin, M. G. (2000). Improved techniques to evaluate the fatigue resistance of asphaltic mixtures. *2nd Eurasphalt & Eurobitume Congress Barcelona*.
- Safaei, F., & Castorena, C. (2020). Improved interpretation of asphalt binder parallel plate dynamic shear rheometer fatigue tests. *International Journal of Pavement Engineering*, 21(1), 74–87. <https://doi.org/10.1080/10298436.2018.1438611>
- Sebaaly, P. E., Hitti, E., & Weitzel, D. (2003). Effectiveness of lime in hot-mix asphalt pavements. *Transportation Research Record*, 1832(1), 34–41. <https://doi.org/10.3141/1832-05>
- van Rooijen, R., Planque, L., Wegmann, M., Di Benedetto, H., Mangiafico, S., Sauzeat, C., Olard, F., & Pouget, S. (2017). *Bitumen fatigue performance evaluation - with or without RAP – A real challenge*. <https://doi.org/10.14311/ee.2016.055>
- Vonk, W., Korenstra, J., & van Hek, J. (2003). Rissbildung in asphaltbelägen: Leicht zu verstehen. *Zeitschrift Bitumen*, 4(3), 166–169.
- Wang, H., Al-Qadi, I. L., Faheem, A. F., Bahia, H. U., Yang, S.-H., & Reinke, G. H. (2011). Effect of mineral filler characteristics on asphalt mastic and mixture rutting potential. *Transportation Research Record: Journal of the Transportation Research Board*, 2208(1), 33–39. <https://doi.org/10.3141/2208-05>
- Wegmann, M., Vienenkötter, L., & Pfitzmann, M. (2016, June 30). Bitumen quality recording – A German approach. *Proceedings of 6th Eurasphalt & Eurobitume Congress*. <https://doi.org/10.14311/EE.2016.339>
- Wellner, F., Falla, G. C., & Leischner, S. (2019). Betrachtungen zur Einschätzung der Bitumenqualitäten unter besonderer Berücksichtigung der Alterung. *Proceedings of the Asphaltstraßentagung*.
- Woldekidan, M. F. (2011). Response Modelling of Bitumen, Bituminous Mastic and Mortar. In *Dissertation for The Degree of Doctor, Technische Universiteit Delft*.
- Wu, J., & Airey, G. (2011). *The influence of mineral fillers on mastic aging properties*. [https://doi.org/10.1061/41186\(421\)342](https://doi.org/10.1061/41186(421)342)
- Yusoff, N. I., Mounier, D., & Airey, G. (2014). The 2S2P1D: An excellent linear viscoelastic model. *Unimas E-Journal of Civil Engineering*, 1(2). <https://doi.org/10.33736/jcest.76.2010>
- Zhou, F., Karki, P., & Im, S. (2017). Development of a simple fatigue cracking test for asphalt binders. *Transportation Research Record*, 2632(1), 79–87. <https://doi.org/10.3141/2632-09>

Influence of Source and Ageing on the Rheological Properties and Fatigue and Rutting Resistance of Bitumen Using a DSR

Mrinali Rochlani, Sabine Leischner, Gustavo Canon Falla, Puneet Goudar, and Frohmut Wellner

Abstract Bitumen of penetration grade 50/70 is the most commonly used binder in asphalt pavements of Europe. This research attempts to differentiate between three bitumen of penetration grade 50/70 that have been acquired from three sources. The rheological properties, fatigue and rutting resistance were analyzed and compared using the results of Dynamic Shear Rheometer (DSR) tests. The rheological test data acquired were modelled and further approximated using the 2S2P1D model. Additionally, to understand the changes in performance due to ageing, all the DSR tests were repeated for Rolling Thin Film Oven Test (RTFOT) aged and Pressure Aging Vessel (PAV) aged bitumen. Finally, the tests results were summarized in a performance diagram to aid in overall ranking of the bitumen taking into consideration relevant parameters.

Keywords DSR tests · Rheology · Rutting · Fatigue · Ageing · 2S2P1D

1 Introduction

Owing to the large expenditure invested in construction and maintenance of road networks, it has become crucial to take into account the quality considerations for bitumen. The quality of bitumen varies not only with the refining procedure used, but also with the crude oil source (Singh and Jain 1997; Oner et al. 2017). Bitumen acquired from a particular refinery might meet the existing specifications, however, fail to provide the required performance during the in-service period under heavy traffic and changing environmental conditions, indicating the insufficiency of the specifications that exist. As of now, conventional testing methods in Germany include needle penetration, softening point ring and ball, flash point, Frass breaking point methods, etc; belonging to the empirical (catalog) approach, these fail to define the rheological properties of the bitumen (Wegmann and Vienenkötter 2017). In Germany the Dynamic Shear Rheometer (DSR) temperature sweep between 30 to

M. Rochlani (✉) · S. Leischner · G. C. Falla · P. Goudar · F. Wellner
Institute of Urban and Pavement Engineering, Technische Universität Dresden,
Georg-Schumann-Straße 7, 01187, Dresden, Germany
e-mail: mrinali_raj कुमार.rochlani@tu-dresden.de

© Springer Nature Switzerland AG 2020

C. Raab (ed.), *Proceedings of the 9th International Conference on Maintenance and Rehabilitation of Pavements—Mairepav9*, Lecture Notes in Civil Engineering 76,
https://doi.org/10.1007/978-3-030-48679-2_46

481

90 °C has been added recently as an additional procedure to gather information, however, it is not a requirement (Wegmann and Vienenkötter 2017).

Other than source related problems, bitumen deterioration due to ageing is of grave concern. Due to bitumen ageing, physical changes and chemical reactions occur within the structures. Physical changes include bitumen hardening and changes in rheology that could result in an increased cracking susceptibility of the pavement (Petersen 2009; Alfaqawi et al. 2018). While, chemical changes include alterations in the reactions with oxygen, evaporation of lighter molecules, polarity changes, crystallisation of paraffinic saturates to name a few affect adsorption, aggregate bonding abilities along with viscosity (Hunter 2015). Hence, it is of utmost importance to study changes in performance due to ageing; this is generally simulated in the lab using short-term (significant rate of ageing due to construction processes—mixing, transport, placement) and long-term ageing (ageing at a much lower rate during the service life of around 8–10 years) procedures to understand the changes in performance of bitumen, thereby affecting those of the final asphalt mix (Jemere 2010). Short-term and long-term ageing can be done using various methods, with Rolling Thin Film Oven (RTFOT) being a popular choice for short-term and Pressure Ageing Vessel (PAV) for long-term.

It would be therefore beneficial to have more detailed specifications that would include more than just the empirical testing procedures so as to enable in the selection of a bitumen on the basis of specific desired performance (Singh and Jain 1997; Oner et al. 2017). Accurate specifications for bitumen could include tests using just one machine - the DSR; each batch of bitumen could be tested for the rheology, ageing, rutting and fatigue performance within a reasonable time and cost frame at point of origin, i.e. as soon as it is derived from the source (Rochlani et al. 2019). This would help in differentiating between batches of superior and inferior quality and saving maintenance costs in the long run (Rochlani et al. 2019).

The desired goal of this research was to verify the performance of three bitumen of the same grade but from three different sources using the results of DSR tests. Performance includes rheology, rutting and fatigue are to be tested to be able to compare and rank. Additionally, a method to appropriately rank all the materials using different parameters from the tests would be required.

2 Materials and Methodology

2.1 Materials

A total of three materials and three ageing conditions were tested, which include three unaged bitumen, three RTFOT aged and three PAV bitumen. The table below summarizes the bitumen used along with their short descriptions. (Table 1)

Table 1 List of bitumen samples tested—each source with 3 aging conditions

Bitumen source	Sample name (unaged, RTFOT aged, PAV aged)
1	B1, B1 RTFOT, B1 PAV
2	B2, B2 RTFOT, B2 PAV
3	B3, B3 RTFOT, B3 PAV

2.2 Ageing Procedure

In order to investigate the short-term and long-term performance of the bitumen, the bitumen were artificially aged in the laboratory. For short-term ageing, the materials were put in a RTFOT at 163 °C for 75 min (EN 12607-1 2007). On the other hand, to replicate the short term + long term ageing effect, generally RTFOT procedure mentioned followed by PAV at 100 °C for 20 h and 3.2 MPa is used. However, in this research, short + long term ageing was simulated using only PAV at 100 °C for 25 h at 2.07 MPa based on the findings of by Migliori and Corte (2007), who concluded that 5 h of PAV is equivalent to the standard RTOFT aging procedure, thereby simplifying the ageing procedure.

2.3 Dynamic Shear Rheometer Tests

An Anton Paar Modular Compact Rheometer 502 was used to evaluate the rheology, fatigue and rutting performance of the bitumen. To study rheology, strain and frequency sweeps were conducted in the temperature range of –10 to 70 °C. The strain sweeps were firstly undertaken to evaluate the linear viscoelastic limit (LVE) strain, which are required to conduct the frequency sweeps. The strains were further reduced by 20% to ensure the LVE region was maintained for the frequency sweeps. A frequency range of 0.0159 to 47.7 Hz was used and the results acquired were superposed and approximated further using the time-temperature superposition principle and the 2 spring – 2 parabolic elements – 1 dashpot (2S2P1D) rheological model respectively (Benedetto et al. 2007). This model is valid for any rheologically simple bituminous material for relevant pavement conditions in terms of frequency and temperature and describes the performance of the material through seven parameters (Benedetto et al. 2007).

Secondly, for evaluating the rutting performance, single stress creep recovery (SSCR) tests were undertaken. This test follows the same procedure as Multiple Stress Creep Recovery (MSCR) test (*AL MSCR-Test (DSR) FGSV 723* 2016) where a sample is subjected to stress for one second, followed by nine seconds without stress, allowing the material to relax at a temperature of 60 °C with the 25 mm plate. This step is repeated consecutively 10 times. The only difference between MSCR and SSCR is that, in MSCR tests multiple stresses are used, while in SSCR tests

only a single stress of 3.2 kPa was utilized. From each cycle two variables—non-recoverable compliance, J_{nr} , and percentage recovery, $\%Rec$ were calculated and averaged.

Lastly, fatigue performance was determined using stress-controlled tests on column cylindrical samples. The tests were carried out at a temperature of 20⁰ C and frequency 10 Hz for both unaged and aged samples. For each material, a total of nine samples were tested at three different stress levels. The stress levels were determined using pre-tests so as to attempt to keep the initial strain level of each material within the range of 0.5 to 2.2% This was done to remain the LVE region.

3 Results and Discussion

3.1 Frequency Sweep Tests

The frequency sweep test data modeled using the time-temperature superposition and 2S2P1D model is presented in terms of the master curves for dynamic shear modulus and phase angle in Fig. 1a and b respectively. Black diagrams and Cole-Cole plots in Fig. 2a and b are presented for only one material (aged and unaged) to observe and appreciate the fit of the model, while 2c and d represent model data for all materials.

From Fig. 1a and b, the dynamic shear modulus and phase angle of different bitumen and the changes that occur can be visually observed. It can be seen from the

Fig. 1 Master curves **a** Dynamic Shear Modulus **b** Phase Angle using 2S2P1D model at 20 °C

Fig. 2 a Black Diagram b Cole-Cole Diagrams for B1 with measured test data (denoted M) and 2S2P1D data for Bitumen B1

shear modulus master curve, for unaged materials, B1 and B3 tend to overlap, while B2 has slightly lower moduli values than the others at lower reduced frequencies (i.e. higher temperatures). If RTFOT aged bitumen are observed, B1 has the greatest visual shift, with an increase of approximately 600% at higher temperatures to 3% at lower temperatures (higher reduced frequencies), followed by B2 with an increase of 134% at higher temperatures and as low as 2% at lower temperatures while B3 shows almost overlapping results for unaged and RTFOT aged, with a numerical increase ranging from 20 to 6.5% as temperatures reduce. For PAV aged materials, all three bitumen, show a relatively higher increase, as expected. B1 shows a numerical increase in the range 4700 to 5% from higher to lower temperatures, while B2 showed 1940% at higher temperatures to 3% at lower temperatures and lastly the highest increase was observed with B3, with 7952% at higher temperatures and 46% at lower temperatures. On the other hand, if the master curves for phase angle are observed, with RTFOT ageing the phase angles reduce slightly, however a much higher decrease is visible for PAV aged materials. As ageing increases, the stiffness increases along with phase angle reductions, that signify a more elastic, rather than a viscous behavior. Overall, B1 and B3 with overlapping curves for PAV ageing would be expected to perform similar and better than B2 due to their increased stiffness and reduced phase angles, signifying an increased elasticity at higher temperatures. This would enable these materials to resist the stresses, and recover faster. A better numerical evaluation of the effect of ageing could be observed using the aging index. From this test, the parameters of shear modulus at 20 and 60 °C at 10 Hz in RTFOT aged conditions were chosen in order to compare and rank the materials in the later section. These conditions were chosen as these are typical conditions for permanent deformation and fatigue criterion of asphalt.

Figure 2 shows the Black diagrams and the Cole-Cole plots using the 2S2P1D model data. The Black diagrams show the relation between the phase angle and the dynamic shear modulus values. The Cole-Cole plots are used to show the model fit between the actual test data and the model data. Below in Fig. 2a and b, show the fit of the model with the test data and for clarity purposes only one material, B1, unaged and aged, is presented below. As observed, the fit is sufficiently visually accurate,

therefore the model can be appropriately used for better comparison purposes to obtain smoother curves and approximate further data.

3.2 Ageing Index

The ageing of bitumen can be expressed numerically in terms of the ageing index. This index is calculated in terms of ratios corresponding to several physical grading tests and is given by the following equation:

$$A.I. = \frac{P_{aged}}{P_{unaged}} \quad (1)$$

Where, P_{unaged} is any physical parameter (e.g. viscosity, softening point, stiffness, etc.) of the unaged bituminous materials and P_{aged} is the same physical parameter as for an aged bituminous materials.

The A.I. was calculated for dynamic shear moduli (bars) and phase angles (lines) at 20 and 60 °C at a frequency of 10 Hz. The lower the ageing index value, lower is the effect of the ageing sensitivity on the material.

From Fig. 3a which represents the A.I. stiffness (with full colors bars for RTFOT and dashed for PAV). At 20 °C for RTFOT, all materials have almost the same A.I. in the range 1.35 to 1.5, while at 60 °C, B1 has the relatively higher A.I. with 2.8, than the 2.0 and 2.1 of B2 and B3. For PAV aged materials, at 20 °C, B3 shows a much higher susceptibility to ageing with the highest value of 3.9 while B1 and B2 are both around 2.5. At 60 °C however, B3 has the lowest A.I., closely followed by B1, with 60% higher than B3. From the results, it can be concluded that B3 was most affected by RTFOT ageing, with B2 being the most susceptible and B3, the least susceptible to PAV ageing at higher temperatures. For phase angles (Fig. 3b), the changes at each temperature and ageing suggest very similar values, with almost horizontal lines for

Fig. 3 Ageing index for **a** shear modulus **b** phase angle at 20 °C and 60 °C and 10 Hz

every temperature and ageing type. The phase angle A.I. for PAV are almost double of the RTFOT values for the same temperatures. The main parameters for this section include the A.I. (Stiffness) at 60 °C for RTFOT materials, as rutting occurs at earlier in the lifetime and at higher temperatures, while the A.I. (Stiffness) at 20 °C for PAV materials w.r.t fatigue. For comparison and ranking, the A.I at 60 °C for RTFOT and 20 °C for PAV were taken into consideration for purpose of rutting and fatigue evaluations.

3.3 Single-Stress Creep Recovery (SSCR) Test

SSCR tests were undertaken to evaluate the rutting performance. These tests were carried out on unaged and RTFOT aged materials. PAV aged materials were not tested, as rutting is crucial in the initial lifespan of a pavement and fatigue is more critical in the long term performance. The test results are presented in Fig. 4—showing the deformation with time for ten cycles of loading and unloading.

From Fig. 4, it can be seen that the unaged materials have much higher deformation than the RTFOT aged materials, with values for unaged being in the order of 105 to 45 to being less than 25 for aged. There are vast differences between the unaged materials, with B1 having a significantly higher cumulative deformation. After ageing however, B1 and B3 overlap, with B2 being slightly higher. In order to evaluate numerically the rutting performance, the J_{nr} and %R values were calculated and are presented in Fig. 5. Unaged B2 has the highest recovery and lowest J_{nr} value, as desired, however, for RTFOT, it has the lowest recovery and the highest J_{nr} value. With RTFOT ageing being more important, it can be concluded that bitumen B1 and B3 performs similar. It can be concluded that all three bitumen show significant different rutting performance - in particular bitumen B2 has much better rutting performance than the other two bitumen. The standard J_{nr} values were considered in RTFOT aged condition of comparison purposes presented in the later section as this is the standard value used under the German standards (*AL MSCR-Test (DSR) FGSV 723 2016*).

Fig. 4 Stress dependant fatigue functions for the bitumen tested

Fig. 5 %R and J_{nr} values for unaged and RTFOT aged bitumen

3.4 Fatigue Tests

The fatigue test results were analysed using the Dissipated Energy ratio approach. This states that the dissipated energy of bitumen at failure can be calculated as a function of the product of number of load cycles and the corresponding dynamic shear modulus. For these stress controlled tests, the stress levels were chosen in a way to maintain an initial strain level at 100 load cycles within the range of 0.5 to 2.2%. Due to this, the unaged were tested at a stress range of 100 to 200 kPa, RTFOT at 150 to 250 kPa and PAV at 250 to 400 kPa. This is expected due to an increase in stiffness with an increase of ageing, therefore, causing a lower strain for the same stress. The fatigue curves for applied stress versus the number of load cycles at failure are presented in Fig. 6.

From the figure, it can be observed that there is a clear distinction between the unaged, RTFOT and PAV aged bitumen curves, with the slope for all the materials other than B1 being relatively similar. The slope could be an indicator of the type of failure, the testing temperature and frequency. Also, all materials showed high R^2 values of at least 0.96, indicating a high accuracy of the test.

Fig. 6 Stress fatigue curves for the bitumen tested

If the ranking is considered, B2 seems to have the highest fatigue curves, with RTFOT being significantly higher than the other two materials. B3 fails the fastest for unaged and aged materials. For comparison purposes, PAV aged material can be considered the main parameter of this test for ranking purposes in terms of the stress required by the bitumen to achieve 100,000 load cycles. All the values are given in Table 2 below.

3.5 Synthesis of the Results

Using the characteristic parameters of the tests undertaken, the diagram presented in Fig. 7 was constructed using to pictorially rank the admixtures based on their stiffness, ageing indexes, fatigue, and rutting behavior. This diagram, which was introduced by the authors in a previous work (Rochlani et al. 2019), gives the possibility of ranking bitumen on the basis of any of the specific parameters studied in this research and obtained via the DSR instrument. From the figure, the ageing indexes and J_{nr} value axis is reversed, as performance relates inversely to these parameters. This gives the

Table 2 Fatigue performance parameter

Unaged	Stress [kPa] @ 1E+5 LC	RTFOT Aged	Stress [kPa] @ 1E+5 LC	PAV Aged	Stress [kPa] @ 1E+5 LC
B1	123	B1 RTFOT	222	B1 PAV	325
B2	118	B2 RTFOT	320	B2 PAV	350
B3	105	B3 RTFOT	212	B3 PAV	290

Fig. 7 Performance diagram

opportunity to rank the materials in a way that a larger enclosed area suggests the best performance overall for the parameters used. Another way to use the diagram is be able to identify the particular material based on properties required. According to the figure, B1 is the best and overall performing bitumen, while for specific properties—B1 is best where rutting is critical, while B2 where fatigue performance is of value. This material is also less sensitive to aging compared to the other two bitumen at both aging conditions. It is to be noted that these diagrams can be modified to incorporate other relevant parameters when necessary; and if properties are considered to be more relevant than others for a specific project, it could be possible to add scalar weights to each axle, which will impact the computation of the overall area.

4 Conclusion

Bitumen of grade 50/70 from three different sources were tested in terms of rheology, rutting and fatigue resistance using the DSR. Moreover, testing was also done for RTFOT and PAV aged materials. It was found that despite the similar penetration grade, there were vast differences found in terms of specific performances. While bitumen B1 and B3 provided almost similar rutting resistance, B2 had the best fatigue related performance, while B3 had the lowest performance in this criteria. While for ageing, the materials had similar phase angle ageing indexes, but their stiffness varied significantly with ageing. It can therefore be concluded that more detailed specifications are necessary for bitumen evaluation, and could be made possible using just the DSR, which provide a cost and time efficient option. Finally, to bring together all test results, important parameters were chosen from each test and synthesized in one performance diagram, to give a visual differentiation between the materials, and provide the opportunity to choose a bitumen required for specific purposes. These diagrams would be further developed at TU Dresden to provide a range of values in each specific performance for bitumen using the results of DSR tests. The test results clearly prelude that the current procedure to group materials using the results of needle penetration and ring and ball tests is not an appropriate procedure to characterize bitumen according to their actual performance.

Acknowledgements We hereby acknowledge the financial support provided by TU Dresden as part of the Scholarship Program for the Promotion of Early-Career Female Scientists for Ms. Rochlani. This paper is also partly based on the research project carried out at the request of the German Research Foundation (DFG), under research project No. WE 1642/1-2 and LE 3649/1-2 (FOR2089). The authors are solely responsible for the content.

References

- AL MSCR-Test (DSR) FGSV 723 (2016): Arbeitsanleitung zur Bestimmung des Verformungsverhaltens von Bitumen und bitumenhaltigen Bindemitteln im Dynamischen Scherrheometer (DSR) (FGSV), Forschungsgesellschaft für Straßen- und Verkehrswesen
- Alfaqawi R, Airey GD, Grenfell JRA (2018) Effects of mineral fillers and bitumen on ageing of asphalt mastics properties. In: bearing capacity of roads, railways and airfields - proceedings of the 10th international conference on the bearing capacity of roads, railways and airfields, BCRRRA 2017
- Benedetto HD, Delaporte B, Sauzéat C (2007) Three-dimensional linear behavior of bituminous materials: experiments and modeling. *Int J Geomech* 7(2)
- EN 12607-1 (2007) EN 12607-1:2007, Bitumen and bituminous binders - Determination of the resistance to hardening under the influence of heat and air - Part 1: RTFOT method. <http://www.aenor.es/>
- Hunter RN (2015) The shell bitumen handbook, 6th edn. ICE Publishing, London
- Jemere Y (2010) Development of a laboratory ageing method for bitumen in porous Asphalt. Delft University of Technology
- Migliori F, Corté J-F (2007) Comparative study of RTFOT and PAV aging simulation laboratory tests. *Transp Res Rec J Transp Res Board*
- Oner J, Sengoz B, Maidanova N, Topal A, Malkoc G (2017) Evaluation of rheological effects of waxes on bitumen from different sources
- Petersen JC (2009) A review of the fundamentals of asphalt oxidation: chemical, physicochemical, physical property, and durability relationships. *Transportation Research E-Circular (E-C140)*, The National Academies: Washington D.C
- Rochlani M, Leischner S, Falla GC, Wang D, Caro S, Wellner F (2019) Influence of filler properties on the rheological properties and performance of mastics. Submitted to *Construction and Building Materials*
- Singh H, Jain PK (1997) Bitumen quality and manufacturing processes—past and present technological status. *Indian J Chem Technol*
- Wegmann M, Vienenkötter L (2017) Bitumen quality recording—a German approach

PART III

SUBMITTED MANUSCRIPTS

PAPERS SUBMITTED TO JOURNALS AND DECLARATION OF WORK DONE

a) Understanding the influence of temperature and frequency on the fatigue resistance of bitumen Mrinali Rochlani, Gustavo Canon Falla, Silvia Caro, Sabine Leischner & Frohmut Wellner. Submitted to Construction and Building Materials in October 2020 (In second round of reviews). Journal Impact Factor – 4.419.

- The preparation of the materials, DSR testing, data analysis, diagrams along with writing of the manuscripts and further revisions were done by Ms. Rochlani independently under the supervision of Prof. Wellner, Dr. Leischner, and Dr. Silvia Caro. The other authors provided valuable comments and feedback based on which the manuscript was edited by Ms. Rochlani.

Mrinali
Rochlani

Digital unterschrieben von
Mrinali Rochlani
Datum: 2020.10.07
10:21:02 +02'00'

Mrinali Rochlani

Sabine
Leischner

Digital unterschrieben von
Sabine Leischner
Datum: 2020.10.07
14:31:55 +02'00'

Sabine Leischner

Silvia Caro

Digitally signed by Silvia
Caro
Date: 2020.10.09
09:31:50 -05'00'

Silvia Caro

Gustavo
Canon Falla

Digitally signed by Gustavo Canon Falla
DN: cn=Gustavo Canon Falla, o=TUD,
ou=ISS,
email=gustavo_adolfo.canon_falla@tu-
dresden.de, c=US
Date: 2020.10.07 16:57:53 +01'00'

Gustavo Canon Falla

Frohmut
Wellner

Digital unterschrieben von
Frohmut Wellner
Datum: 2020.10.08
13:49:15 +02'00'

Frohmut Wellner

Understanding the influence of temperature and frequency on the fatigue resistance of bitumen

Mrinali Rochlani^{1,*}, Silvia Caro², Gustavo Canon Falla¹, Sabine Leischner¹, Frohmut Wellner¹,

¹ *Institute of Urban and Pavement Engineering, Technische Universität Dresden, Germany*

² *Department of Civil and Environmental Engineering, Universidad de los Andes, Bogotá, Colombia*

**Corresponding Author, Email: mrinali_rajkumar.rochlani@tu-dresden.de
Address: Georg-Schumann-Straße 7, 01187 Dresden*

Abstract: Fatigue performance of bitumen holds great importance in the design and fatigue behaviour of asphalt pavements. However, there are still gaps in knowledge about the influence of different experimental conditions, such as temperature and frequency, on the degradation of bitumen under cyclic loading. In this research, stress-controlled fatigue tests at three temperatures (-10°C, 15°C and 20°C) and at two loading frequencies (10Hz and 20Hz) were performed on cylindrical specimens of a 50/70 grade bitumen, using a recently developed fatigue testing protocol in a Dynamic Shear Rheometer (DSR). These state-of-the-art specimens could be efficiently utilised at multiple temperatures and frequencies with low dispersion among results. The number of cycles to fatigue failure was defined using an energy ratio method derived from dissipated energy (DE) approach. Experimental data were analysed following several approaches, including traditional fatigue curves, as well as DE vs. load cycles (N), DE vs. applied stress and load cycles at failure (N_f), and N_f vs. initial DE curves. Moreover, ‘failure lines’ using the DE and N_f values were also constructed and assessed. A testing temperature of 15°C was determined to be a ‘frequency-free transition temperature’ for this bitumen, as the ‘failure lines’ at 10Hz and 20Hz overlapped. Additionally, a temperature and frequency independent fatigue data representation was obtained when analysing the initial DE and N_f data. Lastly, images of the cracked specimens were also used to qualitatively analyse the degradation and fatigue failure caused at the different testing conditions.

Keywords: bitumen, fatigue cracking, dissipated energy, stress-controlled fatigue testing, DSR fatigue testing.

1. Introduction

Fatigue cracking in asphalt pavements results from the repeated action of cyclic loading that leads to damage accumulation and progressive cracking of the asphalt layers [1]. In the past decade, multiple experimental fatigue test procedures on asphalt mixtures have been developed and implemented [2]. Additionally, fatigue failure analysis and characterisation of asphalt mixtures has been performed using different approaches that include phenomenological techniques, continuum damage mechanics, fracture mechanics and energy dissipation methods [1,3,4]. However, most fatigue test procedures and analysis approaches are time and effort consuming. Owing to this challenge and to the considerable amount of research showing a strong relationship between fatigue properties of the asphalt mixture and that of its corresponding bitumen and mastics, the experimental fatigue characterisation of asphalt binders and mastics is a state-of-art field of study with significant research potential [5–9].

The resistance to fatigue cracking of bitumen has been commonly investigated using the Dynamic Shear Rheometer (DSR) with the parallel plate-plate 8mm and 25 mm configurations. In this test, the specimen is subjected to repeated torsional strain- or stress-controlled loading conditions, and the resulting response is correlated to fatigue damage and fatigue life (i.e. number of cycles to failure).

There are multiple methods and failure criteria to evaluate the fatigue resistance of bitumen using DSR results. One of the easiest approaches involves the characterisation of the fatigue life or number of cycles to failure, N_f , of the bitumen through an experimentally-obtained phenomenological power law function [1]:

$$N_f = a \cdot X^b \quad (1)$$

where X can be any loading amplitude (stress, strain or energy dissipated); and a and b are experimentally fitted constants, which are material-property related.

Most traditional fatigue tests are typically performed under strain-controlled conditions, using a common definition of failure as the load cycle where the magnitude of the shear modulus has been reduced by half of its initial modulus. Owing to its simplicity and ease, this method is widely used; however, it has been questioned since the failure criterion is arbitrary and could be inaccurate for modified bitumen [1,10,11].

Another parameter that was introduced as part of the Superpave system to estimate fatigue resistance of bitumen based on DSR testing data, was the $|G^*| \cdot \sin \delta$ parameter, where $|G^*|$ is the dynamic complex modulus and δ is the phase angle of the binder tested at 10 rad/s. The testing

is undertaken at intermediate temperatures and the results are used to determine the low performance grade of the bitumen. Even though simple and easy to determine, this parameter has shown to relate poorly to actual fatigue cracking [12,13]. This is mainly due to the fact that linear viscoelastic properties of a material are damage-free parameters and, consequently, do not properly capture the complexity of fatigue degradation.

Another commonly used approach to characterise fatigue degradation is the quantification and assessment of the dissipated energy (DE) of the material. This concept characterises fatigue behaviour by correlating the energy dissipated per loading cycle to the resulting fatigue damage [14,15]. The DE is quantified as the area under of stress-strain hysteresis loops [1,15]. In a stress-controlled test, as the fatigue test progresses, the loops increase in size, increasing also the DE values. This loss of energy or DE includes mechanical work, viscous losses, heat and mechanical damage [1]. For fatigue tests under stress-controlled conditions, the DE is usually calculated using the following formula:

$$W_i = \pi \sigma_i \varepsilon_i \sin \delta_i \quad (2)$$

where W_i is the DE, σ_i is the stress level; ε_i the strain level; and δ_i the phase angle in the i th cycle.

Another simpler form of the DE approach was developed by Hopman et al. (1989) [16] in the form of the energy ratio, using the following equation:

$$W_N = \frac{N w_0}{w_N} \quad (3)$$

where W_n is the energy ratio; N is the loading cycle; w_0 is the DE in first load cycle; and w_N is the DE at the n th load cycle. Notice that this equation normalizes the progression of DE by the viscous DE of the initial load cycles, in order to only account for the DE associated to damage processes.

Also, in 2000, Rowe and Bouldin [4] used the change in the dynamic shear modulus or stiffness of the material, which is related to the changes in DE, to quantify fatigue damage using the ‘reduced energy ratio’ (R_n) for both strain- (R_n^ε) and stress- (R_n^σ) controlled stress conditions, as follows:

$$R_n^\varepsilon = \frac{N}{|G_N^*|} \quad (4)$$

$$R_n^\sigma = N \cdot |G_N^*| \quad (5)$$

where $|G_N^*|$ is the dynamic shear modulus at the corresponding N loading cycle.

Using the appropriate equation depending on the type of fatigue test, the fatigue life or N_f of the material can be numerically and graphically determined as the peak value of the product of the

stiffness, $|G^*|$, and the number of load cycles, N , in a graph of $|G^*| \cdot N$ vs. N . The peak value in this graph denotes the point where the micro cracks develop into macro cracks [17]. This is considered a practical method to identify fatigue failure, which does not require complex data acquirement and analysis.

A more recently developed approach to determine fatigue damage in bitumen, which has become very popular, is the Linear Amplitude Sweep (LAS) test, which is described in detail in the AASHTO TP 101-14. This test consists on a strain-sweep procedure in the DSR to systematically accelerate damage by increasing the cyclic loading strain amplitudes at a constant frequency. In short, it uses the results of frequency and strain sweep tests in combination with a Viscoelastic Continuum Damage mechanics (VECD) model to determine the fatigue life of a bitumen [18,19]. Although there is not a specific temperature to conduct this test, it is of utmost importance to choose the correct test temperature as it greatly influences the damage mechanism [20]. One recognized challenge of the LAS test is the use of the 8 mm plate, which has commonly reported to lead to failure occurring due to debonding of specimen from the plates [6,20,21]. As a result, sometimes the binder-steel plate bond is tested rather than fatigue damage performance of the bitumen. Furthermore, the gap between the plates have to be increased for modified bitumen and mastics. In addition, while the LAS test is relatively fast and can be easily performed, the use of the VECD model to determine the characteristic damage behaviour of the material has been observed to be insufficient to properly capture changes in the material properties of the bitumen, such as ageing, when estimating its fatigue life [19,22,23]. A recent improvement to the LAS test is the Pure Linear Amplitude Sweep (PLAS) test, which does not require the initial frequency sweep test used in the LAS procedure, uses a new cracking index based on fracture mechanics to analyse the resulting testing data, and has shown to be more sensitive to ageing conditions [22,23]. However, the strain sweep protocol shares the same testing challenges as those mentioned for the LAS test [6,20,21].

As observed, even though there have been important advancements, there are still some limitations when using the parallel plate-plate configuration for fatigue testing in the DSR. In this context, fatigue testing using a modified sample geometry, such as a "cylindrical column", is innovative alternative for bitumen, mastic and mortar testing characterisation. These specimens were initially produced by TU Delft for conducting efficient frequency sweeps of mortars [24]. They have since been adapted for fatigue testing of bitumen. This fatigue bitumen column specimen test has been shown to be effective for the fatigue characterisation of unmodified and modified bitumen, as well as for mastics and mortars [7,25–27].

Other than the specimen and testing DSR geometry discussion, it is still not completely clear which is the most appropriate temperature-frequency combination to perform bitumen and mixture fatigue testing. If the testing temperatures are too high, edge flow can occur during cyclic loading as the bitumen behaves largely in a viscous manner. On the other hand, if the temperatures are too low, adhesion cracking could be observed due to the increase in stiffness of the material [13]. Anderson [28] obtained equivalent conclusions, and also defined a transition temperature between the internal fatigue damage and the unstable plastic flow at the edges of the sample. Safaei and Castorena [20] used 8mm parallel and cone plate geometry in the DSR at temperatures of 5°C, 20°C and 35°C and a 0.1Hz to 30Hz frequency range. They differentiated between three damage mechanisms based on test temperatures: low temperatures lead to failure due to brittleness and loss of adhesion; intermediate temperatures cause cohesive cracking and; high temperatures result in bulging of the sample. They further concluded that the test temperatures should be chosen so that the sample fails due to cohesive cracking, which is the actual representation of the fatigue damage of the bitumen. Hospodka et al. [6] suggested that bitumen and mastic fatigue testing could be properly undertaken in the DSR with a 8mm parallel plate geometry at a temperature of 10°C and 30Hz frequency. Rochlani et al. [7] has conducted tests with small column cylinders in the DSR at a temperature-frequency combination of 20°C and 10Hz for bitumen and mastics. These testing conditions, however, were arbitrarily selected only because they are a common standard for fatigue testing of asphalt mixtures. As seen, there are variations among the specimen geometries and testing conditions to study fatigue resistance of bitumen, hence making it imperative to continue acquiring knowledge about the fatigue mechanisms that could be used to propose a set of proper testing conditions.

The primary objective of this study is to assess the influence of temperature and frequency conditions on bitumen fatigue damage using a recently developed column cylindrical specimen testing in the DSR and a DE analysis approach. To achieve this goal, tests were conducted on one bitumen at three different temperatures (10°C, 15°C and 20°C) and two loading frequencies (10Hz and 20Hz). The choice of these temperatures comes from the fact that the standard conditions for fatigue testing in Germany for asphalt and bituminous materials are 20°C and 10Hz [7]. Hence, temperatures close to 20°C were chosen, while the choice of a higher frequency comes from the need to reduce the testing time. The experimental results were comprehensively evaluated to understand temperature-frequency effects on DE and fatigue life of bitumen.

2. Materials tested

For this study, a bitumen of penetration grade 50/70 that is commonly used for road construction in Germany was selected. The actual penetration was 52 (1/10mm) and the softening point 51.4°C. Figure 1 presents the master curve of the dynamic shear modulus and phase angle (i.e., $|G^*|$ and δ) of the bitumen in unaged condition. Further details about the rheology and other testing conducted on this bitumen can be found in Rochlani et al. [7].

Figure 1. Master curves for dynamic shear modulus and phase angle of the bitumen

3. Testing Specimens

The fatigue testing sample preparation procedure starts with heating the bitumen to a temperature of 160°C. Then small metal rings (outer Ø 8mm, inner Ø 7mm) are added on the top and bottom portion of the moulds. The role of these metal rings is to allow clamping the specimen in the rheometer to avoid direct bitumen contact with the fixtures. After this, the material is stirred for several seconds to ensure homogeneous conditions, and then poured into a specially designed silicone mould with the moulds. The mould is then cooled down to room temperature and stored in a refrigerator at a temperature of 2°C, so as to harden and maintain its shape until tested. The resulting specimens have a height of 20mm, a top and bottom diameter of 8mm with the end rings, and of 7mm without these rings, while the actual dimension of the tested part has a height of 11mm and a 6mm diameter. These dimensions provide the possibility of using the same specimen geometry for testing bitumen, mastics and asphalt mortar

in the future, something that is not possible with the parallel plate configuration. Figure 2a shows the silicone mould that was used to fabricate the samples, while Figure 2b shows the dimensions of the specimen, and Figure 2c shows the testing specimen in the DSR. For testing, the bottom end of the specimen was fixed in the rheometer and the top end was subjected to torque (Figure 2b).

Figure 2. a) Silicone mould with specimens, b) specimen dimensions, and c) fatigue specimen in the DSR

A common problem observed during the initial experimentation with these specimens was that they tended to break near the metal rings due to the stress concentration (i.e., border effects) in this region (Figure 3a). To reduce the stress concentration a smooth fillet with a radius of 0.4mm was provided at the bitumen-ring interface, therefore, the testing column had a lower diameter (6mm) than the inner diameter of the ring (7mm). When failure occurred at or near this region, the specimen was discarded. Only those tests in which failure occurred in the middle of the specimen were further evaluated (Figure 3b). It is noteworthy that these errors have been minimised by experience, including the use of a proper mould, caution during sample preparation and sufficient clamping in the machine. Currently, the number of samples that need be discarded is neglectable, proving that the selected shape and size provides good accuracy for testing bitumen (modified and unmodified) and mastics [7,26,29] .

Figure 3. Failure paths in fatigue test with a column sample in the DSR.

4. Testing Method

Shear stress-controlled fatigue tests were undertaken on the cylindrical column specimens at the three selected temperatures (10°C, 15°C and 20°C) and the two frequencies (10Hz and 20Hz). The choice of 20Hz came from the need to perform the test at a faster rate, since at 10Hz is possible to conduct 36,000 load cycles in an hour, while at 20Hz, 64,000 load cycles are completed in an hour. However, higher frequencies could also result in higher DE values [6], which justifies the necessity to assess the fatigue response of the material under these conditions. Stress-controlled tests were preferred over strain-controlled test because it is easier to pinpoint the fracture point under this configuration [30]. Furthermore, the German standard TP Asphalt-StB, Teil 24 [31] conduct fatigue tests under stress-controlled mode.

A total of seven to eight stress levels were chosen per testing condition, in order to properly construct the fatigue function of the material. One replicate was done for each stress level. The stresses for testing were chosen based on experience to keep the initial strain (strain at 100 load cycles) in the range of 0.5% to 2%, so as to maintain an equivalent point of comparison as mentioned in the German fatigue testing standards [31]. The stress levels at 20°C were 50kPa to 250kPa, at 15°C they were 150kPa to 350kPa and at 10°C they were 250kPa to 525kPa, independently of the loading frequency. In these tests, the initial stiffness was taken as the value at 100 load cycles, as recommended in previous works [4,7]. The number of load cycles at failure or N_f , was defined using the Rowe's energy ratio method, although the results were further analysed using the DE at various load cycles.

5. Typical Test Results

This section briefly presents typical test results obtained. Firstly, the $|G^*|N$ vs. N graphs are used to illustrate how the fatigue life of the specimens was determined. Secondly, selective

hysteresis loops are shown to qualitatively illustrate the progression of fatigue damage in the material.

5.1 Fatigue Life Determination

The fatigue life or N_f at each temperature-frequency-stress level combination was computed using the Rowe's energy ratio. As explained before, failure is defined at the point where the product of the number of load cycles and the dynamic shear modulus ($|G^*|N$) is the highest or, graphically, as the peak in the $|G^*|N$ versus N curve. Figure 4 illustrates the $|G^*|N$ versus N plot after testing the bitumen at three different stresses.

Figure 4. $|G^*|N$ versus the number of load cycles (N) for different stresses applied.

5.2 Hysteresis Loops

The hysteresis loops at five distinct load cycles for some tests were selected to illustrate the typical degradation of the material. They were chosen such that the first loop or point of analysis was at load cycle of 100, while the fourth was the failure point as determined by the energy ratio method. Two intermediate loops were selected between the first and the failure condition, and one additional loop was taken after the failure took place. Figure 5 presents the loops at these five number of load cycles for the tests done at 20°C–10Hz at a stress level of 250kPa; at 15°C–10Hz at a stress level of 300kPa; and at 10°C–10Hz at a stress level of 350kPa respectively.

(a)

(b)

(c)

Figure 5. Hysteresis loops at different load cycles for test at a) 20°C and 10Hz @ 100 kPa b) 15°C and 10Hz @ 300kPa c) 10°C and 10Hz @ 500kPa.

The figures show that, as the tests progress, the slope that represents the stiffness of the material decreases, as expected for a stress-controlled fatigue method. It can be also observed that the area of the hysteresis loops increases with the number of cycles, representing the progression of DE and damage. Often times, a slight distortion in the loop shape can be also observed in the loops especially after the first loop (Figure 5). This is believed to be mainly an indicative of the development of micro cracks that results in discontinuities in the stress paths, thereby leading to distortions in the response or the loop [32].

6. Results and Analysis

6.1 Traditional Fatigue Curves

Figure 6 shows the conventional fatigue curves of N_f vs. applied stress, while Table 1 provides the slope analysis conducted for these fatigue curves.

The influence of frequency and temperature on fatigue life becomes evident in the results of this figure. As temperatures decreases, the fatigue curves tend to shift to the right. The reason is that for applied given stress level, lower temperatures would result in a larger N_f value than higher temperatures. It can also be seen that the curves for the two frequencies (10Hz and 20Hz) intersect for both 20°C and 10°C, while at 15°C, the fatigue curves at the different frequencies tend to be parallel. Furthermore, the 10Hz and 20Hz combinations at 15°C, along with 20°C–10Hz and 10°C–20Hz combinations, appear to be approximately parallel (i.e. slopes of 0.017, 0.015, 0.021 and 0.015 kPa^{-1} , respectively, from Table 1), whereas the 20°C–20Hz and 10°C–10Hz curves also appear parallel (i.e. slopes of 0.032 and 0.027 kPa^{-1} , respectively).

The change in the slopes due to an increase in frequency, presented in Table 1, shows that the slope difference at both frequencies at 15°C was merely 13.33%. Similar slopes at this temperature could represent a similarity in the viscoelastic behaviour of the bitumen, which seems to be relatively unaffected by frequency. On the contrary, there is major shift in the slopes for the other two temperatures that perhaps indicates a change from a viscous to a more solid behaviour with an increase in frequency. Interestingly, Hofko et al. [6] obtained slightly lower slope values (range of 0.010-0.011 kPa^{-1}) for mastic fatigue at 10°C and 30Hz testing, using a hyperboloid specimen shape for similar traditional fatigue curves as presented above. Additionally, Rochlani et al. [33] presented results of three bitumen in different ageing conditions at 20°C and 10Hz, and found a slope value in the range of 0.03-0.04 kPa^{-1} for unaged,

0.02kPa^{-1} for RTFOT aged and PAV aged. These data suggest that the slopes of traditional bitumen fatigue function seem to reduce with ageing and with the addition of fillers.

These and existing results show that the slopes for bitumen, therefore, tend to fall within a similar value range of 0.03-0.015 [-]. Hence with further testing of different bitumen and ageing conditions, perhaps an acceptable area with threshold values on the traditional curves could be created as a quality control for a particular chosen stress level, which would allow an initial quality determination using just two to three tests at a different stress levels.

Figure 6. Fatigue functions for the unaged bitumen and mastics tested

Table 1. Slopes analysis of fatigue curves

Combination	Absolute value of slope [kPa^{-1}]	Percent difference between frequencies [%]
20°C-10 Hz	0.021	52.23
20°C-20 Hz	0.032	
15°C-10 Hz	0.017	13.33
15°C-20 Hz	0.015	
10°C-10 Hz	0.025	40.00
10°C-20 Hz	0.015	

Next section further explores with more detail the fatigue behaviour of the material using DE data.

6.2 Fatigue Curve Representation Based on DE and Applied Stress

Fatigue curves based on DE values are a common alternative to the traditional fatigue curves presented in section 6.1. Thereby, Figure 7 presents the DE at failure with respect to the applied stress at all testing conditions. Triangle markers and unbroken lines correspond to combinations tested at 20Hz frequency, while round markers and dotted lines correspond to 10Hz frequency results.

Figure 7. DE at failure as a function of the applied stress.

As observed, as the temperature decreases, the curves shift to the right, as for the same applied stress level, lower values of DE at failure are obtained at lower temperatures, owing to the higher stiffness of the material resulting in a lower strain. Moreover, at any given temperature and the same stress level, the material tested at 10Hz dissipated more energy at failure than its 20Hz counterpart. This result was also expected, since under a fixed temperature, the stiffness of the bitumen increases with frequency. However, it is interesting to note the differences in DE at both frequencies is lower at lower temperatures. For example, at 200kPa and 20°C, the bitumen dissipated 3.07 times more energy at failure when tested at 10Hz in comparison to 20Hz; while at 300kPa and 15°C, the bitumen dissipated 2.33 times more energy when tested

at 10Hz than at 20Hz; and at 400kPa the bitumen tested at 10°C only dissipated 1.07 times more energy at 10Hz than at 20Hz. This trend suggests, that if the temperature would be further reduced or the frequency increased, there would not have been significant differences in the dissipated energy at failure of the material. However, conducted testing at those conditions is challenging; indeed, most researchers have conducted fatigue testing at temperatures above 10°C as the stiffness of the material is too high at temperatures below this value [21,34–36], and because at lower temperatures the main mechanism of failure of the material might be different from fatigue damage [20].

Another interesting observation is that the curves for 20°C at 20Hz and 15°C at 10Hz are relatively close to one another, indicating that the materials releases similar DE at these combinations. This similarity could be due to the time-temperature superposition behaviour of bitumen. However, it is interesting that this similarity in the degradation process at these two conditions does not imply equal fatigue life, as demonstrated by the slopes of the fatigue life curves in Figure 6 and Table 1.

To deepen the understanding of the effects on DE due to different temperatures and frequencies, failure lines were constructed and discussed in the following section.

6.3 Failure Lines – DE vs. N_f curves

Figures 8, 9 and 10 present the relationship between the dissipated energy and the number of cycles (DE vs. N_f) for 20°C, 15°C and 10°C, respectively. These lines were plotted for each test at each stress level and frequency condition (circular markers for 10Hz tests and triangular markers for 20Hz tests) at the three temperatures. Additionally, ‘failure lines’ were constructed in each figure by running a line through the corresponding DE value at the failure point (i.e., N_f) for each stress level and frequency condition. These DE ‘failure lines’ are presented in red colour in these figures for all temperature-frequency combinations. Dotted red lines represent the failure line for 10Hz testing frequency, while the continuous straight failure lines correspond to 20Hz.

Figure 8. DE vs. N curves at 20°C and ‘failure lines’ for 10Hz (dotted line) and 20Hz (continuous line)

Figure 9. DE vs. N curves at 15°C and failure lines for 10Hz (dotted line) and 20Hz (continuous line)

Figure 10. DE vs. N curves at 10°C and failure lines for 10Hz (dotted line) and 20Hz (continuous line).

As observed, failure lines at 20°C – 10Hz and 20Hz (Figure 8) intersect at an N value of 3×10^5 [-] or at a DE of 2kPa. Before this intersection, the data at 20Hz test conditions exhibit a lower DE at failure than the 10Hz test frequency, for any given value of N . After this intersection, the trend is seen to reverse. However, the differences between the curves before intersection is more significant for lower values of N , while the difference is less significant for higher N . On the other hand, Figure 9 shows that the failure lines at 15°C and both frequencies tend to overlap. This suggests that at this temperature the DE at failure is frequency-independent. Finally, Figure 10 which presents the failure lines at 10°C, presents an opposite trend as that observed for 20°C (Figure 8). That is, before the intersection point (i.e., N equal to 4×10^5), the 10Hz tests have lower DE at failure as compared to the results at 20Hz. This is similar to Figure 6 presented in section 6.1, where the slopes were observed to follow a similar trend; i.e., in that figure, N_f is higher for 10Hz than for 20Hz at 20°C for low stress levels, and vice versa for 10°C; while for 15°C, the slopes were similar. These transitions in DE in this section and slopes in the previous section indicate a transition from brittle to ductile in the behaviour of the bitumen, while at 15°C, the material seems to be in an intermediate transitional phase, where the effects of frequency are negligible.

These same trends could be observed in Figure 11, which summarizes the failure information (DE at failure) of the six temperature-frequency combinations at five different N values (1×10^3 , 1×10^4 , 1×10^5 , 1×10^6 and 1×10^7). This figure clearly shows that the test at 10Hz and 20°C has a higher DE at failure for lower N values in comparison to the results at the same temperature and 20Hz, while the opposite occurs at 10°C. The shift in these trends for values of N larger

than 1×10^6 is also easily observed. As mentioned before, at 15°C , the curves overlap for both frequencies.

Figure 11. Failure lines at 10°C for 10 Hz (dotted line) and 20 Hz (continuous line).

All previous information show that, for this bitumen, 15°C could be considered a ‘frequency-free transition temperature’. This transition temperature could also be indicative of the damage behaviour changing from fatigue damage to plastic deformation or viscous effects or other damage-related processes at higher temperatures. It further enforces the results from Anderson et al. [34], who conducted time-sweeps on bitumen in the range of 10°C to 25°C and concluded that for unmodified RTFOT aged bitumen, there was a transition temperature observed at around 18°C , which represents a change from a the region between pure fatigue damage and instability flow. Shen et al. [37] also identified 12°C to be a transition temperature for unmodified bitumen of penetration grade 50/70 and conducted tests at this temperature. They found that temperatures below 12°C were more representative of fatigue, while over this value the degradation process captures both fatigue and instability flow behaviour of the bitumen. While many researchers have introduced the concept of a transitional intermediate temperature for fatigue testing, the construction of failure lines for its easy identification offers a new way to identified it.

The results herein obtained not only reinforce that each bitumen might have an intermediate ‘transition temperature,’ but they also suggest that, at this temperature, the effects of frequency are neglectable. Before and after this temperature, the influence of temperature in the

mechanical behaviour and degradation of the material (less stiff vs. stiffer) is evident. It is hypothesized that this could be a time-efficient test temperature as a specimen could be subjected to 64000N/hour at 20Hz, instead of 36000N/hour at 10Hz, which would be beneficial from a practical point of view. Nevertheless, additional tests with other bituminous materials at different ageing and modified conditions and within a larger range of temperatures are needed to confirm this hypothesis.

6.4 Temperature-Frequency Independent Fatigue Representation

While the previous section indicated 15°C as being a transition temperature with negligible frequency effects, an interesting temperature-frequency independent fatigue data representation was obtained when analysing the initial DE at N equal to 100 versus N_f . This is presented in Figure 12 for 10Hz (orange line with circles) and 20Hz (blue line with triangles) for all the tests done at the three temperatures (10°C, 15°C and 20°C).

Figure 12. Number of load cycles until fatigue failure as a function of the initial DE for all temperatures at 10Hz (orange circle data points) and 20Hz (blue triangle data points).

Regardless of the temperature value, the two frequency lines show a good correlation in terms of the initial DE and the N_f with R^2 values of 0.93 and 0.92 for 10Hz and 20Hz. Since the 10Hz and 20Hz lines were so similar, the data points of the six combinations were combined, and a single trend line was obtained (Figure 13). This figure shows that the relationship between the

initial DE and N_f is independent of both frequency or temperature, with an R^2 of 0.90. Using the equation of the trend line, the following exponential relation is obtained:

$$N_f = C_1 e^{C_2 D_0} \quad (5)$$

where

C_1 = y-axis intercept or N_f value at 0 initial DE = 1637442.49 kPa

C_2 = slope; equal to -0.57 for this bitumen

D_0 = initial DE at 100 load cycles

Thereby, for the specific bitumen herein studied, the equation is the following:

$$N_f = 1637442.49 e^{-0.57 D_0} \quad (6)$$

Additionally, upper and lower limits were defined using the standard deviation of the data, so that the value of C_1 could be in the range of 1.1×10^6 to 2.17×10^6 .

Figure 13. Combined failure function for all frequency-temperature combinations tested with upper and lower limits

This temperature and frequency independent relationship could provide an alternative way to represent fatigue degradation and predict the N_f value using only the initial DE, regardless of the testing conditions. If the exponential correlation in Equation 5 holds true for other ageing

conditions and bitumen materials, this would mean that the DE at a lower loading cycle obtained at a specific applied stress level, and at any combination of temperature and frequency, would be enough to compare the expected N_f of a set of bitumen materials or to predict N_f of a bitumen at any frequency-temperature-stress combination. To do the later, it would be necessary to first perform fatigue tests at any pair of temperature-frequency combinations, in order to determine the fitting parameters (i.e., C_1 and C_2) of Equation 5. Afterwards, the number of load cycles until fatigue failure N_f at any other frequency-temperature-stress combination could be estimated by only running the initial 100 cycles of the test, computing DE at that point, and using the obtained equation to estimate the expected N_f result. This would make fatigue testing economical, reducing the time and effort required.

6.5 Type of Fracture

While quantitatively many differences were observed among the different temperature-frequency combinations in previous sections, a qualitative comparison of the conditions of the specimens at failure is herein presented to further emphasise the ductile to brittle transition or the ‘fatigue plus plastic deformation’ to ‘pure fatigue’ transition visible when passing from 20°C to 10°C.

While many researchers have shown the fracture of bitumen and mastic specimens with the 8mm plate [6,21,30,37], the failure condition of column cylindrical bitumen specimen are rare. The complete failure or rupture of the testing specimens occurred shortly after N_f was reached. As an example of the results, Figure 14 presents the fractured specimens tested at 250 KPa, at each temperature-frequency combination. Dotted lines indicating cracked planes were also presented in these figures.

Figures 14a and 14b show the fracture plane at 20°C for 10Hz and 20Hz respectively, where a slight swelling of the specimen is visible in both the images, perhaps indicating small levels of localised flow and resulting permanent deformation near the failure plane. Figures 14c and 14d present the fracture plane at 15°C for 10Hz and 20Hz respectively, where a nearly straight diagonal rupture planes (i.e., shear failure plane) can be observed, with no visible swelling of the specimens. Lastly, Figures 14e and 14f illustrate the failure planes at 10°C for 10Hz and 20Hz respectively, where a complete cracked throughout the specimen is observed; in this case, small angular pieces of the bitumen were observed to be expelled from the specimen in the temperature chamber of the DSR. This further evidence that a reduction of temperature changes the cracking mode of the bitumen from ductile to brittle.

Figure 14. Rupture of specimens for different temperature-frequency combinations at a stress level of 250KPa

Additionally, an image analysis was done by changing the contrast on the images to identify crack patterns close to failure. Figure 15a shows images of the specimen during the beginning of the test, while 15b show images towards the end of the test. From the latter image, horizontal cracks can be observed, which are indicative of fatigue damage. Overall, it can be said that the samples fail cohesively, which is a main recommendation of fatigue testing in bitumen, as discussed in [20].

Figure 15. *Cracking mode of the specimens.*

6. Conclusion

Stress-controlled fatigue tests were carried out using small column cylindrical specimens with a DSR on a 50/70 penetration grade bitumen. The tests were undertaken at three temperatures – 10°C, 15°C and 20°C and at two frequencies – 10Hz and 20Hz. Specimens at the six temperature-frequency combinations were tested over a range of stress levels. As expected, it was seen that both temperature and frequency had an impact on the fatigue degradation and failure of the materials.

The following conclusions were drawn based on the experimental results:

- The column cylindrical specimens in the DSR show potential for efficient fatigue testing and hence, could be used as an alternate to existing testing methods. The specimens could be efficiently utilised at multiple temperatures and frequencies.
- Traditional fatigue curves indicated that the slopes were very similar for the two tested frequencies at 15°C. At 20°C, the slope of 10Hz was observed to be steeper than that at 20Hz, and at 10°C the an inverse result of the slope variations with frequency were obtained, indicating the change in the bitumen behaviour from a stiff condition to less stiff and more viscous response. While slopes of traditional curves could be indicative of the material behaviour, the DE at failure provides a more convenient representation of the damage process occurring with the specimen. Therefore, it is highly recommended to include DE considerations in fatigue studies.
- Failure lines of DE and N_f showed that testing frequency had almost no influence on the dissipated energy values at 15°C. Hence, this temperature was identified as the ‘frequency-free transition temperature’ for this bitumen. Thereby, testing at this

temperature would more time efficient and hence beneficial from a practical point of view. This transition temperature could vary from bitumen to bitumen, and is expected to be dependent on modification and aging conditions.

- A temperature and frequency independent fatigue data presentation was developed within this research for the relationship between the initial DE and N_f . This relationship was found to follow an exponential function, and it was identified as a new efficient method to predict the N_f of a bitumen at a specific temperature-frequency-stress level testing conditions based only on the initial DE . While the hypothesis held true for this bitumen, its validity needs to be verified with further intensive testing of this bitumen and other materials.
- The qualitative analysis of the fractured specimens verified the expected change in the damage mechanism from ductile to brittle failure with a reduction in temperature.

In order to verify the conclusions here enlisted, further detailed research is planned and currently in process.

7. Further Research

Future testing would be conducted for different ageing conditions on unmodified and modified bitumen, as well as on mastics and mortars. Also, additional temperature-frequency combinations will be considered. This would enable to understand how material behaviour changes with respect to testing condition variations, and to verify the initial DE vs. N_f relationship herein presented. Additionally, other specimen shapes are also being tested in order to overcome the shortcomings of the current specimen shape and to quicken the failure by adding a notch. Additionally, more detailed research should be undertaken to understand the thermal changes and heating of the specimen during testing e.g. using a thermal imaging camera.

8. Acknowledgements

We hereby acknowledge the financial support provided by TU Dresden as part of the Scholarship Program for the Promotion of Early-Career Female Scientists for Ms. Rochlani. This paper is also partly based on the research project carried out at the request of the German Research Foundation (DFG), under research project No. WE 1642/11 and LE 3649/2 (FOR2089). The authors are solely responsible for the content.

9. Bibliography

- [1] K.A. Ghuzlan, S.H. Carpenter, Energy-derived, damage-based failure criterion for fatigue testing, *Transp. Res. Rec.* (2000). <https://doi.org/10.3141/1723-18>.
- [2] A. Braham, B.S. Underwood, *State of the Art and Practice in Fatigue Cracking Evaluation of Asphalt Concrete Pavements*, 2016.
- [3] C. Maggiore, J. Grenfell, G. Airey, A.C. Collop, Evaluation of fatigue life using dissipated energy methods, *RILEM Bookseries*. (2012). https://doi.org/10.1007/978-94-007-4566-7_63.
- [4] G.M. Rowe, M.G. Bouldin, Improved Techniques to Evaluate the Fatigue Resistance of Asphaltic Mixtures, 2nd Eurasphalt Eurobitume Congr. Barcelona 2000. (2000).
- [5] R. Botella, F.E. Pérez-Jiménez, R. Miró, Application of a strain sweep test to assess fatigue behavior of asphalt binders, *Constr. Build. Mater.* (2012). <https://doi.org/10.1016/j.conbuildmat.2012.06.059>.
- [6] M. Hospodka, B. Hofko, R. Blab, Introducing a new specimen shape to assess the fatigue performance of asphalt mastic by dynamic shear rheometer testing, *Mater. Struct. Constr.* (2018). <https://doi.org/10.1617/s11527-018-1171-6>.
- [7] M. Rochlani, S. Leischner, G.C. Falla, D. Wang, S. Caro, F. Wellner, Influence of filler properties on the rheological, cryogenic, fatigue and rutting performance of mastics, *Constr. Build. Mater.* 227 (2019) 116974. <https://doi.org/10.1016/j.conbuildmat.2019.116974>.
- [8] A. Pereira, R. Micaelo, L. Quaresma, M.T. Cidade, Evaluation of different methods for the estimation of the bitumen fatigue life with DSR testing, in: *RILEM Bookseries*, 2016. https://doi.org/10.1007/978-94-017-7342-3_81.
- [9] M. Partl, H. Bahia, F. Canestrari, C. Roche, H. Benedetto, D. H. Piber, Advances in Interlaboratory Testing and Evaluation of Bituminous Materials. State-of-the-Art Report of the RILEM Technical Committee 206-ATB, 2013. <https://doi.org/10.1007/978-94-007-5104-0>.
- [10] S. Shen, H.M. Chiu, H. Huang, Characterization of fatigue and healing in asphalt binders, *J. Mater. Civ. Eng.* (2010). [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0000080](https://doi.org/10.1061/(ASCE)MT.1943-5533.0000080).
- [11] E. Santagata, O. Baglieri, L. Tsantilis, D. Dalmazzo, Evaluation of self healing properties of bituminous binders taking into account steric hardening effects, *Constr. Build. Mater.* (2013). <https://doi.org/10.1016/j.conbuildmat.2012.11.118>.

- [12] H. Bahia U, D. Hanson I, M. Zeng, H. Zhai, M. Khatri A, R. Anderson M, Characterization of modified asphalt binders in superpave mix design, NCHRP Rep. (2001).
- [13] H. Soenen, B. Eckmann, Fatigue testing of bituminous binders with a dynamic shear rheometer, 2nd Eurasphalt Eurobitume Congr. (2000).
- [14] K. Ghuzlan, S. Carpenter, Traditional fatigue analysis of asphalt concrete mixtures, Urbana. (2002).
- [15] S.H. Carpenter, S. Shen, Dissipated energy approach to study hot-mix asphalt healing in fatigue, in: Transp. Res. Rec., 2006. <https://doi.org/10.3141/1970-21>.
- [16] P. Hopman, P. Kunst, A. Pronk, A renewed interpretation method for fatigue measurements-verification of Miner's rule, in: Proc. 4th Eurobitume Symp., Madrid, Spain, 1989.
- [17] D.A. Ramirez Cardona, S. Pouget, H. Di Benedetto, F. Olard, Viscoelastic Behaviour Characterization of a Gap-graded Asphalt Mixture with SBS Polymer Modified Bitumen, Mater. Res. (2015). <https://doi.org/10.1590/1516-1439.332214>.
- [18] C. Hintz, R. Velasquez, C. Johnson, H. Bahia, Modification and validation of linear amplitude sweep test for binder fatigue specification, Transp. Res. Rec. (2011). <https://doi.org/10.3141/2207-13>.
- [19] R. van Rooijen, L. Planque, M. Wegmann, H. Di Benedetto, S. Mangiafico, C. Sauzeat, F. Olard, S. Pouget, Bitumen fatigue performance evaluation - with or without RAP - a real challenge, in: 2017. <https://doi.org/10.14311/ee.2016.055>.
- [20] F. Safaei, C. Castorena, Improved interpretation of asphalt binder parallel plate dynamic shear rheometer fatigue tests, Int. J. Pavement Eng. (2020). <https://doi.org/10.1080/10298436.2018.1438611>.
- [21] C. Hintz, H. Bahia, Understanding mechanisms leading to asphalt binder fatigue in the dynamic shear rheometer, Road Mater. Pavement Des. (2013). <https://doi.org/10.1080/14680629.2013.818818>.
- [22] F. Zhou, P. Karki, S. Im, Development of a Simple Fatigue Cracking Test for Asphalt Binders, Transp. Res. Rec. (2017). <https://doi.org/10.3141/2632-09>.
- [23] K. Pravat, F. Zhou, Evaluation of Asphalt Binder Performance with Laboratory and Field Test Sections. Report No. FHWA/TX-18/0-6674-01-R1, Austin, 2018. <https://static.tti.tamu.edu/tti.tamu.edu/documents/0-6674-01-R1.pdf>.
- [24] M.F. Woldekidan, Response Modelling of Bitumen, Bituminous Mastic and Mortar,

- 2011.
- [25] P. Cong, N. Liu, H. Shang, H. Zhao, Rheological and fatigue properties of epoxy asphalt binder, *Int. J. Pavement Res. Technol.* 8 (2015) 370–376. [https://doi.org/10.6135/ijprt.org.tw/2015.8\(5\).370](https://doi.org/10.6135/ijprt.org.tw/2015.8(5).370).
 - [26] M. Rochlani, S. Leischner, D. Wareham, S. Caro, G.C. Falla, F. Wellner, Investigating the performance-related properties of crumb rubber modified bitumen using rheology-based tests, *Int. J. Pavement Eng.* (2020). <https://doi.org/10.1080/10298436.2020.1776868>.
 - [27] L.T. Mo, M. Huurman, S.P. Wu, A.A.A. Molenaar, Research of bituminous mortar fatigue test method based on dynamic shear rheometer, *J. Test. Eval.* (2012). <https://doi.org/10.1520/JTE103738>.
 - [28] D.A. Anderson, Y.M. Le Hir, M.O. Marasteanu, J.-P. Planche, D. Martin, G. Gauthier, Evaluation of Fatigue Criteria for Asphalt Binders, *Transp. Res. Rec. J. Transp. Res. Board.* (2001). <https://doi.org/10.3141/1766-07>.
 - [29] M.R. Mitchell, R.E. Link, L.T. Mo, M. Huurman, S.P. Wu, A.A.A. Molenaar, Research of Bituminous Mortar Fatigue Test Method Based on Dynamic Shear Rheometer, *J. Test. Eval.* 40 (2012) 84–90. <https://doi.org/10.1520/jte103738>.
 - [30] G. Al-Khateeb, A. Shenoy, A simple quantitative method for identification of failure due to fatigue damage, *Int. J. Damage Mech.* (2011). <https://doi.org/10.1177/1056789509343084>.
 - [31] Forschungsgesellschaft für Straßen- und Verkehrswesen (FGSV), Technische Prüfvorschriften für Asphalt (TP Asphalt-StB), Teil 24: Spaltzug-Schwellversuch – Beständigkeit gegen Ermüdung (2018), Köln, 2018.
 - [32] G. Al-Khateeb, A. Shenoy, A distinctive fatigue failure criterion, in: *Asph. Paving Technol. AAPT*, 2004.
 - [33] M. Rochlani, S. Leischner, G.C. Falla, P. Goudar, F. Wellner, Influence of Source and Ageing on the Rheological Properties and Fatigue and Rutting Resistance of Bitumen Using a DSR, in: *Lect. Notes Civ. Eng.*, 2020. https://doi.org/10.1007/978-3-030-48679-2_46.
 - [34] D.A. Anderson, Y.M. Le Hir, M.O. Marasteanu, J.P. Planche, D. Martin, G. Gauthier, Evaluation of fatigue criteria for asphalt binders, in: *Transp. Res. Rec.*, 2001. <https://doi.org/10.3141/1766-07>.
 - [35] B. Hofko, A. Cannone Falchetto, J. Grenfell, L. Huber, X. Lu, L. Porot, L.D. Poulikakos,

- Z. You, Effect of short-term ageing temperature on bitumen properties, *Road Mater. Pavement Des.* (2017). <https://doi.org/10.1080/14680629.2017.1304268>.
- [36] S. Shen, Dissipated Energy Concepts for HMA Performance: Fatigue and Healing, ProQuest Diss. Theses. (2006).
- [37] S. Shen, G.D. Airey, S.H. Carpenter, H. Huang, A Dissipated Energy Approach to Fatigue Evaluation, *Road Mater. Pavement Des.* 7 (2007) 47–69. <https://doi.org/10.3166/rmpd.7.47-69>.

Notes: