Bioprinting of Functionalized Bone Grafts

D i s s e r t a t i o n s s c h r i f t

zur Erlangung des akademischen Grades

Doctor of Philosophy (Ph.D.)

vorgelegt

der Medizinischen Fakultät Carl Gustav Carus

der Technischen Universität Dresden

von

Dipl.-Ing. Tilman von Strauwitz geb. Ahlfeld

aus Dresden

Dresden 2020

2. Blatt

1. Gutachter: Prof. Dr. Michael Gelinsky

2. Gutachter: Prof. Dr. Adrian Dragu

Tag der mündlichen Prüfung: 16.03.2021

gez.: -----

Vorsitzender der Promotionskommission

Anmerkung:

Die Eintragung der Gutachter und Tag der mündlichen Prüfung (Verteidigung) erfolgt nach Festlegung von Seiten der Medizinischen Fakultät Carl Gustav Carus der TU Dresden. Sie wird durch die Promovenden nach der Verteidigung zwecks Übergabe der fünf Pflichtexemplare an die Zweigbibliothek Medizin in gedruckter Form oder handschriftlich vorgenommen.

A fluorescence microscopy image of a bone graft, showing a central dark region surrounded by a ring of green and red fluorescent spots. The background is dark blue.

BIOPRINTING OF FUNCTIONALIZED BONE GRAFTS

Tilman von Strauwitz geb. Ahlfeld

Dissertation

Philosophiae Doctor (Ph.D.)

Centre for Translational Bone, Joint and Soft Tissue Research

Faculty of Medicine Carl Gustav Carus

Technische Universität Dresden

2020

Creating something out of nothing, that's the magic we do.

ABSTRACT

BACKGROUND The number of trauma-related bone fractures, fragility fractures resulting from osteoporosis or bone defects after tumor resections is increasing. The usability of autologous, but also allogeneous and xenogeneous bone grafts is limited. Bone grafts being manufactured using a tissue engineering approach are a promising alternative. For this, resorbable biomaterials are combined with biological components such as cells and growth factors. These functionalized constructs stimulate the formation of novel bone tissue after implantation in the patient and resorb in favor of regrowing, native bone.

A new form of tissue engineering is 3D bioprinting. Biologically active proteins and/or cells are mixed with biomaterials and get fabricated to constructs by a convenient additive manufacturing technology. This offers great advantages. For example, the patient-specific tissue engineered constructs can be manufactured fitting exactly to the respective defect. Further, it allows full control about the porosity of the final construct which is considered to be advantageous for nutrient supply and vascularization. Most crucial, it allows the spatial distribution of cells within the three-dimensional construct, which facilitate the maturation of the construct to the tissue-like graft.

RESEARCH QUESTIONS In the last decade some technological challenges in the field of bioprinting have been solved. Nevertheless, for bone tissue engineering only a small number of approaches had been developed. One of the reasons for this is that bioprinting technologies usually enable the processing of materials that are chemically and mechanically rather distant from the bone, particularly hydrogels. These materials are less suitable as bone substitutes.

The aim of this work was to research new approaches of extrusion-based (bio-)printing for bone tissue engineering strategies. For this purpose two promising approaches were investigated:

- (I) Multichannel printing of bioactive calcium phosphate cements in combination with biologically active hydrogels which were loaded either with growth factors or cells.
- (II) Development of a new bioink by supplementation of growth factor- or cell-laden hydrogels with a bioactive filler material.

The presented studies of this thesis demonstrate the feasibility of these approaches as well as their limits. In addition, fundamental mechanical and biological properties of the bioprinted bone constructs are investigated.

MATERIALS AND METHODS A technology that makes the principle of bioprinting possible is the so-called 3D plotting. With the aid of a multichannel plotter, multiphasic constructs can be fabricated (approach I), but of course also monophasic constructs are possible (approach II). For approach I, a clinically certified calcium phosphate cement (CPC) was used as bioactive component. For approach II, a less investigated nanomaterial called Laponite was used which was shown before to hold great potential for tissue engineering applications.

The biopolymers alginate and methylcellulose formed the basis for plottable, growth factor-laden (biomaterial inks) and cell-laden (bioinks) pastes. For the development of one specific bioink, human fresh frozen plasma was used.

Rheological properties of the newly developed biomaterial inks and bioinks were characterized, additionally mechanical properties of plotted constructs were investigated. Further studies investigated the swelling of the hydrogels and the porosity of the constructs. Particular attention was paid to the shape fidelity of the plotted structures.

Different cell types were used according to the aim of the subject of research; special attention was paid to the use of mesenchymal stem cells which were plotted directly in combination with the biomaterial, forming the bioink. The angiogenic vascular endothelial growth factor (VEGF) was used as model protein for release studies from bioprinted structures; its biological activity was investigated by proliferation studies of human umbilical vein endothelial cells (HUVEC).

RESULTS Firstly, it was investigated whether multichannel plotting is a suitable technology for the fabrication of patient-specific CPC constructs. This was achieved by plotting of a fugitive methylcellulose support ink. This procedure allowed the manufacturing of inner cavities which would not have been possible with other scaffold fabrication methods. Moreover, it was possible to extract a scaphoid bone from a CT scan of a human hand which was modeled virtually and fabricated subsequently with high shape fidelity. Later it was demonstrated that this procedure can be adapted to biphasic constructs consisting of CPC and cell-laden hydrogels.

This was achieved by developing and processing bioinks. Bioprinted cells can evoke biological effects *in vitro* and *in vivo*. For this purpose two bioinks were developed within this work acting as cell carrier materials. The first bioink contained the nano material Laponite (approach II) which has demonstrated positive effects for bone tissue engineering before. The novel Laponite-based bioink enabled the fabrication of constructs with high shape fidelity. Furthermore, cell viability and cell density were increased compared to a Laponite-free control. Since Laponite offers a heterogeneous charge distribution, it was investigated whether it is a suitable delivery system for VEGF. Scaffolds with Laponite demonstrated a distinct different release profile compared to Laponite-free scaffolds. Thus an initial burst-like release could be avoided and at the same time a uniform release could be observed. The released VEGF was biologically active also after longer time in the scaffold. The second bioink was developed using fresh frozen human blood plasma. Plasma contains fibrinogen which holds a RGD motif for the attachment of MSC. Bioprinted MSC and preosteoblastic cells showed a high affinity to spread within the bioink, which is difficult to achieve for encapsulated cells. The plasma-based bioink was suitable for the combined fabrication of biphasic constructs with CPC (approach I).

To achieve this, firstly a suitable post-processing for biphasic constructs consisting of CPC and cell-laden bioinks had to be developed. From previous studies it is known that plotted CPC constructs form microcracks in aqueous media during setting, which impair mechanical properties. The formation of the microcracks can be avoided by setting in water-saturated atmosphere. In biphasic constructs with bioinks this phase should only be short since a long

incubation in absence of aqueous cell culture media would lead to cell death within the bioink. It could be shown that incubation for 20 min in water-saturated atmosphere is convenient to avoid the formation of microcracks in CPC strands. This time could be tolerated by the cells. In combination with the plasma-based bioink, a strong proliferation and osteogenic maturation of bioprinted preosteoblastic cells could be observed.

CONCLUSION In this thesis, the principle of extrusion-based bioprinting (3D plotting) was used to fabricate biofunctionalized constructs. This was achieved by loading cells or growth factors before manufacturing of the constructs. Bioactive materials could be embedded into the constructs by either multichannel plotting or by supplementation of a bioink with a bioactive filler material. In principle both approaches even could be combined with each other. The results obtained prove that bioprinting is a suitable method for bone tissue engineering. Patient-specific constructs can be fabricated by this technology. Based on these results, further studies should be performed *in vivo* to investigate the potency of the approaches for the development of new regenerative therapies to treat bone defects.

ZUSAMMENFASSUNG

HINTERGRUND Die Anzahl von Knochenfrakturen im Zusammenhang mit Traumata, sowie osteoporosebedingten Fragilitätsfrakturen oder auch Knochendefekten in Folge von Tumoresektionen steigt stetig an. Die Nutzung autologen, aber auch allogenen und xenogenen Spendermaterials ist limitiert. Eine vielversprechende Alternative sind Knochenkonstrukte, die über einen Tissue Engineering-Ansatz hergestellt werden. Dabei werden resorbierbare Biomaterialien mit biologisch aktiven Substanzen wie Wachstumsfaktoren oder Zellen kombiniert. Diese funktionalisierten Konstrukte regen nach einer Implantation in den Patienten die gesunde Knochensubstanz zur Heilung an und resorbieren idealerweise zugunsten des nachwachsenden, natürlichen Knochens.

Eine neuartige Form des Tissue Engineerings ist der 3D-Biodruck („Bioprinting“), bei dem biologisch aktive Proteine und/oder Zellen mit Biomaterialien vermischt werden und anschließend durch ein additives Fertigungsverfahren zu Konstrukten verarbeitet werden. Dies hat einige Vorteile: Z.B. die Fertigung eines patientenspezifischen Konstrukts, welches direkt an den Defekt angepasst ist, aber auch eine gute Einstellbarkeit der Porosität des finalen Konstrukts, was vorteilhaft für die Nährstoffversorgung und Vaskularisierung sein kann. Vor allem erlaubt es eine ortsaufgelöste Verteilung, wodurch beispielsweise Zellen in einem Konstrukt so positioniert werden können, dass diese zu einem gewebeähnlichen Knochenkonstrukt reifen können.

FRAGESTELLUNG Im letzten Jahrzehnt wurden einige technologische Fragestellungen im Bereich des Bioprintings gelöst. Für das Knochen-Tissue Engineering sind bisher allerdings nur wenige Ansätze präsentiert wurden. Dies liegt unter anderem daran, dass im Bioprinting vor allem Hydrogele verarbeitet werden. Diese sind allerdings sowohl chemisch, als auch mechanisch weit von natürlichem Knochengewebe entfernt und daher weniger als Knochenersatz geeignet.

In dieser Arbeit wurde daher untersucht, ob (Bio-)printing eine für Knochen-Tissue Engineering-Strategien geeignete Methode ist. Dazu wurden zwei vielversprechende Ansätze verfolgt:

(I) Mehrphasendruck von bioaktiven Calciumphosphatzementen in Kombination mit Zellen oder mit Wachstumsfaktoren funktionalisierten, biologisch aktiven Hydrogelen.

(II) Entwicklung einer neuen Bioink, indem ein wachstumsfaktor- oder zellbeladenes Hydrogel mit einem bioaktiven Füllstoff geblendet wird.

Die in der Doktorarbeit vorgestellten Studien sollen dabei insbesondere die Entwicklung dieser Ansätze darstellen, sowie deren Grenzen aufzeigen. Zusätzlich sollen grundlegende mechanische und biologische Eigenschaften der biogedruckten Knochenkonstrukte untersucht werden.

MATERIALIEN UND METHODEN Eine Technologie, die das Prinzip des Bioprintings ermöglicht, ist das sogenannte 3D-Plotten. Mit Hilfe eines Multikanal-Plotters können mehrphasige Konstrukte (Ansatz I), aber natürlich auch einphasige Konstrukte (Ansatz II) hergestellt werden. Für Ansatz I wurde ein klinisch zugelassener Calciumphosphatzement (CPC) als bioaktive Komponente verwendet. Für Ansatz II wurde ein bisher noch wenig erforschtes

Nanomaterial namens Laponit verwendet, welches großes Potential für das Tissue Engineering besitzt.

Die Biopolymeren Alginate und Methylcellulose bildeten die Grundlage für plottbare, wachstumsfaktor- und zellbeladene Pasten (Biomaterial-inks bzw. Bioinks). Zur Entwicklung einer spezifischen Bioink wurde humanes gefrorenes Frischplasma verwendet.

Die rheologischen Eigenschaften neu entwickelter Biomaterial-inks und Bioinks, sowie die mechanischen Eigenschaften der geplotteten Hydrogele wurden charakterisiert. Weitere Untersuchungen schlossen die Quellung der Hydrogele und die Porosität der Konstrukte ein. Ein besonderes Augenmerk wurde auf die Formgenauigkeit der geplotteten Strukturen gelegt.

Entsprechend der Untersuchungsansätze wurden verschiedene Zelltypen verwendet, insbesondere mesenchymale Stammzellen (MSC), die direkt mit der Paste verdruckt wurden. Als Modellwachstumsfaktor diente der angiogene *vascular endothelial growth factor* (VEGF). Dessen Freisetzung aus geplotteten Scaffolds wurde mittels ELISA überprüft; die biologische Aktivität wurde anhand des Wachstums von humanen Nabelschnurendothelzellen (HUVEC) untersucht.

ERGEBNISSE Zunächst wurde untersucht, ob Multikanal-Plotten geeignet ist, um CPC-Konstrukte patientenindividuell zu fertigen. Dies wurde mit Hilfe einer auflösbaren Methylcellulosepaste erreicht. Dieses Verfahren erlaubte die Herstellung von inneren Kavitäten, die mit anderen Herstellungsverfahren nicht möglich gewesen wären. Darüber hinaus konnte aus einem CT-Scan einer Hand ein Kahnbein extrahiert und virtuell modelliert werden, welches mit hoher Formgenauigkeit geplottet werden konnte. Es wurde gezeigt, dass dies auch auf biphasige Konstrukte aus CPC und einer Bioink anwendbar ist.

Dies wurde durch die Entwicklung und Verarbeitung von Bioinks ermöglicht. Biogedruckte Zellen können *in vitro* und *in vivo* spezifische biologische Effekte bewirken. Dazu wurden innerhalb der Arbeit zwei Bioinks als plottbare Zellträgermaterialien entwickelt. Eine Bioink enthielt das Nanomaterial Laponit (Ansatz II), welches bereits in anderen Studien vorteilhafte Effekte für Knochen-Tissue Engineering-Ansätze gezeigt hat. Die neuentwickelte Laponithaltige Bioink erlaubte die Fabrikation von Konstrukten mit hoher Formgenauigkeit. Darüber hinaus war die Zellviabilität, sowie die Zelldichteentwicklung erhöht im Vergleich zu einer Laponit-freien Kontrolle. Da Laponit eine heterogene Ladungsverteilung aufweist, wurde überprüft, inwieweit es ein geeignetes Freisetzungssystem für VEGF darstellt. Scaffolds, die aus einer VEGF-haltigen Paste hergestellt wurden, wiesen ein deutlich verändertes Freisetzungsprofil in Anwesenheit von Laponit auf, als Scaffolds ohne Laponit. So konnte eine initiale Freisetzung („Burstrelease“) vermieden und gleichzeitig eine gleichmäßige Freisetzung beobachtet werden. VEGF war auch nach längerer Zeit im Scaffold noch biologisch aktiv. Die zweite Bioink wurde auf Basis gefrorenen, menschlichen Frischplasmas entwickelt. Blutplasma enthält Fibrinogen, das eine RGD-Sequenz für die Anheftung von MSC besitzt. Biogedruckte MSC, aber auch präosteoblastäre Zellen, zeigten eine hohe Neigung, sich in der Bioink aufzuspreizen, was für eingekapselte Zellen erschwert ist. Die plasmahaltige Bioink war dazu geeignet, zusammen mit CPC zu biphasigen Konstrukten (Ansatz I) verarbeitet zu werden.

Dazu musste zunächst ein Postprozessierungsprotokoll für biphasige Konstrukte aus CPC und zellhaltigen Bioinks entwickelt werden. Aus vorherigen Studien ist bekannt, dass geplottete CPC-Konstrukte in wässrigen Lösungen Mikrorisse bilden, die die mechanischen Eigenschaften signifikant verschlechtern. Die Ausbildung der Mikrorisse kann durch eine Aushärtung in wasserdampfgesättigter Atmosphäre vermieden werden. In biphasigen Konstrukten mit Bioinks sollte diese Aushärtungsphase allerdings nur kurz sein, da eine lange Inkubation ohne wässrige Zellmedien zu einem Absterben der biogedruckten Zellen führen würde. Es konnte gezeigt werden, dass eine Inkubation für 20 min in wasserdampfgesättigter Atmosphäre ausreichend ist, um die Ausbildung von Mikrorissen im CPC zu vermeiden. Diese Zeitspanne konnte von den Zellen toleriert werden. In Kombination mit der plasmahaltigen Bioink wurde eine starke Proliferation und osteogene Reifung von biogedruckten präosteoblastären Vorläufern beobachtet.

SCHLUSSFOLGERUNGEN In der vorliegenden Doktorarbeit wurde das Prinzip des extrusionsbasierten Biodrucks (3D-Plotten) verwendet, um biofunktionelle Konstrukte herzustellen. Dies erfolgte entweder durch die Beladung mit Wachstumsfaktoren oder mit Zellen vor der Fabrikation der Konstrukte. Bioaktive Materialien wurden entweder durch Multikanal-Plotten oder durch Supplementierung einer Bioink eingebracht. Beide Ansätze können prinzipiell sogar miteinander kombiniert werden. Die erzielten Ergebnisse belegen, dass Bioprinting eine geeignete Methode für das Knochen-Tissue Engineering darstellt. Patientenindividualisierte Konstrukte können mit dieser Technologie gefertigt werden. Auf diesen Ergebnissen aufbauend können weitere Untersuchungen *in vivo* die Wirksamkeit der vorgestellten Ansätze überprüfen und neue Therapieansätze für die Heilung von Knochendefekten entwickelt werden.

CONTENTS

Abstract	9
Zusammenfassung	13
Index of Abbreviations	19
List of Figures	20
Preface	23

I GENERALIS

1 INTRODUCTION TO THE TOPIC	29
1.1 Background	29
1.2 Terminology	29
1.3 Physiological Properties of Bone Tissue	31
1.3.1 Composition of Bone	31
1.3.2 Bone Cytology	33
1.3.3 Crosstalk	34
1.4 Bone Grafting	34
1.4.1 Biopolymers	35
1.4.2 Calcium Phosphates	38
1.4.3 Nanoclays	41
1.5 Additive Manufacturing in Medicine & Bioprinting	43
1.5.1 Additive Manufacturing in Tissue Engineering	43
1.5.2 Bioprinting Techniques	44
1.6 Bioinks & Biomaterial Inks	48
1.6.1 Rheology	48
1.6.2 Plottability & Shape Fidelity	49
1.6.3 Post-Processing	52
1.6.4 Biocompatibility & Biodegradation	53
1.6.5 The Biofabrication Window	53
2 AIM OF THE THESIS	55
2.1 Preliminary Studies	55
2.2 Research Questions	57

II SPECIALIS

3 A METHYLCELLULOSE HYDROGEL AS SUPPORT FOR 3D PLOTTING OF COMPLEX SHAPED CALCIUM PHOSPHATE SCAFFOLDS	61
4 DEVELOPMENT OF A CLAY BASED BIOINK FOR 3D CELL PRINTING FOR SKELE- TAL APPLICATION	77
5 BIOPRINTING OF MINERALIZED CONSTRUCTS UTILIZING MULTICHANNEL PLOT- TING OF A SELF-SETTING CALCIUM PHOSPHATE CEMENT AND A CELL-LADEN BIOINK	97

6	A NOVEL PLASMA-BASED BIOINK STIMULATES CELL PROLIFERATION AND DIFFERENTIATION IN BIOPRINTED, MINERALIZED CONSTRUCTS	113
 III CONCLUSIO		
7	SUMMARY & CONCLUSION	133
7.1	Bioprinting of bone tissue constructs	133
7.2	Technological Improvements	134
7.3	Bioink Development	136
7.4	Limitations & Future Research Directions	138
 Bibliography		140
 Danke		155
 Appendix		
	Erklärungen zur Eröffnung des Promotionsverfahrens	165
	Erklärung über die Einhaltung gesetzlicher Bestimmungen	166
	Auszug aus dem Journal Citation Report	166
	Conferences	167

INDEX OF ABBREVIATIONS

ALP	Alkaline phosphatase
AM	Additive manufacturing
BSA	Bovine serum albumine
CAD	Computer-aided design
CAM	chorioallantoic membrane
CaP	Calcium phosphates
CPC	Calcium phosphate cement
DCPA	Calcium hydrogen phosphate
DOD	Drop-on-demand
FRESH	Freeform reversible embedding of suspended hydrogels
HAp	Hydroxyapatite
hBMSC	Human bone marrow stem cell
hMSC	Human mesenchymal stem cell
HUVEC	Human umbilical vein endothelial cell
Lap-alg-mc	Laponite-alginate-methylcellulose
PCL	Poly- ϵ -caprolactone
SLAM	Suspended layer additive manufacturing
SLS	Selective Laser Sintering
TCP	Tricalcium phosphate
VEGF	Vascular endothelial growth factor
2PP	Two photon polymerization
3DP	3D plotting

LIST OF FIGURES

Figure 1	Anatomic structure of bone tissue	32
Figure 2	Cells forming the bone environment	32
Figure 3	Structural formula of alginate	36
Figure 4	Structural formula of methylcellulose	37
Figure 5	Crystal structure of fibrinogen	37
Figure 6	Solubility of common CaP phases	39
Figure 7	Structure of Laponite	42
Figure 8	Vision of biomedical additive manufacturing	43
Figure 9	Additive manufacturing technologies allowing bioprinting	45
Figure 10	Principle of three-dimensional multichannel plotting	47
Figure 11	General behavior of materials exposed to shear stress over time . .	50
Figure 12	Development of the shear stress during increasing shear rates . . .	50
Figure 13	The Biofabrication window	54
Figure 14	Performance of plotted nanoclay-based constructs in a CAM model	95
Figure 15	Nanoclay-based constructs foster bone formation.	95

PREFACE

LIST OF PUBLICATIONS OF THIS THESIS

The following peer-reviewed articles are the results of this thesis. All the work is published under my birth name *Tilman Ahlfeld*.

Chapter 3

Ahlfeld T, Köhler T, Czichy C, Lode A, Gelinsky M. 2018. A Methylcellulose Hydrogel as Support for 3D Plotting of Complex Shaped Calcium Phosphate Scaffolds. *Gels* 4:68.

Chapter 4

Ahlfeld T*, Cidonio G*, Kilian D, Duin S, Akkineni AR, Dawson JI, Yang S, Lode A, Oreffo ROC, Gelinsky M. 2017. Development of a clay based bioink for 3D cell printing for skeletal application. *Biofabrication* 9:034103.

Chapter 5

Ahlfeld T, Doberenz F, Kilian D, Vater C, Korn P, Lauer G, Lode A, Gelinsky M. 2018. Bioprinting of mineralized constructs utilizing multichannel plotting of a self-setting calcium phosphate cement and a cell-laden bioink. *Biofabrication* 10:045002.

Chapter 6

Ahlfeld T*, Cubo-Mateo N*, Cometta S, Guduric V, Vater C, Bernhardt A, Akkineni AR, Lode A, Gelinsky M. 2020. A Novel Plasma-Based Bioink Stimulates Cell Proliferation and Differentiation in Bioprinted, Mineralized Constructs. *ACS Appl Mater Interf* 12:12557-12572.

**Equal first-authorship*

Supplementary data to the articles can be found at the respective corresponding homepages.

INDIVIDUAL CONTRIBUTIONS TO THE MANUSCRIPTS

In the first manuscript, described in chapter 3, TA conceptualized the experiments, performed the rheological tests, investigated the extrusion behavior and shape fidelity assessment and performed the experiments regarding plotting of cavities and anatomical models. All analysis was performed by TA. Manuscript writing, editing and revising was performed by TA.

Next, in the manuscript of chapter 4, TA developed the novel bioink together with Dr. Gianluca Cidonio and performed rheology, plotting tests and SEM as well as EDX analysis. The swelling behavior and growth factor release studies were performed by TA with the assistance of Dr. Ashwini Rahul Akkineni. Cell viability studies were performed in equal parts by TA and GC. Manuscript writing, data analysis, editing and revising were done in equal parts by TA and GC.

The following experiments, presented in the manuscript that represents chapter 5, were performed by TA: Multichannel plotting, SEM and stereo light microscopy, mechanical testing, development of the osteochondral model. Cell tests were performed by Falko Doberenz (a student, supervised by TA); analysis of the cell tests was done by TA. Manuscript writing, data acquisition, editing and manuscript revision were performed by TA.

In the manuscript of chapter 6, Nieves Cubo created the plasma-based bioink and performed initial printing tests. Investigations on rheology and shape fidelity as well as the study of cell viability and spreading were performed in equal parts by TA and NC. Biphasic plotting of plasma-alg-mc and CPC and analysis of the structures without cells (swelling tests, morphology) and with cells (studies on cell viability over time) were performed together by NC and TA. Biochemistry was performed by TA. TA and NC wrote the major and essential parts of the manuscript. Data acquisition and editing as well as manuscript revision were performed by TA and NC.

FURTHER PUBLICATIONS

The following chronologically ordered list contains only peer-reviewed articles.

- Akkineni AR, **Ahlfeld T**, Lode A, Gelinsky M. 2016. A versatile method for combining different biopolymers in a core/shell fashion by 3D plotting to achieve mechanically robust constructs. *Biofabrication* 8:045001.
- Akkineni AR, **Ahlfeld T**, Funk A, Waske A, Lode A, Gelinsky M. 2016. Highly concentrated alginate-gellan gum composites for 3D plotting of complex tissue engineering scaffolds. *Polymers* 8:170.
- Ahlfeld T**, Akkineni AR, Förster Y, Köhler T, Knaack S, Gelinsky M, Lode A. 2017. Design and fabrication of complex scaffolds for bone defect healing: combined 3D plotting of a calcium phosphate cement and a growth factor-loaded hydrogel. *Ann Biomed Eng* 45:224-236.
- Kilian D, **Ahlfeld T**, Akkineni AR, Lode A, Gelinsky M. 2017. Three-dimensional bioprinting of volumetric tissues and organs. *MRS Bull* 42:585–592.
- Seidel J, **Ahlfeld T**, Adolph M, Kümmritz S, Steingroewer J, Krujatz F, Bley T, Gelinsky M, Lode A. 2017. Green bioprinting: extrusion-based fabrication of plant cell-laden biopolymer hydrogel scaffolds. *Biofabrication* 9:045011.
- Braham MV, **Ahlfeld T**, Akkineni AR, Minnema MC, Dhert WJ, Öner FC, Robin C, Lode A, Gelinsky M, Alblas J. 2018. Endosteal and perivascular subniches in a 3D bone marrow model for multiple myeloma. *Tissue Eng Part C Methods* 24:300–312.
- Ahlfeld T**, Schuster FP, Förster Y, Quade M, Akkineni AR, Rentsch C, Rammelt S, Gelinsky M, Lode A. 2019. 3D plotted biphasic bone scaffolds for growth factor delivery: biological characterization in vitro and in vivo. *Adv Healthc Mater* 8:1801512.

- Bolte J, Vater C, Culla AC, **Ahlfeld T**, Nowotny J, Kasten P, Disch AC, Goodman SB, Gelinsky M, Stiehler M, Zwingenberger S. 2019. Two-step stem cell therapy improves bone regeneration compared to concentrated bone marrow therapy. *J Orthop Res* 37:1318-1328.
- Duin S, Schütz K, **Ahlfeld T**, Lehmann S, Lode A, Ludwig B, Gelinsky M. 2019. 3D Bioprinting of functional islets of langerhans in an alginate/methylcellulose hydrogel blend. *Adv Healthc Mater* 8:1801631.
- Hodder E, Duin S, Kilian D, **Ahlfeld T**, Seidel J, Nachtigall C, Bush P, Covill D, Gelinsky M, Lode A. 2019. Investigating the effect of sterilisation methods on the physical properties and cytocompatibility of methyl cellulose used in combination with alginate for 3D-bioplotting of chondrocytes. *J Mater Sci Mat Med* 30:10.
- Nowotny J, Bischoff F, **Ahlfeld T**, Goronzy J, Tille E, Nimtschke U, Biewener A. 2019. Biomechanical comparison of bi-and tricortical k-wire fixation in tension band wiring osteosynthesis. *Eur J Med Res* 24:33.
- Richter RF, **Ahlfeld T**, Gelinsky M, Lode A. 2019. Development and Characterization of Composites Consisting of Calcium Phosphate Cements and Mesoporous Bioactive Glass for Extrusion-Based Fabrication. *Materials* 12:2022.
- Ahlfeld T**, Guduric V, Duin S, Akineni AR, Schütz K, Kilian D, Emmermacher J, Cubo-Mateo N, Dani S, von Witzleben M, Spangenberg J, Abdelgaber R, Richer RF, Lode A, Gelinsky M. 2020. Methylcellulose – a versatile printing material that enables biofabrication of tissue equivalents with high shape fidelity. *Biomater Sci* 8:2102-2110.
- Cidonio G, Glinka M, Kim YH, Kanczler JM, Lanham SA, **Ahlfeld T**, Lode A, Dawson JI, Gelinsky M, Oreffo ROC. 2020. Nanoclay-based 3D printed scaffolds promote vascular ingrowth ex vivo and generate bone mineral tissue in vitro and in vivo. *Biofabrication* 12:035010.
- Kilian D, **Ahlfeld T**, Akkineni AR, Bernhardt A, Gelinsky M, Lode A. 2020. 3D Bioprinting of osteochondral tissue substitutes – in vitro-chondrogenesis in multilayered mineralized constructs. *Sci Rep* 10:8277.
- Korn P, **Ahlfeld T**, Lahmeyer F, Kilian D, Sembdner P, Stelzer R, Pradel W, Franke A, Rauner M, Range U, Stadlinger B, Lode A, Lauer G, Gelinsky M. 2020. 3D Printing of Bone Grafts for Cleft Alveolar Osteoplasty – In vivo Evaluation in a Preclinical Model. *Front Bioeng Biotechnol* 8:217.
- Hattab G, **Ahlfeld T**, Klimova A, Koepp A, Schuerer M, Speidel S. 2020. Uniaxial compression testing and Cauchy stress modeling to design anatomical silicone replicas. *Sci Rep* 10:11849.

LEGAL NOTE The articles are republished in form of this thesis with permission of the publishers. All copyrights of the articles remain at the publishers, if not stated differently. This means that IOP Publisher holds the copyrights of the chapters 4&5 and the American Chemical Society (ACS) holds the copyright of chapter 6. Permission for re-use must be addressed directly to the publisher. Chapter 3 is published as open access article with a CC BY 4.0 license.

Part I

GENERALIS

INTRODUCTION TO THE TOPIC

1.1 BACKGROUND

Bones act as stabilizing structure within the human body and have the function to bear mostly all mechanical load in order to protect other tissues and organs from damage. The number of bone fragility fractures resulting especially from osteoporosis has been determined as 765,000 in Germany and 2.65 million in the 6 largest countries of the European Union (EU6) in 2017.(Foundation, 2017a; Foundation, 2017b) The costs for treatment of such fractures were estimated as €11.3 billion (Germany) and €37.5 billion (EU6). Changes in the age distribution of the european societies cause an increase of the number of osteoporosis diseases and thus also an increase of fragility fractures and traumas. Therefore one can estimate the urgent demand for novel bone grafting therapies.

Although exceptional progress has been made in the field, the gold standard for all kind of bone defect therapies still is autologous bone. However, such autografts are clearly limited in availability and harvesting is connected with donor site morbidity. Next to autografts, there are allografts (from other human beings) and xenografts (from animals; use is only allowed after harsh treatment that greatly reduces the suitability of xenografts). The use of allografts and xenografts poses ethical problems and there is a risk of disease transmission, rejection and immune reactions.

Due to these reasons, the development of novel, synthetic, bioresorbable bone grafts is from major interest for regenerative therapies. The technology of 3D printing offers great advantages tackling several problems of more traditional methods to produce such implants. In this doctoral thesis, various approaches were investigated demonstrating why bioprinting can be a real alternative for the manufacturing of bone constructs. The following chapter will briefly introduce important aspects for the research presented in this thesis. Firstly, the hierarchical structure of bone as well as its cells are described, followed by an introduction of the concept and challenges of bone grafting including a brief description of the biomaterials which were used in this work. Then the technology of extrusion based (bio-)printing, called (bio-)plotting, and theoretical considerations for the development of plottable bioinks and biomaterial inks are discussed.

1.2 TERMINOLOGY

Bioprinting has been established as a technique attracting attention not only in academia, but also in a wider, more general, audience. This led to an ambiguous use of the term 'bioprinting'. Therefore, leading researchers tried to establish a guideline to terminology to distinguish state-of-the-art additive manufacturing techniques from bioprinting technologies.

The following definitions aim to introduce the terminology which is important for this work, as proposed by MORONI *et al.* and GROLL *et al.* (Groll et al., 2016; Moroni et al., 2018; Groll et al., 2018). The listed definitions undergo a perpetual change, therefore the manuscripts of this thesis do not take usage of this terminology consistently, but were related to the actual definitions at the time point of the writing process. Nevertheless, for parts I and III of this thesis, the following terminology was set.

BIOFABRICATION The term *Biofabrication* describes the scientific field at the cross section of regenerative medicine and tissue engineering, mechanical engineering, biology, material science and chemistry. Whenever structures of cells, bioactive molecules, biomaterials or a combination of those get fabricated in a predefined form by an automated process, the final result generally is contributed to the Biofabrication research field. (Groll et al., 2016; Moroni et al., 2018)

BIOPRINTING In the field of Biofabrication, two main principles are the blueprint for several fabrication techniques: bioassembly and bioprinting. Bioassembly is defined as the automated fabrication of cell aggregates with or without carriers. In contrast, the principle of bioprinting involves the automated generation of hierarchically organized structures consisting of biomaterials and cells suspended within for this purpose suitable biomaterial matrices. (Moroni et al., 2018) For example, additive manufacturing processes like powder printing, followed by sintering or selective laser melting would destroy sensitive substances and therefore, at present, cannot be counted as techniques allowing the principle of bioprinting.

3D PLOTTING & BIOPLOTTING 3D plotting, also known as microextrusion printing, robotic casting or direct ink writing, is a technique allowing bioprinting. Analogous to the definition of bioprinting, it is often called bioplotting when cells or growth factors are processed. It is the low-temperature form of extrusion-based additive manufacturing. By CAD-CAM driven principles, a pasty material is extruded through a nozzle onto a plotting stage. In most cases, the fabricated structure must be post-processed.

BIOINK & BIOMATERIAL INK A bioink is a printable material containing cells, which can be processed by bioprinting technologies. A similar, but cell-free, material which might contain biological active substances such as proteins or growth factors is defined as a biomaterial ink. (Groll et al., 2018)

BIOACTIVITY & BIOLOGICAL ACTIVITY *Bioactivity* is defined as the ability of a biomaterial to enable precipitation of hydroxyapatite crystals on its surface in simulated body fluids or after implantation. In contrast, the term *biological activity* describes the ability of materials, degradation products, proteins or growth factors to evoke a specific cellular response. The biological activity is also referred to as *biofunctionality*.

1.3 PHYSIOLOGICAL PROPERTIES OF BONE TISSUE

The following sections give a brief and general overview about the physiology of bone and were written with the help of the references (Jerosch et al., 2002; Schumacher, 2015; Hing, 2004).

1.3.1 *Composition of Bone*

Bone is a hierarchically organized tissue. It is composed of organic matrix (30 wt-%), which mainly consists of collagen-I fibers. The other main component is inorganic matrix (70 wt-%), which is mainly composed of calcium and phosphate ions forming a hexagonal hydroxyapatite (HAp) crystal (Fig. 1 A). This crystal can be complemented or/and substituted by various other ions such as Na^+ , K^+ , CO_3^{2-} , Cl^- or F^- . Native bone HAp is a calcium-deficient phase.

Unlike other skeletal tissues such as cartilage, bone constantly reorganizes itself and has a high self-healing capacity. In an early stadium of bone development, i.e. in fetal development, an unordered and random form of bone tissue is formed, which is called woven bone (Figure 1 B, red). Woven bone is characterized by a random orientation of the collagen fibers which are mineralized by HAp crystals. This form of bone usually can be found during callus formation. The woven bone is very porous. Due to interactions of bone-forming and bone-resorbing cells (see section 1.3.2), the bone matrix, including the collagen fibers and the HAp crystals, is newly formed into concentric layers (Figure 1 B, blue), resulting in a more organized and anisotropic structure, which is called lamellar bone. The concentric layers surround small channels (HAVERSIAN canals), which contain a blood vessel and a nerve. The HAVERSIAN canals are connected with each other by smaller VOLKMANN canals. A single unit of the new mineralized, concentric layers, the HAVERSIAN canal and the included vessels and nerves, is called osteon (Figure 1 C). Within the osteon, all relevant bone cells, like osteoblasts, osteoclasts, osteocytes and their precursor cells are located. The orientation of the mineralized collagen fibers in the lamellae, and thus of the entire osteon, is dependent of the mechanical load applied to the bone tissue. Due to this reason, the mechanical properties of native bone cannot be estimated easily as every bone of the human body exhibits various lines of force.

On a larger scale, one distinguishes between two types of bone: the compact bone (*corticalis*) and the cancellous bone (*spongiosa*, Figure 1 D). The compact bone embraces the cancellous bone with the bone marrow. It is located directly in contact to the periosteum and demonstrates a rather dense structure which is interspersed by the osteons and the HAVERSIAN and VOLKMANN canals. Even though the volume of the compact bone is distinctly smaller than the volume of the cancellous bone, more than 80 wt-% of the entire bone mass can be accounted for it. The cancellous bone appears very porous and is characterized by a sponge-like structure composed of the so-called trabeculae. The pores of the cancellous bone contain the bone marrow with haematopoietic stem cells, which are substantial for the formation of the blood system

Figure 1. Anatomic structure of bone. **A:** Hexagonal elemental cell of hydroxyapatite. Adapted from (Rujitanapanich et al., 2014) with permission of the publisher. **B:** Conversion of woven bone to lamellar bone. Adapted from (Jerosch et al., 2002), permitted by German law. **C:** Structure of an osteon. Adapted from (Jerosch et al., 2002), permitted by German law. **D:** General composition of a bone including compact and cancellous bone as well as the bone marrow. Adapted from (Britannica, 2012) in accordance to the Terms of use.

Figure 2. The cells forming the bone tissue originate from the mesenchymal (osteoblasts and osteocytes) or the hematopoietic (osteoclasts) stem cell lineage. Adapted from (Jerosch et al., 2002), permitted by German law.

1.3.2 *Bone Cytology*

The mineralized bone tissue contains three different bone-specific cell types as well as their progenitors: osteoblasts, osteoclasts and osteocytes (Figure 2). All three cell types are communicating with each other; the so-called crosstalk is crucial for the formation and resorption of the bone tissue. This section was written with help of the references (Jerosch et al., 2002; Hing, 2004; Florencio-Silva et al., 2015)

Osteoblasts

Osteoblasts are matured cells of the mesenchymal lineage. The mononuclear cells have a size of approx. 20 μm and take up the function of the synthesis of new bone (osteogenesis). The osteoblasts can be found at the inner walls of the HAVERSIAN canals (see Figures 1 C and 2) and on the surface of the trabeculae, where they secrete the organic matrix of the bone, especially collagen-I. After synthesis of this extracellular matrix, which is called osteoid, the osteoblasts express the enzyme alkaline phosphatase (ALP). The ALP provides a high amount of phosphate ions, which precipitate in presence of calcium ions to calcium phosphate mineral phases transforming into nanocrystalline HAp. Thus, the ALP activity of osteoblast-like cells can be investigated to analyze early stages of bone formation.

Osteocytes

Once an osteoblast has filled its entire surrounding environment with mineralized matrix, it is transforming into an osteocyte. Osteocytes are remaining in the mineralized matrix and have a dendritic morphology, which enables them to take part on the crosstalk between the cells. Although the role of osteocytes and their function is not completely understood, it can be assumed that they are crucial for observing mechanical stimuli which allow them to secrete signaling molecules through the lacunar-canalicular network towards osteoblasts and osteoclasts. The signaling molecules strongly influence the activity of osteoblasts and osteoclasts and thus osteocytes are crucial for bone development.

Osteoclasts

Osteoclasts are multinuclear cells which are differentiated from monocytes or macrophages and belong to the hematopoietic lineage (Figure 2). The size of osteoclasts is up to 100 μm . They are mainly located at the interface of the HAVERSIAN canal and the mineralized matrix as well as on the trabeculae and act as bone-resorbing cells (osteolysis). At this interface, the osteoclasts adhere by formation of the so-called ruffled border, which is a membrane demonstrating a high surface area. Osteoclasts are able to seal the area they are attaching to. After the sealing, protons are pumped from the ruffled border to the underlying mineralized matrix which is dissolved in the acidic environment. Afterwards, the collagen matrix is degraded enzymatically. The dissolved ions are intracellularly metabolized by the osteoclast or get transported through the membrane to the surrounding environment. The resorbed area of the bone is called lacuna.

1.3.3 Crosstalk

The three types of bone cells are sending 'signals' to each other resulting in a mutual regulation called crosstalk.(Matsuo, 2009) This results in the bone remodeling process, which describes the perpetual balanced formation and resorption of bone tissue. Generally, bone cells model the bone tissue according to the load to which it is exposed.(Jerosch et al., 2002) In this case, the bone cells are able to secrete signaling molecules which enhance or impair the functionality of the other cell types. For example, osteoblasts induce the differentiation from monocytes to osteoclasts by secretion of factors like the *receptor activator of nuclear factor κ B ligand* or the *macrophage colony stimulating factor*, which when start to resorb bone tissue. Osteoclasts are able to secrete osteoblast-stimulating growth factors such as bone morphogenetic proteins,(Garimella et al., 2008) which stimulate the proliferation and differentiation of osteoblasts which subsequently form bone tissue. A specific role play osteocytes which sometimes are called the 'mechanosensors' or 'coordinators' of bone remodeling. They experience the change of the mechanical load on the bone tissue by sensing pressure changes in the lacunar-canalicular network and are able to secrete growth factors which trigger or inhibit the activity of osteoblastic and osteoclastic cells such as sclerostin.(Wijenayaka et al., 2011; Thouverey & Caverzasio, 2015) A brief overview about these processes is given in a review by Matsuo.(Matsuo, 2009)

1.4 BONE GRAFTING

Non-Degradable and Degradable Biomaterials

The application of a specific bone graft is dependent on its performance in the human body. Over the last century, researchers developed a range of biocompatible materials for bone replacement including all three material classes such as metals, ceramics and polymers. The load the graft has to bear as well as the lifetime of the implant are crucial parameters for the selection of the biomaterial. For example, a hip implant favorably consists of a non-degradable metal with a high lifetime such as titanium, which is able to withstand high mechanical loads. In contrast many injuries are related to fractures in body regions which do not bear disproportionally much load and the self-healing potential of bone can be supported to enable the regrowth of native bone tissue. For this, a broad range of biodegradable materials such as thermoplastic polymers (e.g. poly- ϵ -caprolactone or polylactic acid), metals (e.g. iron foams or magnesium alloys), bioactive ceramics (e.g. bioactive glasses) or hydrogels (e.g. polyvinyl alcohol or poly N-isopropyl acrylamide) were investigated on their potential to act as bone substitutes. These biodegradable materials undertake some anatomical functions as well as physical and mechanical tasks for a specific time but degrade in favor of regrowing bone tissue. Non-degradable and degradable biomaterials and their very different properties were reviewed comprehensively elsewhere.(García-Gareta et al., 2015; Qu et al., 2019; Pereira et al., 2020) All biodegradable materials interact with bone cells and can be biofunctionalized with growth factors and thus could be implemented into a

tissue engineering process, as proposed by LANGER and VACANTI.(Langer & Vacanti, 1993) In this thesis, biodegradable biopolymers, calcium phosphates and a nanoclay were utilized for bone tissue engineering and are explained in detail in the following sections.

1.4.1 *Biopolymers*

Biopolymers are polymers which are synthesized by living beings, such as algae and plants, but also bacteria or mammals including human beings. This leads to materials of high biocompatibility making them interesting for their use in tissue engineering. As every individual differs, also the synthesized polymers differ in general properties such as molecular weight or chain length. This leads to an unpredictability of the behavior of biopolymers and should be mentioned as clear limitation of their usage. However, although this unpredictability is a critical issue, several biopolymers could be characterized thoroughly and are widely understood on their biological as well as their physical and chemical performance. The performance of biopolymers in bone tissue engineering and the development of biopolymer hydrogel bioinks were reviewed recently.(Gelinsky, 2018; Kashirina et al., 2019; Witzler et al., 2019)

Some biopolymers can be hydrated to a great extent and form, in presence of crosslinks, hydrogels. Biopolymers which do not bind water, but are exposed to an aqueous environment, assemble themselves into stable structures; for example cellulose forms a fibrillar, insoluble structure. Biopolymers are distinguished by each other by the nature of their binding properties, for example proteins are forming amide (peptide) bonds whereas polysaccharides form glycosidic bonds. In this work, polysaccharidic biopolymers were used (alginate and methylcellulose). In chapter 6 human blood plasma containing the protein fibrin was used as a main component for a bioink. These biopolymers are briefly introduced in the following section.

ALGINATE Alginate is synthesized by brown algae as structural element of their cell walls. The chemical structure is shown in Figure 3. It is a linear copolymer with blocks of β -D-mannuronate (M) and α -L-guluronate (G) residues which are linked between the 1 and 4 positions.(Lee & Mooney, 2012) Both, M and G blocks are arranged consecutively or alternating. The M:G ratio was shown to influence the main properties of alginate.(Lee & Mooney, 2012) It is generally assumed that the G blocks coordinate divalent ions (such as Ca^{2+} , Sr^{2+} , Ba^{2+} or Mg^{2+}). Although those ions are chemically rather similar, the crosslinking mechanism and resulting physical and biological effects seem to strongly depend on the ionic radius (Mørch et al., 2006; Topuz et al., 2012). In case of alginate, the divalent ions act as junctions for the polymer chains which when assemble in an eggbox structure leading to a crosslinked hydrogel.(Sun et al., 2012)

Its highly biocompatible nature as well as its ability to store water while increasing viscosity make alginate interesting for encapsulation of either growth factors or living cells. Encapsulated biological substances can be released from the alginate structure setting it in the field of drug delivery systems.(Jain & Bar-Shalom, 2014) Thus, many groups have investigated

the feasibility to use alginate as a material for bone tissue engineering.(Venkatesan et al., 2015) Its wide malleability as well as its versatile structurability are additionally from interest for bone tissue engineering. For example, the gelation process of alginate was modified resulting in an ionotropic gelation process, which led to the formation of anisotropic orientated channels which are interesting for nutrient supply and vascularization.(Despang et al., 2005) Cellular studies with rat bone marrow stem cells revealed that the cellular response to alginate gels is strongly dependent on the M:G ratio.(Wang et al., 2003)

Since the mechanical properties of alginate do not meet the criteria for bone tissue, it was investigated how composites of calcium phosphates and alginate may act as bone substitutes. For example, dental pulp stem cells were able to express osteogenic markers and promoted calcium deposition on alginate/HAp composites, which are signs for differentiation into osteoblasts (Sancilio et al., 2018). Furthermore, blends like oxidized alginate (known as alginate-dialdehyde) and gelatin were shown to promote both, physical and biological properties, bringing the alginate-based scaffolds closer to the required properties of bone substitutes.(Sarker et al., 2015; Sarker et al., 2016)

Figure 3. Structural formula of alginate.

METHYLCELLULOSE Methylcellulose is a water-soluble derivate of cellulose, where several hydrogen atoms of hydroxyl groups of pure cellulose are exchanged by methyl groups. In pure cellulose, the hydroxyl groups form hydrogen bonds, which hinder water molecules to penetrate the cellulose fibres. Due to the introduction of the methyl groups, those hydrogen bonds get disturbed and water molecules can enter inbetween the molecular chains.(Thirumala et al., 2013; Nasatto et al., 2015b) Methylcellulose is a thermogelling polymer, which is in sol state at low temperatures and gel state in high temperatures.(Nasatto et al., 2015a) The applicability of methylcellulose for medical engineering including tissue engineering and additionally for bioprinting was recently reviewed (Sannino et al., 2009; Ahlfeld et al., 2020). The methylcellulose macromolecule is composed of β -(1 $\rightarrow$ 4)-linked D-glucose units (Figure 4).

Methylcellulose is biologically inert, thus it is not expected to enhance bone formation in tissue engineering applications; in contrast it is also not expected to interfere with it. However, it could be shown that a blend of methylcellulose and silk fibroin has a bioactive character because it allowed the precipitation of HAp crystals in simulated body fluid on its surface.(Narayanan & Sumathi, 2019) In another study, a bioceramic powder was successfully mixed with a blend of methylcellulose, gelatin and citric acid. The composite material showed injectable properties and enhanced degradation rates in presence of the bioceramic powders in comparison to the negative controls.(Demir Oğuz & Ege, 2018)

Figure 4. Structural formula of methylcellulose with a degree of substitution of 2.

Finally, an injectable composite of calcium phosphate nanoparticles and methylcellulose demonstrated bone formation in an *in vivo* study.(Kim et al., 2018)

FIBRINOGEN & FIBRIN Next to polysaccharides, there are hydrogel-forming proteins. Amongst others, fibrin and its pre-assembled form fibrinogen belong to the most important proteins produced by mammals. Fibrinogen is a glycoprotein, which is described to consist of two D-domains which are connected by an E-domain.(Laurens et al., 2006) Fibrinogen is produced by hepatocytes in the liver and is assembled from several polypeptide chains (called fibrinogen α -, β - or γ -chains, Figure 5). After an injury, a fibrin clot is formed which is non-soluble and has the function to stop bleeding by blood clotting. In this case, positively charged calcium ions congregate negatively charged proteins, especially prothrombin and thrombocinase. Thrombocinase transforms prothrombin into thrombin which cleaves the fibrinogen molecules which then assemble into fibrin fibrils. Afterwards the fibrin stabilizing factor, an enzyme which is activated by both, thrombin and calcium ions, forces the formation of covalent bonds between the fibrin fibrils constituting in a strong polymer network.(Palta et al., 2014; Weisel & Litvinov, 2017) The fibrin clots are degraded enzymatically by plasmins (a process called fibrinolysis).(Mosesson, 2005; Weisel & Litvinov, 2017) Both, blood clotting and fibrinolysis are in a balanced state in healthy human beings. In a non-balanced state, thrombosis or exceeded bleeding occur. Thus fibrinogen and fibrin play a crucial role in the wound healing process.(Laurens et al., 2006)

Figure 5. Crystal structure of fibrinogen. Cyan: fibrinogen α chain, red: fibrinogen β chain, pink: fibrinogen γ chain, yellow: disulfide bonds, blue: fibrinogen α chain with C-domain which holds a RGD motif for cell attachment.

Since fibrin(ogen) offers binding motifs for various cell types, including mesenchymal stem cells, endothelial cells and, crucial for bone development, osteoblasts, it offers high potential for bone tissue engineered applications.(Ode et al., 2010) Recently, four different application forms of fibrin for bone tissue engineering have been identified: beads, pre-formed

scaffolds, coatings and injectable hydrogels.(Noori et al., 2017) For example, commercially produced and clinically approved fibrin glue enhanced the performance of an autograft in an alveolar cleft in human patients.(Segura-Castillo et al., 2005) However, since the mechanical properties of fibrin gels and their fast degradation properties do not allow a sufficient bone healing of complex shaped, critical defects, a monophasic fibrin gel is not considered to be useful for bone tissue engineering purposes.(Noori et al., 2017)

1.4.2 Calcium Phosphates

Calcium phosphates (CaP) belong to the class of ceramic biomaterials, which are highly biocompatible. CaP are bioactive, that means that they allow the precipitation of HAP crystals on their surface. Further, most CaP-based materials are biodegradable and can be metabolized by osteoclasts.(Detsch et al., 2010; Bernhardt et al., 2014; Sheikh et al., 2015) This is attributed to their chemical similarity to the mineral phase of bone tissue, however the crystal size must be considered (nano-sized CaP crystals have shown a good osteoclastic resorption, whereas micron-sized crystals seem to be limited in their resorbability) (Detsch et al., 2010; MacMillan et al., 2014). CaP phases can be categorized by their stoichiometry (the molar ratio of calcium to phosphorus ions [Ca/P]) or their solubility.(Dorozhkin, 2007) The solubility of CaP phases is not just dependent on the stoichiometry, but also on the pH-value and the temperature, as depicted in Figure 6.(Chow, 2001) A comprehensive review of the different CaP phases was provided by Dorozhkin (Dorozhkin, 2015) and Schumacher (Schumacher, 2015). In the following, the CaP phases α -tricalcium phosphate, calcium hydrogen phosphate and HAP are discussed due to their significance for this thesis.

α -TRICALCIUM PHOSPHATE There are two forms of tricalcium phosphates (TCP): α - and β -TCP. They are prepared by thermal decomposition of calcium-deficient hydroxyapatite or acid-base reactions between acidic calcium phosphate phases and bases like CaO.(Dorozhkin, 2015) TCP-phases are formed when the Ca/P ratio is 1.5. For the formation of β -TCP a temperature above 800 °C is necessary and for the formation of the α -phase a temperature above 1200 °C is required. However, in presence of other ions, those temperatures can be decreased.(Dorozhkin, 2015) The difference between the α - and β -phase is the volume of the crystal structure.(Goto & Katsui, 2015) This results in different solubilities/stabilities, although both phases are better soluble compared to other CaP phases.(Schumacher, 2015) In aqueous solutions, α -TCP is more reactive and will be quickly hydrolyzed to calcium-deficient HAP.(Dorozhkin, 2011)

CALCIUM HYDROGEN PHOSPHATE Calcium hydrogen phosphate exists in an anhydrous and in a hydrated form. It is also known under the name dicalcium phosphate anhydrous or dihydrate (DCPA or DCPD; their minerals are called monetite and brushite, respectively). Both phases are even better soluble in aqueous solutions than TCP.(Schumacher, 2015) The Ca/P ratio is 1.0. DCPD is formed in a solution of this Ca/P ratio, DCPA is formed when

Figure 6. Solubility of common CaP phases. HAp - hydroxyapatite, TTCP - tetracalcium phosphate, β -TCP - β -tricalcium phosphate, α -TCP - α -tricalcium phosphate, OCP - octacalcium phosphate, DCPA - calcium hydrogen phosphate anhydrous, DCPD - calcium hydrogen phosphate dihydrate. Adapted and modified from (Chow, 2001).

the temperature of this solution is above 90 °C.(Dorozhkin, 2015) Both, DCPA and DCPD are known for a long time to initiate HAp formation.(Ishikawa & Eanes, 1993)

HYDROXYAPATITE Hydroxyapatite (HAp) is the least soluble phase of all CaP phases at the physiological pH range. It has a Ca/P ratio of 1.67.(Schumacher, 2015) Its crystal structure is monoclinic, however already small impurities favor the formation of a more hexagonal HAp structure.(Dorozhkin, 2015) Due to this reason, also native HAp is hexagonal.(Dorozhkin, 2015; Rujitanapanich et al., 2014) There is a calcium-deficient variant of HAp with a Ca/P ratio of 1.5-1.67 and thus a higher solubility. HAp with a Ca/P ratio of 1.67, which is not calcium-deficient, can only be achieved at synthetic environmental conditions (90 °C, pH>10).(Markovic et al., 2004) HAp is highly bioactive and osteoconductive. Further, nanocrystalline calcium-deficient HAp was shown to be bioresorbable by osteoclasts which means that it is embedded into the bone remodelling process.(Bernhardt et al., 2014) However, the resorption of HAp is usually considered to be too slow for bone tissue engineered applications.(Thormann et al., 2013; Korn et al., 2020) Calcium-deficient HAp usually is formed by hydrolysis of other CaP, which dissolve, precipitate and re-precipitate according to the environmental pH until the most stable and least soluble phase, provided that the Ca/P ratio is 1.5-1.67.(Dorozhkin, 2015)

Calcium Phosphate Cements

Calcium phosphate cements (CPC, abbreviation will be used for both, singular and plural) are formulations of one or more CaP phases and additional more materials which spontaneously undergo a transformation process in presence of aqueous solutions. The spontaneous transformation process is called self-setting process, thus the CPC formulations are commonly named self-setting CPC. (Xu et al., 2017) The CaP powders (called precursors) are mixed together with the aqueous solution (e.g. water) and form a pasty material until the setting process has been finished. At this stage, the pasty character of the cement formulation has been changed to a more solid character. Due to the time-dependent reactions of CaP phases, which precipitate, hydrolyze and re-precipitate endless until the most insoluble condition is reached, the cement setting is characterized by the initial and final setting time, which represent the times after which the setted cement bears certain loads (following the standard ASTM C266-04) (ASTM, 2004). Nevertheless, a full setting will only occur when an equilibrium state has been reached, which should take longer than the initial and final setting time. The entire setting process, including the chemical reactions, hardening, crystallization and formation of the final reaction products, is mainly dependent on the pH-value. At $\text{pH} > 4.2$, including the physiological pH of 7.4, the most insoluble phase is HAp, but at a $\text{pH} < 4.2$ the most insoluble phase is brushite (DCPD). (Chow, 2001) Due to that reason it is common to differ between HAp- and brushite-forming CPC. (Dorozhkin, 2011)

The clinical application of CPC is usually the injection through the needle or a syringe, in example for treatment of vertebral fractures by kyphoplasty. (Lode et al., 2018) Thus, the injectability of CPC is one of the main properties. (Bohner & Baroud, 2005; O'Neill et al., 2017) The injectability is defined by the force needed to press the cement formulation through the needle. The setting of the CPC leads to an increase of the force impairing the injectability. Latest after the final setting time, a CPC applies as non-injectable. During setting in a needle, the effect of filter-pressing takes place. (Bohner & Baroud, 2005) By precipitation of insoluble CaP phases at the needle tip, a density gradient occurs. Then, the liquid phase of the cement and smaller particles can enter the needle tip, whereas calcium and phosphorus ions precipitate at the nucleation points formed by the previous precipitates of bigger particles. Thus, the cement gets filtered. Once the filter-pressing effect is too high, needle clogging occurs and the injectability is distinctly impaired. (Bohner & Baroud, 2005)

A specific non-CaP phase which often is used in cementous systems is calcium carbonate (CaCO_3). An increase of the CaCO_3 concentration in a CPC was shown to increase the setting time and thus injectability time. (Sariibrahimoglu et al., 2012) Further, a reduction of the particle size increased the injectability as well. (Sariibrahimoglu et al., 2012) Carbonated HAp-forming cements demonstrate a higher degradation after setting in comparison to carbonate-free HAp. This is caused by the crystal formation in presence of CO_3^{2-} ions which replace some PO_4^{3-} ions of the HAp structure. These carbonated apatites are described to have a lower degree of crystallization resulting in faster degradation. (Frank-Kamenetskaya, 2008; Sariibrahimoglu et al., 2012) Due to these reasons, CPC had been proven to demonstrate an enhanced clinical compliance than carbonate-free CPC formulations. (Khairoun et al., 1997)

In this work, a CPC whose precursor consists of α -TCP, DCPA, CaCO_3 and HAp (the latter shall act as nucleation seeds for faster setting and occurrence of smaller crystals) was used which transforms into carbonated HAp following equation 1.1. (Schumacher, 2015) This formulation was firstly invented by DRIESSENS *et al.* and is referred to as Biocement D. (Driessens *et al.*, 1997) Later, the precursors were mixed with a non-aqueous, hydrophobic but biocompatible, carrier liquid which is replaced in an aqueous environment allowing infinite and unhindered injectability. (Heinemann *et al.*, 2013)

Due to their physicochemical similarity to the mineral phase of bone, HAp-forming cements were investigated on their potential to act as bone substitutes. They can be applied to the patient either as injectable formulation which sets due to the presence of blood or as already set and pre-formed grafts. (Xu *et al.*, 2017) They allow cell spreading, proliferation and differentiation, which could be evidenced for mesenchymal stem cells, osteoblastic cells and other bone cells. (Yuasa *et al.*, 2004; Guo *et al.*, 2009; Bernhardt *et al.*, 2014) *In vivo*, CPC revealed a high biocompatibility and fixation to the native bone, however the degradation rate is poor. (Thormann *et al.*, 2013) Further, although it could be demonstrated repeatedly, that CPC acts osteoconductive and the formed HAp is bioactive, CPC have shown only limited osteoinductivity. (Xu *et al.*, 2017) This means that they do not recruit endogeneous cells actively, including bone cells or endothelial cells, neither they act stimulative on proliferation and differentiation. However, it was shown, that intrinsic properties like surface topology, porosity or composition (e.g. by additional ions like Sr^{2+}) influence the osteoinductivity. (LeGeros, 2008; Schumacher & Gelinsky, 2015) Due to that reason, CPC were investigated thoroughly to act as drug carriers enhancing their biological activity. (Ginebra *et al.*, 2012)

1.4.3 Nanoclays

An upcoming material class for several applications in tissue engineering are nanocomposites which are composites involving nanosized filler materials offering unique properties. In contrast to microparticles, the nano-sized fillers interact with macromolecules of polymers by formation of physical or even chemical bonds. For example, a widely studied nanomaterial is nanocellulose, a derivate of cellulose. (Curvello *et al.*, 2019) Novel nanofillers are anorganic clays which exist in various forms and shapes. For example, halloysite nanotubes are able to incorporate ALP in order to stimulate osteogenic differentiation. (Pietraszek *et al.*, 2019)

LAPONITE The nanoclay investigated in this work was Laponite. Laponite consists of nanodiscs, which are cylindric discs with a diameter of 20-25 nm and a height of 1 nm. (Becher *et al.*, 2019) The nanodiscs are synthetic smectite crystals including highly ordered silicon, oxygen and magnesium or lithium ions (Figure 7 A). The order of the ions leads to a highly anisotropic distribution of polarities within the nanodisc. The border of one single disc is positively charged and the top and bottom sides are negatively charged (Figure 7 A). If

Figure 7. Structure of Laponite, adapted from (Ley et al., 2015) with permission of the publisher. **A:** Atomic structure forming a nanodisc with a negatively charged top and bottom and positively charged border. **B:** Laponite in solid state and dissolved in water. Laponite nanodiscs assemble in the so-called 'house-of-cards' structure.

two Laponite discs meet, the center of the one disc will be attracted by the border of the other one. More nanodiscs will follow the same interactions and borders and centers will form electrostatical interactions, resulting in a so-called 'house-of-cards' structure (Figure 7 B). (Tawari et al., 2001) The high affinity to quickly assemble into this structure as well as the high polarity in the system, make Laponite interesting for development of bioinks (see the section rheology in chapter 1.6), as well as for functionalization with growth factors. The opportunities to use Laponite for tissue engineering applications were comprehensively reviewed earlier. (Dawson & Oreffo, 2013) Especially two properties are of great interest: (i) Biologically active molecules can be delivered from Laponite-based systems in a sustained manner, whereas Laponite-free controls usually show a burst release. (Dawson & Oreffo, 2013; Ding et al., 2016) (ii) Clay-polymer nanocomposites demonstrated enhanced mechanical properties and promoted adhesion and differentiation of cells. (Gaharwar et al., 2012; Dawson & Oreffo, 2013)

1.5 ADDITIVE MANUFACTURING IN MEDICINE & BIOPRINTING

1.5.1 Additive Manufacturing in Tissue Engineering

In order to overcome drawbacks of traditional biomaterials, the concept of tissue engineering was conceived (Langer & Vacanti, 1993) and adapted to the needs of regenerating bone tissue (Hutmacher, 2000). In contrast to a classical procedure with a biomaterial, the basic concept of tissue engineering involves two major differences: (i) the engineered graft must be necessarily biodegradable and thus undergoes perpetual morphological changes over time and (ii) the tissue graft promotes tissue maturation, either by usage of autologous cells and/or biologically active growth factors. The utilization of the autologous, patient's own cells, individualizes the tissue graft and, in principle, has the potential to support tissue growth to a great extent.

Additive manufacturing (AM) is the principle of layerwise assembly of materials to generate three-dimensional devices. With the rise of AM, the biomedical sector gained new opportunities for the treatment of rather complex defects. Biomaterials like titanium could be fabricated to patient-individual implants, for example a complete additively manufactured and patient-specific sternum was implanted (Dzian et al., 2018). In the following, AM also was translated to tissue engineering (Landers et al., 2002). Figure 8 demonstrates the integration of AM (formerly called rapid prototyping) into the tissue engineering cycle. In this case, the potential graft gets produced exactly fitting into the three-dimensional defect volume, which easily is recorded in a hospital by computed tomography or magnetic resonance imaging. The fabricated tissue graft can be seeded with the patient's own cells, matured *in vitro* and implanted into the patient. As seen in Figure 8, the cells also could be introduced directly into the AM process and fabricated, together with a suitable matrix, in a spatially defined manner. In a nutshell, this describes the basic principle of bioprinting.

Figure 8. Envisioned extension of the classical tissue engineering concept by means of additive manufacturing to produce patient-individualized grafts. Adapted from (Landers et al., 2002) with permission of the publisher.

1.5.2 *Bioprinting Techniques*

In the last decades, several AM technologies were refined to enable the principle of bioprinting (see Figure 9). These technologies can be categorized generally into three groups: laser-assisted bioprinting, inkjet-based bioprinting and extrusion-based bioprinting.

Laser-assisted Bioprinting

The most common laser-assisted bioprinting technique is called laser-induced forward transfer (Figure 9 A). A laser is beamed onto an energy-absorbing optical system, which consists of three layers (from top to bottom): a donor substrate, the laser-absorbing slide and a cell-containing material (the bioink). The energy of the laser is used to generate an air bubble between the laser-absorbing slide and the bioink. The volume of the air bubble displaces the bioink which falls down in form of a drop onto an underlying substrate. The substrate can be positioned in an x-y-z system and thus the cells can be spatially defined and the obtained cell-matrix construct is assembled in a layerwise structure. (Serra & Piqué, 2019) A novel laser-based bioprinting technique was recently introduced coupling the algorithms of 3D imaging of computed tomography with photo-initiated crosslinking of optically transparent materials (Figure 9 B). (Bernal et al., 2019) This allows the fabrication of volumetric constructs without the need of a layerwise assembly, however a big drawback is that neither the bioprinted cells can be spatially defined, nor the multiple materials can be combined in this process. Nevertheless this novel approach establishes a set of design principles and paradigms which might overcome drawbacks of more common bioprinting techniques. In general, the laser-assisted printing technique of two-photon polymerization (2PP) enables the additive manufacturing of most filigree feature sizes by avoiding artefacts which occur in a standard stereolithography setup (Figure 9 C, left image: stereolithography, right image: 2PP). (Zipfel et al., 2003) Recently, a Gelatin–Norbornene gel was developed which allows embedded cells to survive the high energies used in the 2PP process, introducing this technique into the field of bioprinting. (Dobos et al., 2019)

Inkjet-based Bioprinting

Inkjet-based bioprinting deals with the generation of small droplets containing cells. The droplets are deposited in a spatially defined manner by a multi-axis robot. Since shear forces were shown to be a crucial factor in inkjet-based bioprinting (Blaeser et al., 2016), many groups investigated various ways to generate the droplets (Figure 9 D-F). In contrast to extrusion-based bioprinting (chapter 1.5.2), the viscosities of the applied biomaterials are distinctly lower. A good overview about inkjet-based technologies were given earlier. (Gudapati et al., 2016; Leberfinger et al., 2017) In brief, there are two types of inkjet-based bioprinting technologies: continuous generation of droplets and drop-on-demand (DOD). The continuous generation of droplets means, that pressure is given to a cell-material reservoir and the material flows through a nozzle and forms a droplet which is detaching from the tip after a

Figure 9. Additive manufacturing technologies allowing bioprinting. Credits: **A,D,G:** (Malda et al., 2013) with permission of the publisher, **B:** (Bernal et al., 2019), distributed under the CC BY 4.0 license, **C:** (Zipfel et al., 2003) with permission of the publisher, **E:** GeSIM product catalogue, **F:** (Leberfinger et al., 2017) permitted by German law, **H:** (Colosi et al., 2016) with permission of the publisher.

specific volume is reached. In contrast, DOD techniques allows for the application of single droplets which enables a better spatial distribution. Thus DOD has been acknowledged as preferable, although the pressures needed are higher which could impair cell viability.

For the generation of droplets for DOD bioprinting, various technologies were applied. Most common are valves, which can be controlled by actuators.(Malda et al., 2013) These actuators can be controlled by thermal or magnetic influence or by piezo elements, as depicted in Figure 9 D. Further, pipettes were developed, which have only a small reservoir, that gets filled up from the tip side. For example, piezo pipettes were developed, which are able to dose volumes from the pico- to the microliter range (Figure 9 E).(Detsch et al., 2016) A nozzle-free variant is the generation of droplets by acoustic sound waves (Figure 9 F). Surface tension holds the bioink in a reservoir. For printing, soundwaves are applied to the tip which apply a force to the reservoir. When this force is higher than the surface tension, a droplet is generated.(Demirci & Montesano, 2007) By this method, shear forces are avoided which is beneficial for cell survival. However, the feasibility to deposit the droplets is impaired, since the moving of the print head disruptes the soundwaves.(Leberfinger et al., 2017)

Extrusion-based Bioprinting: Bioplotting

Three-dimensional (bio-)plotting, also known as direct ink writing or robocasting, is an additive manufacturing technique, which is based on (micro-)extrusion of a material through a dispensing unit, for example a needle. To the best knowledge of the author, the first report about this method was given in 2000 by fabricating a moisture-curable silicone resin.(Landers & Mülhaupt, 2000) By applying force (e.g. by a piston, a screw or, as utilized in this work, by controlled air pressure, Figure 9 G) the material is forced to flow out of the needle. The application of force defines the difference to the well-studied fused deposition modeling (also known as fused filament fabrication): In this case, force has to be applied, but also high temperatures are needed to generate a material suitable for extrusion, which impairs inclusion of biological components. After the material is extruded through the needle, the material is laid down as a strand onto the plotting stage. By ordering strands to each other, a layer with a specific pore structure is assembled. After plotting of one layer, a new layer can be plotted on top, achieving a volumetric construct. The architecture and geometry of a layer is independent of previous layers, but must equal the same outer dimensions. Materials applicable for 3D plotting are known as biomaterial inks or bioinks (see chapter 1.2). The first hydrogel printed by 3D plotting was agarose as well as a blend of alginate, fibrin and gelatin.(Landers et al., 2002) Remarkably, this early study defined the first challenges on the way to extrusion-based bioprinting: (i) the relation of viscosity of an ink and the shape fidelity of a scaffold (sections 1.6.1 and 1.6.5), (ii) the need of stabilization of an ink after fabrication (section 1.6.3), (iii) the swelling of a plotted hydrogel is going to negate the shape fidelity, (iv) cells demand a highly biocompatible environment, which limits the number of materials being applicable for (bio-)plotting.

In contrast to more traditional seeding approaches, three-dimensional plotting allows the processing of in materials incorporated proteins or cells, which overcomes issues of seeding

Figure 10. Principle of three-dimensional multichannel plotting. Two or more materials are plotted in a layerwise assembly obtaining volumetric, biphasic scaffolds with predefined pore structure, spatially defined features (i.e. strands) and tissue mimicing properties.

efficiencies and drug loading capacities.(Wilson & Boland, 2003; Fedorovich et al., 2008) Additionally, the porosity and pore structure can be tailored suiting to the healing process, nutrient supply and vascularization of the demanded tissue.

With the upcoming technology of microfluidic chips, also the way of extrusion-based bioprinting could be changed. This technology is relatively new, however it has great potential since it enables the processing of bioinks which usually could not be processed by extrusion-printing. Further, the morphology of strands can be modulated easily (Figure 9 H).(Colosi et al., 2016) In addition, it has the potential to overcome empirical approaches in bioink development and allows profound investigations of cell-material interactions, since the mixing ratios can be modulated in wide differences. Experimental setups could be designed due to the high throughput and precise control of microfluidic systems.

A further advantage of extrusion-based technologies is the easy handling of several material containers, which allow the combination of more than one material per scaffold, as schematically demonstrated in Figure 10. Multichannel plotting is an advanced technology allowing the control about processing parameters like plotting velocity or dosing pressure independently for each bioink or biomaterial ink. In addition, the inks can be arranged in spatially defined manner within the x-y-z coordinate system (Figure 10). This technological aspect defines a new way of tissue engineering concepts: A spatial arrangement of cells, proteins, growth factors and (artificial) extracellular matrix has the potential to mimic native tissue and promote tissue maturation *in vitro* and *in vivo* in an advanced manner.

1.6 BIOINKS & BIOMATERIAL INKS

The materials being processed with 3D plotting are called biomaterial inks (without cells) and bioinks (with cells). (Groll et al., 2018) In this work, a plottable CPC is used as biomaterial ink and blends of alginate and methylcellulose were used as bioinks. The material properties needed for 3D plotting are independent of the material class and could in general be applied to metals, ceramics and polymers. Nevertheless, polymeric hydrogels are the most frequently used materials applied to extrusion-based bioprinting. The following paragraphs will shortly summarize the most important properties of materials applicable to 3D (bio-)plotting. These properties are rheology, plottability, post-processing and biocompatibility. Crucial for the development of bioinks is the *Biofabrication window*, which will be explained as well.

1.6.1 Rheology

Rheological properties of materials describe their ability to respond to shear forces. In extrusion-based printing, materials are exposed to periodically changing shear stresses. In order to understand physicochemical changes of inks during plotting and after plotting, rheology should be assessed carefully. A good overview is given in (Gan & Lam, 2013).

The most ideal solid will respond to an applied shear stress by a complete reduction of the deformation to its original condition. This behavior can be considered as a full elastic response (Figure 11 A). In contrast, an ideal viscous fluid (also called NEWTONIAN fluid) will perform no change of the deformation after a shear stress was applied (Figure 11 B). Plastic deformation is a condition, when a material can be deformed indefinitely without retention, but only after a critical shear stress is reached (Figure 11 C). The elastic response of a material can be described by a spring, the viscous response by a damper and the plastic deformation behavior is described by an element sliding down a rough surface, which only will move after the kinetic energy is higher than the static friction (St. VENANT element).

Apart from ideal behavior, viscoelastic response can be expected from most materials. Viscoelasticity is the time-dependent change of the deformation of a material after exposure to shear stress. A viscoelastic solid is able to recover its shape completely. This behavior is described by the KELVIN-VOIGT model, which is a parallel circuit of a spring and a damper. For extrusion-based plotting, fluid-like behavior is mandatory. This behavior is called MAXWELL fluid, which is described by a series circuit of a spring and a damper. After exposure to shear stress, the material undergoes a strong deformation. After the shear stress declines, a small elastic part can recover and the deformation will decrease exactly by the amount of the elastic component (Figure 11 D).

A viscoelastic fluid, which only undergoes deformation, which can be equalized to flow through a needle in extrusion-based processes, after a critical shear stress is reached, is called BINGHAM fluid. A BINGHAM fluid is a series circuit of a spring (elastic component) and a parallel circuit of a damper (viscous component) and a St. VENANT element (allowing only deformation after a specific level of energy input, in form of mechanical energy). Most biomaterial inks and bioinks demonstrate intrinsic properties of BINGHAM fluids. Thus, to

process them, a specific shear stress at the inner wall of the needle has to be applied to extrude them. This shear stress is dependent on the needle material, as well as the needle diameter. The implied shear stress is dependent on the mass flow (Emmermacher et al., 2020).

The viscosity of an ink is the most important value for plotting processes. A low-viscous material needs to be externally stabilized to stay in shape, whereas a highly viscous material will not flow and the shape of a plotted strand can be maintained. The viscosity η is connected with the shear stress τ by its implying shear rate γ :

$$\eta = \frac{\tau}{\gamma} \quad (1.2)$$

As a consequence of equation 1.2, the shear stress of a BINGHAM fluid can be calculated as

$$\tau = \eta\gamma + \tau_0 \quad (1.3)$$

with τ_0 as the critical shear stress which needs to be surpassed for flowing of the ink through the needle.

Whereas NEWTONIAN and BINGHAM fluids follow the equations 1.2 and 1.3 indicating that the stress will linearly increase with increasing shear rates, there are numerous materials which undergo non-linear changes of the shear stress with increasing shear rates. These non-NEWTONIAN fluids can be categorized and mathematically described. Materials increasing the viscosity with increasing shear rates are called dilatant or shear thickening materials. In contrast, materials (like all plottable bioinks and biomaterial inks) decreasing their viscosity with increasing shear rates are called pseudoplastic or shear thinning. A shear thinning material can be described by the POWER LAW-model (see Figure 12 C). If the material will only flow, after a critical shear stress is reached, but behaves shear thinning as well, it can be described by the HERSCHEL-BULKLEY model (Figure 12 D). Non-NEWTONIAN fluids are described by the equation

$$\tau = \tau_0 + k \cdot \gamma^n \quad (1.4)$$

with $\tau_0 > 0$ for BINGHAM-like fluids, k as the flow consistency index, and n as the flow behavior index, which is <1 for shear thinning fluids and >1 for dilatant fluids.

A shear thinning behavior is the most important property to evaluate whether a material is suitable for three-dimensional plotting.

1.6.2 Plottability & Shape Fidelity

The rheological properties of a bioink or biomaterial ink can be used to analyze the change of the material properties during extrusion and after plotting of a strand. However, the plottability of a feature, which can be a single plotted strand or a 3D construct consisting of multiple strands, is mainly characterized by its shape in comparison to the desired shape of the original CAD file, which is called *shape fidelity*. The following paragraph aims to deliver a brief overview about different aspects of shape fidelity evaluations of plotted features.

Figure 11. General behavior of materials exposed to shear stress (red line) over time. **A:** A deformation occurs which recovers completely after dropping the shear stress. **B:** The deformation permanently increases and will stay after dropping the shear stress. **C:** A permanent deformation will be induced by shear stresses which are higher than a critical value. **D:** Viscoelastic materials can recover by its elastic part over time, viscoelastic Maxwell fluids recover immediately after disabling the shear stress. **E:** Bingham fluids act like viscoelastic materials with a critical value of the shear stress. (Gan & Lam, 2013)

Figure 12. Development of the shear stress of different materials during increasing shear rates. Materials suitable for three-dimensional plotting are shear thinning and therefore can be described by the POWER LAW-model or the HERSCHEL-BULKLEY model.

The shape of a single strand is dependent on the needle size, the applied pressure, the ink's viscosity and the plotting speed. Moreover, environmental aspects, like the plotting temperature, the plotting stage temperature, the plotting medium (which can be air, but also a liquid) and interactions with the plotting stage or already plotted features influence the shape of a strand distinctly. The characterization of all these parameters is complicated, therefore it is common to compare the width of a plotted strand with independent parameters. A recently developed method proposed by Gao *et al.* compares the width of a plotted strand W with the needle diameter d by the equation

$$W = d \cdot \alpha \cdot \beta \quad (1.5)$$

with a fabrication window at $1.2 < \alpha < 1.5$ and $0.9 < \beta < 1.2$. α and β are dimensionless values which are calculated from the ratio of the strand diameter after extrusion compared to the nozzle diameter (α) and from the ratio of the diameter of the plotted strand to the diameter of the extruded, but not laid down, strand (β). (Gao *et al.*, 2019)

A second strategy to evaluate the plottability of a strand is the evaluation of the *minimum feature size*, which is the smallest possible strand width, which can be achieved. This strategy demands investigations on the optimal pressure/plotting speed relation for the smallest possible needle.

In order to consider attractions of an extruded ink with already plotted features, RIBEIRO *et al.* proposed to fabricate a meandering structure with increasing strand-to-strand distances. (Ribeiro *et al.*, 2018) By comparing the ratio of the width at the meander M and actual strand width W with the strand-to-strand distance s (equation 1.6), an optimum for plotting of a strand in a porous structure can be found with the aim to fabricate a predefined pore design which does not change due to the plotting process.

$$\frac{M}{W} \sim s \quad (1.6)$$

Until now, only rare studies were made to investigate the shape fidelity of plotted volumetric constructs. GAO *et al.* define the quality of the shape fidelity of an entire plotted construct only by the height, but not by all three dimensions. (Gao *et al.*, 2019) Most studies concentrate on plotting of ear- and nose-shaped constructs showing the ability of the investigated bioinks and biomaterial inks to be stacked into volumetric tissues. A possible solution would be to use three-dimensional imaging of the plotted constructs and a comparison of the obtained three-dimensional image with the virtual CAD file.

The determination of shape fidelity is still under discussion in the scientific community. Mostly, the shape fidelity is examined after plotting. However, it must be critically assessed that the post-processing of a plotted structure influences the shape fidelity as well, just as material degradation over time.

1.6.3 *Post-Processing*

Bioinks and biomaterial inks, which can be processed by three-dimensional plotting, need to be stabilized after fabrication of the scaffold structure. For example, plottable CPC set in an aqueous environment. After the setting process, the pasty character of the CPC changes to a complete non-deformable state stabilizing the plotted structure. (Akkineni et al., 2015) To enable bioprinting, this post-processing must be cytocompatible and therefore must not be conducted utilizing elevated temperatures, unphysiological pH and without exposure to cytotoxic chemical or physical factors.

Bioinks are based on hydrogels. Hydrogels exist in a sol form, which are the macromolecules of the polymeric material dissolved in an aqueous solution, as well as in a gel form, which are the macromolecules in crosslinked state. There are different strategies to crosslink hydrogels; in the past many groups investigated the applicability of these crosslinking methods for bioinks and biomaterial inks. (Min et al., 2015) The following paragraph will summarize the most important crosslinking strategies for hydrogel-based bioinks and biomaterial inks.

Physical crosslinking methods are reversible, this means that a crosslinked hydrogel can retransform into its sol form by dissipating the crosslinks. Forms of physical crosslinking are thermal crosslinking, ionic crosslinking and stereocomplex crosslinking. Hydrogels like gelatin or agarose are gelled by thermal crosslinking. At a specific temperature, the macromolecules lose their ability to flow through the aqueous solution and develop electrostatic interactions which fix them by entanglements between the macromolecular chains. For example, gelatin is an uncrosslinked sol at temperatures $>37^{\circ}\text{C}$. Then cooled down to temperatures $<37^{\circ}\text{C}$, crosslinks are formed and the gelatin gets a rather stable gel. (Ouyang et al., 2020) Thermal crosslinking is not necessarily dependent on cooling mechanisms. For example, a 2 % methylcellulose solution is a sol at temperatures below 75°C , and forms a crosslinked gel at temperatures above 75°C . (Ahlfeld et al., 2020) Ionic crosslinking of macromolecules in hydrogels is induced by charged ions, like Ca^{2+} , Sr^{2+} or Ba^{2+} . The ions diffuse through the hydrogel matrix and form complex bonds with the macromolecules. For example, alginate is crosslinked in the presence of calcium and other divalent cations. (Schütz et al., 2017) Dependent on the hydrogel concentration, different amounts of ions have to be applied to the hydrogel to ensure full crosslinking. The degradation and swelling properties of ionically crosslinked hydrogels are strongly dependent on the release of the crosslinking ions, which will diffuse out of the hydrogel into surrounding medium *in vitro* or *in vivo*. (Lee & Mooney, 2012) The diffusion of ions into the hydrogel and out of the hydrogel is related to the osmotic pressure in the system and plays a crucial role for scaffold stability. Stereocomplex crosslinking describes the formation of gel structures by formation of molecules with opposite chirality which interact with each other. (Jong et al., 2001) However, to the best knowledge of the author, stereocomplex crosslinking was not used for stabilizing bioprinted structures so far.

Chemical crosslinks are defined as covalent, and thus permanent bonds between molecules. There are two main principles for chemical crosslinking methods: Free-radical polymerization and crosslinking of functional groups. For the free-radical crosslinking method,

a photoinitiator is incorporated into the gel. Once the sol with the photoinitiator is exposed to light of a specific wave length, it absorbs the energy and becomes radicalized. Then, the unpaired electron makes it highly reactive leading to a very homogeneous polymerization of the surrounding molecules.(Lee et al., 2020a) The wavelengths usually used in bioprinting are in the range of UV light, but some novel approaches have shown that also visible light might be an alternative.(Lim et al., 2016) For crosslinking of functional groups, there are several chemical reaction mechanisms available, among them SCHIFF-Base formations (Kim et al., 2019) or click chemistry (Gopinathan & Noh, 2018; Stichler et al., 2017b). A good overview about the mechanisms are provided by MIN *et al.*.(Min et al., 2015) A special form of covalent bonds are dynamic covalent bonds, which were introduced recently to bioprinting.(Lee et al., 2020b)

1.6.4 Biocompatibility & Biodegradation

Plottable inks which formulate the claim to provide alternative implants mandatorily have to be biocompatible. The term biocompatibility is defined in the standard DIN EN ISO 10993-5 and declares every material as biocompatible which allows a cell survival of more than 70 % after 24 h of culture time. However, it has become accepted, that biomaterial inks (being seeded with cells) should promote proliferation and, in best case, allow differentiation of cells towards an induced lineage. Moreover, bioinks (with encapsulated, plotted cells) should show no sign of decreasing cell viability and promote a typical cell response like in the specified tissue. Additionally, both, biomaterial inks and bioinks are required to degrade in a specific time, which allows remodeling of the tissue by plotted or ingrowing cells *in vitro* or *in vivo*. Thus, it must be considered that the requirements on plottable inks are higher than on usual biomaterials and especially higher than defined in the ISO standard. For bioprinting of cell-laden polymers, not just the material must be biocompatible, but also the fabrication process and the post-processing method.

1.6.5 The Biofabrication Window

In 2013, MALDA *et al.* defined in a trend-setting paper the so-called *Biofabrication window*.(Malda et al., 2013) A modified form of it is shown in Figure 13. It highlights the difficulties involved in bioink development.

There are two requirements which bioinks have to fulfill: Enabling an adequate cell response (high cell viability and preferably also tissue-like behavior of the cells, this is meant by compatibility in Figure 13) and high shape fidelity of the fabricated structure. In principle, also low-viscosity bioinks can be processed by bioprinting technologies and one would expect a relatively good cell compatibility since the diffusion of nutrients is facilitated in the water-rich environment which does not contain a lot of barriers, e.g. crosslinks. However, these materials are not capable to stay in any desired shape, neither they enable the spatial distribution of the bioprinted features. Nevertheless, low-viscosity bioinks gained attention in combination with multichannel plotting of cell-free materials, which can be printed with high

Figure 13. The Biofabrication window. Adapted and modified from (Malda et al., 2013) with permission of the publisher.

resolution like poly- ϵ -caprolactone. (Schuurman et al., 2011) These shape-defining materials allow the fabrication of high-shape fidelity constructs, however, due to their high solid content, encapsulated cells would not survive. These materials belong to the class of biomaterial inks. First studies which tried to establish the different bioprinting technologies or investigated its frontiers commonly have used conventional bioinks which had both, acceptable but not outstanding cytocompatibility and shape fidelity. Emerging bioinks try to meet both criteria in high standards. In the field, there is a general consent, that this can be reached by hydrogel reinforcement strategies. A good overview about some of these strategies was given by CHIMENE *et al.* (Chimene et al., 2019)

AIM OF THE THESIS

2.1 PRELIMINARY STUDIES

The aim of bone tissue engineering is the fabrication of patient-specific degradable ceramic implants. Materials with a high potential to mimic the mineral component of bone are calcium phosphate cements (CPC). Problematically, most CPC undergo a fast setting process after mixing the powder with the aqueous component leading to steadily increasing viscosity. This effect inhibits the plottability of such CPC. In the recent years, some groups investigated possibilities to retard the setting reaction of CPC for a specific time frame which allows extrusion through a nozzle without filter-pressing. For example, α -TCP-based CPC formulations were mixed with hydrogels like gelatin or Pluronic F127.(Maazouz et al., 2014; Barba et al., 2017) Since hydrogels contain water, the application time for extrusion through a needle is limited. Interestingly, the application time for gelatin was only about 30 min, whereas Pluronic F127 allowed extrusion for many hours.(Barba et al., 2017; Diloksumpan et al., 2020) Another plottable CPC was developed by HEINEMANN *et al.* by mixing the CPC precursors with a biocompatible oil as carrier liquid.(Heinemann et al., 2013) The setting mechanism of this CPC is similar to the other formulations, but the oil must be exchanged with water which prolongs the setting time. Since the exchange process only occurs at a water concentration above 50 %, this CPC formulation can be applied infinitely if the environmental humidity is lower than this value.

LODE *et al.* firstly fabricated volumetric scaffolds by 3D plotting using this CPC.(Lode et al., 2014) Later, AKKINENI *et al.* could evidence that plotted CPC structures should set in water-saturated atmosphere (humidity > 95 %) since this avoids the formation of microcracks which significantly decrease mechanical properties of the structures.(Akkineni et al., 2015) In the following, plotted CPC scaffolds were evaluated thoroughly *in vivo*.(Moussa et al., 2015; Reitmaier et al., 2018; Baranowski et al., 2018; Korn et al., 2020) All four groups concluded independently from each other that plotted CPC scaffolds allow ongoing bone formation and that the macroporous constructs act as guide for ingrowing bone. Thus, plotted CPC scaffolds act osteoconductive, but miss biofunctional, osteoinductive stimuli. However, in further tests it was stated that the application of CPC scaffolds with additional osteoinductive stimulants like bone morphogenetic protein-2 (Moussa et al., 2015), bone sialoprotein (Baranowski et al., 2018) or strontium ions (Reitmaier et al., 2018) are better for bone development. These biologically active components were applied to the CPC structures by dip coating or amendment of the CPC formulation like in case of Sr^{2+} (Schumacher et al., 2013; Lode et al., 2018).

The biofunctionalization potential by dip coating is limited, as this process misses spatiotemporal release of the growth factors. The spatiotemporal release should be beneficial as it allows release of biologically active growth factors for a prolonged time at the specific areas

within the constructs and can be realized by several Biofabrication technologies, amongst them extrusion-based bioplotting.(Bittner et al., 2018)

At the Centre for Translational Bone, Joint and Soft Tissue Research, some strategies were investigated to enable a spatial biofunctionalization of plotted CPC constructs.

(i) Multichannel plotting of biphasic constructs consisting of CPC and growth factor-laden hydrogels. Firstly, CPC and a highly concentrated alginate paste loaded with bovine serum albumin (BSA, used as model protein) were plotted and post-processed together.(Luo et al., 2013) Due to the enhanced setting process developed by AKKINENI *et al.*,(Akkineni et al., 2015) the proteins were not released during the setting process which usually is performed in aqueous solutions.(Luo et al., 2013) Later this concept was extended and further investigated by the combination of CPC and an alginate-gellan gum blend loaded with the vascular endothelial growth factor (VEGF) as model growth factor.(Ahlfeld et al., 2017) VEGF is a proangiogenic growth factor which chemotactically attracts endothelial cells. Due to this reason it can be used to stimulate the growth of angiogenic precursor structures, for example endothelial capillaries enabling oxygen and nutrient supply in tissue engineered structures. By a gradient-like distribution of the VEGF-laden hydrogel, a spatial release of VEGF was expected with the highest concentration at the center of the scaffold.(Ahlfeld et al., 2017) The released VEGF was biologically active and could stimulate endothelial cells *in vitro*.(Ahlfeld et al., 2019) Further, a pilot *in vivo* study in a rat femur model indicated the formation of a higher number of blood vessels in the VEGF-containing group compared to control groups, evidencing the advantages of biologically active tissue constructs.(Ahlfeld et al., 2019)

(ii) In a second approach, VEGF-laden microcarriers were embedded directly into the CPC formulation prior to plotting.(Akkineni et al., 2015) Although the released amount of VEGF was considerably low, it promoted the adhesion and proliferation of endothelial cells seeded onto the plotted structures.(Akkineni et al., 2015) Later this approach was translated to mesoporous bioglass, which also can act as drug delivery system as well as it releases therapeutic doses of osteogenically stimulative ions.(Richter et al., 2019)

These studies have evidenced clearly the benefits of biofunctionalized CPC scaffolds. Next to growth factors, the functionality can also be achieved by living cells which either synthesize their matrix *in vitro* or support the regeneration process *in vivo* (as a cell delivery system). The bioprinting of cells is achieved by processing bioinks, which are hydrogels with embedded cells (see chapter 1.6). A bioink allowing plotting of cells with high shape fidelity was developed by SCHÜTZ *et al.* by blending alginate and methylcellulose.(Schütz et al., 2017) In this bioink, alginate enables fast and cytocompatible crosslinking, whereas methylcellulose enhances the viscosity during and after plotting. Since the methylcellulose is not crosslinked, it is able to diffuse from the matrix to the surrounding medium leading to the formation of micropores.(Schütz et al., 2017) Although this bioink has several favorable features, which makes it particularly interesting for encapsulation and bioprinting of pancreatic islet cells, chondrocytes or algae,(Lode et al., 2015; Duin et al., 2019; Kilian et al., 2020) it might not be optimal for bioprinting of bone tissue. The major limitation is the lack of osteogenic cues, which enable the cells to differentiate into the osteogenic direction. Further, this bioink does not promote the adhesion of cells, which is accepted as beneficial since a spread and

adhered cell can show an osteoblast-like morphology which should promote the osteogenic maturation.

2.2 RESEARCH QUESTIONS

UNSOLVED TECHNOLOGICAL PROBLEMS Until now, 3D plotted CPC constructs were always manufactured as model bodies, that means that cylinders or cubes were plotted - shapes which are useful for experiments *in vitro*. However, bone defects are shaped diversely offering both, concave and convex shapes. Based on multichannel plotting, it was investigated whether CPC can be plotted in any shape. A possible solution was examined in chapter 3, by establishing a process chain for the manufacturing of patient-specific implants, which was demonstrated exemplary for a human scaphoid bone. The shape of the scaphoid bone was achieved by multichannel plotting of CPC and a removable supportive ink, which will be described in detail in chapter 3. Later, a biofunctional scaphoid bone incorporating cells could also be fabricated by multichannel plotting of the supportive ink, CPC and the bioink (chapter 6).

BIOINK DEVELOPMENT Based on the blend developed by SCHÜTZ *et al.* (Schütz *et al.*, 2017), new bioinks should be developed which bring alginate-methylcellulose-based bioinks closer to bone bioprinting. Laponite was used to enhance the protein binding affinity of the bioink. The proteins (such as growth factors) would be released from the bioprinted structure and additionally presented to the bioprinted cells. This was developed and investigated in chapter 4. The interaction of alginate and methylcellulose with embedded cells are limited. To enhance the interaction, fresh frozen plasma was used to modify the matrix (chapter 6). The bioinks were characterized on plotting behavior, shape fidelity and cell viability in comparison to the already developed blend.

COMBINATION OF CPC AND BIOINKS The mentioned previous studies clearly showed that the post-processing of CPC-based scaffolds is crucial for its mechanical properties and biological activity. (Luo *et al.*, 2013; Lode *et al.*, 2014; Akkineni *et al.*, 2015; Ahlfeld *et al.*, 2017) It was becoming apparent, that a setting procedure in water-saturated atmosphere is advantageous for both, setting of the CPC and release of growth factors from CPC-based tissue constructs. It would be a fruitful approach to combine the CPC also with bioinks. However, a setting in water-saturated atmosphere for several days would not be sufficient for bioprinted cells which aim for an aqueous environment. Further, a stabilization procedure of the bioink must not interfere with the setting process of the CPC. Thus, a novel post-processing must be developed ensuring both, optimal setting of the CPC as well as maintenance of the cell viability within the bioink. This process was investigated and characterized in chapter 5.

Further, the behavior of bioprinted cells in novel CPC/bioink-constructs was investigated as well as cell viability and proliferation. In combination with the novel plasma-based bioink, remarkable effects on cells were observed which were studied in detail in chapter 6.

Part II

SPECIALIS

A METHYLCELLULOSE HYDROGEL AS SUPPORT FOR
3D PLOTTING OF COMPLEX SHAPED CALCIUM PHOSPHATE SCAFFOLDS

Article

A Methylcellulose Hydrogel as Support for 3D Plotting of Complex Shaped Calcium Phosphate Scaffolds

Tilman Ahlfeld ¹, Tino Köhler ¹, Charis Czichy ², Anja Lode ^{1,*} and Michael Gelinsky ^{1,*}

¹ Centre for Translational Bone, Joint and Soft Tissue Research, University Hospital Carl Gustav Carus and Faculty of Medicine, Technische Universität Dresden, 01307 Dresden, Germany; tilman.ahlfeld@tu-dresden.de (T.A.); Tino.Koehler@tu-dresden.de (T.K.)

² Institute of Fluid Mechanics, Chair of Magnetofluidynamics, Measuring and Automation Technology, Technische Universität Dresden, 01069 Dresden, Germany; charis.czichy@tu-dresden.de

* Correspondence: anja.lode@tu-dresden.de (A.L.); michael.gelinsky@tu-dresden.de (M.G.); Tel.: +49-351-45816692 (A.L.); +49-351-4586694 (M.G.)

Received: 16 July 2018; Accepted: 9 August 2018; Published: 11 August 2018

Abstract: 3D plotting is an additive manufacturing technology enabling biofabrication, thus the integration of cells or biologically sensitive proteins or growth factors into the manufacturing process. However, most (bio-)inks developed for 3D plotting were not shown to be processed into clinically relevant geometries comprising critical overhangs and cavities, which would collapse without a sufficient support material. Herein, we have developed a support hydrogel ink based on methylcellulose (mc), which is able to act as support as long as the co-plotted main structure is not stable. Therefore, 6 w/v %, 8 w/v % and 10 w/v % mc were allowed to swell in water, resulting in viscous inks, which were characterized for their rheological and extrusion properties. The successful usage of 10 w/v % mc as support ink was proven by multichannel plotting of the support together with a plottable calcium phosphate cement (CPC) acting as main structure. CPC scaffolds displaying critical overhangs or a large central cavity could be plotted accurately with the newly developed mc support ink. The dissolution properties of mc allowed complete removal of the gel without residuals, once CPC setting was finished. Finally, we fabricated a scaphoid bone model by computed tomography data acquisition and co-extrusion of CPC and the mc support hydrogel.

Keywords: calcium phosphate cement; methylcellulose; 3D plotting; support; hydroxyapatite

1. Introduction

In the past, high-temperature extrusion based additive manufacturing, known as fused deposition modeling (FDM) was used to fabricate scaffolds with high diversity of shapes [1,2]. Low-temperature extrusion, called 3D plotting, was shown to combine the geometrical features of FDM with more advanced functionalities like inclusion of proteins and growth factors or bioplotting of cell-laden scaffolds with spatially defined cell distribution [3,4]. However, in contrast to FDM, until now, 3D plotting of either cell-laden bioinks or cell-free biomaterial inks rarely was shown for manufacturing complex shaped, volumetric constructs ($>10 \times 10 \times 10 \text{ mm}^3$) [5]. These shapes include critical overhangs which produce a bending moment which cannot be balanced by the main body of the scaffold and cavities which collapse due to gravity. Even the fabrication of constructs without flat side (created by deposition of material on the flat building platform of the printer) is impossible. Maybe, therefore, it is common until now that most publications show the fabrication of an ear-shaped model to demonstrate the capability of novel materials or printing technologies, but an ear displays neither a critical overhang nor a cavity, but has a flat bottom side.

First attempts to overcome shape limitations of 3D plotting were developed by usage of a support bath [6–8]. However, the support bath will interact with the main structure limiting the material variety of this method, as the interaction might cause needle clogging, hinder controlled post-processing, or even might bind physically to the main structure.

Multichannel plotting of a temporary supporting material together with the actual main ink could extend both, material variety and shape diversity of 3D plotted constructs. An ideal ink should comprise two functionalities: (i) the material ink acts as support for the main ink, preventing plotted strands from collapsing and (ii) the material ink acts as sacrificial material, which means that it is vanishing after post-processing and stabilization of the main scaffold. Additionally, material inks applicable for 3D plotting of support structures must not only meet the requirements mentioned, but also those of viscosity, plottability, and post-plotting stability. Within this manuscript, the term support ink is used, however the developed biomaterial ink also meets the requirement acting as sacrificial material.

Hydrogels have been developed for several applications of 3D plotting and their viscoelastic properties make them ideal for usage not just as bioink but also as cell-free support ink [9]. The ink mostly used for 3D plotting of support structures is Pluronic® F127 (poloxamer 407—a synthetic, nonionic triblock copolymer). Previous studies investigated its use to create channel-like structures or sacrificial molds [10–12]. However, Pluronic® F127 is also used to create bioinks acting as a main structure and is needed in high concentrations to show enhanced plotting properties [11,13,14]. Thus, there is a high demand on new, versatile applicable materials acting as support material.

Water-soluble methylcellulose (mc) could be a promising candidate. mc is a synthetic cellulose ether with methyl groups substituting hydrogen atoms of the cellulose molecules. It showed unique viscosity enhancement of aqueous solutions, as well as increased dissolution properties at decreasing temperatures (sol-gel transition was observed in a temperature range between 20–50 °C, depending on the molecular weight and addition of salts) [15–17]. Already in the 1940s, mc was investigated for medical use in ophthalmology [18] and furthermore is registered in the list of *Inactive Ingredients Search for Approved Drug Products* by the FDA [19], minimizing the risk of negative effects caused by possible residues at the main scaffold. Recently it was shown that pure mc is a promising material for extrusion-based printing [20].

For our study, we have chosen to use a ceramic calcium phosphate cement (CPC) as the main ink. CPCs are composites of inorganic precursors and an aqueous solution. In contact with water molecules, the setting process of CPC is initiated and, for example just like within this work, α -tricalcium phosphate is precipitating to nanocrystalline hydroxyapatite (HAp). Nonetheless, the usage of the classical cements does not allow fabrication by 3D plotting (or sometimes also referred to as robocasting), as the fast setting process leads to needle clogging. Therefore, organic carrier liquids were developed substituting the aqueous phase. They were shown to retard the hydroxyapatite precipitation reaction [21–23] and prevent needle clogging, enabling extrusion of CPC for a sufficient time to fabricate scaffolds. After extrusion to scaffolds and setting of the scaffolds either in water or water-saturated atmosphere, pure nanocrystalline and resorbable HAp scaffolds were achieved demonstrating high potential for bone applications in vivo [24–26].

Within this paper, we investigated the suitability of mc as support ink for CPC constructs, carried out by multichannel plotting of mc and CPC. We aimed to: (i) develop a mc paste fitting the support ink requirements; (ii) which was characterized for its extrusion and plotting properties. Based on these results, CPC constructs were fabricated with (iii) critical overhangs and (iv) cavities in order to enable fabrication of complex shaped CPC constructs, suitable as scaffolds for bone reconstruction or tissue engineering purposes.

2. Results

2.1. Development and Rheological Characterization of Methylcellulose Based Support Inks

Methylcellulose was dissolved in water in three different concentrations: 6 *w/v* %, 8 *w/v* % and 10 *w/v* %; therefore, the resulting support inks within this manuscript are referred to as mc6, mc8, and mc10, respectively. Higher concentrations of mc were excluded from this study, as it was not possible to achieve homogeneous gels with uniform viscosity. Furthermore, a low concentration was intended to be advantageous in terms of the sacrificial behaviour of mc inks. It was decided to dissolve mc at 4 °C to ensure full hydration of the mc chains. After complete dissolution, all three combinations, mc6, mc8, and mc10, were almost transparent, homogeneous and viscous pastes, which were used for further characterization.

To evaluate suitability of the pastes for 3D plotting, rheological properties at increasing shear rates were investigated (Figure 1A). All pastes showed shear thinning behaviour, which is the most important property of inks for extrusion-based application. As expected, the viscosity of mc pastes was highly dependent on the concentration; mc10 showed the highest viscosity, followed by mc8 and mc6. For further comparison of the mc pastes, the viscosity of the biomaterial inks was evaluated at a shear rate of 10 s^{−1}, which is in our experience applicable to assess the plotting behavior of a material (Figure 1B) [27]. The viscosity of mc6 was 101.9 ± 6.6 Pa·s and significantly lower compared to mc8 (224.7 ± 7.8 Pa·s) and mc10 (377.5 ± 16.6 Pa·s).

Figure 1. Rheological investigations on shear thinning behavior of mc6, mc8, and mc10 support bioinks. (A) Representative viscosity measurements at increasing shear rates; (B) Viscosity at a shear rate of 10 s^{−1} (mean ± SD, *** *p* < 0.001, *n* = 3).

Furthermore, the shear recovery of the support inks was tested, following the proposed protocols of Paxton and co-workers and Kesti and co-workers [13,28]. Therefore, firstly a low shear rate of 5 s^{−1} was applied for 200 s, followed by a hundred-fold higher shear rate of 500 s^{−1} for 100 s. This procedure was repeated two times. Representative curves are shown in Figure 2. All three tested inks, mc6, mc8, and mc10, respectively, showed a shear recovery behavior over time. The first low-shear phase displayed higher viscosities of the inks compared to the three following low-shear phases, indicating an initial and not reversible breakage of inner polymer structures after a high shear rate was applied to the pastes. However, the viscosity progress of the pastes at the second, third and fourth low shear region was similar, showing full recovery to the previous state without further significant molecular changes of the polymers after the first high shear rate was applied.

Figure 2. Representative curves of shear recovery experiments of mc6, mc8, and mc10 pastes.

2.2. Extrusion Properties of Methylcellulose Support Biomaterial Inks

The extrusion properties were tested using a cylindrical needle with an inner diameter of 250 μm . Firstly, mass flow through the needle was evaluated as function of the applied air pressure (Figure 3). All three pastes showed increased mass flow with increased air pressure, but a significant ($p < 0.001$) higher mass flow of the mc6 paste was observed in comparison to mc8 and mc10. For example, at an air pressure of 200 kPa the mass flow of the mc6 paste was $12.72 \pm 1.0 \text{ mg}\cdot\text{s}^{-1}$, whereas the mass flows of mc8 and mc10 were calculated as 0.75 ± 0.12 and $0.19 \pm 0.02 \text{ mg}\cdot\text{s}^{-1}$. Based on these results, the following air pressure values were set for good extrusion with a plotting speed of $10 \text{ mm}\cdot\text{s}^{-1}$: mc6—100 kPa, mc8—200 kPa, and mc10—250 kPa.

Figure 3. Mass flow of mc6, mc8, and mc10 pastes through a cylindrical needle (inner diameter 250 μm); consider the changes of the y-axes (mean $\pm$ SD, $n = 3$).

Shape fidelity of the mc inks was evaluated by a filament fusion test, as proposed by Ribeiro and co-workers [29]. Shortly, three layers of the tested ink are plotted on top of each other. The layers are plotted as meanders and the strand distances increase continuously (Figure 4). By comparison of the fused segment length at the meanders to the strand width, the shape fidelity can be evaluated (the quotient should be near to 1.0). The resulting quotients of the filament fusion test are shown in Figure 4A–C as a function of the strand distance. For all pastes the shape fidelity was increased at higher strand distances. In comparison to the mc6 and mc8 biomaterial inks, mc10 displayed the smallest ratios at every strand distance, indicating higher shape fidelity. The measured strand widths of mc6, mc8, and mc10 were $1.20 \pm 0.15 \text{ mm}$, $0.75 \pm 0.05 \text{ mm}$, and $0.62 \pm 0.04 \text{ mm}$, respectively; the differences between the strand widths are clearly visible in Figure 4D–F. This indicates collapses of the inks in z-direction with smallest collapse of the mc10 paste.

Figure 4. Representative fused filament tests of mc6 (A,D), mc8 (B,E), and mc10 (C,F) pastes.

Based on the results of rheology and extrusion, mc10 was chosen to be the favorite support ink for 3D plotting of complex shaped CPC structures.

2.3. D Plotting of Calcium Phosphate Scaffolds with Overhanging Structures and Inner Cavities

Firstly, the shape fidelity of CPC constructs with overhangs was compared to structures of the same geometry, which were plotted without supporting material. The setup of the plotting process is shown in Figure 5A. A Mayan pyramid with macropores, consisting of CPC was plotted from the large bottom to the small top with a 610 μm needle. The layer structure was clearly visible (Figure 5B), macropores between the CPC strands were stable after setting and clearly visible in μCT (Figure 5C). The macroporosity calculated from micro computed tomography data was 69.6%.

Figure 5. 3D plotting of a Mayan pyramid with and without support structure. Principles (A,D) show the calcium phosphate cement (CPC) in white and mc in yellow. The upright and the inverted pyramids (B,C & E,F) revealed no changes of the inner structures, but at the borders.

Then, the pyramid was plotted in an inverted orientation displaying critical overhangs which would collapse without supporting material. The principle of plotting is shown in Figure 5D, by plotting the pyramid from the small top to the large bottom. The turned pyramid was plotted together with the mc10 ink (inner diameter of the needle: 610 μm) as support (Supplementary video SV 1).

After plotting and post-processing, mc10 could be dried and removed mechanically without alteration of the CPC structure (Figure 5E). Micro-computed tomography revealed distinct macropores and the determined macroporosity was 66.8% (Figure 5F). Whilst the inner structure of the pyramids was comparable to each other without remarkable changes, the boundaries of the pyramids were different. The pyramid plotted without support structure in an upright orientation revealed roundish strands at the borders, while the pyramid plotted with support structure (upside down) had flatten borders and edges, probably as a result of the CPC pressing against the mc at their interface.

In contrast to a Mayan pyramid, there are structures which cannot be plotted without support. For example, big cavities within a construct would lead to a collapse of the layers plotted above. To demonstrate the suitability of the mc10 support ink for such applications, a cube-inside-cube structure was plotted as shown in Figure 6A. CPC (strand distance 2 mm) and mc10 were plotted successfully to a cuboid structure of $25 \times 25 \times 25 \text{ mm}^3$. The inner cube plotted with mc10 (plotted without strand distance/macropores) had a volume of $15 \times 15 \times 15 \text{ mm}^3$. After plotting, stereomicroscopical images showed clearly the presence of the non-porous mc10 cube (Figure 6C). Afterwards, the biphasic structure was incubated in humid atmosphere for 3 d, allowing the CPC to set to nanocrystalline HAp. Then, the biphasic scaffold was incubated in distilled water over night at 4°C . Stereomicroscopy evidenced, that mc10 vanished (Figure 6C) and the pores in z-direction, being closed by mc before, were completely open. Micro-computed tomography and cutting of the CPC structure revealed that the inner cube, which now could be referred to as cavity, preserved the shape of the previous mc cube without collapse of the CPC layers above (Figure 6D). Additional images demonstrating the achieved even surface of CPC are shown in Supplementary Figure S1.

Figure 6. Generation of an inner cavity inside a CPC scaffold. (A) Principle of the CPC (red) structure with an inner cavity, filled with support material (mc, purple). (B) Fabrication and post-plotting appearance of the cubic structure with $410 \mu\text{m}$ needles. (C) After plotting (left), pores in z-direction of the CPC part are not interconnected but closed by mc at the interface of both materials. After methylcellulose vanished (right), the pores were clearly open and interconnected (scale bars 4 mm). (D) Virtual cut of micro computed tomography of the cube and photograph of the cut cube after mc vanished, revealing the cubical-shaped cavity inside the macroporous CPC structure. More images are provided in Supplementary Figure S1.

2.4. D plotting of a Clinically Relevant Structure

Plotted CPC structures show great potential for scaffolds in regenerative bone applications. Until now, CPC plotting was already further developed concerning utilization of different material combinations, growth factor loading or integration of live cells into the fabrication process [30–32]. Utilization of mc10 as support material opens the window to plot clinically relevant shapes, fitting to patient-specific anatomical structures or individual defects. To show the potential of CPC for these purposes, fabrication of a human scaphoid bone was chosen as example (Figure 7). For this, open

source software (Invesalius 3.1 [33]) was used to reconstruct and separate the scaphoid bone from a set of CT data (Figure 7A). The resulting stl-file was transferred to the BioScaffolder 3.1 software generating the support structure. Afterwards, CPC and mc10 were plotted together layer by layer (Figure 7B shows CPC in white and mc10 appearing opaque) by usage of needles with an inner diameter of 230 and 250 μm , respectively. Finally, the plotted construct demonstrated high shape equivalence to the stl-file and the characteristic curvature of the anatomical correct scaphoid (Figure 7C).

Figure 7. Fabrication of a scaphoid bone from clinical CT data. (A) 3D rendered human right hand and selection of the scaphoid by usage of 3D rendering software. (B) 3D multichannel plotting of the scaphoid bone consisting of CPC with mc10 as support ink. (C) Comparison of the stl-file and the real plotted structure with the characteristic shape of the human scaphoid.

3. Discussion

Methylcellulose was investigated for its use as biomaterial ink for 3D plotting. A concentration of 10% was convenient to act as support material for plotted structures consisting of a calcium phosphate cement.

Generally, there are two main strategies to apply support to 3D plotted structures: utilization of a supportive bath, which later on gets removed or, as used within this study, the co-extrusion with a temporary support material. For example, the usage of a nanoclay support bath successfully was shown by Jin and co-workers [7]. However, the hydrophilic character of the bath is not applicable for calcium phosphate cements, as the setting reaction would start immediately in the plotting needle, which would result in fast needle clogging. Therefore, an alternative was shown by Miranda and co-workers, who successfully extruded a calcium phosphate cement into a hydrophobic oil-bath, preventing the fast setting reaction and needle clogging [34]. However, the oil bath properties would impair the possibilities of integration of biological sensitive factors and inhibit the inclusion of cells into the plotting process. Thus, co-extrusion of the support is most promising for 3D plotting of complex shaped, anatomical relevant CPC structures. Although the mc10 ink was especially developed for the purpose of support ink for CPC scaffolds, it should be applicable for several other cell-free and cell-laden inks, which act as main structure.

In this study, extrusion of mc6, mc8, and mc10 support inks was performed at room temperature, without heating or cooling the plotting needle. Due to its thermo-reversible properties, plotting and post-processing temperatures influence the behaviour of mc crucially [20,35]. Representative temperature sweep experiments of all three materials are shown in Supplementary Figure S2. For all

inks, the sol-gel transition was above 37 °C. Thus, mc was in non-crosslinked state during both, extrusion and post-processing.

The plotting properties of the tested mc support inks were strongly dependent on their concentration. Especially mc10 and mc8 showed good printability and furthermore shape fidelity after extrusion, whereas plotted mc6 strands tended to collapse. The enhancement of shape fidelity of materials for 3D plotting was shown before in blends with alginate or a nanoclay-alginate composite [27,36]. Pure cellulose, or derivatives like bacterial nanocellulose were used to enhance viscosity and shape fidelity of 3D plotted scaffolds and cell-laden constructs [37–39]. However, the solubility of mc makes it an optimal material as support ink, which can vanish at a defined time point.

Herein, we have proven the suitability of co-plotting mc as support material for CPC constructs. Rheological and extrusion properties were investigated, showing high applicability for extrusion-based additive manufacturing. The viscosity of mc was increasing with increasing concentration. Further development of mc-based support inks could involve the presence of additives in the support paste. The gel point, and thus the gel strength/viscosity of mc can be adjusted by additives like sucrose, propylene glycol, or glycerin, which should impact the dissolution properties [40]. Recently, it was shown, that cationic dodecyltrimethylammonium salts (bromide, DTAB) was lowering the gel strength of mc [41]; also the addition of salts to mc was shown to change the transition temperature, and thus the gel point [17,35,42,43]. Cochis and co-workers investigated the effect of the extrusion temperature of salt-doped mc for extrusion-based applications [20]. This principle could help to further control the removal of plotted mc support structures.

There are two mechanisms for removal of mc10 from the main structure: Mechanical action or dissolving of the support ink. In case of the pyramids, mc10 was removed mechanically without damaging the CPC main structure. However, this method could harm the plotted main structure if it is mechanically unstable (like filigree structures or hydrogels) and cannot be applied to more complex geometries like cavities. Moreover, residues of mc are likely to remain. Therefore, the hydration process of mc should be the favorable method to remove mc after the main structure is post-processed and stable.

Herein, we successfully have developed a support ink based on methylcellulose, specifically applicable for a self-setting CPC. mc10 has comparable thermoresponsive properties like the commonly used Pluronic® F127 (so it can be easily dissolved at 4 °C within a few hours), but additionally can dissolve at 37 °C, as it is still a non-crosslinked sol. For example, mc was shown to be released out of an alginate matrix at 37 °C, without harming cell viability of embedded cells [36]. In a recent study of our group, we have observed, that mc dissolution out of an alginate matrix at 37 °C is ongoing over 21 days and release kinetics can be influenced by control of the molecular weight [44] or, as shown for pure mc, by addition of several salts [17]. This is advantageous for several future applications, either for plotting-then-seeding or bioplotting of cells: mc-based support inks can dissolve without affecting cell viability at cell culture conditions (37 °C). Moreover, the utilization of mc as new support material opens up new fabrication methods; for example, some inks are based on Pluronic® F127 [14], and might need another material as sacrificial support structure which can be dissolved at temperatures at which Pluronic® F127 is stable.

For the first time, CPC was plotted with a support ink to obtain complex shaped constructs of clinical relevance. In the past, complex shaped calcium phosphate scaffolds were manufactured by powder printing [45–47], or selective laser sintering [48] with the powder bed automatically also working as stabilizing support. Calcium phosphate scaffolds, fabricated by stereolithography, did not collapse, due to the stabilizing effect of the surrounding resin, before the resulting scaffolds were sintered [49,50]. Furthermore, calcium phosphate scaffolds were additively manufactured by indirect printing [51], lithography-based ceramic manufacturing [52] or robocasting [34]. All of these methods have in common that combination with biologically sensitive proteins is difficult and the inclusion of cells into the fabrication process is impossible. In contrast, extrusion of CPC is conducted in

mild conditions (at room or physiological temperature, without any organic solvents involved or energy-intensive post-processing steps etc.). This enables fabrication of CPC together with temperature sensitive substances even living cells [26,31,32,53]. Therefore, 3D plotting of CPC with support material does not only allow creation of complex shaped structures or implants, but also enables biofunctionalization of calcium phosphate implants in a spatially defined manner, which is superior to most other additive manufacturing methods.

Firstly, the influence of plotting a support structure together with a CPC main structure was evaluated. The inner structure of the tested pyramids was not affected, whereas the outer borders were changed distinctly. The pyramid plotted without support comprised more roundish strands, as it is expected for strands at a surface of every plotted scaffold. In contrast, the pyramid plotted with mc10 as support ink in reversed orientation revealed flattened strands at the interface to mc. Both, roundish and flattened strands are approximations of the real geometry of the pyramid. In the case of a possible implant, there are neither right angles nor complete convex surfaces. Therefore, the geometry of a single strand might never mimic the real geometry of a human bone specimen. As the resorption of the nanocrystalline HAp by osteoclasts is part of the natural bone remodeling process [54,55], the surface of plotted CPC implants will change over the whole healing time; thus, the strand surface does not necessarily have to reproduce the real surface of the bone completely.

However, the rough geometry of anatomical structures can be plotted: the example of the human scaphoid bone showed sufficient shape reproduction in comparison with the three-dimensional image file. Parameters influencing the plotted shape were on the one hand the resolution of the computed tomography data set and the precision of the generation of the stl-file. On the other hand, the strand distance and orientation, the used needle diameters for extrusion of CPC and mc and plotting properties like the layer thickness, applied air pressure and plotting velocity influence the outcome significantly. For CPC, these parameters were optimized in our group, achieving filigree strands and scaffolds with high inner complexity [53].

Crucially, CPC scaffolds could be fabricated containing large inner cavities. Such closed inner pores can only be generated by additive manufacturing methods. The dissolution properties of mc allowed fast vanishing of the internal mc cube after CPC was set (3 days), leaving behind a cavity of the desired cubic shape. This might enable the fabrication of scaffolds with highly controlled (macro)porosity to improve the ingrowth of cells and vascular structures, both accepted as main challenges in bone tissue engineering.

4. Conclusions

The usage of a newly developed methylcellulose-based support ink was sufficient to enable fabrication of structures with critical overhangs and to produce controlled cavities inside a CPC construct. For the first time, it was shown that CPC can be used to fabricate constructs of any clinical and anatomical relevant shape by 3D plotting. Furthermore, a human scaphoid bone model of high shape-fidelity could be produced. Further work should concentrate on more control of the dissolution properties of mc, which basically could be tailored for any application by addition of gel-strengthening and gel-weakening substances. The principle of biphasic plotting of the support ink and CPC will facilitate the production of patient-individual HAp implants, fabricated by 3D plotting.

5. Materials and Methods

5.1. Preparation of Plotting Paste

CPC was manufactured by InnoTERE GmbH (Radebeul, Germany). For the support material, methylcellulose powder (M0512, Sigma, St. Louis, MO, USA, molecular weight ≈ 88 kDa, 4000 cP) was dissolved for 12 h in deionized water at 4 °C in different concentrations (6 w/v%, 8 w/v% and 10 w/v%, respectively). To ensure full binding of water to mc, solutions were stirred every 2 h. The resulting support inks are referred to as mc6, mc8, and mc10.

5.2. Rheology

Rheological examinations of the mc pastes were performed with a plate-plate rheometer (Rheotest RN 4, Medingen, Germany; $d = 36$ mm, distance of the plates 0.1 mm) at 25 °C. Shear thinning was characterized by increasing the shear rate from 0–100 s^{−1} over 1200 s (increment 0.08 s^{−1}) and viscosity was measured ($n = 3$). Shear recovery of the mc pastes ($n = 3$) was characterized orientating at the protocols proposed by Paxton and co-workers and Kesti and co-workers [13,28]. Firstly, a constant shear rate of 5 s^{−1} was applied for 200 s, followed by a hundred-fold higher shear rate of 500 s^{−1} for 100 s. This procedure was repeated two times. Then, again a shear rate of 5 s^{−1} was applied for 200 s. For the whole time of observation, viscosity was measured and shear recovery was obtained. Stress ramps of mc6, mc8, and mc10 were performed to evidence flowing of the inks at high shear rates (data not shown).

5.3. Mass Flow and Filament Fusion Test

The mass flow of mc6, mc8, and mc10 was conducted through a conical needle with an inner diameter of 250 µm (Globaco, Rödermark, Germany); needle and plate were at room temperature. The inks ($n = 3$) were allowed to flow through the needle for 50 s at different air pressures (100, 150, 200, 250 kPa), then the mass of the extruded volume was measured. Resulting mass flow $\dot{m}$ was calculated:

$$\dot{m} = \frac{m}{50 \text{ s}}$$

Filament fusion tests of the mc inks ($n = 3$) were performed following the protocol of Ribeiro and co-workers [29]. Shortly, three layers of the inks were plotted on top of each other. Each layer consisted of meandering strands with increasing strand distances. Immediately after plotting, the scaffolds were imaged by a stereo light microscope (Leica M205 C equipped with DFC295 camera, Wetzlar, Germany). Resulting images were analyzed by Fiji Image software [56] and actual strand distance, fused segment length and strand width were obtained from the data. The quotient of segment length to strand width was evaluated as function of the strand distance.

5.4. Fabrication of Volumetric Constructs and Post-Fabrication Treatment

Both, CPC and mc support inks, were filled into cartridges and plotted at room temperature (needle and plate) to scaffolds (sizes given in Figure captions) utilizing a three-axis multichannel plotter (BioScaffolder 3.1, GeSiM mbH, Radeberg, Germany). The needle (Globaco) dependent plotting parameters are summarized in Table 1. After plotting, CPC was allowed to set in water-saturated atmosphere (>95%) for 3 days. Afterwards, residual mc of biphasic CPC-mc constructs was dissolved in water at 4 °C.

Table 1. Plotting parameters of CPC and mc support inks.

Material Ink	Needle Size [µm]	Air Pressure [kPa]	Printing Speed [mm·s ^{−1}]	Layer Thickness [µm]
CPC	230	250	10	120
	410	200	10	260
	610	150	10	360
mc6	250	100	10	120
mc8	250	200	10	120
	250	250	10	120
mc10	410	180	10	260
	610	130	10	360

5.5. Microcomputed Tomography

Micro X-ray computed tomography was conducted by a custom-built setup called TomoTU of TU Dresden, Institute of Fluid Mechanics, Chair of Magnetofluidynamics, Measurement and Automation Technology. The grey value images of the sample were generated with 0.5° angular

increment (720 images in total) for a tube current of 170 μ A and an acceleration voltage of 90 kV. The size of the photodiode array and therefore of the images was 2304×2940 (vertical $\times$ horizontal) pixel. A magnification of 3.55 was chosen, which resulted in a resolution of 1 pixel = 13.95 μ m. Reconstructions of the 3D-images was created by grey value analysis (threshold = 120) with Paraview 5.5 software [57]. Macroporosity of the scaffolds was determined by grey value analysis of the reconstructed image stacks (threshold = 120).

Supplementary Materials: Supplementary materials can be found at <http://www.mdpi.com/2310-2861/4/3/68/s1>.

Author Contributions: Conceptualization T.A., A.L., and M.G.; Experimental, data analysis, and visualization T.A., T.K., and C.C.; Funding attraction A.L. and M.G.; Supervision A.L. and M.G.; Paper writing and editing T.A., C.C., A.L., and M.G.

Funding: This research was funded by the German Federal Ministry for Economic Affairs and Energy (BMW) in collaboration with the German Federation of Industrial Research Associations (AiF; ZIM project, contract No. KF3359301AK4) and by the European Social Fund (ESF) together with the Free State of Saxony in course of the Young Researchers Group “IndivImp”.

Acknowledgments: The authors thank Ortrud Zieschang and Anna-Maria Placht for excellent technical assistance and Stefan Günther and Stefan Odenbach for support at the TomoTU and fruitful discussion about results of micro-computed tomography.

Conflicts of Interest: The authors declare no conflicts of interest.

References

1. Probst, F.A.; Hutmacher, D.W.; Müller, D.F.; Machens, H.-G.; Schantz, J.-T. Calvarial reconstruction by customized bioactive implant. *Handchir. Mikrochir. Plast. Chir.* **2010**, *42*, 369–373. [CrossRef] [PubMed]
2. Melchels, F.; Wiggemhauser, P.S.; Warne, D.; Barry, M.; Ong, F.R.; Chong, W.S.; Hutmacher, D.W.; Schantz, J.-T. CAD/CAM-assisted breast reconstruction. *Biofabrication* **2011**, *3*. [CrossRef] [PubMed]
3. Landers, R.; Pfister, A.; Hübner, U.; John, H.; Schmelzeisen, R.; Mülhaupt, R. Fabrication of soft tissue engineering scaffolds by means of rapid prototyping techniques. *J. Mater. Sci.* **2002**, *37*, 3107–3116. [CrossRef]
4. Mir, T.A.; Nakamura, M. Three-dimensional bioprinting: Toward the era of manufacturing human organs as spare parts for healthcare and medicine. *Tissue Eng. Part B Rev.* **2017**, *23*, 245–256. [CrossRef] [PubMed]
5. Kilian, D.; Ahlfeld, T.; Akkineni, A.R.; Lode, A.; Gelinsky, M. Three-dimensional bioprinting of volumetric tissues and organs. *MRS Bull.* **2017**, *42*, 585–592. [CrossRef]
6. Hinton, T.J.; Jallerat, Q.; Palchesko, R.N.; Park, J.H.; Grodzicki, M.S.; Shue, H.-J.; Ramadan, M.H.; Hudson, A.R.; Feinberg, A.W. Three-dimensional printing of complex biological structures by freeform reversible embedding of suspended hydrogels. *Sci. Adv.* **2015**, *1*, e1500758. [CrossRef] [PubMed]
7. Jin, Y.; Liu, C.; Chai, W.; Compaa, A.; Huang, Y. Self-Supporting Nanoclay as Internal Scaffold Material for Direct Printing of Soft Hydrogel Composite Structures in Air. *ACS Appl. Mater. Interfaces* **2017**, *9*, 17456–17465. [CrossRef] [PubMed]
8. Jin, Y.; Compaa, A.; Bhattacharjee, T.; Huang, Y. Granular gel support-enabled extrusion of three-dimensional alginate and cellular structures. *Biofabrication* **2016**, *8*. [CrossRef] [PubMed]
9. Malda, J.; Visser, J.; Melchels, F.P.; Jüngst, T.; Hennink, W.E.; Dhert, W.J.A.; Groll, J.; Hutmacher, D.W. 25th Anniversary Article: Engineering hydrogels for biofabrication. *Adv. Mater.* **2013**, *25*, 5011–5028. [CrossRef] [PubMed]
10. Müller, M.; Becher, J.; Schnabelrauch, M.; Zenobi-Wong, M. Printing thermoresponsive reverse molds for the creation of patterned two-component hydrogels for 3D cell culture. *J. Vis. Exp.* **2013**. [CrossRef] [PubMed]
11. Kolesky, D.B.; Truby, R.L.; Gladman, A.S.; Busbee, T.A.; Homan, K.A.; Lewis, J.A. 3D Bioprinting of vascularized, heterogeneous cell-laden tissue constructs. *Adv. Mater.* **2014**, *26*, 3124–3130. [CrossRef] [PubMed]
12. Suntornnond, R.; Tan, E.Y.S.; An, J.; Chua, C.K. A highly printable and biocompatible hydrogel composite for direct printing of soft and perfusable vasculature-like structures. *Sci Rep.* **2017**, *7*, 16902. [CrossRef] [PubMed]

13. Paxton, N.; Smolan, W.; Böck, T.; Melchels, F.; Groll, J.; Jungst, T. Proposal to assess printability of bioinks for extrusion-based bioprinting and evaluation of rheological properties governing bioprintability. *Biofabrication* **2017**, *9*, 044107. [[CrossRef](#)] [[PubMed](#)]
14. Gioffredi, E.; Boffito, M.; Calzone, S.; Giannitelli, S.M.; Rainer, A.; Trombetta, M.; Mozetic, P.; Chiono, V. Pluronic F127 Hydrogel Characterization and Biofabrication in Cellularized Constructs for Tissue Engineering Applications. *Procedia CIRP* **2016**, *49*, 125–132. [[CrossRef](#)]
15. Sanz, T.; Fernández, M.A.; Salvador, A.; Muñoz, J.; Fiszman, S.M. Thermogelation properties of methylcellulose (MC) and their effect on a batter formula. *Food Hydrocoll.* **2005**, *19*, 141–147. [[CrossRef](#)]
16. Nasatto, P.L.; Pignon, F.; Silveira, J.L.M.; Duarte, M.E.R.; Nosedá, M.D.; Rinaudo, M. Methylcellulose, a cellulose derivative with original physical properties and extended applications. *Polymers* **2015**, *7*, 777–803. [[CrossRef](#)]
17. Altomare, L.; Cochis, A.; Carletta, A.; Rimondini, L.; Farè, S. Thermo-responsive methylcellulose hydrogels as temporary substrate for cell sheet biofabrication. *J. Mat. Sci. Mat. Med.* **2016**, *27*. [[CrossRef](#)] [[PubMed](#)]
18. Swan, K.C. Use of methyl cellulose in ophthalmology. *Arch. Ophthalmol.* **1945**, *33*, 378–380. [[CrossRef](#)]
19. Inactive Ingredient Search for Approved Drug Products. Available online: <https://www.accessdata.fda.gov/scripts/cder/iig/index.cfm> (accessed on 9 July 2018).
20. Cochis, A.; Bonetti, L.; Sorrentino, R.; Contessi Negrini, N.; Grassi, F.; Leigheb, M.; Rimondini, L.; Farè, S. 3D printing of thermo-responsive methylcellulose hydrogels for cell-sheet engineering. *Materials* **2018**, *11*, 579. [[CrossRef](#)] [[PubMed](#)]
21. Maazouz, Y.; Montufar, E.B.; Guillem-Martí, J.; Fleps, I.; Öhman, C.; Persson, C.; Ginebra, M.P. Robocasting of biomimetic hydroxyapatite scaffolds using self-setting inks. *J. Mater. Chem. B* **2014**, *2*, 5378–5386. [[CrossRef](#)]
22. Maazouz, Y.; Montufar, E.B.; Malbert, J.; Espanol, M.; Ginebra, M.-P. Self-hardening and thermoresponsive alpha tricalcium phosphate/pluronic pastes. *Acta Biomater.* **2017**, *49*, 563–574. [[CrossRef](#)] [[PubMed](#)]
23. Heinemann, S.; Rössler, S.; Lemm, M.; Ruhnow, M.; Nies, B. Properties of injectable ready-to-use calcium phosphate cement based on water-immiscible liquid. *Acta Biomater.* **2013**, *9*, 6199–6207. [[CrossRef](#)] [[PubMed](#)]
24. Lode, A.; Meissner, K.; Luo, Y.; Sonntag, F.; Glorius, S.; Nies, B.; Vater, C.; Despang, F.; Hanke, T.; Gelinsky, M. Fabrication of porous scaffolds by three-dimensional plotting of a pasty calcium phosphate bone cement under mild conditions. *J. Tissue Eng. Regen. Med.* **2014**, *8*, 682–693. [[CrossRef](#)] [[PubMed](#)]
25. Barba, A.; Diez-Escudero, A.; Maazouz, Y.; Rappe, K.; Espanol, M.; Montufar, E.B.; Bonany, M.; Sadowska, J.M.; Guillem-Martí, J.; Öhman-Mägi, C. Osteoinduction by foamed and 3D-printed calcium phosphate scaffolds: Effect of nanostructure and pore architecture. *ACS Appl. Mater. Interfaces* **2017**, *9*. [[CrossRef](#)] [[PubMed](#)]
26. Akkineni, A.R.; Luo, Y.; Schumacher, M.; Nies, B.; Lode, A.; Gelinsky, M. 3D plotting of growth factor loaded calcium phosphate cement scaffolds. *Acta Biomater.* **2015**, *27*, 264–274. [[CrossRef](#)] [[PubMed](#)]
27. Ahlfeld, T.; Cidonio, G.; Kilian, D.; Duin, S.; Akkineni, A.R.; Dawson, J.I.; Yang, S.; Lode, A.; Oreffo, R.O.C.; Gelinsky, M. Development of a clay based bioink for 3D cell printing for skeletal application. *Biofabrication* **2017**, *9*, 034103. [[CrossRef](#)] [[PubMed](#)]
28. Kesti, M.; Fisch, P.; Pensalfini, M.; Mazza, E.; Zenobi-Wong, M. Guidelines for standardization of bioprinting: A systematic study of process parameters and their effect on bioprinted structures. *BioNanoMaterials* **2016**, *17*, 193–204. [[CrossRef](#)]
29. Ribeiro, A.; Blokzijl, M.M.; Levato, R.; Visser, C.W.; Castilho, M.; Hennink, W.E.; Vermonden, T.; Malda, J. Assessing bioink shape fidelity to aid material development in 3D bioprinting. *Biofabrication* **2018**, *10*, 014102. [[CrossRef](#)] [[PubMed](#)]
30. Akkineni, A.R.; Ahlfeld, T.; Lode, A.; Gelinsky, M. A versatile method for combining different biopolymers in a core/shell fashion by 3D plotting to achieve mechanically robust constructs. *Biofabrication* **2016**, *8*, 045001. [[CrossRef](#)] [[PubMed](#)]
31. Luo, Y.; Lode, A.; Sonntag, F.; Nies, B.; Gelinsky, M. Well-ordered biphasic calcium phosphate–alginate scaffolds fabricated by multi-channel 3D plotting under mild conditions. *J. Mater. Chem. B* **2013**, *1*, 4088–4098. [[CrossRef](#)]
32. Ahlfeld, T.; Doberenz, F.; Kilian, D.; Vater, C.; Korn, P.; Lauer, G.; Lode, A. Michael Gelinsky Bioprinting of mineralized constructs utilizing multichannel plotting of a self-setting calcium phosphate cement and a cell-laden bioink. *Biofabrication* **2018**, *10*, 045002. [[CrossRef](#)] [[PubMed](#)]

33. Amorim, P.; Moraes, T.; Silva, J.; Pedrini, H. In *Vesalius: An Interactive Rendering Framework for Health Care Support*. In *Advances in Visual Computing*; Springer: Cham, Switzerland, 2015; pp. 45–54.
34. Miranda, P.; Saiz, E.; Gryn, K.; Tomsia, A.P. Sintering and robocasting of β -tricalcium phosphate scaffolds for orthopaedic applications. *Acta Biomater.* **2006**, *2*, 457–466. [[CrossRef](#)] [[PubMed](#)]
35. Contessi, N.; Altomare, L.; Filippini, A.; Farè, S. Thermo-responsive properties of methylcellulose hydrogels for cell sheet engineering. *Mater. Lett.* **2017**, *207*, 157–160. [[CrossRef](#)]
36. Schütz, K.; Placht, A.-M.; Paul, B.; Brüggemeier, S.; Gelinsky, M.; Lode, A. Three-dimensional plotting of a cell-laden alginate/methylcellulose blend: Towards biofabrication of tissue engineering constructs with clinically relevant dimensions. *J. Tissue Eng. Regen. Med.* **2017**, *11*. [[CrossRef](#)] [[PubMed](#)]
37. Li, L.; Zhu, Y.; Yang, J. 3D bioprinting of cellulose with controlled porous structures from NMMO. *Mater. Lett.* **2018**, *210*, 136–138. [[CrossRef](#)]
38. Markstedt, K.; Mantas, A.; Tournier, I.; Martínez Ávila, H.; Hägg, D.; Gatenholm, P. 3D Bioprinting Human Chondrocytes with Nanocellulose-Alginate Bioink for Cartilage Tissue Engineering Applications. *Biomacromolecules* **2015**, *16*, 1489–1496. [[CrossRef](#)] [[PubMed](#)]
39. Wang, Q.; Sun, J.; Yao, Q.; Ji, C.; Liu, J.; Zhu, Q. 3D printing with cellulose materials. *Cellulose* **2018**, 1–27. [[CrossRef](#)]
40. Levy, G.; Schwarz, T.W. The Effect Of Certain Additives On The Gel Point Of Methylcellulose, University of California School of Pharmacy, San Francisco 22. *J. Am. Pharm. Assoc.* **1958**, *47*, 44–46. [[CrossRef](#)]
41. Villetti, M.A.; Bica, C.I.D.; Garcia, I.T.S.; Pereira, F.V.; Ziembowicz, F.I.; Kloster, C.L.; Giacomelli, C. Physicochemical Properties of Methylcellulose and Dodecyltrimethylammonium Bromide in Aqueous Medium. *J. Phys. Chem. B* **2011**, *115*, 5868–5876. [[CrossRef](#)] [[PubMed](#)]
42. Chen, C.-H.; Tsai, C.-C.; Chen, W.; Mi, F.-L.; Liang, H.-F.; Chen, S.-C.; Sung, H.-W. Novel Living Cell Sheet Harvest System Composed of Thermoreversible Methylcellulose Hydrogels. *Biomacromolecules* **2006**, *7*, 736–743. [[CrossRef](#)] [[PubMed](#)]
43. Xu, Y.; Li, L.; Zheng, P.; Lam, Y.C.; Hu, X. Controllable Gelation of Methylcellulose by a Salt Mixture. *Langmuir* **2004**, *20*, 6134–6138. [[CrossRef](#)] [[PubMed](#)]
44. Hodder, E.; Duin, S.; Kilian, D.; Ahlfeld, T.; Seidel, J.; Nachtigall, C.; Bush, P.; Covill, D.; Gelinsky, M.; Lode, A. Investigating the effect of sterilisation methods on the physical properties and cytocompatibility of methyl cellulose used in combination with alginate for 3D-bioplotting of chondrocytes. *J. Mater. Sci. Mater. Med.* (under review).
45. Castilho, M.; Moseke, C.; Ewald, A.; Gbureck, U.; Groll, J.; Pires, I.; Teßmar, J. Elke Vorndran Direct 3D powder printing of biphasic calcium phosphate scaffolds for substitution of complex bone defects. *Biofabrication* **2014**, *6*, 015006. [[CrossRef](#)] [[PubMed](#)]
46. Seitz, H.; Deisinger, U.; Leukers, B.; Detsch, R.; Ziegler, G. Different Calcium Phosphate Granules for 3-D Printing of Bone Tissue Engineering Scaffolds. *Adv. Eng. Mater.* **2009**, *11*, B41–B46. [[CrossRef](#)]
47. Vorndran, E.; Klarner, M.; Klammert, U.; Grover, L.M.; Patel, S.; Barralet, J.E.; Gbureck, U. 3D Powder Printing of β -Tricalcium Phosphate Ceramics Using Different Strategies. *Adv. Eng. Mater.* **2008**, *10*, B67–B71. [[CrossRef](#)]
48. Duan, B.; Wang, M.; Zhou, W.Y.; Cheung, W.L.; Li, Z.Y.; Lu, W.W. Three-dimensional nanocomposite scaffolds fabricated via selective laser sintering for bone tissue engineering. *Acta Biomater.* **2010**, *6*, 4495–4505. [[CrossRef](#)] [[PubMed](#)]
49. Bian, W.; Li, D.; Lian, Q.; Li, X.; Zhang, W.; Wang, K.; Jin, Z. Fabrication of a bio-inspired beta-Tricalcium phosphate/collagen scaffold based on ceramic stereolithography and gel casting for osteochondral tissue engineering. *Rapid Prototyp. J.* **2012**, *18*, 68–80. [[CrossRef](#)]
50. Seol, Y.-J.; Kim, J.Y.; Park, E.K.; Kim, S.-Y.; Cho, D.-W. Fabrication of a hydroxyapatite scaffold for bone tissue regeneration using microstereolithography and molding technology. *Microelectron. Eng.* **2009**, *86*, 1443–1446. [[CrossRef](#)]
51. Schumacher, M.; Deisinger, U.; Detsch, R.; Ziegler, G. Indirect rapid prototyping of biphasic calcium phosphate scaffolds as bone substitutes: Influence of phase composition, macroporosity and pore geometry on mechanical properties. *J. Mater. Sci. Mater. Med.* **2010**, *21*, 3119–3127. [[CrossRef](#)] [[PubMed](#)]
52. Pfaffinger, M.; Hartmann, M.; Schwentenwein, M.; Stampfl, J. Stabilization of tricalcium phosphate slurries against sedimentation for stereolithographic additive manufacturing and influence on the final mechanical properties. *Int. J. Appl. Ceram. Tec.* **2017**, *14*, 499–506. [[CrossRef](#)]

53. Ahlfeld, T.; Akkineni, A.R.; Förster, Y.; Köhler, T.; Knaack, S.; Gelinsky, M.; Lode, A. Design and Fabrication of Complex Scaffolds for Bone Defect Healing: Combined 3D Plotting of a Calcium Phosphate Cement and a Growth Factor-Loaded Hydrogel. *Ann. Biomed. Eng.* **2017**, *45*, 224–236. [[CrossRef](#)] [[PubMed](#)]
54. Bernhardt, A.; Schumacher, M.; Gelinsky, M. Formation of osteoclasts on calcium phosphate bone cements and polystyrene depends on monocyte isolation conditions. *Tissue Eng. Part C Methods* **2014**, *21*, 160–170. [[CrossRef](#)] [[PubMed](#)]
55. Kular, J.; Tickner, J.; Chim, S.M.; Xu, J. An overview of the regulation of bone remodelling at the cellular level. *Clin. Biochem.* **2012**, *45*, 863–873. [[CrossRef](#)] [[PubMed](#)]
56. Schindelin, J.; Arganda-Carreras, I.; Frise, E.; Kaynig, V.; Longair, M.; Pietzsch, T.; Preibisch, S.; Rueden, C.; Saalfeld, S.; Schmid, B. Fiji: An open-source platform for biological-image analysis. *Nat. Methods* **2012**, *9*, 676–682. [[CrossRef](#)] [[PubMed](#)]
57. Ahrens, J.; Geveci, B.; Law, C. ParaView: An End-User Tool for Large-Data Visualization. In *Visualization Handbook*; Elsevier: Amsterdam, The Netherlands, 2005; pp. 717–731. ISBN 978-0-12-387582-2.

© 2018 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).

DEVELOPMENT OF A CLAY BASED BIOINK FOR 3D CELL PRINTING FOR SKELETAL APPLICATION

Biofabrication

PAPER

Development of a clay based bioink for 3D cell printing for skeletal application

T Ahlfeld^{1,4}, G Cidonio^{2,3,4}, D Kilian¹, S Duin¹, A R Akkineni¹, J I Dawson², S Yang³, A Lode¹, R O C Oreffo^{2,5} and M Gelinsky^{1,5}

¹ Centre for Translational Bone, Joint and Soft Tissue Research, University Hospital Carl Gustav Carus and Faculty of Medicine, Technische Universität Dresden, Dresden, Germany

² Bone and Joint Research Group, Centre for Human Development, Stem Cells and Regeneration, Institute of Developmental Sciences, University of Southampton, Southampton, United Kingdom

³ Engineering Materials Research Group, Faculty of Engineering and the Environment, University of Southampton, Southampton, United Kingdom

⁴ These authors contributed equally.

⁵ Authors to whom any correspondence should be addressed.

E-mail: michael.gelinsky@tu-dresden.de and richard.oreffo@soton.ac.uk

Keywords: Laponite, bioink, bioprinting, growth factor delivery, hydrogels, additive manufacturing

Abstract

Three-dimensional printing of cell-laden hydrogels has evolved as a promising approach on the route to patient-specific or complex tissue-engineered constructs. However, it is still challenging to print structures with both, high shape fidelity and cell vitality. Herein, we used a synthetic nanosilicate clay, called Laponite, to build up scaffolds utilising the extrusion-based method 3D plotting. By blending with alginate and methylcellulose, a bioink was developed which allowed easy extrusion, achieving scaffolds with high printing fidelity. Following extrusion, approximately 70%–75% of printed immortalised human mesenchymal stem cells survived and cell viability was maintained over 21 days within the plotted constructs. Mechanical properties of scaffolds comprised of the composite bioink decreased over time when stored under cell culture conditions. Nevertheless, shape of the plotted constructs was preserved even over longer cultivation periods. Laponite is known for its favourable drug delivery properties. Two model proteins, bovine serum albumin and vascular endothelial growth factor were loaded into the bioink. We demonstrate that the release of both growth factors significantly changed to a more sustained profile by inclusion of Laponite in comparison to an alginate-methylcellulose blend in the absence of Laponite. In summary, addition of a synthetic clay, Laponite, improved printability, increased shape fidelity and was beneficial for controlled release of biologically active agents such as growth factors.

1. Introduction

As more traditional additive manufacturing methods, such as 3D powder printing or selective laser sintering, are commonly used to build up 3D structures/scaffolds with complex geometries [1–4], methods such as extrusion-based 3D plotting are becoming more focused with the potential for bioprinting, namely the layer-by-layer fabrication of scaffolds including cells or biologically active factors, with the advantage of a spatially defined arrangement of cells and/or growth factors within a scaffold [5, 6]. Hydrogels are commonly used for cell encapsulation given their water-rich, biocompatible environment [7, 8].

Based on inkjet printing technologies, the term ‘bioink’ has been established to describe cell-containing hydrogels and was translated to materials of higher viscosity, which are useful for extrusion-based bioprinting. The highly viscous properties demonstrate the pasty character of these materials; hence the term ‘paste’ is used for the bioink presented within this manuscript. The characteristics of the printing pastes have to be tailored with respect to both, printing fidelity and cell compatibility [9]. This includes, amongst others, parameters such as: (i) viscosity of the hydrogel, (ii) the gelation process, (iii) the built network structure and its influence on diffusion and mechanical strength, and furthermore the induced

shear stress caused by the needle gauge [9, 10]. Crucially, printing fidelity is strongly linked to the printing of large-scale, three-dimensional constructs [9]. There are two main strategies to achieve bio-printed constructs at clinically relevant dimensions by extrusion-based 3D printing in air, i.e. without using a liquid or suspension bath as supporting medium: (i) usage of rigid support materials such as poly- ϵ -caprolactone (PCL) that acts as a shape-defining grid offering space and structural integrity to print a soft bioink between the stiff strands [11, 12]. Furthermore, the strand morphology can be modified from a commonly extruded homogeneous strand to a core/shell strand with a stiff shell surrounding a soft core presenting the bioink [13–15]. (ii) Enhancement of the rheological properties, which can be achieved either through pre-crosslinking of the paste [16], or by a crosslinking step immediately after extrusion, e.g. photopolymerization [17]. A third strategy is the temporary increase of the viscosity of the paste by the addition of hydrogels, which do not get stabilised by a further crosslinking step afterwards [18]. Schütz *et al* presented an approach in which the viscosity of a 3 w/v% alginate solution was temporarily increased during fabrication by addition of 9 w/v% methylcellulose to achieve a paste with high viscosity, strong shear thinning behaviour, and therefore good printing fidelity [19]. As methylcellulose is not ionically cross-linked, it was washed out and the alginate, crosslinked by calcium ions, retained the shape of the scaffolds. Extrusion-based printing (3D plotting) of the alginate/methylcellulose blend laden with human mesenchymal stromal cells (hMSC) revealed that 3D constructs with clinically relevant dimensions could be achieved and that a significant proportion of the cells survived the plotting process, however, methylcellulose did not show any functional or biological benefit for the resulting hydrogel matrix. This aspect is addressed in the present work, through the addition of Laponite, a nanosilicate clay with high potential for tissue engineering purposes, in favour of methylcellulose.

Laponite is a synthetic magnesium silicate clay widely employed as filler or thickening agent in the cosmetic industry [20]. Laponite offers significant potential for tissue engineering applications [21] and has been shown to augment cell spreading and osteogenesis in tissue-engineered constructs [22, 23]. The crystalline structure of Laponite consists of layered silicate similar to other clay minerals housing a central magnesium core between two silica sheets. Laponite comprises disc-shaped particles of about 25 nm in diameter and 1 nm in thickness. With a highly negatively charged face and a positively charged rim, Laponite particles can self-assemble through electrostatic interactions to form gel (or glassy) states showing typical characteristics of shear thinning gels [21, 24–26]. Nanosilicates have been widely employed in tissue engineering applications [21, 27]. Blended with

polymers, beneficial improvements of mechanical and biological properties have been found to be a direct consequence of the physical strong interaction between polymeric chains and monodispersed clay [21]. For example, a Laponite gel has been used as bioactive excipient in combination with gelatine methacrylate (GelMA) resulting in a biocompatible hydrogel that could stimulate cell adhesion, proliferation and differentiation [22]. Laponite has been applied as drug delivery agent and proved capable of localising and delivering albumin, lysozyme and bioactive vascular endothelial growth factor (VEGF) in a sustained manner [26]. Crucially, degradation products of Laponite such as Na^+ , Mg^{2+} , $\text{Si}(\text{OH})_4$ and Li^+ are non-toxic and may also exhibit a positive influence on bone metabolism and calcification [28]. Moreover, Laponite continues to attract much interest as rheological enhancer of polymeric solutions, due to its strong shear thinning properties [29, 30].

Alginate is widely used for cell encapsulation and 3D printing applications [31–34]. Ghadiri *et al* showed that the combination of Laponite and alginate increased the viscosity of an injectable hydrogel and improved the Young's modulus of crosslinked scaffolds [35]. Recently, Laponite-alginate gels have been shown to sustain the release of cationic drugs [36]. For example, the suspension significantly improved the release kinetics of doxorubicin [37]. The suspension of Laponite and alginate has been studied for 3D printing by Hong *et al* [38]. The authors reported, that printing of Laponite-alginate was not possible. Printable pastes were achieved in combination with 40% poly(ethylene glycol) diacrylate resulting in the fabrication of scaffolds with high toughness and stretchability [38], however, the potential of this material combination for bioprinting remains to be demonstrated. Most recently, Jin *et al* reported on a highly concentrated Laponite-alginate blend with enhanced shape fidelity, which was seeded with cells after printing [39]. The blend revealed enhanced printability and biocompatibility.

In the present work, we have used 3D plotting as fabrication method for a new developed bioink based on Laponite, alginate and methylcellulose. 3D plotting is an extrusion-based method, without the requirement for high temperatures enabling fabrication at room temperature or physiological conditions [40]. The integration of Laponite led to a decrease of the requisite methylcellulose, while the printing fidelity was maintained as indicated by scaffolds, which could be fabricated in clinically relevant dimensions with high shape fidelity. Moreover, cell survival was observed to be increased in comparison to alginate-methylcellulose scaffolds. In addition, we demonstrate high cell viability of hTERT-MSC after extrusion. The current studies demonstrate the new bioink displayed significant mechanical weakening *in vitro*, probably due to the interaction of nanosilicates and alginate. Laponite inside the alginate-methylcellulose blend led

Table 1. Nomenclature of the tested pastes (all numbers in weight%).

Label	Laponite	Alginate	Methylcellulose
3-0-0	3	0	0
0-0-3	0	0	3
3-3-0	3	3	0
3-3-3	3	3	3
3-3-6	3	3	6
0-3-9	0	3	9

to favourable drug delivery properties evidenced by sustained release of a model protein bovine serum albumin (BSA) and an angiogenically relevant growth factor VEGF.

2. Materials and methods

2.1. Paste preparation

The composition of the plotting pastes tested in this study is shown in table 1. 0.3 g of Laponite powder (Laponite XLG, BYK Additives & Instruments, UK) was dispersed under rapid agitation in 10 ml deionized water. For the blends, 0.3 g alginate (alginic acid sodium salt from brown algae, 71238, Sigma, UK, M/G ratio 1:2) were added and dissolved under stirring until a homogeneous solution was obtained. Optionally, 0.3 or 0.6 g methylcellulose powder (M0512, Sigma, USA, molecular weight $\approx 88\,000$ Da, 4 000 cP) were carefully mixed in with a spatula; the resulting blends were set overnight to allow swelling of the methylcellulose. Pure methylcellulose was made accordingly by dissolving 0.3 g of the raw powder in 10 ml water. Materials for cell incorporation were sterilised by autoclaving. 3 w/v% alginate/9 w/v% methylcellulose was prepared as described by Schütz *et al* [19]. Briefly, alginate was dissolved in PBS overnight. Autoclaved methylcellulose was subsequently added and swelling of methylcellulose was allowed for 2 h to obtain a plottable paste.

2.2. Rheology

Viscosity of the pastes was measured both at constant and increasing shear rates using a plate rheometer (Rheotest RN 4, Medingen, Germany) with a plate-plate-distance of 0.1 mm. Viscosity of the pastes was determined by applying a constant shear rate of 10 s^{-1} for 300 s. Shear thinning was tested by increasing the shear rate from 0 to 50 s^{-1} over 600 s (increment = 0.08 s^{-1}). After an initial amplitude sweep test to detect the viscoelastic region, oscillatory frequency sweep tests ($f = 0.01\text{--}10\text{ s}^{-1}$) were performed on 0-0-3, 3-3-0 and 3-3-3 pastes (see table 1 for labels) and storage modulus as well as loss modulus were measured.

2.3. Scaffold fabrication

The 3-3-3 paste was used for scaffold fabrication and cell plotting. The paste was extruded through γ -irradiated conical plastic needles with an inner diameter of $410\text{ }\mu\text{m}$ using compressed air (air pressure: 80–95 kPa); 3D plotting was conducted in air using a Bioscaffolder 3.1 (GeSiM, Radeberg, Germany) with a speed of $8\text{--}10\text{ mm s}^{-1}$. Scaffolds were plotted in different dimensions. If not differently detailed within this manuscript, scaffolds were plotted with a base of $10 \times 10\text{ mm}^2$ with an alternating layer pattern (ABAB, $0^\circ/90^\circ$), a layer height of $230\text{ }\mu\text{m}$ and a strand distance of 2 mm. Immediately after plotting, scaffolds were incubated for 10 min in 100 mM CaCl_2 solution to enable crosslinking.

2.4. Characterisation of the plotted scaffolds

2.4.1. Microscopy

Macroporous structure of the scaffolds was imaged using a stereo light microscope (Leica M205 C equipped with DFC295 camera, Germany). Further analysis was performed using scanning electron microscopy (SEM; Philips XL 30/ESEM, operated in SEM mode) at a voltage of 3 kV (spot size 3) with field emission gun. Prior to SEM, samples were dehydrated through an ascending ethanol series ending in 100% ethanol and finally by critical point drying. Energy-dispersive electron spectroscopy (EDX) mapping was performed at a voltage of 12 kV.

2.4.2. Volumetric strand swelling

Volumetric swelling of the plotted scaffolds was investigated by measuring the strand width at different time points: before crosslinking, after crosslinking, and after 1, 2, 3, 5, 7, 14 and 21 days of incubation in cell culture medium consisting of DMEM (Dulbecco's Modified Eagle's Medium, Gibco, Thermo Fisher), 10% fetal calf serum (FCS), 100 U ml^{-1} penicillin and 100 mg ml^{-1} streptomycin (Pen/Strep) (all from Biochrom, Berlin, Germany) under cell culture conditions. For measuring, pictures of different scaffolds ($n = 5$) were taken using a stereo light microscope and analysed with ImageJ (1.44p, National Institutes of Health, Bethesda, Maryland, USA).

2.4.3. Mechanical test

To evaluate the mechanical behaviour of the plotted scaffolds, two different geometries were compared: a porous scaffold with a strand distance of 2 mm and a solid scaffold without pores obtained by depositing strands next to each other without a strand gap. Uniaxial compressive tests were applied to scaffolds ($A = 10 \times 10\text{ mm}^2$, $h = 5\text{ mm}$) after 1 day and 21 days of incubation in cell culture medium and Young's modulus and compressive strength were obtained from the data. Furthermore, dynamic mechanical analysis (DMA) was performed to investigate the resistance of the scaffolds against shear stress.

Therefore, frequency sweep tests ($f = 0.01\text{--}10\text{ s}^{-1}$) were applied with a plate rheometer (Rheotest RN 4). Scaffolds were twisted between two plates at a strain of 10% and the storage moduli were measured.

2.5. Fabrication of cell-laden scaffolds

For cell plotting, an immortalised human mesenchymal stem cell line expressing hTERT (human telomerase reverse transcriptase) [41] was used. The hTERT-MSCs were kindly provided by Professor Matthias Schieker (Laboratory of Experimental Surgery and Regenerative Medicine, University Hospital Munich (LMU), Germany). The cells were expanded in cell culture medium (DMEM + 10% FCS + 1% Pen/Strep); after harvesting, 5×10^6 cells were suspended in 100 μl of cell culture medium and then carefully mixed into 1 g of the 3-3-3 blend. 3D plotting of cell-laden scaffolds was performed with the parameters mentioned before, crosslinking was carried out following incubation in 100 mM CaCl_2 for 10 min.

2.5.1. Viability of cells in plotted scaffolds

Initially, hTERT-MSCs were labelled using lipophilic carbocyanine DiD (1,1'-dioctadecyl-3,3,3',3'-tetramethylindodicarbocyanine) (Vybrant DiD cell-labelling solution, Thermo Fisher Scientific, Eugene, OR, USA) following the manufacturer's protocol. Living cells were identified by Calcein AM staining (Molecular Probes, Eugene, OR, USA) after 1, 7, 14 and 21 days. Viable cells were marked with both, DiD and Calcein staining while dead cells only showed DiD signal. Therefore, conclusions on cell viability ratio could be drawn following confocal laser scanning microscopy (cLSM) (Leica TCS SP5, Leica Microsystems, Wetzlar, Germany) at specific fluorescence wavelengths of DiD (Ex: 644 nm; Em: 665 nm) and Calcein (Ex: 494 nm; Em: 517 nm). Quantification of the percentage of living cells was achieved by relating the number of Calcein stained cells (green) to the number of DiD stained cells (red). Therefore, three scaffolds per time point were imaged at five positions, respectively. The resulting z-stacks were analysed. Counting was performed by the particle analyser of ImageJ (1.44p, National Institutes of Health, Bethesda, Maryland, USA). To avoid artefacts of fluorescent Laponite, cell sizes were evaluated to be in dimensions of 20–600 pixel.

2.5.2. Cell density determination

Cell density within the scaffolds at different time points was calculated by evaluation of the confocal pictures, utilising ImageJ Particle analyser. Areas of $800 \times 800\text{ }\mu\text{m}^2$ were analysed with respect to the stack height. Resulting cell numbers were divided by the observed scaffold volume.

2.6. Protein and growth factor release

2.6.1. BSA loading and release

Bovine serum albumin (BSA, Sigma-Aldrich) was loaded within the 3-3-3 paste by adding 100 μl of BSA stock solution ($c = 10\text{ mg ml}^{-1}$) to 1 g of the paste. To examine the influence of Laponite, release was compared to a Laponite-free paste, 0-3-9, which was loaded equally. Immediately after loading, the pastes were used for plotting scaffolds (4 layers, $10 \times 10\text{ mm}^2$), followed by crosslinking with a 100 mM CaCl_2 solution for 10 min. Samples ($n = 5$) were incubated in 1 ml of Hank's balanced salt solution at 37°C over 21 days. Release solution was replaced after certain time points (2 h, 4 h, 1 d, 2 d, 3 d, 5 d, 7 d, 10 d, 14 d, 21 d) and BSA amount in the supernatants was quantified by Bradford assay using Roti® Nanoquant (Roth, Karlsruhe, Germany).

2.6.2. VEGF loading and release

3-3-3 and 0-3-9 pastes were loaded with VEGF (rhVEGF-A165; Biomol, Hamburg, Germany) by mixing 100 μl of VEGF stock solution ($c = 100\text{ }\mu\text{g ml}^{-1}$) to 1 g of the paste. Immediately after mixing, the VEGF-containing hydrogel pastes were plotted to scaffolds (6 layers, $10 \times 10\text{ mm}^2$), aiming for a theoretical loading of 700 ng each. After crosslinking with 100 mM CaCl_2 , samples ($n = 8$) were incubated in 1 ml of release medium consisting of Endothelial Cell Basal Medium MV (Promocell, Heidelberg, Germany) supplemented with 15% heat-inactivated FCS and Pen/Strep under cell culture conditions. Supernatants were taken at various time points (2 h, 4 h, 1 d, 2 d, 3 d, 5 d, 7 d) and replaced by fresh medium. Plotted scaffolds without VEGF were used as negative controls. VEGF in the supernatants was quantified by ELISA; an endothelial cell proliferation assay was performed to study maintenance of its biological activity.

2.6.3. ELISA for VEGF quantification

ELISA using goat anti-human VEGF (Sigma-Aldrich) as capture and biotinylated goat anti-human VEGF (R&D Systems, Minneapolis, USA) as detection antibody was applied as described previously [42]. VEGF standard was used to perform a calibration line.

2.6.4. Endothelial cell proliferation assay

Biological activity of released VEGF was previously examined as described [42]. Briefly, human dermal microvascular endothelial cells (HDMEC, Promocell) were seeded in 96 well plates (2000 cells/well) and incubated in fresh release medium (Endothelial Cell Basal Medium MV with 15% heat-inactivated FCS and Pen/Strep), mixed 1:1 with the release solutions from either VEGF-laden samples or negative controls. After 72 h, the cell number was determined by DNA quantification utilising the Quantifluor® dsDNA system (Promega). Determined DNA values of VEGF-

laden samples were compared to DNA of the negative controls at every time point (set as 1).

2.7. Statistical analysis

All values were evaluated by one-way analysis of variance followed by Bonferroni's multiple comparison tests (GraphPad Prism 7). Significant differences were assumed at $p < 0.05$.

3. Results

3.1. Blend preparation and evaluation of rheological behaviour

The Laponite-alginate-methylcellulose pastes were prepared by blending 3 w/v% of Laponite suspension with 3 w/v% of alginate and 3 w/v% and 6 w/v% of methylcellulose, respectively. Viscosities of the different paste compositions are shown in figure 1(a), compared to a Laponite-free control 0-3-9. Autoclaving was chosen as the sterilisation method and performed on the final paste ('autoclaving of paste') or on the powders prior to dissolving ('autoclaving of powder'). Viscosities were investigated and compared to non-autoclaved materials ('w/o autoclaving'). All groups showed that viscosity is not strongly altered following autoclaving of the final paste. In contrast, autoclaving of the powders before suspension led to significantly lower viscosities. Pure Laponite paste (3-0-0) demonstrated a low viscosity of 2–7 Pa s. The addition of alginate (3-3-0) increased the viscosity to 7–18 Pa s. In combination with methylcellulose a paste with high viscosity increase was observed. After 3% methylcellulose addition (3-3-3), viscosity increased significantly to 60–100 Pa s. Further increase of methylcellulose content (3-3-6) led to higher viscosity of 200–250 Pa s. 0-3-9 revealed a viscosity of 42.1 ± 5.2 Pa s, which was lower than the viscosities of the 3-3-3 pastes. All compositions showed shear thinning effects at increasing shear rates, enabling extrusion through nozzles, evidenced by pastes w/o autoclaving in figure 1(b). Subsequently, the pastes were tested for their plotting behaviour. While pastes comprising 3-0-0 and 3-3-0 were not useful to generate three-dimensional structures (plotted strands collapsed immediately after extrusion), 3-3-3 paste allowed plotting with high shape fidelity. 3-3-3, sterilised by powder autoclaving, was extrudable at lower pressures compared to 3-3-3, which was autoclaved as paste. As expected, the 3-3-6 blend was also able to generate scaffolds with excellent shape fidelity, although needed high pneumatic air pressures (>250 kPa) for extrusion, which may have been to harmful for cell plotting. Therefore, a 3-3-3 blend, powder autoclaved, was chosen as a suitable paste for bioprinting, given the excellent shape fidelity of the plotted constructs, as well as the modest pressure (80 kPa) needed for extrusion. All further results relate to scaffolds, fabricated using this material. Figure 1(c)

shows oscillatory frequency sweep tests of the powder autoclaved 3-3-3 blend in comparison to pure methylcellulose (0-0-3) and the blend without methylcellulose (3-3-0). The pastes revealed viscoelastic behaviour and had been tested at an amplitude in the viscoelastic region, determined by amplitude sweep tests (data not shown). The storage modulus G' can be seen as an elastic, gelled component, while the loss modulus G'' describes the viscous, non-gelled component of the paste. The 3-3-0 and 3-3-3 pastes displayed a higher storage modulus than loss modulus over a broad range of angular velocities. 0-0-3 had a higher loss modulus until an angular velocity of 24.5 s^{-1} . At this crossover point, the paste lost its viscous properties and behaved like an elastic solid, evidenced by the higher shear modulus.

3.2. 3-3-3 plotted scaffolds with high shape fidelity and appearance of plotted structures

Plotting of the 3-3-3 paste was successfully performed without any stabilising liquid by extrusion in air using a dosing needle with an inner diameter of $410 \mu\text{m}$. After crosslinking, constructs of high accuracy in dimensions suitable for cell culture and clinical applications ($20 \times 20 \text{ mm}^2$) were achieved (figure 2). Tubular, vessel-like structures (figures 2(a) and (b)) were plotted without limitations at scaffold heights of 2 cm. Cubic structures with 30 layers revealed shape preservation with increasing height (figures 2(c) and (d)). Figures 2(e)–(h) show complex geometries plotted by change of the layer orientations (20° , 45° , 60° , 72°), remained stable after crosslinking yielding different pore geometries. By changing the stacking sequence from ABAB ($0^\circ/90^\circ/0^\circ/90^\circ$) to AABB ($0^\circ/0^\circ/90^\circ/90^\circ$), pores in lateral direction were formed and stayed stable even at profiles with more than 25 layers (figures 2(i) and (j)).

SEM analysis of 3-3-3 plotted scaffolds revealed differences of the microstructure between the outer surface and the inner structure of the strands. Figure 3 shows a top view of the observed surfaces (a), (b), (e), (f) with a dense, smooth surface, which remained predominantly unaltered over 21 days of culture. The lateral view of sliced scaffolds (c), (d), (g), (h) displayed inhomogeneous strand structures with rough (i), (iii) and smooth (ii), (iv) areas. The rough surfaces appeared porous and netlike, while the smooth surfaces were noted to be dense and compact. After 21 days, these surfaces appeared smoother in contrast to day 1.

Energy-dispersive x-ray spectroscopy (EDX) analysis demonstrated the presence of Laponite and integration within the plotted structure (figure 4). As expected, a small amount of sodium was detected, arising from alginate and Laponite crystal structure. Moreover, calcium ions were observed, as a consequence of crosslinking with the CaCl_2 solution. Mapping of silicon and magnesium, shown in

figures 4(c)–(f), revealed distribution of Laponite across the whole cross section of the strand. However, silicon and magnesium were noted to be heterogeneously distributed evidenced by areas in which these ions could not be detected.

3.3. *In vitro* stability of plotted 3-3-3 scaffolds

Plotted 3-3-3 scaffolds were crosslinked using 100 mM CaCl_2 solution and incubated in cell culture medium over 21 days. At fixed time points, the scaffolds were imaged and strand diameters were determined (figure 5). After plotting, the strand diameter was noted to be $420 \pm 32 \mu\text{m}$, which is slightly larger than the needle diameter ($410 \mu\text{m}$). After 10 min incubation in CaCl_2 solution, the strand diameter increased significantly to $500 \pm 57 \mu\text{m}$.

Following incubation in cell culture medium, the strands were observed to further swell slightly to a diameter of $553 \pm 49 \mu\text{m}$ within the first 6 h. After day 7, no significant changes in the strand diameter were detected. After 14 days, strand diameter increased to $607 \pm 46 \mu\text{m}$, but did not change significantly until day 21. In conclusion, the strands of plotted 3-3-3 scaffolds were observed to swell by approximately 46% after plotting and 20% after crosslinking and subsequent incubation in cell culture medium at physiological conditions (37°C) over 21 days.

During incubation, it was observed that plotted scaffolds retained their three-dimensional shape. However, the scaffold handling changed dramatically, from a flexible and tough scaffold to a softer scaffold, with reduced mechanical properties. Mechanical

Figure 2. Scaffolds can be plotted from the 3-3-3 paste with high accuracy in clinically relevant dimensions and shapes. (a) Tube-like structures with varying heights (2 cm, 1.5 cm, 1 cm). (b) Top view of tube (2 cm). (c) Cubic structures with 30, 20 and 10 layers. (d) Top view of cube (30 layers). (e)–(h) Top view of scaffolds with different layer orientations. (i), (j) Pores in lateral direction in scaffolds with double layers (AABB).

Figure 3. SEM pictures of plotted 3-3-3 scaffolds after 1 day and 21 days of incubation under cell culture conditions. The top view (a), (b), (e), (f) revealed strands with low roughness. Side views of cut, double-layered scaffolds (stacking sequence: AABB) (c), (d), (g), (h) showed lateral macropores and a more heterogeneous appearance of the strand cross sections with different areas, marked by white arrows and shown at higher magnification (i), (ii), (iii), (iv).

characterisation of 3-3-3 plotted scaffolds was performed to study softening over time and long-term stability of the scaffold. Young's modulus and compressive strength of uniaxial compressive tests were obtained at day 1 and 21 (figures 6(a) and (b)). As expected, both the Young's modulus and the compressive strength were higher for non-porous, solid scaffolds compared to porous ones. The Young's moduli

decreased significantly from day 1 to day 21 (176 ± 8.9 kPa to 28.6 ± 9.3 kPa (porous) and 226 ± 28.8 kPa to 54 ± 32.3 kPa (solid), respectively). The compressive strength was also observed to change significantly from 40.8 ± 4.7 kPa to 1.6 ± 0.4 kPa (porous) and 53.8 ± 11.4 kPa to 8.4 ± 3.0 kPa (solid). DMA was performed on the scaffolds. After defining the viscoelastic region by

amplitude sweeps (data not shown), oscillatory frequency sweeps were measured. Data obtained at day 1 demonstrated a higher storage modulus for porous scaffolds (~ 730 Pa) compared to solid scaffolds (~ 70 Pa) (figure 6(c)). Both curves were almost constant over the observed range of angular velocities. After 21 days, both the porous and solid scaffolds exhibited increasing storage moduli with linear slopes. The storage moduli of solid scaffolds were noted to be slightly higher than those of porous scaffolds.

3.4. Cell-laden constructs preserved morphological properties and cell viability after 21 days

An immortalised human stem cell line (hTERT-MSC) was used to demonstrate the viability of cells encapsulated in 3D plotted constructs comprising of 4 layers (figure 7). The technique of Calcein/ethidium homodimer-1 (live/dead staining) for cell characterisation could not be used as the Laponite absorbed the ethidium homodimer-1 providing a misleading result. Therefore, DiD prestaining was employed to alleviate artefacts from Laponite adsorption and to show cell presence and viability (DiD signal is independent from cell viability) (figure 7: red). Crucially, we were able to demonstrate the presence of metabolically active, viable cells using Calcein (figure 7: green). The cells were observed to be distributed homogeneously over the whole scaffold retaining a round, circular morphology and an absence of cell spreading. For cell viability determination, 3-3-3 was compared to a Laponite-free 0-3-9 blend, which was developed before [19]. Comparison of the number of living cells inside the 3-3-3 blend revealed a cell viability of approximately 70%–75% after plotting (figure 8(a)). In the Laponite-free

control, cell viability was slightly lower after plotting and significantly lower after 7 d (60%–65%) compared to the 3-3-3 blend. At later time points, cell viability within the 0-3-9 blend increased and was significantly higher after 21 days. The cell density of the plotted cell-containing scaffolds of 3-3-3 and 0-3-9 is shown in figure 8(b) (day 1 set as 100%). While the cell density inside 3-3-3 did not change significantly over time, it decreased significantly from day 1 to day 14 for the Laponite-free control 0-3-9 ($p < 0.001$). This indicates that the number of both living and total cells was stable inside 3-3-3, while it decreased inside 0-3-9.

3.5. Laponite enhanced the BSA and VEGF release kinetics of alginate-methylcellulose blends

To study the growth factor release capabilities of plotted 3-3-3 scaffolds, the model proteins BSA and VEGF were used. To evaluate the influence of Laponite, release from a 0-3-9 blend was studied in comparison to 3-3-3 scaffolds. 3-3-3 and 0-3-9 pastes were loaded with the same amount of BSA ($c = 10 \text{ mg ml}^{-1}$) or VEGF ($c = 100 \text{ µg ml}^{-1}$) prior to plotting. Cumulative release of BSA over 21 days is shown in figures 9(a) and (b). While 0-3-9 showed a high initial burst release of $53.8 \pm 5.7 \text{ µg}$ after 4 h, BSA released from 3-3-3 scaffolds was observed at only $2.2 \pm 0.7 \text{ µg}$. Up to day 21, only restricted release of BSA from 0-3-9 was measured, the cumulative release increased to a level of $61.7 \pm 6.5 \text{ µg}$. In contrast, release between 4 h and 21 days from 3-3-3 was significantly higher and after 21 days, $18.0 \pm 1.5 \text{ µg}$ had been released. However, results indicated, that a significant amount of BSA was retained within the 3-3-3 blend. Figures 9(c) and (d) show the release of

VEGF over 7 days. Again, 0-3-9 revealed an initial burst release, with 149.0 ± 12.9 ng VEGF after 4 h. In contrast, VEGF release from 3-3-3 scaffolds was 0.26 ± 0.05 ng. While the release of 0-3-9 decreased over time, the cumulative release profile of 3-3-3 was almost linear, indicating a sustained release of VEGF. After 7 days, 0-3-9 showed a total release of 275.7 ± 22.4 ng; while the 3-3-3 scaffolds released significantly less (8.3 ± 1.0 ng). As observed for BSA, a significant amount of the growth factor was retained inside the 3-3-3 blend. Released VEGF from 3-3-3 maintained its bioactivity at all evaluated time points (figure 9(e)). Endothelial cells, incubated in the release medium from VEGF-laden scaffolds showed enhanced proliferation in comparison to cells incubated in the supernatants of negative controls (set as 1).

4. Discussion

Bioprinting has evolved as excellent approach to arrange cells in an ordered fashion [43]. However, printing of three-dimensional structures with high shape fidelity while simultaneously providing an appropriate environment for embedded cells remains challenging. The approach presented in this paper

sought to blend alginate as a bioink with two materials, methylcellulose and Laponite, in order to enhance both, viscosity and biofunctionality. Alginate was shown before to be beneficial for 3D printing applications, due to its printability and biocompatible cross-linking capabilities with calcium ions [16, 44, 45]. Earlier studies presented methylcellulose to heavily increase the viscosity of a cell-laden alginate hydrogel enabling printing of scaffolds with embedded hMSC in clinically relevant dimensions [19]. Aqueous Laponite suspensions possess shear thinning properties drawing interest as injectable material and for 3D printing [23]. Moreover, the significantly high potential of Laponite gels for cell embedding and drug delivery in tissue engineering has been demonstrated [21, 26].

Plain Laponite suspension only (3-0-0) as well as a Laponite-alginate combination (3-3-0) did not enable the generation of three-dimensional structures. In contrast, the addition of 3% and 6% methylcellulose (3-3-3 and 3-3-6) resulted in a significant increase in viscosity and allowed the plotting of strands with a shape fidelity comparable to the 0-3-9 blend described previously [19]. Preparation of an alginate-free paste was not possible, given methylcellulose separated from the Laponite suspension. The gel-like Laponite-alginate composite prevented phase separation of

dehydrated methylcellulose agglomerates, which enabled homogeneous hydration of the methylcellulose chains resulting in a uniform paste. The reduced content of methylcellulose required to achieve appropriate plotting results is likely to have arisen from additional electrostatic interactions between Laponite surfaces and alginate chains, as demonstrated by other groups exploring Laponite-alginate based nanocomposites [35, 46]. These crosslinks were indicated by frequency sweep tests, as the shear modulus (elastic response of a hydrogel) of 3-3-0 and 3-3-3 was higher than the loss modulus (presenting the viscous response). The elastic response is mainly a consequence of crosslinks between polymer chains [10]. Earlier, the elastic response of a Laponite-polymer blend was shown to result from Laponite mediated crosslinks between the polymer chains [30]. The loss modulus of the 3-3-0 paste was furthermore noted to decrease over angular velocity confirming the nature of non-covalent interaction between Laponite and alginate chains. At low angular speeds, pure methylcellulose (0-0-3) had a higher loss modulus than storage modulus, demonstrating absent crosslinked polymer chains and flowing of the material. With increasing angular speeds, the chains entanglements acted increasingly like fixed junctions, resulting in a faster increasing storage modulus. Hence, after the crossover point, when the storage modulus was higher than the loss modulus, the methylcellulose paste behaved like an elastic solid [47]. However, Laponite-alginate

nanocomposite interaction remains to be fully investigated and understood. Ghadiri *et al* have shown hydrogen bonds between silica nanoparticles and alginate carboxylic groups [35]. Although an interaction of methylcellulose with Laponite gel cannot be excluded, it is expected that Laponite will bind preferentially to alginate, due to the strong electrostatic polarities of Laponite and alginate and the negligible polarity of methylcellulose. Critically, Laponite-alginate composite structure assembly has not been postulated theoretically before. Thus, we hypothesise a specific supramolecular assembly interaction between Laponite and alginate. Laponite nanodiscs, given their dual ionic character, interact with guluronic and mannuronic acid groups present in the alginate polysaccharide chain occupying ionic pocket where calcium ions should be positioned, providing a temporary linkage between the long alginate molecules.

The rheological behaviour of the pastes was strongly dependent on the sterilisation process. When the individual components are autoclaved, there is literature evidence for the following: (i) alginate suspension degrades with a measurable loss of molecular weight leading to decreased viscosities [48], (ii) high temperature is likely to facilitate the Laponite gel aging process, enhancing the gel structure [49], and (iii) methylcellulose is a thermoreversible gel; at higher temperatures aggregation will occur and gelation of methylcellulose starts, resulting in higher viscosities [50]. However, after cooling down, gelation declines

Figure 7. cLSM images of all cells (red), living cells (green) and merged channels including the brightfield image as a comparison over 21 days. All cells (red) were prelabelled prior to plotting with DiD lipophilic dye and represent both viable and dead cells. Metabolically active cells (green) were stained additionally with Calcein and represent the amount of living cells (scale bars = 250 μm).

Figure 8. Ratio of viable cells in relation to total cell count over 21 days, determined by cell number analysis in cLSM pictures. (a) 3-3-3 samples revealed a cell viability of 70%–75% for all time points. The 0-3-9 control showed a lower cell viability of 60%–65% at day 1 and 7 before a higher cell viability after 14 d and 21 d was observed. (b) Cell density obtained by the image stacks (day 1 was set as 100%). No significant change of the cell number and density was detected over a culture period of 21 days for 3-3-3 samples. The cell density of 0-3-9 decreased significantly over time (mean $\pm$ SD, $n = 15$, *** $p < 0.001$).

and viscosity enhancement may be caused by hydration of the polar groups of methylcellulose [51], independently of the sterilisation method. In pastes, autoclaved after mixing the components, alginate degradation after sterilisation was compensated by Laponite strengthened network (3-3-0). This could explain why slightly increased viscosities were measured. When autoclaving all three materials prior to mixing ('autoclaving of powders'), a strong network

formation of Laponite nanodiscs did not take place. The reduction of the viscosity compared to other autoclaving methods might only be caused by alginate degradation.

Scaffolds plotted from 3-3-3 paste displayed high shape fidelity and could be plotted in clinically relevant dimensions. Importantly, through changing the stacking sequence to double layers (AABB) lateral pores were achieved. The high shape fidelity is

Figure 9. Release of model proteins from 0-3-9 and 3-3-3 plotted scaffolds. (a), (b) Cumulative release curves of BSA. 0-3-9 showed a high initial burst, while 3-3-3 demonstrated a more sustained release. Data suggest, that a significant amount of BSA remained inside 3-3-3 blend after 21 days. (c), (d) Cumulative release curves of VEGF. Again, high initial burst was observed from 0-3-9 scaffolds, while VEGF from 3-3-3 was released in a sustained manner. After 7 days, 3-3-3 released significantly less VEGF than 0-3-9. However, from day 5 and day 7, absolute release of both scaffolds was roughly the same. (e) Bioactivity of VEGF in supernatants of 3-3-3 scaffolds in comparison to supernatants of negative controls (set as 1). VEGF retained its bioactivity at every time point.

connected to the viscosity enhancement by methylcellulose addition, which is not crosslinked by cations, and therefore could diffuse out of the material blend [19]. EDX confirmed Laponite integration into the hydrogel matrix and distribution within the strands. Based on the heterogeneous pattern observed for silicon and magnesium ion distribution, it is assumed that there are areas enriched with Laponite gel adjacent to areas predominantly formed by the alginate hydrogel. Due to the differences in the chemical composition of Laponite and alginate, reflected e. g. by charge density and distribution [21], it is possible that

the heterogeneous material/ion pattern had an influence on cell behaviour. However, no obvious cell clustering or cell morphology pattern across the scaffolds was observed. Moreover, it is likely the topography of the cross sections which could alter electron detection during EDX mapping, and therefore limiting comparison to the different zones, which were seen in the electron microscopy images. Ongoing work is focused on a detailed investigation of the behaviour of skeletal stem cell populations embedded in the 3-3-3 bioink.

Comparison of SEM images of day 1 and day 21 revealed that plotted strands retained their shape over

the culture period with only modest increase in strand dimensions; quantification of volumetric swelling supported this observation, as the increase of the width of plotted 3-3-3 strands was approximately 20% from day 1 to day 21. It has been previously shown, that Laponite has a positive impact on the swelling properties of alginate gels [36]. However, uniaxial compressive tests revealed a strong change in the mechanical behaviour of the scaffolds. Moreover, comparison of the storage moduli from DMA after 1 and 21 days showed a change from a linear curve, indicating a crosslinked hydrogel, to an increasing line with a linear slope, indicating a less crosslinked condition [52]. It has been reported that changes in the degree of crosslinking of an alginate hydrogel network affect both, swelling and resistance against mechanical load [53, 54].

The network of the crosslinked 3-3-3 blend appeared to change over time. Alginate gets cross-linked by divalent cations such as calcium [55], but was also shown to interact with Laponite [35]. The zwitterionic charge structure of Laponite presents a range of possible modes of interaction with charged polymers. Furthermore the presence of ions such as calcium can cause aggregation of dispersed clay particles and initiate gelation through particle-particle interactions. [27]. Therefore, a strong mutual influence of the alginate network formation and the Laponite arrangement can be expected. Migration of calcium ions from the alginate chains to the Laponite particles followed by a rearrangement of the single components might have occurred and resulted in changes of the network structure which caused the drop of stiffness and changes of viscoelastic properties after 21 days. The significant decrease of Young's moduli after 21 days of culture additionally could be related to excessive protein adsorption by 3-3-3 paste. The interaction of cations, proteins, Laponite discs and alginate chains and its influence on network formation will be object of further investigations.

Although, degradation of tissue engineering scaffolds is essential for their use *in vivo* [56], a preservation of the network structure could prove beneficial effects for culture *in vitro*, e.g. for applying long-term cell culture experiments, which are important for further characterisation or differentiation and maturation of cells *in vitro*. The latter could be achieved by additional crosslinking steps (e.g. immersion in CaCl_2 solutions) carried out regularly at certain time points of culture or by an increased calcium concentration in the medium, which even was shown to be beneficial for skeletal tissue applications [57, 58]. Moreover, the presence of alginate inside the bioink enables further control over mechanical properties, due to its strong dependency on the concentration and type of covalent cation, which crosslinks alginate polymer chains [45, 59]. In general, the mechanical degradation was observed for solid and porous scaffolds, respectively. As expected, the non-porous, solid scaffolds revealed

higher mechanical strength, than porous scaffolds (porosity is central in consideration of mechanical impairment) [56]. Oscillatory frequency sweep measurements showed a distinct lower storage modulus of solid scaffolds, which could be a sign of a less cross-linked hydrogel compared to macroporous scaffolds. The higher surface area of these macroporous scaffolds should be responsible for more effective cross-linking compared to scaffolds with closed macropores.

Cells embedded in the 3-3-3 paste exhibited a higher cell viability (70%–75% active cells) after plotting compared to cells suspended in the 0-3-9 blend [19]. In the absence of Laponite a slight drop in cell viability was observed at earlier time points in 0-3-9 blends whereas cell viability was stable across the time-course in the 3-3-3 blend. This was reflected in the significantly lower viability in 0-3-9 versus 3-3-3 at day 7. Interestingly, the cells that remained at later time points in 0-3-9 blend displayed a higher proportion of viable cells, albeit at a considerably lower total cell density. In conclusion, Laponite inclusion was beneficial for biological function of the paste. This could be related to the positive influence of Laponite itself, as well as the reduction of the total solid content [9] or the content of methylcellulose. The analysis of living cells was performed by comparison of metabolically active cells and pre-stained cells, defining both, living and dead cells. Counting of the cell number was performed by analysis of microscopic pictures. Thresholding was applied for every single picture, averaged and then applied to all pictures. Then, number of cells was analysed and cell viability was calculated. Cell viability was stable over 21 days, without significant decrease of the cell number over time. Therefore, metabolically inactive, dead cells could likely be a consequence of shear forces during the extrusion process or mixing of the cells with the plotting paste prior to extrusion. Bioprinting through nozzles, forces shear stress inside a gel that can cause cell death [17, 60]. Over the culture period of 21 days, cells presented a round-shaped morphology indicating limited interaction with the blend components. Favourable characteristics of Laponite, including support of cell proliferation or adhesion [22], were not observed. Alginate is known for its poor cell adhesive properties [61], apparently, in this study, preventing strong cell activity within the cell-laden 3-3-3 paste. Furthermore, the drop of stiffness of the scaffolds could limit cell activity [62]. However, the favourable interactions of Laponite with polarised substances suggest promising options for loading of adhesive and growth factors to the material prior or after plotting, which might promote cell functions [26, 63].

In this respect, initial steps were made by loading model proteins BSA and VEGF to Laponite-containing 3-3-3 paste and Laponite-free paste 0-3-9 before plotting and studying their release from plotted scaffolds. The inclusion of Laponite to the hydrogel changed the protein release kinetics dramatically. Thus,

while 0-3-9 showed a high initial burst release of both proteins, 3-3-3 compositions limited burst release of proteins. This may be due to the higher inner porosity of 0-3-9, but likely results from the strong electrostatic binding sites of 3-3-3 caused by Laponite nanodiscs [26], which are not present in 0-3-9. The electrostatic interaction of Laponite with BSA and VEGF may also explain smaller differences in the release curves of BSA and VEGF. BSA is negatively charged, while VEGF has a positive total charge. Therefore, different bond strengths of the proteins and Laponite could be a reason for differences between BSA and VEGF release. The obtained results suggested that most of the proteins were still retained inside the 3-3-3 blend after 7 and 21 days, respectively. Similar effects have been found by Ding *et al* following FGF2 loading, who demonstrated, that pure Laponite gels released only negligible amount of growth factor after 35 days [63]. It was shown, that different electrostatic interactions within Laponite blends changed growth factor binding, and therefore its release [63]. The physical interaction of alginate and Laponite could influence the factor binding capabilities as well; in consequence, a release of growth factors might only be possible due to polymer presence.

5. Conclusion

Nanocomposite hydrogels represent an intriguing alternative for 3D bioprinting materials. Particularly, Laponite silicate clay as a versatile nanomaterial can be employed as filler for multiple polymeric platforms. In this paper, a novel nanocomposite from Laponite, alginate and methylcellulose has been synthesised and characterised. The potential of Laponite as a colloidal ligand in alginate and methylcellulose paste has been investigated, allowing decreasing polymeric content and a development towards a potential composite drug delivery system. Autoclaving of the single components before dissolution led to a paste with appropriate shear thinning properties for extrusion. Post-printing *in vitro* degradation of the plotted structures could arise from Laponite interaction with alginate and methylcellulose polymeric chains. Further experiments are ongoing to confirm the final interaction between 3-3-3 components. After plotting, a high cell viability was obtained, which was maintained over 21 days. Moreover, the bio-functional benefits of Laponite inside the paste were evidenced by the sustained release of the model proteins BSA and VEGF. The current studies demonstrate the exciting potential of a Laponite-alginate-methylcellulose (3-3-3) paste as a robust, scalable, reliable bioink for 3D printing applications.

Acknowledgments

We thank Professor M Schieker (University Hospital of LMU Munich, Germany) for kindly providing the hTERT-MSC. We acknowledge Ms Ortrud Zieschang for preparation of SEM samples and microscopy facility CFCI for providing equipment and support in cell imaging. The authors are very grateful for the help of the group of Professor J Alblas (UMC Utrecht, The Netherlands) in the prestaining of cells. The work carried out in this manuscript was supported by project grants from the German Federal Ministry for Economic Affairs and Energy (BMWi) in collaboration with the German Federation of Industrial Research Associations (AiF; ZIM project, contract No. KF3359301AK4) as well as from the Biotechnology and Biological Sciences Research Council UK (BB/L00609X and BB/LO21072/1) and University of Southampton IFLS, FortisNet and Postgraduate awards to ROCO.

References

- [1] Castilho M, Moseke C, Ewald A, Gbureck U, Groll J, Pires I, Teßmar J and Vorndran E 2014 Direct 3D powder printing of biphasic calcium phosphate scaffolds for substitution of complex bone defects *Biofabrication* **6** 015006
- [2] Williams JM, Adewunmi A, Schek RM, Flanagan CL, Krebsbach PH, Feinberg SE, Hollister SJ and Das S 2005 Bone tissue engineering using polycaprolactone scaffolds fabricated via selective laser sintering *Biomaterials* **26** 4817–27
- [3] Butscher A, Bohner M, Doeblin N, Galea L, Loeffel O and Müller R 2013 Moisture based three-dimensional printing of calcium phosphate structures for scaffold engineering *Acta Biomater.* **9** 5369–78
- [4] Schumacher M, Deisinger U, Detsch R and Ziegler G 2010 Indirect rapid prototyping of biphasic calcium phosphate scaffolds as bone substitutes: influence of phase composition, macroporosity and pore geometry on mechanical properties *J. Mater. Sci., Mater. Med.* **21** 3119–27
- [5] Lode A, Krutzat F, Brüggemeier S, Quade M, Schütz K, Knaack S, Weber J, Bley T and Gelinsky M 2015 Green bioprinting: fabrication of photosynthetic algae-laden hydrogel scaffolds for biotechnological and medical applications *Eng. Life Sci.* **15** 177–83
- [6] Pfister A, Landers R, Laib A, Hübner U, Schmelzeisen R and Mülhaupt R 2004 Biofunctional rapid prototyping for tissue-engineering applications: 3D bioplotting versus 3D printing *J. Polym. Sci. Part Polym. Chem.* **42** 624–38
- [7] Nicodemus GD and Bryant SJ 2008 Cell encapsulation in biodegradable hydrogels for tissue engineering applications *Tissue Eng. B* **14** 149–65
- [8] Gasperini L, Mano JF and Reis RL 2014 Natural polymers for the microencapsulation of cells *J. R. Soc. Interface* **11** 20140817
- [9] Malda J, Visser J, Melchels FP, Jüngst T, Hennink WE, Dhert WJA, Groll J and Huttmacher DW 2013 25th anniversary article: engineering hydrogels for biofabrication *Adv. Mater.* **25** 5011–28
- [10] Jüngst T, Smolan W, Schacht K, Scheibel T and Groll J 2016 Strategies and molecular design criteria for 3D printable hydrogels *Chem. Rev.* **116** 1496–539
- [11] Lee J-S, Hong JM, Jung JW, Shim J-H, Oh J-H and Cho D-W 2014 3D printing of composite tissue with complex shape applied to ear regeneration *Biofabrication* **6** 024103
- [12] Schuurman W, Khristov V, Pot M W, van Weeren P R, Dhert WJA and Malda J 2011 Bioprinting of hybrid tissue

- constructs with tailorable mechanical properties *Biofabrication* **3** 021001
- [13] Akkineni A R, Ahlfeld T, Lode A and Gelinsky M 2016 A versatile method for combining different biopolymers in a core/shell fashion by 3D plotting to achieve mechanically robust constructs *Biofabrication* **8** 045001
 - [14] Raja N and Yun H 2016 A simultaneous 3D printing process for the fabrication of bioceramic and cell-laden hydrogel core/shell scaffolds with potential application in bone tissue regeneration *J. Mater. Chem. B* **4** 4707–16
 - [15] Cornock R, Beirne S, Thompson B and Wallace G G 2014 Coaxial additive manufacture of biomaterial composite scaffolds for tissue engineering *Biofabrication* **6** 025002
 - [16] Kesti M, Eberhardt C, Pagliccia G, Kenkel D, Grande D, Boss A and Zenobi-Wong M 2015 Bioprinting complex cartilaginous structures with clinically compliant biomaterials *Adv. Funct. Mater.* **25** 7406–17
 - [17] Billiet T, Gevaert E, De Schryver T, Cornelissen M and Dubruiel P 2014 The 3D printing of gelatin methacrylamide cell-laden tissue-engineered constructs with high cell viability *Biomaterials* **35** 49–62
 - [18] Markstedt K, Mantas A, Tournier I, Martínez Ávila H, Hägg D and Gatenholm P 2015 3D Bioprinting human chondrocytes with nanocellulose-alginate bioink for cartilage tissue engineering applications *Biomacromolecules* **16** 1489–96
 - [19] Schütz K, Placht A-M, Paul B, Brüggemeier S, Gelinsky M and Lode A 2017 Three-dimensional plotting of a cell-laden alginate/methylcellulose blend: towards biofabrication of tissue engineering constructs with clinically relevant dimensions *J. Tissue Eng. Regen. Med.* **11** 1574–87
 - [20] Carretero M I 2002 Clay minerals and their beneficial effects upon human health, a review *Appl. Clay Sci.* **21** 155–63
 - [21] Dawson J I and Oreffo R O C 2013 Clay: new opportunities for tissue regeneration and biomaterial design *Adv. Mater.* **25** 4069–86
 - [22] Xavier J R, Thakur T, Desai P, Jaiswal M K, Sears N, Cosgriff-Hernandez E, Kaunas R and Gaharwar A K 2015 Bioactive nanoengineered hydrogels for bone tissue engineering: a growth-factor-free approach *ACS Nano* **9** 3109–18
 - [23] Schexnailder P and Schmidt G 2009 Nanocomposite polymer hydrogels *Colloid Polym. Sci.* **287** 1–11
 - [24] Thompson D W and Butterworth J T 1992 The nature of Laponite and its aqueous dispersions *J. Colloid Interface Sci.* **151** 236–43
 - [25] Gibbs D M R, Black C R M, Hulsart-Billstrom G, Shi P, Scarpa E, Oreffo R O C and Dawson J I 2016 Bone induction at physiological doses of BMP through localization by clay nanoparticle gels *Biomaterials* **99** 16–23
 - [26] Dawson J I, Kanczler J M, Yang X B, Attard G S and Oreffo R O C 2011 Clay gels for the delivery of regenerative microenvironments *Adv. Mater.* **23** 3304–8
 - [27] Zhao L Z, Zhou C H, Wang J, Tong D S, Yu W H and Wang H 2015 Recent advances in clay mineral-containing nanocomposite hydrogels *Soft Matter* **11** 9229–46
 - [28] Hoppe A, Güldal N S and Boccaccini A R 2011 A review of the biological response to ionic dissolution products from bioactive glasses and glass-ceramics *Biomaterials* **32** 2757–74
 - [29] Abou B, Bonn D and Meunier J 2003 Nonlinear rheology of Laponite suspensions under an external drive *J. Rheol.* **47** 979–88
 - [30] Pozzo D C and Walker L M 2004 Reversible shear gelation of polymer–clay dispersions *Colloids Surf. Physicochem. Eng. Asp.* **240** 187–98
 - [31] Luo Y, Lode A and Gelinsky M 2013 Direct plotting of three-dimensional hollow fiber scaffolds based on concentrated alginate pastes for tissue engineering *Adv. Healthc. Mater.* **2** 777–83
 - [32] Sarker B, Singh R, Silva R, Roether J A, Kaschta J, Detsch R, Schubert D W, Cicha I and Boccaccini A R 2014 Evaluation of fibroblasts adhesion and proliferation on alginate–gelatin crosslinked hydrogel *PLoS One* **9** e107952
 - [33] Gaetani R, Doevendans P A, Metz C H G, Alblas J, Messina E, Giacomello A and Sluijter J P G 2012 Cardiac tissue engineering using tissue printing technology and human cardiac progenitor cells *Biomaterials* **33** 1782–90
 - [34] Wu Z, Su X, Xu Y, Kong B, Sun W and Mi S 2016 Bioprinting three-dimensional cell-laden tissue constructs with controllable degradation *Sci. Rep.* **6** 24474
 - [35] Ghadiri M, Chrzanowski W, Lee W H, Fathi A, Dehghani F and Rohanizadeh R 2013 Physico-chemical, mechanical and cytotoxicity characterizations of Laponite®/alginate nanocomposite *Appl. Clay Sci.* **85** 64–73
 - [36] Li Y, Maciel D, Tomás H, Rodrigues J, Ma H and Shi X 2011 pH sensitive Laponite/alginate hybrid hydrogels: swelling behaviour and release mechanism *Soft Matter* **7** 6231–8
 - [37] Gonçalves M, Figueira P, Maciel D, Rodrigues J, Shi X, Tomás H and Li Y 2014 Antitumor efficacy of doxorubicin-loaded Laponite/alginate hybrid hydrogels *Macromol. Biosci.* **14** 110–20
 - [38] Hong S, Sycks D, Chan H F, Lin S, Lopez G P, Guilak F, Leong K W and Zhao X 2015 3D Printing of highly stretchable and tough hydrogels into complex, cellularized structures *Adv. Mater.* **27** 4035–40
 - [39] Jin Y, Liu C, Chai W, Compaan A and Huang Y 2017 Self-supporting nanoclay as internal scaffold material for direct printing of soft hydrogel composite structures in air *ACS Appl. Mater. Interfaces* **9** 17456–65
 - [40] Landers R, Pfister A, Hübner U, John H, Schmelzeisen R and Mülhaupt R 2002 Fabrication of soft tissue engineering scaffolds by means of rapid prototyping techniques *J. Mater. Sci.* **37** 3107–16
 - [41] Böcker W *et al* 2008 Introducing a single-cell-derived human mesenchymal stem cell line expressing hTERT after lentiviral gene transfer *J. Cell. Mol. Med.* **12** 1347–59
 - [42] Knaack S, Lode A, Hoyer B, Rösen-Wolff A, Gabrielyan A, Roeder I and Gelinsky M 2014 Heparin modification of a biomimetic bone matrix for controlled release of VEGF *J. Biomed. Mater. Res. A* **102** 3500–11
 - [43] Ferris C J, Gilmore K G, Wallace G G and In het Panhuis M 2013 Biofabrication: an overview of the approaches used for printing of living cells *Appl. Microbiol. Biotechnol.* **97** 4243–58
 - [44] Khalil S and Sun W 2009 Bioprinting endothelial cells with alginate for 3D tissue constructs *J. Biomech. Eng.* **131** 111002
 - [45] Tabriz A G, Hermida M A, Leslie N R and Shu W 2015 Three-dimensional bioprinting of complex cell laden alginate hydrogel structures *Biofabrication* **7** 045012
 - [46] Bandeira L C, Calefi P S, Ciuffi K J, de Faria E H, Nassar E J, Vicente M A and Trujillo R 2012 Preparation of composites of Laponite with alginate and alginic acid polysaccharides *Polym. Int.* **61** 1170–6
 - [47] Knarr M and Bayer R 2014 The shear dependence of the methylcellulose gelation phenomena in aqueous solution and in ceramic paste *Carbohydr. Polym.* **111** 80–8
 - [48] Bernhardt A, Wehr M, Paul B, Hochmuth T, Schumacher M, Schütz K and Gelinsky M 2015 Improved sterilization of sensitive biomaterials with supercritical carbon dioxide at low temperature *PLoS One* **10** e0129205
 - [49] Ruzicka B, Zulian L and Ruocco G 2004 Routes to gelation in a clay suspension *Phys. Rev. Lett.* **93** 258301
 - [50] Nasatto P L, Pignon F, Silveira J L M, Duarte M E R, Nosedá M D and Rinaudo M 2015 Methylcellulose, a cellulose derivative with original physical properties and extended applications *Polymers* **7** 777–803
 - [51] Sarkar N and Walker L C 1995 Hydration–dehydration properties of methylcellulose and hydroxypropylmethylcellulose *Carbohydr. Polym.* **27** 177–85
 - [52] Choi B, Loh X J, Tan A, Loh C K, Ye E, Joo M K and Jeong B 2015 Introduction to *in situ* forming hydrogels for biomedical applications *In-situ Gelling Polymers (Series in BioEngineering)* ed X J Loh (Singapore: Springer) pp 5–35
 - [53] Naficy S, Kawakami S, Sadegholvaad S, Wakisaka M and Spinks G M 2013 Mechanical properties of interpenetrating polymer network hydrogels based on hybrid ionically and

- covalently crosslinked networks *J. Appl. Polym. Sci.* **130** 2504–13
- [54] Kuo C K and Ma P X 2001 Ionically crosslinked alginate hydrogels as scaffolds for tissue engineering: I. Structure, gelation rate and mechanical properties *Biomaterials* **22** 511–21
- [55] Lee K Y and Mooney D J 2012 Alginate: properties and biomedical applications *Prog. Polym. Sci.* **37** 106–26
- [56] O'Brien F J 2011 Biomaterials & scaffolds for tissue engineering *Mater. Today* **14** 88–95
- [57] Nakamura S, Matsumoto T, Sasaki J-I, Egusa H, Lee K Y, Nakano T, Sohmura T and Nakahira A 2010 Effect of calcium ion concentrations on osteogenic differentiation and hematopoietic stem cell niche-related protein expression in osteoblasts *Tissue Eng. A* **16** 2467–73
- [58] Danoux C B S S, Bassett D C, Othman Z, Rodrigues A I, Reis R L, Barralet J E, van Blitterswijk C A and Habibovic P 2015 Elucidating the individual effects of calcium and phosphate ions on hMSCs by using composite materials *Acta Biomater.* **17** 1–15
- [59] Mørch Y A, Donati I, Strand B L and Skjåk-Braek G 2006 Effect of Ca^{2+} , Ba^{2+} , and Sr^{2+} on alginate microbeads *Biomacromolecules* **7** 1471–80
- [60] Blaeser A, Duarte Campos D F, Puster U, Richtering W, Stevens M M and Fischer H 2016 Controlling shear stress in 3D bioprinting is a key factor to balance printing resolution and stem cell integrity *Adv. Healthc. Mater.* **5** 326–33
- [61] Sarker B, Rompf J, Silva R, Lang N, Detsch R, Kaschta J, Fabry B and Boccaccini A R 2015 Alginate-based hydrogels with improved adhesive properties for cell encapsulation *Int. J. Biol. Macromol.* **78** 72–8
- [62] Mason B N, Califano J P and Reinhart-King C A 2012 Matrix stiffness: a regulator of cellular behavior and tissue formation *Engineering Biomaterials for Regenerative Medicine* ed S K Bhatia (New York: Springer) pp 19–37
- [63] Ding X, Gao J, Wang Z, Awada H and Wang Y 2016 A shear-thinning hydrogel that extends *in vivo* bioactivity of FGF2 *Biomaterials* **111** 80–9

The newly developed Laponite-alginate-methylcellulose (Lap-alg-mc) bioink holds great promise for bone bioprinting. It revealed an outstanding shape fidelity, allowed a sustained release of model proteins like bovine serum albumin or VEGF and the viability of bioprinted human mesenchymal stem cells was at an elevated level. A follow-up study was published recently.(Cidonio et al., 2020) In the following, the results are briefly described. Printed and externally functionalized scaffolds were investigated in an *ex vivo* chorioallantoic membrane (CAM) model to study the feasibility to promote angiogenesis and vascularization. The results are depicted in Figure 14. Four groups were compared to each other: (3DP) a 3D plotted Lap-alg-mc scaffold, (3DP+VEGF) a 3D plotted Lap-alg-mc-scaffold with VEGF (concentration $100 \mu\text{g}\cdot\text{ml}^{-1}$) pipetted onto the scaffold after fabrication, (3DP+HUVECs) a Lap-alg-mc construct which was seeded with $6\cdot 10^5$ human umbilical vein endothelial cells (HUVECs) per scaffold, and (3DP+HUVECs+VEGF) a 3D plotted Lap-alg-mc construct which was seeded with $6\cdot 10^5$ HUVECs per scaffold and contained the same amount of VEGF like the group 3DP+VEGF. After 7 days of incubation in the egg, the infiltration of blood vessels was assessed by the CHALKLEY score. It could be shown that a significant increase of blood vessel ingrowth was detected when the 3D plotted Lap-alg-mc was functionalized either with VEGF or with HUVECs and a further significant improvement was achieved in the group functionalized with both, HUVECs and VEGF. This might be attributed to synergistic effects of VEGF and HUVECs.

Further, in the same study it was investigated whether the material is osteoinductive and whether the bioprinted Lap-alg-mc construct is superior to cell-free approaches. As control groups, casted samples were compared to plotted cell-free and cell-laden samples (Figure 15). The samples were implanted subcutaneously into BALB/c athymic nude mice which were immunodeficient. Quantitative bone formation was obtained from micro-computed tomography data. Both, casted and plotted samples with and without human bone marrow stem cells (hBMSCs) allowed ongoing bone formation over 8 weeks. Casted samples showed mineral deposition at the surface of the constructs whereas 3D plotted scaffolds mineralized in their full volume. Interestingly, only bioprinted, hBMSC-laden constructs allowed a significant increasing bone formation over 8 weeks, whereas the other three groups were not significantly different from each other evidencing that a biologically active, plotted construct can be advantageous compared to bulk scaffolds, but also that bioprinted cells seem to evoke beneficial effects.

Figure 14. Performance of 3D plotted nanoclay-based constructs in a CAM model. **A-D:** Photograph of the constructs integrated into the CAM and images of Goldner's Trichrome stainings. **E:** CHALKLEY scores of the samples compared to an empty control defect. Mean $\pm$ standard deviation, $n=4$, * $p<0.05$, ** $p<0.01$, **** $p<0.0001$. Reproduced from (Cidonio et al., 2020) with CC BY 3.0 license.

Figure 15. Suitability of a bioprinted nanoclay-based construct to foster bone formation. **A:** Micro-computed tomography images of a bioprinted, hBMSC-laden scaffold which was implanted subcutaneously into a mouse model. Scans were taken after 2,4,6 and 8 weeks, respectively. **B:** Bone volume of the investigated groups after 2,4,6 and 8 weeks. Mean $\pm$ standard deviation, $n=6$, *** $p<0.001$, **** $p<0.0001$. Reproduced from (Cidonio et al., 2020) with CC BY 3.0 license.

BIOPRINTING OF MINERALIZED CONSTRUCTS UTILIZING
MULTICHANNEL PLOTTING OF A SELF-SETTING CALCIUM
PHOSPHATE CEMENT AND A CELL-LADEN BIOINK

Biofabrication

PAPER

Bioprinting of mineralized constructs utilizing multichannel plotting of a self-setting calcium phosphate cement and a cell-laden bioink

Tilman Ahlfeld¹, Falko Doberenz¹, David Kilian¹, Corina Vater¹, Paula Korn^{1,2}, Günter Lauer², Anja Lode^{1,3} and Michael Gelinsky^{1,3}

¹ Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine Carl Gustav Carus, Technische Universität Dresden, Dresden, Germany

² Department of Oral and Maxillofacial Surgery, Faculty of Medicine Carl Gustav Carus, Technische Universität Dresden, Dresden, Germany

³ Authors to whom any correspondence should be addressed.

E-mail: anja.lode@tu-dresden.de and michael.gelinsky@tu-dresden.de

Keywords: calcium phosphate cement, bioink, bioprinting, alginate, bone

Supplementary material for this article is available [online](#)

RECEIVED
20 March 2018

REVISED
21 June 2018

ACCEPTED FOR PUBLICATION
13 July 2018

PUBLISHED
27 July 2018

Abstract

Due to their characteristic resemblance of the mineral component of bone, calcium phosphates are widely accepted as optimal bone substitute materials. Recent research focused on the development of pasty calcium phosphate cement (CPC) formulations, which can be fabricated into various shapes by low-temperature extrusion-based additive manufacturing, namely 3D plotting. While it could be demonstrated that sensitive substances like growth factors can be integrated in such printed CPC scaffolds without impairment of their biological activity live cells cannot be suspended in CPC as they may not be functional when enclosed in a solid and stiff matrix. In contrast, 3D bioprinting of soft cell-laden hydrogels (bioinks) enables the fabrication of constructs with spatially defined cell distribution, which has the potential to overcome problems of conventional cell seeding techniques—but such objects lack mechanical stability. Herein, we combine 3D plotting of CPC and bioprinting of a cell-laden bioink for the first time. As model bioink, an alginate-methylcellulose blend (alg/mc) was used, previously developed by us. Firstly, a fabrication regime was established, enabling optimal setting of CPC and cell survival inside the bioink. As the cells are exposed to the chemical changes of CPC precursors during setting, we studied the compatibility of the complex system of CPC and cell-laden alg/mc for a combined extrusion process and characterized the cellular behavior of encapsulated human mesenchymal stroma cells within the bioink at the interface and in direct vicinity to the CPC. Furthermore, biphasic scaffolds were mechanically characterized and a model for osteochondral tissue grafts is proposed. The manuscript discusses possible impacts of the CPC setting reaction on cells within the bioink and illustrates the advantages of CPC in bioprinting as alternative to the commonly used thermoplasts for bone tissue engineering.

1. Introduction

The arrangement of cells and extracellular matrix of native tissues is highly sophisticated and mostly impossible to recreate with existing technologies. Therefore, the main goal of tissue engineering is the entire functional imitation of the requested tissue or organ, which means resemblance of chemical composition as well as biological and mechanical properties. However, the demands concerning spatial cell distribution within a tissue are too complex to follow usual

cell seeding techniques onto scaffolds. An alternate route to deliver different cell types in spatially defined manner is three-dimensional (3D) bioprinting. Amongst other bioprinting techniques, extrusion-based 3D bioplotting has established as one of the simplest methods to fabricate cell-laden scaffolds in clinical relevant dimensions [1]. Materials requested for cell plotting are cytocompatible hydrogels with shear thinning properties, which were optionally refined to enhance cellular functions, commonly known as bioinks [2]. In the last years, a remarkable

progress was made in development of advanced bioinks for cell plotting [3–8]. However, the resulting hydrogel scaffolds are not applicable for tissues requiring high mechanical stability, especially not for mineralized tissues such as bone.

In 2011, Schuurman *et al* showed, that multi-channel printing of molten thermoplasts, especially of poly- ϵ -caprolactone (PCL), and cell-laden, low-viscous hydrogels enhanced mechanical stiffness of such bioprinted constructs significantly [9]. Afterwards, PCL was used in combination with bioprinting in several approaches for cartilage [10–14], bone [12, 15, 16] or osteochondral [17, 18] tissue equivalents. This combination of fused deposition modeling and bioplotting has the disadvantage, that cells are exposed to the high temperature of molten thermoplasts, limiting the material choice severely, for instance polylactide acid (PLA) cannot be used for cell printing without protection layers of PCL [19]. Moreover, for bone tissue engineering, a mineralized matrix is beneficial. Recent work focused on blending thermoplasts with calcium phosphates, such as tricalcium phosphate or hydroxyapatite (HAp) [20–22]. However, a mineral phase directly accessible by the cells is advantageous and could be achieved by usage of pure calcium phosphate-based materials. This paper targets to broaden the suitable material classes for combined cell printing by introduction of pure calcium phosphate-based materials as mechanical and functional support.

Additive manufacturing of calcium phosphate ceramics was first established by powder printing [23, 24], robocasting of a slurry into an oil bath [25, 26] or indirect printing [27]. All these techniques require sintering of the scaffolds at high temperatures ($>1000^{\circ}\text{C}$) for stabilization, prohibiting bioprinting. Potential candidates for extrusion-based 3D plotting are self-setting calcium phosphate cements (CPC). Usually, CPC pastes used for clinical treatment of bone defects are produced immediately prior to application during surgery, by mixing of the precursor powder (mainly α -TCP) with an aqueous liquid. After the hydraulic setting reaction has taken place, these cements present a nanocrystalline, resorbable hydroxyapatite structure mimicking the mineral part of bone and exhibit suitable mechanical properties. However, the conventional powder/liquid CPC cannot be plotted, due to too fast setting (only a few minutes) of the precursors resulting in permanently increasing viscosity. Therefore, several studies described the development of self-setting α -TCP based CPC by blending the cement precursor phases with other carriers than water to enhance injectability and prolong shelf life of the pasty state. These carriers were gelatin (injection time 15–30 min post mixing; no storability) [28], Pluronic (injection time dependent on temperature, more than 1500 min at 7°C ; long-term storability prior to surgery at -80°C) [29, 30] or, as used in the present study, a biocompatible oil-based carrier liquid (unlimited injection time, long-term

storability prior to surgery at room temperature) [31]. These newly developed cements were successfully utilized for 3D plotting.

Recently, we have shown that oil-based CPC pastes are excellent biomaterial inks which can be processed at room temperature in mild conditions [32]. We proved, that plotted scaffolds composed of CPC started a setting reaction to hydroxyapatite (HAp) directly after immersion in aqueous solution while the oil phase is replaced by water [33]; moreover the excellent biocompatibility of the plotted CPC scaffolds was demonstrated [32]. Later on, the CPC paste was bio-functionalized before plotting by integration of growth factor-laden microparticles that resulted in plotted CPC scaffolds with precisely and spatially tunable drug release properties [34]. To hinder loss of growth factor during the setting process, a new regime was established by aging the plotted CPC scaffolds in water-saturated atmosphere (humidity). Intriguingly, the modified post-plotting treatment also prevented formation of microcracks, which occurred during immersion in water and resulted in impaired mechanical properties [34]. Later on, we used multichannel plotting to extrude highly concentrated hydrogels next to CPC which were loaded with proteins and growth factors extending the range of growth factor release with respect to quantity and kinetics [33, 35].

In the present work, we studied the combination of the plottable CPC [32] together with a cell-laden bioink for bioprinting of biphasic scaffolds with high stiffness and a bone mimicking mineral structure of nanocrystalline HAp as well as integrated cells. As model bioink, we have used a blend of 3 w/v% alginate and 9 w/v% methylcellulose (alg/mc), that enables plotting of 3D scaffolds with high shape fidelity and adequate biological function [36]. The challenge, however, is that the setting of the CPC, a complex reaction of dissolution and precipitation processes [37], proceeds in close vicinity to living cells. Therefore, we developed a new setting regime for the biphasic, cell-laden scaffolds which prevents microcrack formation within CPC strands on the one hand and ensure maintenance of cytocompatibility on the other hand. Moreover, we studied the compatibility of CPC for biofabrication of cell-laden biphasic scaffolds in detail. We characterized mechanical properties and cell response and discuss potential applications of bioprinted constructs consisting of CPC and bioinks for bone tissue and its interfaces.

2. Materials and methods

2.1. Plotting pastes

The CPC paste (precursor powder: α -tricalcium phosphate, dicalcium phosphate anhydrous, calcium carbonate hydroxyapatite and potassium hydrogen phosphate; carrier liquid: Miglyol, Cremophor ELP and Amphisol A) [31] was manufactured by

Table 1. Plotting parameters of CPC and alg/mc pastes.

Material	Nozzle diameter (μm)	Plotting speed (mm s^{-1})	Dosing pressure (kPa)	Layer thickness (μm)
CPC	230	12	230–250	130
	410	10	200	250
	610	10	150	360
alg/mc	250	9	80	130
	410	10	70	250
	610	10	50	360

INNOTERE GmbH (Radebeul, Germany) and sterilized by γ -irradiation (25 kGy). The alg/mc bioink was prepared as described before [36]. Briefly, alginate (alginic acid sodium salt from brown algae, 71238, Sigma, UK, M/G ratio 1:2) was dissolved in phosphate buffered saline overnight to obtain a 3 w/v% alginate solution. Afterwards, 9 w/v% methylcellulose powder (M0512, Sigma, USA; molecular weight $\approx$ 88 kDa, 4000 cP s) was carefully mixed into the alginate solution and methylcellulose was allowed to swell for 2 h. Both, alginate solution and methylcellulose powder were sterilized by autoclaving. For the development of the osteochondral tissue model, fluorescent beads (fluorescence encoded PMMA beads; PolyAn Green 10, PolyAn GmbH, Berlin, Germany) were mixed to alg/mc prior to plotting.

2.2. 3D plotting

Cuboid scaffolds (base $12 \times 12 \text{ mm}^2$, height 1 mm for cell culture experiments and 5 mm for the other experiments) with an alternating layer pattern (orientation of strands $0^\circ/90^\circ$) were produced by using the BioScaffolder 3.1 (GeSiM mbH, Radeberg, Germany), operated in a laminar flow bench. Plotting parameters are summarized in table 1. If not differently mentioned, CPC and alg/mc were plotted utilizing a needle with an inner diameter of $410 \mu\text{m}$ (Globaco, Rödermark, Germany) and a layer thickness of $250 \mu\text{m}$. There were no changes in plotting parameters for monophasic or biphasic scaffolds.

2.3. Post-plotting treatment of scaffolds

All three scaffold types, monophasic alg/mc and CPC scaffolds or biphasic CPC-alg/mc scaffolds were treated equally. If not differently mentioned, scaffolds were allowed to set for 20 min in humidity ($>95\%$ at 37°C in the sterile incubator) immediately after plotting. For investigations of the post-plotting treatment, monophasic alg/mc and CPC scaffolds were stored in humidity for 0, 10, 20, 30, 60 or 120 min, respectively. Afterwards 100 mM CaCl_2 solution was added for 10 min, subsequently followed by incubation in cell culture medium consisting of DMEM (Dulbecco's Modified Eagle's Medium, Gibco, Thermo Fisher), 10% fetal calf serum (FCS), 100 U ml^{-1} penicillin and 100 mg ml^{-1} streptomycin (Pen/Strep) (all from Biochrom, Berlin, Germany) for 1 d (alg/mc) and 3 d

(CPC), respectively, to study the influence on either cell viability inside alg/mc or microstructure and mechanical properties of CPC.

2.4. Characterization of plotted scaffolds

2.4.1. Microscopy

Macroporous structure of the scaffolds was imaged using a stereo light microscope (Leica M205 C equipped with DFC295 camera, Germany). Freeze-dried samples were further analyzed by scanning electron microscopy (SEM; Philips XL 30/ESEM, operated in SEM mode) at a voltage of 3 kV (spot size 3) with field emission gun ($n = 3$).

2.4.2. Mechanical test

Plotted scaffolds (base $12 \times 12 \text{ mm}^2$, height 5 mm, strand distance 2 mm, $n = 4$) were tested mechanically. For determination of the post-plotting treatment, monophasic CPC scaffolds were tested 3 d after incubation in humidity and cell culture medium, both at 37°C . Furthermore, the biphasic structure was tested after 3 d in cell culture in comparison to monophasic scaffolds consisting either of alg/mc or CPC. All groups were mechanically characterized by uniaxial compressive tests utilizing a universal testing machine (Zwick-Roell Z010 equipped with a 10 kN load cell for scaffolds with CPC and a 100 N load cell for alg/mc scaffolds; Zwick, Germany) with a compression velocity of $5\% \times \text{L}_0 \text{ min}^{-1}$. Compressive modulus and compressive strength were calculated from the obtained data.

2.5. Fabrication of cell-laden scaffolds

The cell-laden alg/mc blend contained cells of an immortalized human mesenchymal stem cell line expressing hTERT (human telomerase reverse transcriptase) [38]. It was shown, that these cells behave similarly to primary MSC, but can be expanded without limitation [38] so that a sufficient amount of cells for basic bioprinting studies can be easily provided. The hTERT-MSCL line was kindly provided by Prof. Matthias Schieker (Laboratory of Experimental Surgery and Regenerative Medicine, University Hospital Munich (LMU), Germany). Cells were expanded in cell culture medium (DMEM + 10% FCS + 100 U ml^{-1} penicillin and $100 \mu\text{g/ml}$ streptomycin); after harvesting, 5×10^6 cells were suspended in $100 \mu\text{l}$ of cell culture medium and then carefully mixed into 1 g of the alg/mc bioink prior to plotting (ratio cell culture medium to paste: 10 vol%). Plotting and postprocessing of the cell-laden scaffolds was performed as describe above.

2.5.1. Cell viability in plotted scaffolds

The viability of hTERT-MSCL was determined by usage of the Live/Dead viability kit (Invitrogen by Thermo Fisher Scientific, Carlsbad, CA, USA). For determination of the post-plotting treatment, monophasic

alg/mc scaffolds were incubated in humidity at 37 °C, crosslinked and incubated in cell culture medium for 24 h. Biphasic structures were investigated after 1, 7 and 21 d. Cell-laden scaffolds were incubated for 30 min in 0.6 $\mu\text{l ml}^{-1}$ Calcein AM und 1.2 $\mu\text{l ml}^{-1}$ ethidium homodimer-1, followed by washing with Hank's balanced salt solution (HBSS, Gibco Life Technologies, USA). Confocal laser scanning microscopy (cLSM) was performed using a Leica TCS SP5 (Leica Microsystems, Wetzlar, Germany). Excitation of calcein was carried out with at 488 nm (emission 498–525 nm), and ethidium homodimer-1 was excited at 543 nm (emission 553–765 nm). For each time point, cells within two scaffolds were examined at five different locations, respectively ($n = 10$), z-stacks of 404 μm depth were merged and analyzed; quantification was performed via the particle analyzer of ImageJ (1.44p, National Institutes of Health, Bethesda, Maryland, USA). To verify the results, the experiments were performed twice.

2.5.2. Cell morphology

After fixation with 3.7% formaldehyde in HBSS, cells inside 3D plotted scaffolds were stained (cytoskeletons with 0.17 μM AlexaFluor 488 phalloidin and nuclei with 1 $\mu\text{g ml}^{-1}$ DAPI, both purchased from Gibco Life Technologies, USA). Cell morphology was analyzed using a Leica TCS SP5.

2.6. Statistical evaluation

All values were evaluated by one-way analysis of variance followed by Turkey's multiple comparison tests (GraphPad Prism 7). Significant differences were assumed at $p < 0.05$.

3. Results

3.1. Combined plotting of a CPC and an alginate-methylcellulose bioink

CPC and alg/mc have been successfully combined by multichannel plotting to produce biphasic scaffolds of clinically relevant dimensions by alternating extrusion of both materials (figure 1(A)). Combination of strands extruded by various nozzle sizes (minimum inner diameter: 250 μm) was demonstrated (supplementary figure S1 is available online at stacks.iop.org/BF/10/045002/mmedia). Top and side views of cubic model structures are shown in figure 1. In vertical direction (z-direction), the biphasic scaffolds consisting of CPC and alg/mc had a defined, open pore structure very similar to those of the monophasic scaffold types (figure 1 top view). Scaffolds were plotted either with mono layers (layer pattern 0°/90°) or double layers (0°/0°/90°/90°) (figure 1, mono layer and double layer). The side views show cuts of these scaffolds in wet state. Micrographs revealed the

characteristic pore collapse of the soft alg/mc scaffolds both in mono layered and double layered structure with closed pores observed at the side views, whereas for CPC scaffolds open lateral pores were observed in mono layered scaffolds which are larger in double layered scaffolds. For biphasic scaffolds, open lateral pores were observed in mono layered scaffolds which, however, tended to be smaller compared to those of pure CPC scaffolds. In contrast, in double layered biphasic scaffolds the lateral pores between CPC strands seemed to be comparable to the pores in monophasic CPC counterparts. For both architectures, mono and double layered scaffolds, the pores between strands consisting of the alg/mc bioink were closed. The results showed, that neither CPC nor alg/mc changed their plotting behavior in presence of the respective other material.

3.2. Ascertaining a post-plotting treatment for biphasic CPC-alg/mc scaffolds

The previously defined fabrication procedures of monophasic alg/mc and CPC scaffolds, respectively, are shown schematically in figures 2(A) and (B), summarizing previous results [34, 36]. After plotting, alg/mc scaffolds are immersed into a CaCl_2 bath for 10 min to allow crosslinking of alginate, afterwards, scaffolds get incubated in cell culture medium (figure 2(A)). CPC scaffolds optimally set in humidity for 3 d to avoid formation of microcracks (figure 2(B)). However, a combined scaffold composed of CPC and a cell-laden bioink requires a fabrication procedure which ideally does not cause microcrack formation in the CPC strands but is concurrently not harming the cells within the bioink. Based on our previous observations we assumed that initial setting at the surface of the CPC strands happens within minutes (<10 min) of incubation in humidity [31, 34, 39] and therefore considered a strategy for such biphasic structures, which is shown in figure 2(C): after combined extrusion of the CPC and alg/mc pastes, the biphasic scaffolds should be exposed to humidity for initial CPC setting, which might be sufficient to prevent formation of microcracks. Due to the high water content of hydrogels, cells should be able to survive within plotted structures for the short time storage in water-saturated atmosphere. Afterwards, cell-compatible crosslinking of the bioink is performed by immersion in CaCl_2 solution as usual followed by incubation of the scaffolds in cell culture medium that simultaneously allows completion of the cement setting reaction. To prove this strategy, we investigated, whether storage in humidity for a short time period is sufficient to (i) prevent crack formation at the CPC surface without (ii) harming cells embedded in the alg/mc bioink.

3.2.1. Microcrack formation in plotted CPC scaffolds after short-term storage in humidity

Monophasic CPC scaffolds were fabricated and stored in water-saturated atmosphere for 0–120 min, afterwards CaCl_2 solution was added for 10 min and cell culture medium was applied for 3 d (figure 3(A)). SEM micrographs of these scaffolds are shown in figure 3(B). As expected, scaffolds directly immersed in the CaCl_2 solution without any pre-incubation in humidity (0 min) showed a distinct formation of microcracks. Besides, formation of microcracks was also detected for a 10 min treatment. However, after 20 min incubation in humidity, no microcrack formation was observed

indicating that this storage time would be sufficient for initial setting in humidity. Figure 3(C) shows results of uniaxial compressive test of those scaffolds (representative stress-strain curves are shown in supplementary figure S2). The compressive strength of scaffolds without incubation in humidity (0 min) was 1.14 ± 0.3 MPa. Pre-incubation in humidity resulted in an increase of the strength which was even more pronounced the longer the incubation in humidity lasted. After 120 min storage in humidity, CPC scaffolds had a compressive strength of 1.90 ± 0.5 MPa. However, it has to be stressed, that the high standard deviations impeded statistical analysis of differences.

3.2.2. Cell viability inside bioplotted alg/mc scaffolds after short-term storage in humidity

Viability of hTERT-MSC inside monophasic alg/mc scaffolds was evaluated after different time periods of storage in humidity ($>95\%$ at 37°C). After plotting, the cell-laden scaffolds were placed in water-saturated atmosphere for 0–120 min, before crosslinking solution was added for 10 min, followed by final incubation in cell culture medium (figure 4(A)). The cell viability of these differently treated scaffolds was measured after 1 d of incubation in cell culture medium and is shown in figure 4(B) in relation to the cell viability determined for scaffolds which were not pre-incubated in humidity (0 min, set as 100%). The relative cell viability did not decrease significantly over a time span of 30 min. Only for longer storage without immersion in aqueous solutions, relative cell viability decreased to $79.4\% \pm 10.5\%$ after 60 min and $48.8\% \pm 19.3\%$ after 120 min in humid atmosphere, respectively.

Based on these results, the following post-plotting treatment was evaluated to be optimal for multichannel

plotting of CPC and alg/mc: after fabrication, scaffolds immediately get transferred to humid atmosphere ($>95\%$ at 37°C) for 20 min. Next, aqueous solution is applied; in case of the alg/mc bioink in form of CaCl_2 crosslinking solution for 10 min and afterwards cell culture medium. This treatment was used for further studies on mechanical properties and cell behavior.

3.3. Mechanical evaluation of biphasic CPC-alg/mc scaffolds

Mechanical behavior of monophasic and biphasic scaffolds was examined by uniaxial compressive tests. The obtained results of compressive modulus and compressive strength are summarized in figure 5 (representative stress-strain curves are shown in supplementary figure S2). Monophasic scaffolds consisting of alg/mc had a compressive modulus of 36.7 ± 4.7 kPa. As expected, addition of the stiff CPC significantly enhanced mechanical properties. Biphasic scaffolds with 50% of CPC strands showed compressive modulus of 30.7 ± 9.1 MPa. Pure CPC scaffolds without cell-laden

Figure 3. Investigations of microcrack formation in monophasic CPC scaffolds. (A) Fabrication steps. (B) Representative SEM pictures of monophasic CPC scaffolds, pre-incubated in water-saturated atmosphere (>95% humidity at 37 °C) for 0–120 min prior to immersion in 100 mM CaCl₂ solution for 10 min and cell culture medium for 3 d (needle size 610 μm, scale bars 1 mm). (C) Compressive strength of these scaffolds (mean ± SD, $n = 4$).

alg/mc had the highest compressive modulus of 52.0 ± 15.1 MPa, which was significantly higher than the modulus of the biphasic scaffolds. The same trend was observed for the compressive strength. Pure alg/mc scaffolds (16.9 ± 1.9 kPa) had a lower compressive strength than biphasic scaffolds with CPC and the bioink (1.3 ± 0.2 MPa). Scaffolds consisting only of CPC showed the highest compressive strength of 4.1 ± 2.0 MPa.

3.4. Bioplotting of cell-laden, biphasic scaffolds

Biphasic scaffolds consisting of CPC and cell-laden alg/mc were plotted and treated with the optimized post-plotting regime. At first, the influence of the interaction between the CPC strands and the cell culture medium during setting, that includes exchange of the oil phase and occurs in close vicinity to the cell-laden hydrogel strands, on cell survival was investigated. Therefore, cell viability of biphasic CPC-alg/mc scaffolds and monophasic alg/mc scaffolds was compared at alg/mc strand-junctions in the scaffolds (representative cLSM images of live/dead stained samples are shown in supplementary figure S3). Quantification of cell viability at day 1 and 7 is shown in figure 6(A). Neither at day 1, nor at day 7, a significant change of cell viability within the alg/mc strands of biphasic scaffolds was detected, indicating that the oil–water exchange into cell culture medium and the cement setting reaction did not impair cell viability in the adjacent hydrogel strands. Afterwards,

cell viability at the CPC-alg/mc interface was examined. Interestingly, cell viability distinctly decreased when the CPC and the alg/mc bioink were in direct contact: the number of viable cells declined whereas a higher number of dead cells was visible (figure 6(B)).

After local differences in cell viability were observed at day 1, a cultivation of cell-laden biphasic scaffolds over 21 d was performed to study long-term effects (figure 7(A)). After this period, more or less no dead cells could be detected inside the alg/mc bioink anymore, whereas the number of living cells was maintained. Between 7 and 21 d, cells started to migrate from the alg/mc hydrogel to the CPC strand surface where they adhered and spread. The images additionally imply, that cells survived and proliferated along the CPC surface and stayed viable (figure 7(A), day 21), compensating the drop of cell viability at the interface region on day 1. Staining of cytoskeletons and nuclei revealed that cells after migration to the CPC surface exhibited a spread, elongated morphology whereas living cells inside the bioink maintained their roundish shape (figure 7(B)).

3.5. Towards bioplotting constructs for repair of osteochondral defects

Using high viscous and rigid bioinks like alg/mc together with bone mimetic CPC enables developing scaffolds for further applications in the field of bone and its interfaces to other tissues. Figure 8(A) shows a concept for 3D bioplotting of osteochondral scaffolds.

The subchondral bone consists of monophasic CPC, whereas the cartilage part is made out of alg/mc. Both materials can be plotted accurately. To mimic the porous structure of subchondral bone, it was intended to plot CPC with a strand distance of at least 0.4 mm. As articular cartilage has no porous structure, plotting of the bioink without pores was suggested. Both CPC and alg/mc have no physical interaction. Weak stabilizing effects between the materials might occur due to local crosslinking effects by the divalent calcium ions of CPC which could interact with alginate. However, this chemical interaction was not proven yet and, if so, the crosslinking effect is limited. Considering this, physical connection was intended; an interwoven network zone was shown before to be beneficial [33]. This zone has to be applied between CPC and alg/mc and could be seen as calcified cartilage at the interface (figure 8(A)). Figures 8(B) and (C) show real plotted scaffolds in clinically relevant dimensions following the theoretical design. The scaffolds

consisted of CPC and the alg/mc bioink. Furthermore, alg/mc was loaded with fluorescent beads. Figure 8(D) shows the cross section of the plotted scaffolds. It shows the subchondral bone consisting of autofluorescent CPC (blue), the interwoven network zone with both, blue CPC strands and green fluorescent beads inside alg/mc strands, and the cartilage consisting only of alg/mc. Further work will concentrate on bioplotting of such multiphasic constructs.

4. Discussion

The most prominent material for bioprinted scaffolds with enhanced stiffness is poly- ϵ -caprolactone (PCL) [9, 40]. This thermoplastic polymer extruded at high temperatures has great printing properties to achieve scaffolds with high shape fidelity [41, 42]. Melchels *et al* developed a poloxamer-based hydrogel enabling biphasic extrusion together with bioinks, which can be processed at low temperatures [43]. However, for bone

applications, the development of plottable CPC offers several advantages. After setting of the cement precursors, nanocrystalline HAp is formed, mimicking the mineral phase of natural bone. The mechanical stiffness of the ceramic hydroxyapatite (HAp) is higher compared to the organic polymer PCL, shown also by addition of HAp to PCL in several studies [20, 44]. The investigations of the compressive modulus of biphasic scaffolds in this study confirm this expectation, as the modulus was higher compared to the reports of Schuurman *et al* [9] or Cunniffe *et al* [16]. However, it has to be stressed that this comparison is limited due to the different scaffold geometries. Furthermore, HAp should better promote cell adhesion *in vivo*, due to the distinct smaller contact angle (HAp 7° [45], PCL 119.2° [46]) [47], and its higher capacity to bind serum proteins [48, 49]. Besides, CPC can be laden with therapeutically effective substances like strontium ions or even, due to the mild process conditions, sensitive drugs and growth factors [34, 50, 51]. As being resorbed by osteoclasts, CPC is actively integrated in the bone remodeling process [52, 53].

For the first time, scaffolds consisting of a resorbable CPC and a cell-laden bioink have been fabricated in the present study. Both materials, CPC and the bioink, were combined in a strand wise assembly, similarly as it was shown before for the combination of

CPC and highly concentrated hydrogels, which contained growth factors, but were not suitable for cell encapsulation [33, 35]. CPC can be plotted to scaffolds or implants of any dimension in the scale of relevant bone defects and any shape [54]; combined plotting of CPC and alg/mc with various needle sizes was successfully performed (supplementary figure S1) indicating that the shape fidelity of plotted CPC structures is not restricted by combination with the bioink. For this study, alg/mc was used as model bioink whose advantage is its high shape fidelity that allows the creation of macropores [36], which are beneficial for supply of the embedded cells with oxygen and nutrients *in vitro* and *in vivo* [4]; as well as the integration of more complex substructures, such as tubular structures colonized with cells as blood vessel precursors. However, the aim of the present study was to investigate the compatibility of CPC plotting and bioprinting and therefore, a simplified scaffold geometry was used as *in vitro* model structure without raising the claim to provide a suitable pore structure for bone regeneration *in vivo*.

The fabrication of biphasic constructs consisting of these two very different materials requires compromises: the bioink should be transferred to aqueous solution after plotting to prevent dehydration followed by undesirable structural changes, whereas penetration of water into the CPC strands should be

Figure 7. Cell behavior within biphasic CPC-alg/mc scaffolds during 21 d of cultivation. (A) Representative cLSM images of live/dead stained hTERT-MSC in biphasic scaffolds. Locations of decreased cell viability are marked by red arrows, while adhering and proliferating cell populations are tagged by green arrows (scale bars 500 µm). (B) Staining of actin cytoskeleton (green) and nuclei (blue) of cells, attached to the CPC strand surface at day 21 (scale bar 250 µm).

slowly for best mechanical properties. Furthermore, all fabrication steps have to be tailored to ensure cytocompatibility. Problematically, a simple immersion of plotted CPC structures into cell convenient aqueous liquids led to formation of microcracks, which were shown to compromise mechanical properties before [34]. However, our experiments have proven that an initial incubation in humidity for at least 20 min is sufficient to prevent microcrack formation. Crucially, cell viability inside alg/mc constructs did not decrease during 20 min incubation in humidity that opens a process window for bioplotted constructs consisting of CPC and bioinks. Although there was not seen a significant increase of compressive strength in differently treated CPC samples, a positive trend is visible (figure 3(C)) and the avoidance of microcracks should retard material fatigue at later time points and at cyclic load [55, 56].

Generally, CPC are cytocompatible. However, until now this was only investigated using pre-set

cement samples *in vitro*, i.e. cements, which already finished setting of the precursors. For the current approach of combined bioprinting of CPC and bioinks *in vitro*, the initial setting reaction with its variations in pH and several ion exchanges from and into CPC proceeds in the presence of cells. During cLSM analysis, we found that cells, which were embedded in alg/mc and located in the vicinity of CPC strands are not affected by the setting process; however, the number of dead cells increased at the direct interface of both materials in biphasic constructs at day 1 after plotting. As during the further cultivation cells migrated to the CPC surface and attached there (figure 7), one can conclude, that either the setting reaction of CPC precursors or the carrier liquid consisting of oil and surface-active additives play a role for this early, local cytotoxic effect. However, the CPC paste is approved for clinical use and the carrier liquid is biocompatible [31] implying that rather the cement setting reaction than the carrier liquid is responsible for

the temporary decrease in cell viability. This assumption is supported by cell experiments in which hMSC were seeded on cement platelets, immediately after their preparation from either CPC paste (containing the carrier liquid) or a powder/liquid CPC with comparable mineral composition (i.e. without the carrier liquid), respectively. One day after seeding, a significantly higher number of attached, living cells was observed on the cements containing the carrier liquid (supplementary figure S4), excluding a cytotoxic effect of the oil or the surface-active additives. Thus, we identified the early setting reaction as originator of the local cytotoxic effects. Starting from the precursor mainly consisting of α -tricalcium phosphate, dicalcium phosphate (calcium monohydrogen phosphate) anhydrous and calcium carbonate, phase transition during setting leads to the formation of (carbonated) HAp with the intermediate transition phases dicalcium phosphate dihydrate (brushite) and octacalcium phosphate [57]. Octacalcium phosphate is unstable against HAp, its precipitation reaction is releasing hydrogen ions [58], which acidify the local milieu [37, 39, 58]. At the interface of the setting CPC to the alg/mc bioink, this effect could have caused a decrease of the pH in the contact region with a severe effect on the cells. Accordingly, cells inside the bioink were only affected in direct contact to the CPC. This notion is supported by initial investigations of the pH value utilizing universal indicator solution inside the bioink which indicated a shift to a more acidic pH value at the interface of alg/mc and CPC at early time points (supplementary figure S5). Thus, the initial setting process in humidity with pH change and ion exchange occurs

at the whole CPC surface but is only noticeably active at the interface of both materials. Therefore, we examined the influence of cell culture medium on the biphasic scaffolds after printing without any time in humidity (supplementary figure S6). The results did not show any difference in cell viability or dead cell distribution, indicating that the local effect of the setting reaction at the CPC-alg/mc interface cannot be influenced by the surrounding environment. A possible further factor influencing the cells could be the exchange of calcium and phosphate ions from CPC to the alg/mc bioink, which reportedly could have cytotoxic effects [37]. In a study of Song *et al*, hBMSC survived cement setting inside alginate-fibrin beads, which were mixed with an tetracalcium phosphate-based powder-liquid cement [59]. Thus, further research should concentrate on the influence of different precursors and transition phases of the CPC, as well as bioinks with less ion exchange sensibility.

In biphasic constructs, the cells inside the alg/mc behaved similarly to those in pure alg/mc scaffolds. Over time, the number of dead cells declined nearly completely until day 21, whereas living cells survived; in conclusion cell viability increased over time, confirming the results shown before [36]. Crucially, cells started to actively migrate from the alg/mc bioink to the CPC strands between day 7 and day 21. This might be caused by the microroughness and stiffness of the CPC strands [60, 61]. Most probably, the surface charge of the CPC strands, which allows binding of serum proteins from the cell culture medium, resulted in a very attractive surface for cells [48]. Finally, the observed cell proliferation at the CPC strands

compensated the initial decrease of cell viability at day 1, proving a high potential of CPC for bone biofabrication.

Our general findings regarding CPC-alg/mc interaction should be transferable to other bioinks. The migration of cells to CPC after a longer culture period can be expected, as the protein saturation at the CPC surface is very prominent. However, the cell damage at the CPC-bioink interface during setting is currently limiting the bioink variety of biphasic scaffolds. The usage of more rigid bioinks with high shape fidelity like the alg/mc blend can be seen as advantageous for combination with CPC, because they allow fabrication of biphasic scaffolds with a minimum distance of 300 μm between CPC and cell-laden bioink strands ensuring cell survival in the initial phase. The pore size and shape of the biphasic CPC-alg/mc combination could be adapted by usage of smaller nozzle diameters and change of the layer orientations and strand sequences [35], to realize scaffold structures with suitable mechanical properties and pore structures but without significant change of the cellular properties. In order to reduce the cytotoxic effect in direct contact to CPC during setting, caused by the drop of the pH value, bioinks should be designed to buffer the change to acidic milieu.

On the basis of these results, different tissue engineering approaches can be pursued. The combined processing of cell-laden bioinks together with CPC is an alternative route to develop calcium phosphate scaffolds with high cell seeding efficiency. It will be possible to produce CPC based scaffolds with spatially defined cell arrangement, no matter if using one or more cell types. Furthermore, the incorporation of prevascular structures could be generated by usage of core/shell-bioplotting, if the CPC structure acts as stabilizing shell [62, 63]. Another possible approach is the development of constructs mimicking bone tissue interfaces as shown herein with a model scaffold for regeneration of osteochondral defects (figure 8). This concept should work especially with the rigid bioinks like alg/mc, which allow bioplotting without need of a stabilizing and shape forming grid structures, as it was used in other applications [9, 64]. In future, the possibility of CPC plotting next to cell-laden bioinks will allow the development of specific bone tissue engineering applications.

5. Conclusion

CPC are suitable for bone tissue engineering. Within this study, we demonstrated that plottable CPC pastes can be processed by 3D plotting in combination with bioinks to achieve bioplotting constructs with highest bone compatibility. We developed an optimal post-plotting regime, which prevents microcrack formation inside CPC strands, but conserves cell viability. The combination of CPC with even more than one cell-laden hydrogel will be the basis for many tissue

engineering applications. The present work focused on general properties of this biphasic system *in vitro*. We discovered an initial and very local decrease of the cell viability only in direct contact at the interface of CPC and the alg/mc model bioink which is compensated by cell migration during further cultivation. Starting from the investigations made in this study, CPC scaffolds can be produced in clinical relevant dimensions and with controlled cell seeding for bone and its interfaces. Due to its resemblance of bone mineral, CPC are an intriguing alternative to the commonly used thermoplasts in bioprinting.

Acknowledgments

This project was supported by project grants from the German Federal Ministry for Economic Affairs and Energy (BMWi) in collaboration with the German Federation of Industrial Research Associations (AiF; ZIM project, contract No. KF3359301AK4) and from Faculty of Medicine of Technische Universität Dresden (MeDDrive start grant). The authors thank Dr. Matthias Schumacher for fruitful discussions, Ms. Ortrud Zieschang and Ms. Anna-Maria Placht for excellent support during the study. We thank Prof. Matthias Schieker (University Hospital of LMU Munich, Germany) for kindly providing hTERT-MSC and company PolyAn GmbH (Berlin, Germany) for providing fluorescent PMMA microbeads. Cell viability was examined in the Core Facility Cellular Imaging (CFCI) of Technische Universität Dresden.

The authors declare no competing financial interest.

ORCID iDs

Anja Lode <https://orcid.org/0000-0001-7704-6435>
Michael Gelinsky <https://orcid.org/0000-0001-9075-5121>

References

- [1] Landers R, Pfister A, Hübner U, John H, Schmelzeisen R and Mülhaupt R 2002 Fabrication of soft tissue engineering scaffolds by means of rapid prototyping techniques *J. Mater. Sci.* **37** 3107–16
- [2] Malda J, Visser J, Melchels F P, Jüngst T, Hennink W E, Dhert W J A, Groll J and Huttmacher D W 2013 25th anniversary article: engineering hydrogels for biofabrication *Adv. Mater.* **25** 5011–28
- [3] Billiet T, Gevaert E, De Schryver T, Cornelissen M and Dubruiel P 2014 The 3D printing of gelatin methacrylamide cell-laden tissue-engineered constructs with high cell viability *Biomaterials* **35** 49–62
- [4] Kesti M, Eberhardt C, Pagliccia G, Kenkel D, Grande D, Boss A and Zenobi-Wong M 2015 Bioprinting complex cartilaginous structures with clinically compliant biomaterials *Adv. Funct. Mater.* **25** 7406–17
- [5] Lee J, Yeo M, Kim W, Koo Y and Kim G H 2017 Development of a tannic acid cross-linking process for obtaining 3D porous cell-laden collagen structure *Int. J. Biol. Macromol.* **110** 497–503

- [6] Markstedt K, Mantas A, Tournier I, Martínez Ávila H, Hägg D and Gatenholm P 2015 3D bioprinting human chondrocytes with nanocellulose-alginate bioink for cartilage tissue engineering applications *Biomacromolecules* **16** 1489–96
- [7] Melchels F, Dhert W, Huttmacher D and Malda J 2014 Development and characterisation of a new bioink for additive tissue manufacturing *J. Mater. Chem. B* **2** 2282–9
- [8] Schacht K, Jüngst T, Schweinlin M, Ewald A, Groll J and Scheibel T 2015 Biofabrication of cell-loaded 3D spider silk constructs *Angew. Chem., Int. Ed. Engl.* **54** 2816–20
- [9] Schuurman W, Khrstov V, Pot M W, van Weeren P R, Dhert W J A and Malda J 2011 Bioprinting of hybrid tissue constructs with tailorable mechanical properties *Biofabrication* **3** 021001
- [10] Kundu J, Shim J-H, Jang J, Kim S-W and Cho D-W 2015 An additive manufacturing-based PCL–alginate–chondrocyte bioprinted scaffold for cartilage tissue engineering *J. Tissue Eng. Regen. Med.* **9** 1286–97
- [11] Lee J-S, Hong J M, Jung J W, Shim J-H, Oh J-H and Cho D-W 2014 3D printing of composite tissue with complex shape applied to ear regeneration *Biofabrication* **6** 024103
- [12] Kang H-W, Lee S J, Ko I K, Kengla C, Yoo J J and Atala A 2016 A 3D bioprinting system to produce human-scale tissue constructs with structural integrity *Nat. Biotechnol.* **34** 3413
- [13] Pati F, Jang J, Ha D-H, Won Kim S, Rhie J-W, Shim J-H, Kim D-H and Cho D-W 2014 Printing three-dimensional tissue analogues with decellularized extracellular matrix bioink *Nat. Commun.* **5** 3935
- [14] Stichter S *et al* 2017 Double printing of hyaluronic acid/poly (glycidol) hybrid hydrogels with poly(ϵ -caprolactone) for MSC chondrogenesis *Biofabrication* **9** 044108
- [15] Cuniffe G M, Gonzalez-Fernandez T, Daly A, Sathy B N, Jeon O, Alsberg E and Kelly D J 2017 Three-dimensional bioprinting of polycaprolactone reinforced gene activated bioinks for bone tissue engineering *Tissue Eng. A* **23** 891–900
- [16] Daly A C, Cuniffe G M, Sathy B N, Jeon O, Alsberg E and Kelly D J 2016 3D bioprinting of developmentally inspired templates for whole bone organ engineering *Adv. Health. Mater.* **5** 2353–62
- [17] Shim J-H, Lee J-S, Kim J Y and Cho D-W 2012 Bioprinting of a mechanically enhanced three-dimensional dual cell-laden construct for osteochondral tissue engineering using a multi-head tissue/organ building system *J. Micromech. Microeng.* **22** 085014
- [18] Shim J-H *et al* 2016 Three-dimensional bioprinting of multilayered constructs containing human mesenchymal stromal cells for osteochondral tissue regeneration in the rabbit knee joint *Biofabrication* **8** 014102
- [19] Kim B S, Jang J, Chae S, Gao G, Kong J-S, Ahn M and Cho D-W 2016 Three-dimensional bioprinting of cell-laden constructs with polycaprolactone protective layers for using various thermoplastic polymers *Biofabrication* **8** 035013
- [20] Jing X, Mi H-Y and Turng L-S 2017 Comparison between PCL/hydroxyapatite (HA) and PCL/halloysite nanotube (HNT) composite scaffolds prepared by co-extrusion and gas foaming *Mater. Sci. Eng. C* **72** 53–61
- [21] Kim J-W, Shin K-H, Koh Y-H, Hah M J, Moon J and Kim H-E 2017 Production of poly(ϵ -caprolactone)/hydroxyapatite composite scaffolds with a tailored macro/micro-porous structure, high mechanical properties, and excellent bioactivity *Materials* **10** 1123
- [22] Dávila J L, Freitas M S, Inforçatti Neto P, Silveira Z C, Silva J V L and d'Ávila M A 2016 Fabrication of PCL/ β -TCP scaffolds by 3D mini-screw extrusion printing *J. Appl. Polym. Sci.* **133** n/a–n/a
- [23] Butscher A, Bohner M, Doebelin N, Galea L, Loeffel O and Müller R 2013 Moisture based three-dimensional printing of calcium phosphate structures for scaffold engineering *Acta Biomater.* **9** 5369–78
- [24] Castilho M, Moseke C, Ewald A, Gbureck U, Groll J, Pires I, Te/s smar J and Vorndran E 2014 Direct 3D powder printing of biphasic calcium phosphate scaffolds for substitution of complex bone defects *Biofabrication* **6** 015006
- [25] Miranda P, Saiz E, Gryn K and Tomsia A P 2006 Sintering and robocasting of β -tricalcium phosphate scaffolds for orthopaedic applications *Acta Biomater.* **2** 457–66
- [26] Franco J, Hunger P, Launey M E, Tomsia A P and Saiz E 2010 Direct write assembly of calcium phosphate scaffolds using a water-based hydrogel *Acta Biomater.* **6** 218–28
- [27] Schumacher M, Deisinger U, Detsch R and Ziegler G 2010 Indirect rapid prototyping of biphasic calcium phosphate scaffolds as bone substitutes: influence of phase composition, macroporosity and pore geometry on mechanical properties *J. Mater. Sci., Mater. Med.* **21** 3119–27
- [28] Maazouz Y, Montufar B E, Guillem-Marti J, Fleps I, Öhman C, Persson C and Ginebra M P 2014 Robocasting of biomimetic hydroxyapatite scaffolds using self-setting inks *J. Mater. Chem. B* **2** 5378–86
- [29] Barba A *et al* 2017 Osteoinduction by foamed and 3D-printed calcium phosphate scaffolds: effect of nanostructure and pore architecture *ACS Appl. Mater. Interfaces* **9** 41722–36
- [30] Maazouz Y, Montufar F, Hanke T and Gelinsky M 2014 Fabrication of porous scaffolds by three-dimensional plotting of a pasty calcium phosphate bone cement under mild conditions *J. Tissue Eng. Regen. Med.* **8** 682–93
- [31] Heinemann S, Rössler S, Lemm M, Ruhnow M and Nies B 2013 Properties of injectable ready-to-use calcium phosphate cement based on water-immiscible liquid *Acta Biomater.* **9** 6199–207
- [32] Lode A, Meissner K, Luo Y, Sonntag F, Glorius S, Nies B, Vater C, Despang F, Hanke T and Gelinsky M 2014 Fabrication of porous scaffolds by three-dimensional plotting of a pasty calcium phosphate bone cement under mild conditions *J. Tissue Eng. Regen. Med.* **8** 682–93
- [33] Luo Y, Lode A, Sonntag F, Nies B and Gelinsky M 2013 Well-ordered biphasic calcium phosphate–alginate scaffolds fabricated by multi-channel 3D plotting under mild conditions *J. Mater. Chem. B* **1** 4088–98
- [34] Akkineni A R, Luo Y, Schumacher M, Nies B, Lode A and Gelinsky M 2015 3D plotting of growth factor loaded calcium phosphate cement scaffolds *Acta Biomater.* **27** 264–74
- [35] Ahlfeld T, Akkineni A R, Förster Y, Köhler T, Knaack S, Gelinsky M and Lode A 2017 Design and fabrication of complex scaffolds for bone defect healing: combined 3D plotting of a calcium phosphate cement and a growth factor-loaded hydrogel *Ann. Biomed. Eng.* **45** 224–36
- [36] Schütz K, Placht A-M, Paul B, Brüggemeier S, Gelinsky M and Lode A 2017 Three-dimensional plotting of a cell-laden alginate/methylcellulose blend: towards biofabrication of tissue engineering constructs with clinically relevant dimensions *J. Tissue Eng. Regen. Med.* **11** 1574–87
- [37] Hempel U, Reinstorf A, Poppe M, Fischer U, Gelinsky M, Pompe W and Wenzel K W 2004 Proliferation and differentiation of osteoblasts on bio cement D modified with collagen type I and citric acid *J. Biomed. Mater. Res. B* **71B** 130–43
- [38] Böcker W *et al* 2008 Introducing a single-cell-derived human mesenchymal stem cell line expressing hTERT after lentiviral gene transfer *J. Cell. Mol. Med.* **12** 1347–59
- [39] Schumacher M, Henß A, Rohnke M and Gelinsky M 2013 A novel and easy-to-prepare strontium(II) modified calcium phosphate bone cement with enhanced mechanical properties *Acta Biomater.* **9** 7536–44
- [40] Ji S and Guvendiren M 2017 Recent advances in bioink design for 3D bioprinting of tissues and organs *Front. Bioeng. Biotechnol.* **5** 23
- [41] Huttmacher D W, Schantz T, Zein I, Ng K W, Teoh S H and Tan K C 2001 Mechanical properties and cell cultural response of polycaprolactone scaffolds designed and fabricated via fused deposition modeling *J. Biomed. Mater. Res.* **55** 203–16
- [42] Temple J P, Hutton D L, Hung B P, Huri P Y, Cook C A, Kondragunta R, Jia X and Grayson W L 2014 Engineering anatomically shaped vascularized bone grafts with hASCs and 3D-printed PCL scaffolds *J. Biomed. Mater. Res. A* **102** 4317–25
- [43] Melchels F P W, Blokzijl M M, Levato R, Peiffer Q C, Ruijter M, de, Hennink W E, Vermonden T and Malda J 2016 Hydrogel-based reinforcement of 3D bioprinted constructs *Biofabrication* **8** 035004

- [44] Morouço P, Biscaia S, Viana T, Franco M, Malça C, Mateus A, Moura C, Ferreira F C, Mitchell G and Alves N M 2016 Fabrication of poly(ϵ -caprolactone) scaffolds reinforced with cellulose nanofibers, with and without the addition of hydroxyapatite nanoparticles *BioMed Res. Int.* **2016** 1596157
- [45] Boanini E, Torricelli P, Boga C, Micheletti G, Cassani M C, Fini M and Bigi A 2016 (9R)-9-hydroxystearate-functionalized hydroxyapatite as antiproliferative and cytotoxic agent toward osteosarcoma cells *Langmuir* **32** 188–94
- [46] Lee E-J, Teng S-H, Jang T-S, Wang P, Yook S-W, Kim H-E and Koh Y-H 2010 Nanostructured poly(ϵ -caprolactone)-silica xerogel fibrous membrane for guided bone regeneration *Acta Biomater.* **6** 3557–65
- [47] Liao H-T, Chen Y-Y, Lai Y-T, Hsieh M-F and Jiang C-P 2014 The osteogenesis of bone marrow stem cells on mPEG-PCL-mPEG/hydroxyapatite composite scaffold via solid freeform fabrication *BioMed Res. Int.* **2014** 321549
- [48] Sawyer A A, Hennessy K M and Bellis S L 2007 The effect of adsorbed serum proteins, RGD and proteoglycan-binding peptides on the adhesion of mesenchymal stem cells to hydroxyapatite *Biomaterials* **28** 383–92
- [49] Phipps M C *et al* 2011 Mesenchymal stem cell responses to bone-mimetic electrospun matrices composed of polycaprolactone, collagen I and nanoparticulate hydroxyapatite *PLoS One* **6** e16813
- [50] Lode A, Heiss C, Knapp G, Thomas J, Nies B, Gelinsky M and Schumacher M 2018 Strontium-modified premixed calcium phosphate cements for the therapy of osteoporotic bone defects *Acta Biomater.* **65** 475–85
- [51] Ginebra M-P, Canal C, Espanol M, Pastorino D and Montufar E B 2012 Calcium phosphate cements as drug delivery materials *Adv. Drug Deliv. Rev.* **64** 1090–110
- [52] Bernhardt A, Schumacher M and Gelinsky M 2014 Formation of osteoclasts on calcium phosphate bone cements and polystyrene depends on monocyte isolation conditions *Tissue Eng. C* **21** 160–70
- [53] Kular J, Tickner J, Chim S M and Xu J 2012 An overview of the regulation of bone remodelling at the cellular level *Clin. Biochem.* **45** 863–73
- [54] Heller M *et al* 2016 Materials and scaffolds in medical 3D printing and bioprinting in the context of bone regeneration *Int. J. Comput. Dent.* **19** 301–21
- [55] Roohani-Esfahani S-I, Newman P and Zreiqat H 2016 Design and fabrication of 3D printed Scaffolds with a mechanical strength comparable to cortical bone to repair large bone defects *Sci. Rep.* **6** 19468
- [56] Cordell J M, Vogl M L and Wagoner Johnson A J 2009 The influence of micropore size on the mechanical properties of bulk hydroxyapatite and hydroxyapatite scaffolds *J. Mech. Behav. Biomed. Mater.* **2** 560–70
- [57] Graham S and Brown P W 1993 The low temperature formation of octacalcium phosphate *J. Cryst. Growth* **132** 215–25
- [58] Wang L and Nancollas G H 2008 Calcium orthophosphates: crystallization and dissolution *Chem. Rev.* **108** 4628–69
- [59] Song Y, Zhang C, Wang P, Wang L, Bao C, Weir M D, Reynolds M A, Ren K, Zhao L and Xu H H K 2017 Engineering bone regeneration with novel cell-laden hydrogel microfiber-injectable calcium phosphate scaffold *Mater. Sci. Eng. C* **75** 895–905
- [60] Mason B N, Califano J P and Reinhart-King C A 2012 Matrix stiffness: a regulator of cellular behavior and tissue formation *Engineering Biomaterials for Regenerative Medicine* ed S K Bhatia (New York: Springer) pp 19–37
- [61] Li L, Crosby K, Sawicki M, Shaw L L and Wang Y 2012 Effects of surface roughness of hydroxyapatite on cell attachment and proliferation *J. Biotechnol. Biomater.* **2** 150
- [62] Akkineni A R, Ahlfeld T, Lode A and Gelinsky M 2016 A versatile method for combining different biopolymers in a core/shell fashion by 3D plotting to achieve mechanically robust constructs *Biofabrication* **8** 045001
- [63] Raja N and Yun H 2016 A simultaneous 3D printing process for the fabrication of bioceramic and cell-laden hydrogel core/shell scaffolds with potential application in bone tissue regeneration *J. Mater. Chem. B* **4** 4707–16
- [64] Mekhilei N V, Lim K S, Brown G C J, Mutreja I, Schon B S, Hooper G J and Woodfield T B F 2018 Automated 3D bioassembly of micro-tissues for biofabrication of hybrid tissue engineered constructs *Biofabrication* **10** 024103

A NOVEL PLASMA-BASED BIOINK STIMULATES CELL
PROLIFERATION AND DIFFERENTIATION IN BIOPRINTED,
MINERALIZED CONSTRUCTS

A Novel Plasma-Based Bioink Stimulates Cell Proliferation and Differentiation in Bioprinted, Mineralized Constructs

Tilman Ahlfeld,[‡] Nieves Cubo-Mateo,[‡] Silvia Cometta, Vera Guduric, Corina Vater, Anne Bernhardt, A. Rahul Akkineni, Anja Lode,^{*} and Michael Gelinsky^{*}

Cite This: *ACS Appl. Mater. Interfaces* 2020, 12, 12557–12572

Read Online

ACCESS |

Metrics & More

Article Recommendations

Supporting Information

ABSTRACT: Extrusion-based bioprinting, also known as 3D bioplotting, is a powerful tool for the fabrication of tissue equivalents with spatially defined cell distribution. Even though considerable progress has been made in recent years, there is still a lack of bioinks which enable a tissue-like cell response and are plottable at the same time with good shape fidelity. Herein, we report on the development of a bioink which includes fresh frozen plasma from full human blood and thus a donor/patient-specific protein mixture. By blending of the plasma with 3 w/v% alginate and 9 w/v% methylcellulose, a pasty bioink (plasma-alg-mc) was achieved, which could be plotted with high accuracy and furthermore allowed bioplotting mesenchymal stromal cells (MSC) and primary osteoprogenitor cells to spread within the bioink. In a second step, the novel plasma-based bioink was combined with a plottable self-setting calcium phosphate cement (CPC) to fabricate bone-like tissue constructs. The CPC/plasma-alg-mc biphasic constructs revealed open porosity over the entire time of cell culture (35 d), which is crucial for bone tissue engineered grafts. The biphasic structures could be plotted in volumetric and clinically relevant dimensions and complex shapes could be also generated, as demonstrated for a scaphoid bone model. The plasma bioink potentiated that bioplotting MSC were not harmed by the setting process of the CPC. Latest after 7 days, MSC migrated from the hydrogel to the CPC surface, where they proliferated to 20-fold of the initial cell number covering the entire plotted constructs with a dense cell layer. For bioplotting and osteogenically stimulated osteoprogenitor cells, a significantly increased alkaline phosphatase activity was observed in CPC/plasma-alg-mc constructs in comparison to plasma-free controls. In conclusion, the novel plasma-alg-mc bioink is a promising new ink for several forms of bioprinted tissue equivalents and especially gainful for the combination with CPC for enhanced, biofabricated bone-like constructs.

KEYWORDS: plasma, bioprinting, bone, hydroxyapatite, calcium phosphate cement, alginate, bioink, plotting

1. INTRODUCTION

Additive manufacturing (AM) has become an intriguing principle for implant fabrication in healthcare. The bottom-up concept allows the manufacturing of implants with patient-specific sizes and shapes, providing better surgical treatment and improved acceptance by the patient.¹ AM was introduced to tissue engineering,² combining the patient-specific shape of a scaffold with the patient's autologous cells, improving the biological response and enabling self-healing of the damaged tissues.

One of the most studied AM techniques in biofabrication is extrusion-based bioprinting. The processing in mild conditions, e.g. the absence of unphysiological temperatures like in fused filament fabrication of thermoplastics, is called 3D (bio)-plotting.³ Bioplotting allows the fabrication of 3D constructs containing temperature sensitive substances, such as growth factors but also cells encapsulated into an artificial extracellular matrix. The plottable cell-matrix mixture is termed bioink.⁴ In

the past decade, different groups have developed various bioinks based on biopolymers^{5–9} or synthetic hydrogels.^{10–13}

To further strengthen the patient-specific concept of bioprinting, bioinks which are directly derived from the patient by the use of human plasma were recently introduced.^{14–17} Human plasma is the largest component of blood and makes up about 55% of its total volume; it contains over 700 proteins (such as fibrinogen, fibronectin, or albumin as major components but also growth factors, hormones, and cytokines).¹⁸ It has been widely used as base material for tissue engineering to treat skin, bone, muscles, nerves, eye lesions,

Received: January 13, 2020

Accepted: February 24, 2020

Published: February 24, 2020

ACS Publications

© 2020 American Chemical Society

12557

<https://dx.doi.org/10.1021/acsami.0c00710>
ACS Appl. Mater. Interfaces 2020, 12, 12557–12572

Figure 1. Characterization of growth factors included in the pooled plasma. Exemplarily displayed are the most highly expressed proteins. The used protein arrays showed (A) angiogenic proteins and (B) cytokines/chemokines. The full angiogenic protein analysis is shown in Figure S1.

etc.,¹⁹ as it promotes the natural process of wound healing, resembling the induced conditions when a tissue is injured.

There are two main plasma products used in the clinic: platelet-rich plasma (PRP) and fresh frozen plasma (FFP). The difference between PRP and FFP lies in the speed and time of centrifugation used to separate the different components from the blood, mainly removing the red blood cells (erythrocytes). For the PRP, a more complex and slower process (slow spin) is required to prevent pelleting of the platelets. However, in the case of FFP a high spin is used, which induces the breakage of some platelets causing the release of growth factors to the collected plasma. This method is faster and cheaper and allows clinicians to use the platelets and white blood cells as other product. Therefore, although FFP contains a reduced number of platelets, it still encloses a large variety of proteins and factors that can stimulate the regeneration of tissues.

The first study investigating the potential of blood plasma for bioprinting was carried out by Gruene et al. using laser-based bioprinting.¹⁴ The applicability of plasma for extrusion-based bioprinting was first investigated by Cubo et al. (FFP)¹⁵ and Faramarzi et al. (PRP).¹⁶ All these studies showed a path to develop plasma-based, patient-specific bioinks suitable for bioprinting of constructs with patient-specific shape, material composition, and cells; however, the obtained constructs lacked high shape fidelity and high layer numbers. Furthermore, in a recent study, Mendes et al. blended PRP with cellulose nanocrystals and bioprinted cell-laden structures into an agarose support bath evidencing the high potential of plasma-based bioinks.¹⁷

Herein we aimed to develop a plasma-based bioink suitable for extrusion-based bioprinting, without the need of a support bath to maintain its structure in air without collapsing. We expected that this simple approach might be applicable for more advanced technologies like multichannel or core/shell plotting, since the applied materials do not have to be tailored to compatibility with a support bath material or similar environmental changes. We utilized FFP, which from now on will be referred to as plasma in this manuscript. Such a plasma-based bioink would have a beneficial potential for several types of tissue equivalents, due to its broad range of growth factors as well as its composition.

As a possible application, we investigated whether the developed bioink is suitable for bioplotting of bone tissue equivalents. According to general understandings, we considered the three following points: (i) bone constructs should contain mineral phases providing a physicochemical and

mechanical similarity to native hydroxyapatite (HAp),^{20–22} (ii) for clinical relevance, the engineered grafts should be scalable to volumetric size ($>10 \times 10 \times 10 \text{ mm}^3$),²³ (iii) cells in the center of a volumetric tissue need nutrient and oxygen supply and therefore tissue engineered constructs should contain macropores to allow good cell vitality in the center of the bioprinted construct and potentially also ingrowth of blood vessels after implantation.^{7,24}

Recently, we figured out a fabrication window for the combination of a plottable calcium phosphate cement (CPC) and bioinks.²⁵ This fabrication window allows optimal setting of the CPC matrix (20 min incubation in water-saturated atmosphere, followed by immersion into aqueous solution) without impairing cell viability within the bioink. The CPC is based on α -tricalcium phosphate which transforms into calcium-deficient nanocrystalline hydroxyapatite (HAp),²⁶ which is resorbable by osteoclasts *in vivo*. Therefore, plotted CPC constructs are directly involved in the bone remodeling process.^{27,28} The HAp-forming character, good plottability, and mechanical stiffness, as well as its osteoconductive properties tag the CPC as outstanding material for bioprinted, mineralized bone equivalents.

First, human plasma was characterized regarding its composition and content of growth factors. Based on rheological tests, a plasma-based bioink, which can be used in extrusion-based plotting, was developed. Cells encapsulated into the plasma-based bioink revealed good postfabrication viability and spreading within the hydrogel. Afterward, the bioink was plotted in combination with CPC and the maintenance of pores was studied over a cultivation period of 35 days. The plasma-based bioink and CPC synergistically complemented each other leading to strong cell proliferation in the biphasic system and support of osteogenic differentiation of bioplotting osteoprogenitor cells. Deducing from these results, a prototype of a perfusable vascularized bone model with a bioplotting coculture of endothelial cells and MSC was fabricated.

2. RESULTS

2.1. Development and Characterization of a Plasma-Based Bioink. **2.1.1. Characterization of Plasma and Rheological Investigations.** Whereas the composition of PRP has been thoroughly investigated in the past, the composition of FFP remains unclear. Because of this, plasma from 5 donors (derived from the local blood donation service) was pooled to obtain a uniform mixture. Afterward, protein content as well as presence of growth factors was investigated in order to better

Figure 2. Representative curves of (A) shear thinning experiments of plasma, 3 w/v% alginate dissolved in plasma and 3 w/v% alginate-9 w/v% methylcellulose dissolved in plasma and (B) shear recovery tests of plasma-alg-mc.

Figure 3. Extrusion-based printing of the plasma-alg-mc ink. (A) Stereomicroscopic image of a cubic scaffold plotted with a 0°/90° layer orientation (4 layers). (B, C) Images of a plotted logo of the Technische Universität Dresden (50 layers). (D) Image of a plotted large-sized logo of the Centre for Translational Bone, Joint and Tissue Research (4 layers). (E–G) Scanning electron microscopical images of the plasma-alg-mc ink. (H) Fused filament test, demonstrating that plasma-alg-mc can be plotted utilizing various needle diameters with the acceptance of altered shape fidelity. Scale bars: (A) 2 mm, (B) 10 mm, (D) 20 mm, (E) 1 mm, (F) 200 μm , (G) 50 μm .

estimate the biological performance of the plasma used in this study. First, 3 mL of the pooled plasma was lyophilized and weighed. The determined solid content of the plasma pool was $84.4 \text{ mg}\cdot\text{mL}^{-1}$. Additionally, the fibrinogen content was determined as $2.26 \text{ mg}\cdot\text{mL}^{-1}$. Furthermore, growth factor composition was investigated using protein arrays, as they might influence the response of cells to a plasma-based bioink. Results for the 10 highest expressed angiogenic proteins are shown in Figure 1A. The array revealed a total of 28 angiogenic factors (see Figure S1), which could contribute actively to vascularization of bioprinted grafts. Moreover, these proteins might provide pro-inflammatory and anti-inflammatory cues, as well as support for the proliferation of endothelial cells and the sprouting of angiogenic progenitors, such as angiogenin.²⁹ Also serpin E1 (an inhibitor of fibrinolysis³⁰) and leptin (impacting bone metabolism³¹) were detected, which might be influential for

bone tissue development. Furthermore, five cytokines that play a role in inflammation and mediate the crosstalk between cells, especially of the hematopoietic system, could be detected (Figure 1B). Overall, the plasma pool contained a large variety of proteins and growth factors that might function together more effectively than single proteins can impact the response of cells to the bioink.

Rheological evaluation of the plasma revealed a low viscosity comparable to that of pure water, as well as a shear thinning behavior, most probably as an effect of the contained fibrinogen (Figure 2A). Pure plasma could not be plotted as a single substance into macroporous structures, as the strands would fuse together after deposition leading to a complete unporous structure which inhibits diffusion of oxygen and nutrients. Hence, plasma was evaluated for its capability to be blended with biopolymers to enhance its plottability (Figure 2A). First, 3

Figure 4. Investigations on the behavior of bioplotting MSC in the plasma-alg-mc bioink, a PBS-alg-mc bioink served as plasma-free control. (A) Representative images of a cell viability staining of MSC (live cells green, dead cells red) at day 1 of cultivation in PBS-alg-mc and plasma-alg-mc. Scale bars represent 300 μm . (B) Calculated cell viability within the plotted bioinks at day 1 ($n = 7$, mean $\pm$ SD, *** $p < 0.001$). (C) Fluorescence stainings of the cytoskeletons (Phalloidin, green) and the nuclei (DAPI, blue) of MSC within the plasma-alg-mc constructs after 1 and 14 d of cultivation. Cells were able to spread and form cell–cell contacts.

w/v% alginate (alg) was dissolved in the plasma solution, resulting in a significantly increased viscosity. Furthermore, incorporation of alginate into the bioink would allow fast and cytocompatible cross-linking after fabrication. However, initial plotting tests displayed a collapse of plotted strands in the z -direction, and macropores were not stable after plotting (data not shown). Therefore, 9 w/v% methylcellulose (mc) was added to the plasma-alg solution, resulting in a significant increase of ink viscosity (Figure 2A), similarly as already shown for 3% alg dissolved in PBS.³² The final plasma-alg-mc ink displayed tolerable fusion of the strands in the z -direction after plotting, and macropores were clearly observed; hence, this blend was

selected for the following experiments. A frequency sweep test of plasma-alg-mc is shown in Figure S2. Both, storage and loss modulus increased with the angular velocity. Until a crossover point at $3.2 \text{ rad}\cdot\text{s}^{-1}$, the loss modulus was higher compared to the storage modulus, indicating that plasma-alg-mc was not cross-linked in zero-shear state. Also shear recovery behavior of plasma-alg-mc was tested (Figure 2B). Even after repeated exposure to high shear rates, plasma-alg-mc was able to increase viscosity in low-shear regions, and full recovery, compared to previous cycles, was achieved. The average recovery time was determined as 39.1 ± 13 , which is a rather high value compared to values reported in the literature like those for highly

Figure 5. (A–C) Stereo light and scanning electron microscopical images of biphasic CPC/plasma-alg-mc scaffolds. Open macroporosity was achieved in the vertical direction after plotting and cross-linking with 100 mM CaCl_2 solution. (C) The biphasic composition allowed building up volumetric structures with high shape fidelity and lateral porosity. (D) Virtually sliced 3D model of a scaphoid bone and (E) layer design of one layer; blue: sacrificial ink, white: CPC, red: plasma-alg-mc. (F, G) Plotting process of the biphasic scaphoid bone, the sacrificial ink appears transparent, CPC white and plasma-alg-mc yellowish.

concentrated poloxamer 407 inks (25 s)³³ or alginate-carrageenan inks (5–15 s).³⁴

2.1.2. 3D Plotting and Fused Filament Test of Plasma-alg-mc. Plasma-alg-mc could be plotted in $0^\circ/90^\circ$ layer patterns resulting in rectangular macropores between the strands (Figure 3A). Additionally, more complex structures of larger scales were achieved with high accuracy as exemplarily demonstrated with the logo of the Technische Universität Dresden in which more than 50 layers were easily stacked achieving volumetric structures (Figure 3B,C). Moreover, the logo of the Centre for Translational Bone, Joint and Soft Tissue Research with a basic area of approximately 176 cm^2 was successfully plotted (Figure 3D). In scanning electron microscopy (SEM) images of the surface and the cross section of plasma-alg-mc strands (Figure 3E–G) no heterogeneous phases were observed, indicating that alginate and methylcellulose, but also the fibrinogen of the plasma were homogeneously distributed throughout the entire scaffold. Most crucially, fibrinogen did not self-assemble to fibrin during the storage in the cartridge prior to the plotting process, which otherwise would have led to an inhomogeneous material deposition. Additionally, a distinct microporosity of the plasma-alg-mc ink was observed. Finally, the extrusion behavior was investigated by plotting meandering structures with continuously increasing strand distances (Figure 3H), allowing the assessment of the shape fidelity.³⁵ The ink could be plotted using various needle diameters (250, 410, and $610 \mu\text{m}$). Resulting strand widths were $0.53 \pm 0.03 \text{ mm}$, $0.84 \pm 0.14 \text{ mm}$, and $1.13 \pm 0.17 \text{ mm}$, respectively. No significant width changes were observed between plotted strands. As expected, shape fidelity was dependent on the used needle diameter; those structures plotted with a $250 \mu\text{m}$ needle demonstrated the best shape fidelity (Figure 3H).

2.1.3. Bioplotting of MSC in the Plasma-alg-mc Bioink. In order to investigate the applicability of the plasma-alg-mc ink for bioplotting, human mesenchymal stem cells (MSC), immortal-

ized by ectopic expression of human telomerase reverse transcriptase (hTERT) by lentiviral gene transfer,³⁶ were used. MSC were encapsulated into the bioink at a concentration of $5 \times 10^6 \text{ cells mL}^{-1}$ of paste, subsequently plotted and cross-linked with 100 mM CaCl_2 for 10 min before incubation in cell culture medium. As plasma-free control, a bioink with similar concentrations of alginate and methylcellulose but dissolved in PBS (PBS-alg-mc), was used, which was described before.³² Viability of MSC in the plotted scaffolds, assessed at day 1 by live/dead staining (Figure 4A, B), was significantly increased in the plasma-alg-mc bioink ($77.6 \pm 2.7\%$) compared to the PBS-alg-mc bioink ($49.7 \pm 4.7\%$). In the case of PBS-alg-mc, cell viability increased over time (up to 95%); however, MSC stay roundish, as the ink lacks binding motifs for cell attachment.³² In contrast, a dense network of MSC was found within the plasma-alg-mc ink, as well as MSC spread over the scaffold surface after 14 days of incubation (Figure 4C).

2.2. Multichannel Plotting of a Calcium Phosphate Cement and Plasma-alg-mc for Biphasic Bone Constructs.

2.2.1. Fabrication of Open-Porous, Volumetric Constructs in Clinically Relevant Dimensions. The plasma-alg-mc bioink promoted MSC spreading within the hydrogel matrix, exhibiting a fibroblast-like phenotype, features that have been shown beneficial for the differentiation to osteoblasts.³⁷ We therefore investigated the applicability of the plasma-alg-mc bioink for bone tissue engineering. Plottable CPC are promising materials for bone replacement, due to their physicochemical resemblance of the native bone mineral. Therefore, it was examined, whether plasma-alg-mc could be combined with CPC in a multichannel plotting process in order to come closer to bone-like tissue equivalents. Biphasic CPC/plasma-alg-mc scaffolds were successfully plotted with alternating layer deposition ($0^\circ/90^\circ$) (Figure 5A–C). Structural characterizations of the scaffolds were performed through stereo and scanning electron microscopy. Top views of the scaffolds after

Figure 6. (A) Change of the strand width (◆) of plasma-alg-mc strands and change of the pore size (□) in either a monophasic (shown as black) or a biphasic (shown as blue) structure, where CPC strands were intercalated ($n = 5$, mean $\pm$ SD). (B–E) Stereo light microscopical pictures of the monophasic plasma-alg-mc (B, C) and the biphasic CPC/plasma-alg-mc (D, E) structures after 1 and 35 days of incubation in cell culture medium. Even after 35 days of incubation, open-porous structures were observed in both configurations.

plotting, initial humidity setting for 20 min, and cross-linking with 100 mM CaCl_2 solution for 10 min revealed open porosity and high shape fidelity of the biphasic structures in multiple layers. The CPC strands contributed positively to the shape fidelity of every single plotted layer, and thereby for the entire plotted structure, as they did not fuse in the z -direction (Figure 5B). In the biphasic structures even horizontal pores between the layers could be achieved (Figure 5C), which was not possible with the monophasic plasma-alg-mc scaffolds (Figure 3). It was concluded that biphasic structures consisting of CPC and plasma-alg-mc are beneficial to achieve volumetric constructs of clinically relevant size. To prove that, a scaphoid bone model was reconstructed from cone beam computed tomography data and plotted utilizing a sacrificial ink based on pure methylcellulose, as recently published.³⁸ The sacrificial ink was needed during fabrication to support overhanging structures and concave and convex surfaces of the scaphoid bone. The biphasic scaphoid bone model could be plotted with high shape accuracy, exhibiting the typical peanut-like shape (Figure 5D–G, Video S1). The sacrificial ink was washed away without residues after postprocessing (hardening/cross-linking) of the biphasic structure. In addition, the combination of CPC and plasma-alg-mc allowed the fabrication of more complex layer arrangements ($0^\circ/72^\circ/144^\circ/216^\circ/288^\circ$) and advanced pore geometries like a gyroid structure (Figure S3).

2.2.2. Volumetric Strand Swelling of Plasma-alg-mc. Open porosity is crucial for nutrient supply in bone tissue engineering. Therefore, volumetric swelling investigations were carried out on both, monophasic plasma-alg-mc and biphasic CPC/plasma-alg-mc constructs. Volumetric swelling was studied as the change of the strand width and the change of the pore size at the following time points: after plotting (after pl), after cross-linking (after cl), and after 1, 2, 3, 4, 5, 7, 14, 21, and 35 days of incubation in cell culture medium.

It was observed that the strand width of plasma-alg-mc within biphasic scaffolds was higher compared to the strand width of monophasic plasma-alg-mc scaffolds over the whole time of investigation, indicating stronger swelling; moreover, the average pore size decreased more strongly for the biphasic construct (Figure 6A). In general terms, both groups showed the same swelling kinetics: the strand width increased significantly ($p < 0.05$) within the first 3 days and then decreased slightly and afterward showed an almost constant value. In the 35 days

studied, plasma-alg-mc strands in monophasic scaffolds showed an increase of approximately 1.4-fold of their original width, whereas those strands in biphasic structures increased their strand widths up to 1.7-fold. The pore sizes after plotting were determined as 1.20 ± 0.17 mm and 1.14 ± 0.17 mm for plasma-alg-mc and CPC/plasma-alg-mc constructs, respectively. After 35 d, the average pore size decreased to 1.10 ± 0.07 mm (plasma-alg-mc) and 0.91 ± 0.15 mm (CPC/plasma-alg-mc), evidencing the observation of the increased strand swelling of the hydrogel in the presence of CPC strands. Crucially for our approach, in both conditions an open porosity over the whole time of observation was achieved and the pore sizes were acceptable for bone-like constructs (Figure 6C, E).

2.3. Biplotting of Mineralized Constructs. **2.3.1. Cell Viability of MSC in the Plasma-Based Bioink within Biphasic, Mineralized Constructs.** Biphasic constructs consisting of cell-laden plasma-alg-mc and CPC were plotted and evaluated for postplotting cell viability at day 1, giving evidence of cell damage caused by extrusion and by interaction of the cells with the two materials. To study the effect of plasma, a PBS-alg-mc bioink was used as control. Representative confocal fluorescence microscopy image stacks are shown in Figure 7A. The black and therefore optically opaque structures in the brightfield mark the CPC strands, which show no signal under the confocal microscope. In PBS-alg-mc, a clear drop of cell viability was observed at the CPC/bioink interface, as the number of living cells decreased distinctly when they are in direct contact of the bioink with the CPC in comparison to the cells surrounded only by the bioink, which are separated from the CPC by the macropores. This observation confirmed the results of our previous findings.²⁵ Interestingly, the drop of cell viability was not observed for plasma-alg-mc; living and dead cells were homogeneously distributed throughout the whole bioink strands without notable change at the CPC/bioink interface. The calculated cell viabilities are presented in Figure 7B. Monophasic PBS-alg-mc and plasma-alg-mc constructs revealed cell viabilities of $49.8 \pm 4.9\%$ and $77.6 \pm 2.7\%$, respectively (Figure 4). Biphasic PBS-alg-mc scaffolds did not show a significantly different cell viability (denoted as *biphasic global* in Figure 7B), repeatedly proving our previous findings.²⁵ However, at the interface to CPC, denoted as *biphasic CPC interface* the cell viability was significantly decreased in comparison to monophasic constructs ($37.8 \pm 14.5\%$, $p <$

Figure 7. (A) Representative images of living (green) and dead (red) cells in plasma-alg-mc and PBS-alg-mc bioinks at the CPC-bioink crossing point (for the observation, the bioink was on top of the CPC). Dotted lines mark the acellular CPC strand. Scale bars present 350 μ m. (B) Calculated cell viabilities of biphasic CPC/bioink constructs (denoted as biphasic global) and cell viabilities in biphasic constructs at the CPC/bioink interface (denoted as biphasic CPC interface; $n = 7$, mean $\pm$ SD, *** $p < 0.001$).

0.05). In CPC/plasma-alg-mc constructs, no differences in the cell viability were observed; the viability in biphasic scaffolds at

the interface between CPC and plasma-alg-mc was determined as $79.2 \pm 5.6\%$.

2.3.2. Cell Migration and Proliferation of MSC in Long-Time Culture. After bioplotting, a cell-laden CPC/plasma-alg-mc construct was imaged by optical coherence tomography (OCT), whose reconstruction is shown in Figure 8A. The OCT measurement confirmed that stable macropores were also achieved with cell-laden plasma-alg-mc bioinks. Cell behavior over a long-period of time in culture was investigated by evaluating live/dead stainings (Figure 8B, lower magnifications are provided in Figure S4). Three different zones within the biphasic constructs were identified as areas of interest: the interface of two bioink strands (bioink–bioink interface), the interface of two CPC strands (CPC–CPC interface), and the interface of the bioink and CPC (bioink–CPC interface). Figure 8B shows selected images of the CPC–bioink interface at day 1 and day 7 as well as the CPC–CPC interface at day 14 and 21. After 1 day of culture, live and dead cells were found within the plasma-alg-mc bioink without significant changes on the cell viability at the bioink–bioink and bioink–CPC interface. There were no cells at the CPC–CPC interface. MSC had a roundish shape (Figure 8B(i)). Latest after 7 days, MSC migrated from the bioink to the CPC strands at the bioink–CPC interface, where they attached and elongated (Figure 8B(ii), white arrows; a SEM image of this process is shown in Figure S5). Cells in the vicinity of the bioink were found to be metabolically active; in addition, some dead cells were observed at regions of the CPC strands which were more distant from the bioink. With ongoing culture, the cell density in the bioink, especially at the bioink–bioink interface was decreased. However, remaining cells showed an elongated and spread morphology. Subsequently, cell migration progressed until the CPC strands were further populated by MSC. After 14 days, nearly all zones of the biphasic constructs were covered by cells originating from the bioink–CPC interface; only at the CPC–CPC interface some cell-free zones were observed (Figure 8B(iii)). After day 21, these areas

Figure 8. (A) 3D reconstruction of an optical coherence tomography analysis of a cell-laden biphasic construct consisting of CPC (white) and the cell-laden plasma-alg-mc bioink (opaque-porous). (B) Cell viability of bioplotting, biphasic constructs consisting of a cell-laden plasma-alg-mc bioink and CPC. Living cells appear green, dead cells appear red, CPC shows a weak blue autofluorescence. After plotting, MSC were encapsulated in the hydrogel (day 1, i). Later on, the MSC migrated to the CPC strands (day 7, ii) where they attached and proliferated to a great extent (day 14 and day 21, iii, iv), covering the whole CPC surface and bridging the macropores. Scale bars represent 300 μ m.

appeared to be fully covered by a dense cell-network. Furthermore, MSC still proliferated and started bridging the macropores around the CPC–CPC interface (Figure 8B(iv)). This strong cell layer did not detach from the biphasic construct but was stable for longer than a culture time of 35 days (Figure S4). At the CPC–CPC interface, a few dead cells were found after day 14 and 21, respectively.

The number of MSC in the biphasic system was evaluated by measurement of the DNA content (Figure 9). After a slow

Figure 9. Cell number per scaffold in bioplotting biphasic CPC/plasma-alg-mc constructs, determined by measurements of the DNA content. MSC proliferated within the mineralized constructs until day 28, afterward no significant change of the cell number was measured ($n = 5$ for d 1–d 28, $n = 3$ for d 35, mean $\pm$ SD, ** $p < 0.01$, n.s. not significant).

increase of the cell number during the first 7 days, the cell number significantly increased until day 28. Exemplarily, at day 1 the cell number per scaffold was determined as $0.32 \times 10^5 \pm 0.04 \times 10^5$ and at day 28 the cell number per scaffold increased to $6.71 \times 10^5 \pm 1.91 \times 10^5$, which complies with a 20-fold higher cell number after 4 weeks of cell culture, most probably due to the proliferation of the MSC on the CPC strands. After 28 days, no significant change of the cell number was determined.

2.4. Osteogenic Differentiation of Primary Osteoprogenitor Cells in Biphasic Constructs. The capability of bioplotting primary osteoprogenitor cells to differentiate along the osteogenic lineage was investigated determining the alkaline phosphatase (ALP) activity in biphasic CPC/bioink constructs (Figure 10). Again, in order to evaluate the influence of plasma on osteogenic differentiation, the plasma-alg-mc bioink in a biphasic construct was compared to PBS-alg-mc in a biphasic construct. Human preosteoblasts (hOB) and human dental pulp stem cells (hDPSC) were used for these investigations. Both, hOB and hDPSC are osteoprogenitor cells which can be found in different zones of the skeleton. hOB were bioplotting with a concentration of $2.65 \times 10^6 \text{ cells mL}^{-1}$ bioink and hDPSC with a concentration of $4.0 \times 10^6 \text{ cells mL}^{-1}$ bioink. After postprocessing, cells were allowed to recover for 7 d in medium containing 15% fetal calf serum (FCS) before either osteogenic media with 10% FCS and osteogenic supplements (OS+) or basal media with 10% FCS but without osteogenic supplements (OS–) were applied.

For hOB, biphasic scaffolds of both bioinks, PBS-alg-mc and plasma-alg-mc revealed a higher cell number for constructs cultured in basal medium compared to constructs cultured in osteogenic medium, though differences could not be estimated as significant. In addition, hOB proliferated significantly more in the structures with plasma-alg-mc compared to PBS-alg-mc (Figure 10A). Live/dead images of the CPC/bioink interface are provided in Figure S6. Microscopy revealed that hOB tended to

spread to a greater extent within the plasma-alg-mc bioink, whereas hOB did not spread in PBS-alg-mc. The specific ALP activity of hOB (Figure 10B) was increased for those scaffolds cultured in osteogenic medium and the differences were significant latest at day 28 of culture. Hence, the absolute ALP activity (ALP activity per scaffold) was only significantly ($p < 0.01$) increased over time for CPC/plasma-alg-mc scaffolds after cultivation in osteogenic medium due to the high proliferation of cells which could be stimulated by the osteogenic agents, but not for CPC/plasma-alg-mc cultured in basal medium or CPC/PBS-alg-mc constructs regardless the presence of osteogenic media.

For hDPSC, the cell number increased until day 14, and decreased afterward (Figure 10D). Again, cells were able to spread within the bioink and migrated quickly in the presence of plasma (Figure S6). At day 14, biphasic scaffolds with plasma-alg-mc contained significantly more cells than biphasic scaffolds with PBS-alg-mc (Figure 10D). The specific ALP activity of the bioplotting hDPSC was significantly higher in the presence of osteogenic supplements; moreover, the presence of plasma in the bioink significantly increased the specific ALP activity at day 14 in biphasic scaffolds (Figure 10E). To further evidence osteogenic differentiation of hDPSC, the ALP was stained in CPC/plasma-alg-mc and CPC/PBS-alg-mc samples at day 28 of culture in osteogenic media (Figure 10E–G). The ALP-positive staining is red and was only observed in CPC/plasma-alg-mc (Figure 10G), but not in CPC/PBS-alg-mc scaffolds (Figure 10F).

2.5. Toward Fabrication of Vascularized Bone-like Constructs by Bioplotting of Endothelial Cells in a Complex Volumetric Bone Model. Challenging for bone tissue engineering is the vascularization of the respective cell-matrix construct to ensure oxygen and nutrients supply of the cells. With the aid of bioplotting, a prevascularization of scaffolds seems to be possible by spatial distribution of endothelial cells. Therefore, it was investigated whether the combination of CPC and plasma-alg-mc is useful to achieve complex prevascular structures in volumetric dimensions. Figure 11 shows the proof-of-concept study of this system. First, a model of a blood vessel spreading into four branches within a CPC scaffold was constructed using CAD (Figure 11A). As the plasma contains a huge variety of angiogenic factors, it was intended that the plasma-alg-mc forms the wall of the lumen of the constructs. The CAD file was successfully plotted by the multichannel plotter. The resulting scaffold (Figure 11B–D) consisted of more than 120 layers and demonstrated a very regular pore structure between the CPC strands, evidencing the high shape fidelity of CPC constructs. The plotted blood vessel structure had a diameter of 5 mm. After postprocessing of the scaffold, an undiluted phenol red solution, known to stain materials strongly, was injected into the artificial vessel starting from the unbranched side. The solution could perfuse the four branches of the vessel staining them red (Figure 11E), which crucially evidenced the suitability of the biphasic system for perfusion through a predesigned vessel. In a first test, a HUVEC cell-containing plasma-alg-mc bioink was plotted in a model structure. Previously it was reported that endothelial cells have a higher tendency to mature to angiogenic structures in cocultures with MSC,³⁹ which additionally could be demonstrated in a bone-like environment with osteogenically differentiated human bone marrow-derived stem cells.⁴⁰ Thus, for this pilot test, the HUVEC cell suspension was supplemented with MSC prior to mixing with the bioink. The bioplotting coculture showed high cell viability in the plasma-alg-mc bioink after

Figure 10. Osteogenic differentiation of primary human osteoprogenitor cells in bioplotting mineralized constructs consisting of CPC/PBS-alg-mc (red) or CPC/plasma-alg-mc (blue) with preosteoblasts (hOB, A,B) or dental pulp stem cells (hDPSC, C–G). After 7 d of culture, basal medium (OS–) or osteogenic medium enriched with osteogenic supplements (OS+) was added. The presence of the plasma-based bioink promoted the proliferation and differentiation of hOB and hDPSC. Significantly increased ALP activity was observed in CPC/plasma-alg-mc samples treated with osteogenic media ($n = 3$, mean $\pm$ SD, $*p < 0.05$, $**p < 0.01$, $***p < 0.001$). (E–G) ALP staining of CPC/PBS-alg-mc (F) and CPC/plasma-alg-mc (G) scaffolds; the positive staining (i.e., red color) was only observed in plasma-containing scaffolds.

fabrication (Figure 11F). The cells stayed viable over 35 days in an endothelial cell growth medium, and the lumen was open in the entire period of cell culture. After 35 days, cells were observed to cover the surface of the lumen (Figure S7). In conclusion, biphasic constructs consisting of CPC and the novel plasma-alg-mc bioink are suitable for the fabrication of vascularized bone constructs, which marks a good starting point for further investigations.

3. DISCUSSION

Herein, we developed a novel plasma-based bioink, which can be utilized for extrusion-based bioprinting in air as plotting environment. Porous 3D constructs with excellent shape fidelity could be fabricated independently from additional assistive equipment like a support bath or a cross-linking atmosphere—that broadens the applicability of this bioink in comparison to the plasma-based bioinks which have been developed before.^{15–17}

Although a full analysis of the composition of fresh frozen plasma remains a subject of research, it was previously

demonstrated that various proteins supporting cell adhesion, such as fibrinogen, as well as active growth and differentiation factors are present in human blood plasma.¹⁸ The amount of these components varies from human to human; for example, the fibrinogen concentration can vary from $2 \text{ mg}\cdot\text{mL}^{-1}$ to $4.5 \text{ mg}\cdot\text{mL}^{-1}$ in healthy individuals.⁴¹ Especially fibrinogen and its assembled form of fibrin play a crucial role in the wound healing process and are involved in several cell-matrix interactions during healing,⁴² making it particularly interesting for biofabrication. Our analyses of the integrated fibrinogen content as well as the variety of included proteins in the plasma pool are in line with the literature indicating that the obtained results of this study should be valid for every plasma sample obtained from potential patients. Considering the patient-specific character of a plasma-based bioink, and especially the presence of immunoregulatory proteins detected in the plasma (Figure 1), this new generation of bioinks might be advantageous for both the immune response and the stimulation of the self-healing capacity of the damaged tissue.

Figure 11. Development of a perfusable CPC/plasma-alg-mc construct. (A) Full and section view of the designed CAD model; white: CPC, red: the perfusable channel which shall be lined with plasma-alg-mc. The channel branches from one into four channels. (B–D) Photograph and stereomicroscopic images of the plotted biphasic construct. Scale bars of C and D represent 10 mm. (E) The plotted scaffold was manually perfused with undiluted phenol red solution, after perfusion only the hydrogel was stained evidencing perfusion through the plotted channel structure. (F) Fluorescence microscopic image of a live/dead stained bioplot model structure with an inner lumen at day 1. The stained cells are a coculture of endothelial HUVEC and MSC; green: living cells, red: dead cells, blue: autofluorescent CPC.

As the low viscosity of plasma alone would not allow 3D plotting of strands with sufficient shape fidelity, which is mandatory for open porosity within bioplot constructs, we blended it with alginate, for enhancement of viscosity and ability for fast and cytocompatible gelation with divalent ions, as well as with methylcellulose, which was shown in several studies to significantly increase the viscosity of bioinks and allows extrusion bioprinting with high accuracy.^{32,43–45} This approach combines the favorable cell-supportive properties of plasma with the excellent fabrication properties of alginate-methylcellulose blends.³² Alginate and methylcellulose cannot be cleaved by enzymes synthesized by humans.^{46,47} The degradation of these polymers only happens as a result of the decomposition of the matrix, which occurs by release of calcium ions and non-cross-linked methylcellulose molecules *in vitro* and *in vivo*.⁴⁸ This results in swelling of the hydrogel matrix. Our results showed that slow swelling of plasma-alg-mc occurred over time, but macropores were not closed after 35 days under cell culture conditions (Figure 6). Moreover, the swelling of plasma-alg-mc strands was increased in the presence of CPC, but macropores were clearly maintained as well. This shows that macroporous (CPC//)plasma-alg-mc constructs are able to provide nutrient and oxygen supply even after a longer period of time.

Alginate and methylcellulose do not provide binding motifs for mammalian cells. As demonstrated before³² and evidenced in this study (Figure S6), a plasma-free alginate-methylcellulose bioink forces encapsulated cells to stay roundish without visible signs of spreading and attachment to the matrix. In contrast, the inclusion of plasma promoted cell spreading and the formation of intercellular interactions. This might be attributed to the presence of fibrinogen within the plasma-based bioink, which offers integrin binding motifs for cell attachment.^{49,50} Fibrinogen has been used before as a component of different bioinks where final concentrations between 10 and 30 mg·mL^{−1}

were applied.^{24,51,52} Our plasma-based bioink contains less fibrinogen (2.26 mg·mL^{−1}); however, proliferation of MSC and their intercellular interactions inside the novel plasma-based bioink was substantially supported indicating that this amount of fibrinogen is sufficient to trigger cell adhesion at least in the presence of other plasma proteins which could function in a costimulatory manner.

The great potential of the plasma-alg-mc bioink was tested for engineering of bioplot bone grafts. The complex structure, need of vascular supply, and opportunity to combine bone-like constructs with those mimicking other tissues (like cartilage—for the treatment of osteochondral defects) make bone an interesting target to use the methods of bioprinting.⁵³ In the past, three strategies for bioprinting of bone grafts were investigated. The first strategy was the maturation from MSC-derived osteoblasts within hydrogels followed by mineralization processes as reported by Duarte-Campos et al. for agarose-collagen type I blends.⁵⁴ The second strategy was the supplementation of the bioink with bioceramic precursors which enhanced the stiffness of the bioprinted constructs and offered chemical cues to bioprinted cells.^{55,56} The third strategy was the usage of multichannel printing to spatially arrange a stiff material, enhancing mechanical properties as needed for bone substitutes, next to a soft cell-laden bioink. That can be realized for example by core/shell printing, as described for a self-setting α -tricalcium phosphate-hydroxypropyl methylcellulose paste (core) and a cell-laden alginate bioink (shell); these constructs showed advanced resistance against compression compared to pure alginate scaffolds without deterioration of cell viability.⁵⁷ Another option to modulate the rigidity of bioplot constructs is the alternating strand deposition of stiff materials and cell-laden bioinks.⁵⁸ For example, thermoplastic poly- ϵ -caprolactone (PCL)-bioink constructs were successfully matured from cartilaginous templates to bone tissue,⁵⁹ enhanced the development of mineralized tissue by usage of gene activated bioinks,⁶⁰ or were spatially ordered to osteon-like structures.⁶¹

Recently, our group introduced self-setting calcium phosphate cements as alternative stiff material for multichannel bioplotting that enables bioprinting of mineralized bone constructs.²⁵ Utilizing PBS-alg-mc as model bioink, we investigated the fabrication window for bioplot constructs consisting of cell-laden bioinks and CPC. This fabrication window involves as postprocessing incubation in water-saturated atmosphere of the hybrid constructs for 20 min before applying aqueous solutions, namely the CaCl₂ cross-linking solution and finally cell culture medium. This process allows optimal setting of the CPC without the formation of microcracks, which were shown to impair the mechanical stability of plotted constructs.⁶² The cell viability was not impaired by this preincubation step.²⁵ However, the setting reaction taking place in the presence of the cells seems to negatively affect the cell viability directly at the interface between CPC and bioink; this effect occurred after plotting but vanished at later time points. We concluded that the transformation process of the CPC precursors to HAP evoked a local, short-time cytotoxic environment, most possibly as a consequence of local pH changes.^{25,63} Similar hazardous effects on cells in the presence of transforming calcium phosphate phases were also described in the literature.^{64,65} To overcome that limitation, bioinks for combined plotting with CPC should contain components which are able to buffer those local pH changes. The novel plasma-based bioink was a potential candidate addressing this problem, because fresh frozen plasma

holds a bicarbonate and protein-based buffering system.^{66,67} Our observations of the postplotting cell viability at the CPC/bioink interface (Figure 7) clearly showed that the presence of plasma prevented the local reduction of cell viability, indicating the higher efficacy of these native buffers in comparison to PBS.

A crucial point for bone tissue engineered constructs is the maintenance of open pores during the healing period in order to ensure nutrient supply and vascularization. The alginate in the plasma-alg-mc bioink is the component that stabilizes the plotted strands by formation of a cross-linked hydrogel network in the presence of divalent cations like Ca^{2+} . Recently we found that the calcium ions within the CPC interact with plottable alginate-pastes probably inducing a local cross-linking effect at the interface between CPC and alginate which further stabilizes the ink during fabrication.^{68,69} This stabilization effect allows the fabrication of scaffolds with high layer numbers, as it was observed also in the present study for the plasma-alg-mc bioink. After postprocessing (including immersion in a CaCl_2 solution for cross-linking of the bioink), the calcium-deficient HAP formed during CPC setting competes with the reversibly cross-linked alginate for Ca^{2+} , which influences the degradation properties of the hydrogel.^{69,70} The findings of the increased volumetric swelling of plasma-alg-mc strands in the biphasic scaffolds in comparison to monophasic scaffolds without CPC confirm this interaction between the two materials in such biphasic structures after setting. Crucially, the slightly increased swelling was not annihilating the pore structure of the biphasic constructs and open macropores were maintained over the entire period of observation, i.e. 35 days. The mechanical properties of such plotted, porous constructs are mainly dependent on the CPC, which strongly increases parameters such as the compressive modulus (approximately 40 kPa for monophasic bioink only and approximately 30 MPa for biphasic constructs) or the compressive strength (approximately 15 kPa and 1.3 MPa for monophasic and biphasic constructs, respectively).²⁵ Since the HAP degrades only as a result of osteoclastic resorption, it can be assumed that the general mechanical properties of biphasic constructs do not change *in vitro* and only in course of the bone remodeling process *in vivo*.

All examined cell types, hMSC, hOB, and hDPSC proliferated in biphasic CPC/plasma-alg-mc scaffolds. We observed the formation of a dense cell network in the plasma-bioink; however, the additional coverage of the CPC strands might be the main reason for the strong increase of the cell number. The charges of the HAP surface might facilitate adhesion of proteins from the cell culture medium and from soluble parts of the plasma, and thus enabled ongoing cell migration from the CPC/bioink interface to the CPC surface. Additionally, the CPC strands exhibit a much higher stiffness compared to the soft hydrogels which likely attracted the osteoblastic cells.⁷¹ This effect was also observed in the plasma-free CPC/PBS-alg-mc system, but delayed and to a considerably smaller extent. Indeed, the presence of the plasma-based bioink in the biphasic system evoked significantly increased cell numbers compared to the plasma-free control (Figure 10). This might be caused by the significant higher number of living cells in the plasma-based bioink after plotting resulting in improved migration of the cells to the CPC.⁷² The typical spread phenotype of the bone cells in the plasma-based bioink and on the CPC strands, as well as the high cell number in the biphasic CPC/plasma-alg-mc system were most probably responsible for the significant increase of the ALP activity in response to osteogenic induction, indicating bone tissue formation. Interestingly, the ALP activity of the

hDPSC showed its maximum already after 7 days of osteogenic differentiation, while the ALP activity of the hOB increased until the end of the observation time. This is in line with monitoring of conventional 2D cultures on polystyrene surfaces, indicating that the cells did not lose their intrinsic properties through the fabrication and postprocessing process.

Plasma is part of the blood system and contains fibrinogen promoting angiogenesis as well as angiogenesis stimulating proteins. In the future, the novel plasma-based bioink might be a promising candidate for the fabrication of blood vessels. Our data show that HUVEC encapsulated in plasma-alg-mc can be spatially defined arranged in multiphasic tissue constructs. Such prevascularized structures can be biofabricated in clinically relevant dimensions and have the ability to get perfused which would enhance the additional formation of vascular sprouts by the endothelial cells.

4. CONCLUSION

In this work, a novel bioink was developed, which combines the favorable biological of human plasma, which can potentially be derived as autologous material from the patient to be treated, with the excellent plotting properties and high shape fidelity of alginate-methylcellulose blends. It can be bioplotted with good shape fidelity and promotes high postplotting cell viability and cell attachment resulting in the formation of intercellular interactions. The plasma-based bioink was successfully combined with a HAP-forming calcium phosphate cement which resembles the native mineral of bone. Our results showed that the plasma-based bioink and CPC form a synergistic system supporting adhesion, proliferation, and osteogenic differentiation of bone cells. Both, the plasma-based bioink and the biphasic CPC/plasma-alg-mc system are promising candidates for the fabrication of tissue engineered (bone) grafts comprising a patient-specific bioink, a defect-adapted shape and autologous cells for a fully patient-tailored tissue graft.

5. MATERIALS AND METHODS

5.1. Materials. CPC paste (precursor powders: α -tricalcium phosphate, calcium hydrogen phosphate anhydrous, calcium carbonate, hydroxyapatite, and as catalyst potassium hydrogen phosphate; carrier liquid: Miglyol, Cremophor ELP and Amphisol A)^{26,73} was manufactured by INNOTERE GmbH (Radebeul, Germany) and sterilized by γ -irradiation (25 kGy). Fresh frozen human plasma was provided by a local blood bank (Deutsches Rotes Kreuz - Blutspendedienst Nord-Ost, Dresden, Germany). As plasma contains many coagulation factors that can vary strongly from one human to another, the plasma of 5 donors was pooled for all the experiments to avoid variations along the study. The pool was analyzed on its qualitative protein content utilizing Proteome Profiler Arrays (Human Angiogenesis Array Kit and Human Cytokine Array, R&D Systems Inc., Minneapolis, MN, USA) according to the manufacturer's protocol. Alginic acid sodium salt from brown algae (M/G ratio 1:2) and methylcellulose (M0512, Sigma, USA, molecular weight ≈ 88 kDa, 4.000 cP.s) were purchased by Sigma-Aldrich (Germany). Alginate (alg) and methylcellulose (mc) powders were sterilized by dry autoclaving at 121 °C for 20 min before used. Phosphate buffered saline (PBS) was purchased by Fisher Scientific.

5.2. Ink Preparation. CPC was used as ready-to-use paste without further modification. A plasma-alginate-methylcellulose (plasma-alg-mc) ink was prepared as follows: alg was dissolved at a concentration of 30 $\text{mg}\cdot\text{mL}^{-1}$ directly in the thawed plasma. 0.7 mg of tranexamic acid (Amchafibrin, Rottapharm, Barcelona, Spain) was added per mg of fibrinogen (fibrinogen content within pooled plasma was 2.26 $\text{mg}\cdot\text{mL}^{-1}$) to prevent early fibrinolysis, allowing plotted constructs to be stable *in vitro* for a longer period of time. Afterward, mc was added at a

concentration of 90 mg·mL⁻¹. The blend was homogenized by gentle manual stirring with a spatula and methylcellulose was allowed to swell for 30 min for complete dissolution before the blend was further processed. PBS-alg-mc was prepared as described before.³² Briefly, a 3 w/v% alg solution was mixed with 9 w/v% mc and the blend was allowed to swell for 2 h before further processing.

5.2.1. Rheology. Plasma, plasma-alg, and plasma-alg-mc pastes were evaluated for rheological behavior (Ares-G2, TA Instruments, New Castle, Delaware, USA, and Rheotest RN 4, Medingen, Germany). Shear thinning was tested at constantly increasing shear rates from 0 to 100 s⁻¹ over 1200 s (increment 0.08 s⁻¹) using a plate–plate geometry (d = 60 mm for liquid plasma; d = 50 mm for plasma-alg and plasma-alg-mc) with a gap distance of 0.1 mm at 25 °C. After an initial amplitude sweep test to detect the linear viscoelastic region, oscillatory frequency sweep tests ($f = 0.01\text{ s}^{-1}$ – 10 s^{-1}) were performed on the plasma-alg-mc paste and storage modulus as well as loss modulus were obtained from the data. Shear recovery tests of plasma-alg-mc were performed as follows: a low shear rate (5 s⁻¹) inducing shear stresses of the linear viscoelastic region (LVR), was applied for 200 s, afterward a 100-fold higher shear rate inducing shear stresses outside the LVR of 500 s⁻¹ was applied for 100 s. The procedure was repeated three times, and viscosity was measured during the entire experiment. Shear thinning experiments, frequency sweep tests, and shear recovery tests were repeated three times.

5.3. Scaffold Fabrication. **5.3.1. Three-Dimensional Plotting of Monophasic and Biphasic Constructs.** Plasma-alg-mc and CPC were transferred into 10 mL cartridges (Nordson EFD, Oberhaching, Germany) and processed by a pneumatic-driven multichannel extrusion plotter (Bioscaffolder 3.1, GeSiM mbH, Radeburg, Germany). The inks were dispensed through dosing needles (Globaco, Rödermark, Germany); the plotting parameters are summarized in Table 1. Cubic-shaped (base area 16 × 16 mm² and 20 × 20 mm²)

Table 1. Plotting Parameters

	Needle [μm]	Layer height [μm]	Air pressure [kPa]	Plotting speed [mm·s ⁻¹]
CPC	410	260	135	12
	250	120	65	10
Plasma-alg-mc	410	260	55	10
	610	360	50	10
PBS-alg-mc	410	260	85	9

monophasic and biphasic scaffolds were fabricated with a strand distance of 2 mm and layer-to-layer orientation of 90°. If not differently mentioned, scaffolds were plotted with 4 layers and needles of an inner diameter of 410 μm were used. Monophasic scaffolds were cross-linked for 10 min in a bath of 100 mM CaCl₂ solution. Biphasic constructs were postprocessed as described previously.²⁵ In brief, biphasic constructs were allowed to set in water-saturated atmosphere (humidity >95%) at 37 °C for 20 min, afterward cross-linking solution (100 mM CaCl₂) was added to the scaffolds for 10 min and subsequently scaffolds were transferred to cell culture medium before they were used for further experiments.

5.3.2. Microscopy. Macroporous structure of the plotted constructs was imaged by a stereo light microscope (Leica M205 C equipped with DFC295 camera, Germany). Freeze-dried samples were further analyzed by scanning electron microscopy (SEM; Philips XL 30/ESEM, operated in SEM mode) at a voltage of 3 kV (spot size 3) with a field emission gun ($n = 3$).

5.3.3. Filament Fusion Test. Plasma-alg-mc was evaluated for its plotting behavior and shape fidelity, as proposed by Ribeiro et al.³⁵ First, plasma-alg-mc was plotted in three layers on top of each other with three different needle diameters (250 μm, 410 and 610 μm). In every layer, the strand-to-strand distances increased by 0.2 mm between the single strands. Afterward, strand widths, strand distances, and fused segment lengths were measured in images taken by stereomicroscopy. The fused segment length was divided by the strand width to obtain the

shape fidelity ratio, which was assigned to its allocated strand distance. Optimal shape fidelity was defined at a ratio of 1.

5.3.4. Volumetric Strand Swelling and Pore Size. Monophasic plasma-alg-mc and biphasic CPC/plasma-alg-mc constructs were plotted (base area 12 × 12 mm², 4 layers) and volumetric strand swelling of the hydrogel ink as well as the pore size were investigated by measuring the strand width and the smallest distance between two adjacent strands at different time points: before and after cross-linking, and at days 1, 2, 3, 5, 7, 14, and 21 of incubation in cell culture medium consisting of DMEM (Dulbecco's Modified Eagle's Medium, Gibco, Thermo Fisher), 10% fetal calf serum (FCS), 100 U·mL⁻¹ penicillin and 100 μg·mL⁻¹ streptomycin (Pen/Strep) (all from Biochrom, Berlin, Germany). For measuring, photographs of different scaffolds ($n = 5$) were taken by stereo light microscopy and strand widths were analyzed with Fiji.⁷⁴

5.4. Cell Plotting of Monophasic and Biphasic Constructs.

5.4.1. Cell Isolation and Expansion. Immortalized human mesenchymal stem cells expressing human telomerase reverse transcriptase (MSC)³⁶ were expanded in monolayer culture at 37 °C and 5% CO₂ in DMEM (Biochrom, Germany), containing 10% FCS (Corning), 100 U·mL⁻¹ penicillin, and 100 μg·mL⁻¹ streptomycin (PS) (Biochrom). Culture medium was changed twice a week.

Human preosteoblasts (hOB) were isolated from the femoral head of an osteoarthritic patient (female, 56 years) undergoing total hip replacement at the University Hospital Carl Gustav Carus Dresden (Germany) after informed consent (approval by the ethics commission of TU Dresden, EK 303082014) as previously published.⁷⁵ In short, spongy bone fragments (1–2 mm in diameter) were dissected, washed 4–5 times with Hanks balanced salt solution (HBSS, ThermoFisher Scientific), and treated twice with collagenase II solution (1 mg·mL⁻¹ collagenase II, 235 U·mg⁻¹, Biochrom, Berlin, Germany in Minimal Essential Medium, α -modification (α -MEM), 10% FCS, 2 mM L-glutamine, PS, 3 mM CaCl₂). The supernatant of the second collagenase treatment was harvested, cells were pelleted by centrifugation and expanded in α -MEM containing 15% FCS (Corning) and PS. Cells of the fourth passage were used for the experiments.

Human dental pulp stem cells (hDPSC) were isolated from human wisdom teeth as previously published.⁷⁶ The ethics commission of TU Dresden approved the application of hDPSC for *in vitro* experiments (EK 106042010). Cells were expanded to the fifth passage in monolayer culture at 37 °C and 5% CO₂ in DMEM (Biochrom), containing 20% FCS (Corning) and PS. Culture medium was changed twice a week.

Human Umbilical Vein Endothelial Cells (HUVEC) were purchased from Promocells (Heidelberg, Germany). Cells were expanded in Endothelial Cell Growth Medium (Promocell) to the fourth passage; the culture medium was changed twice a week.

5.4.2. Fabrication of Cell-Laden Constructs. After trypsinization from cell culture flasks, cells were centrifuged and resuspended in 100 μL cell culture medium per gram of the used bioink. The final cell concentrations were 5 × 10⁶ cells·mL⁻¹ bioink for MSC, 2.5 × 10⁶ cells·mL⁻¹ bioink for hOB, 4 × 10⁶ cells·mL⁻¹ bioink for hDPSC and 6 × 10⁶ cells·mL⁻¹ bioink for a HUVEC/MSC coculture (ratio 1:1). Afterward, cell suspensions were mixed by hand into plasma-alg-mc and PBS-alg-mc, transferred into the plotter cartridges and afterward deposited and postprocessed as described before in a sterile environment. Bioplotting constructs containing MSC were cultured in DMEM supplemented with 10% FCS and P/S. Constructs containing hOB and hDPSC were cultured in α -MEM with 15% FCS and PS for 7 days, afterward osteogenic media (α -MEM with 10% FCS, PS, 10⁻⁷ M dexamethasone, 10 mM β -glycerophosphate and 0.05 mM ascorbic acid 2-phosphate, denoted as OS+) or basal media (α -MEM with 10% FCS and PS, denoted as OS-) were applied for 21 days. The bioplotting HUVEC/MSC coculture was cultured in Endothelial Cell Growth Medium.

5.4.3. Cell Viability and Morphology. Cell viability was investigated by a live/dead assay using Calcein AM/ethidium homodimer-1 staining (LIVE/DEAD Viability/Cytotoxicity Kit, for mammalian cells, ThermoFisher Scientific) following the manufacturer's protocol. Confocal laser scanning microscopy (cLSM, Leica TCS SP5, Leica Microsystems, Wetzlar, Germany) was used to determine quantitative

cell viability of MSC at day 1 of plasma-*alg-mc*, PBS-*alg-mc*, and its biphasic equivalents ($n = 3$). Cell viability was assessed by semiautomatic counting of living cells and dead cells with averaged thresholds derived by all image stacks ($n = 7$ per group). The viability was determined as the ratio of living cells divided by the total cell number (which equals the sum of living and dead cells). At later time points, fluorescence microscopy (Keyence 9000 fluorescent light microscope) was used to investigate cell morphology. In differentiation experiments, live/dead staining was performed to control cell morphology, but only one scaffold per group and time point was assessed due to the limited available number of primary cells.

5.4.4. Quantification of Cell Number and ALP Activity. At distinct time points, plotted constructs containing MSC, hOB, or hDPSC were washed with HBSS (Fisher Scientific) and frozen at -80°C until biochemical analysis. After thawing, samples were incubated with 2 mL lysis buffer (1% Triton X-100 in PBS) for 3 h on ice. DNA determination was performed using Quantifluor ds DNA quantification reagent (Promega, WI, USA) according to the manufacturer's instructions. A calibration line was constructed from cells with different concentrations, which were frozen and lysed in the same way. Ten μL of cell lysates were transferred in triplicate into a 96 well plate, and 190 μL of the Quantifluor working solution was added to each sample. The plate was protected from light and incubated for 5 min at room temperature. Fluorescence was read with a multifunction microplate reader (Infinite 200 PRO, Tecan, Switzerland) at an excitation and emission wavelength of 485 and 535 nm, respectively.

ALP activity was quantified by incubating 20 μL of each lysate with 80 μL substrate solution (1 $\text{mg}\cdot\text{mL}^{-1}$ 4-nitrophenylphosphate in 0.1 M diethanolamine, 0.1% Triton X-100, 1 mM MgCl_2 , pH 9.8—all from Sigma) for 30 min at 37°C . After stopping the enzymatic reaction with 1 M NaOH, absorbance at 405 nm was determined with the microplate reader. A calibration line was established using different concentrations of 4-nitrophenol. ALP activity was related to cell number from the same lysate to obtain specific ALP activity.

5.5. Statistical Evaluation. All values were evaluated by one-way Analysis of Variance (ANOVA), followed by Tukey's multiple comparison test with GraphPad Prism 8 software. Significant differences were assumed at $p < 0.05$.

■ ASSOCIATED CONTENT

SI Supporting Information

The Supporting Information is available free of charge at <https://pubs.acs.org/doi/10.1021/acsami.0c00710>.

Figure S1: Full analysis of the angiogenic protein array. Figure S2: Frequency sweep test of plasma-*alg-mc*. Figure S3: Various 3D plotted structures of CPC/plasma-*alg-mc* constructs. Figure S4: Live/dead images of bioplotting MSC in CPC/plasma-*alg-mc* constructs over 35 d. Figure S5: SEM image of MSC at day 7. Figure S6: Live/dead images of bioplotting osteoprogenitor cells at day 7 and day 14. Figure S7: Live/dead images of bioplotting HUVEC/MSK at day 35. (PDF)

Video S1: Fabrication process of a scaphoid bone model consisting of CPC and plasma-*alg-mc* by use of a methylcellulose support ink. (MP4)

■ AUTHOR INFORMATION

Corresponding Authors

Anja Lode — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany; Email: anja.lode@tu-dresden.de

Michael Gelinsky — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany; orcid.org/0000-0001-9075-5121; Email: michael.gelinsky@tu-dresden.de

Authors

Tilman Ahlfeld — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany; orcid.org/0000-0002-6350-3399

Nieves Cubo-Mateo — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany

Silvia Cometta — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany

Vera Guduric — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany

Corina Vater — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany

Anne Bernhardt — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany

A. Rahul Akkineni — Centre for Translational Bone, Joint and Soft Tissue Research, Faculty of Medicine, TU Dresden 01307 Dresden, Germany

Complete contact information is available at:

<https://pubs.acs.org/doi/10.1021/acsami.0c00710>

Author Contributions

†TA and NCM contributed equally.

Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript. TA and NCM planned and conducted all experiments, evaluated the obtained data and wrote the major and essential parts of the manuscript. SC, VG, CV, AB, and ARA assisted during realization and evaluation of experiments and contributed significantly to preparation of the manuscript. AL and MG set the direction of research, supervised the experiments, evaluated the obtained data, gained funding and contributed to as well as revised the manuscript.

Funding

This research was supported by the European Space Agency through its General Study Program (GSP) scheme (project “3D printing of living tissues for space exploration”) and by a grant of the German Federal Ministry of Education and Research (BMBF; project Innopoly, grant number 13XP5067).

Notes

The authors declare no competing financial interest.

■ ACKNOWLEDGMENTS

We would like to kindly thank Oliver Tiebel and his team for analysis of the fibrinogen content, Anna-Maria Placht for her continued support in the lab, David Kilian and the research group Clinical Sensing and Monitoring of the Technische Universität Dresden for taking and reconstructing the OCT image of Figure 7A, and Tommaso Ghidini, head of Structures, Mechanisms and Materials Division at the European Space Agency (ESTEC, Noordwijk, The Netherlands), for his personal interest in the project and for supporting our work. We thank the group of Matthias Schieker, Technical University of Munich, Germany for kindly providing MSC and Carola Petto, University Hospital Dresden, Clinic and Polyclinic of Maxillofacial Surgery, for isolating DPSC.

■ ABBREVIATIONS

FFP, fresh frozen plasma; PRP, platelet-rich plasma; CPC, calcium phosphate cement; HAp, hydroxyapatite; alg, alginate; mc, methylcellulose; ALP, alkaline phosphatase; MSC, mesenchymal stem cells; hOB, human preosteoblasts; HDPSC, human dental pulp stem cells; HUVEC, human umbilical vein endothelial cells

■ REFERENCES

- (1) Dzian, A.; Živčák, J.; Penciak, R.; Hudák, R. Implantation of a 3D-Printed Titanium Sternum in a Patient with a Sternal Tumor. *World J. Surg. Oncol.* **2018**, *16*, 7.
- (2) Landers, R.; Pfister, A.; Hübner, U.; John, H.; Schmelzeisen, R.; Mülhaupt, R. Fabrication of Soft Tissue Engineering Scaffolds by Means of Rapid Prototyping Techniques. *J. Mater. Sci.* **2002**, *37*, 3107–3116.
- (3) Moroni, L.; Boland, T.; Burdick, J. A.; Maria, C. D.; Derby, B.; Forgacs, G.; Groll, J.; Li, Q.; Malda, J.; Mironov, V. A.; Mota, C.; Nakamura, M.; Shu, W.; Takeuchi, S.; Woodfield, T. B. F.; Xu, T.; Yoo, J. J.; Vozzi, G. Biofabrication: A Guide to Technology and Terminology. *Trends Biotechnol.* **2018**, *36*, 384–402.
- (4) Groll, J.; Burdick, J. A.; Cho, D.-W.; Derby, B.; Gelinsky, M.; Heilshorn, S. C.; Juengst, T.; Malda, J.; Mironov, V. A.; Nakayama, K.; Ovsianikov, A.; Sun, W.; Takeuchi, S.; Yoo, J. J.; Woodfield, T. B. F. A Definition of Bioinks and Their Distinction from Biomaterial Inks. *Biofabrication* **2019**, *11*, 013001.
- (5) Markstedt, K.; Mantas, A.; Tournier, I.; Martínez Ávila, H.; Hägg, D.; Gatenholm, P. 3D Bioprinting Human Chondrocytes with Nanocellulose-Alginate Bioink for Cartilage Tissue Engineering Applications. *Biomacromolecules* **2015**, *16*, 1489–1496.
- (6) Zehnder, T.; Sarker, B.; Boccaccini, A. R.; Detsch, R. Evaluation of an Alginate-Gelatin Crosslinked Hydrogel for Bioplotting. *Biofabrication* **2015**, *7*, 025001.
- (7) Kesti, M.; Eberhardt, C.; Pagliccia, G.; Kenkel, D.; Grande, D.; Boss, A.; Zenobi-Wong, M. Bioprinting Complex Cartilaginous Structures with Clinically Compliant Biomaterials. *Adv. Funct. Mater.* **2015**, *25*, 7406–7417.
- (8) Law, N.; Doney, B.; Glover, H.; Qin, Y.; Aman, Z. M.; Sercombe, T. B.; Liew, L. J.; Dilley, R. J.; Doyle, B. J. Characterisation of Hyaluronic Acid Methylcellulose Hydrogels for 3D Bioprinting. *J. Mech. Behav. Biomed. Mater.* **2018**, *77*, 389–399.
- (9) Schacht, K.; Jungst, T.; Schweinlin, M.; Ewald, A.; Groll, J.; Scheibel, T. Biofabrication of Cell-Loaded 3D Spider Silk Constructs. *Angew. Chem., Int. Ed.* **2015**, *54*, 2816–2820.
- (10) Melchels, F.; Dhert, W.; Huttmacher, D.; Malda, J. Development and Characterisation of a New Bioink for Additive Tissue Manufacturing. *J. Mater. Chem. B* **2014**, *2*, 2282.
- (11) Stichler, S.; Böck, T.; Paxton, N. C.; Bertlein, S.; Levato, R.; Schill, V.; Smolan, W.; Malda, J.; Tessmar, J.; Blunk, T.; Groll, J. Double Printing of Hyaluronic Acid/Poly(Glycidol) Hybrid Hydrogels with Poly(ϵ -Caprolactone) for MSC Chondrogenesis. *Biofabrication* **2017**, *9*, 044108.
- (12) Ouyang, L.; Highley, C. B.; Sun, W.; Burdick, J. A. A Generalizable Strategy for the 3D Bioprinting of Hydrogels from Nonviscous Photo-Crosslinkable Inks. *Adv. Mater.* **2017**, *29*, 1604983.
- (13) Billiet, T.; Gevaert, E.; De Schryver, T.; Cornelissen, M.; Dubrue, P. The 3D Printing of Gelatin Methacrylamide Cell-Laden Tissue-Engineered Constructs with High Cell Viability. *Biomaterials* **2014**, *35*, 49–62.
- (14) Gruene, M.; Deiwick, A.; Koch, L.; Schlie, S.; Unger, C.; Hofmann, N.; Bernemann, L.; Glasmacher, B.; Chichkov, B. Laser Printing of Stem Cells for Biofabrication of Scaffold-Free Autologous Grafts. *Tissue Eng., Part C* **2011**, *17*, 79–87.
- (15) Cubo, N.; Garcia, M.; Cañizo, J. F. d.; Velasco, D.; Jorcano, J. L. 3D Bioprinting of Functional Human Skin: Production Andin Vivoanalysis. *Biofabrication* **2017**, *9*, 015006.
- (16) Faramarzi, N.; Yazdi, I. K.; Nabavinia, M.; Gemma, A.; Fanelli, A.; Caizzzone, A.; Ptaszek, L. M.; Sinha, I.; Khademhosseini, A.; Ruskini, J. N.; Tamayol, A. Patient-Specific Bioinks for 3D Bioprinting of Tissue Engineering Scaffolds. *Adv. Healthcare Mater.* **2018**, *7*, 1701347.
- (17) Mendes, B. B.; Gomez-Florit, M.; Hamilton, A. G.; Detamore, M. S.; Domingues, R. M. A.; Reis, R. L.; Gomes, M. Human Platelet Lysate-Based Nanocomposite Bioink for Bioprinting Hierarchical Fibrillar Structures. *Biofabrication* **2020**, *12*, 015012.
- (18) Schwenk, J. M.; Omenn, G. S.; Sun, Z.; Campbell, D. S.; Baker, M. S.; Overall, C. M.; Aebersold, R.; Moritz, R. L.; Deutsch, E. W. The Human Plasma Proteome Draft of 2017: Building on the Human Plasma Peptide Atlas from Mass Spectrometry and Complementary Assays. *J. Proteome Res.* **2017**, *16*, 4299–4310.
- (19) Anitua, E.; Nurden, P.; Prado, R.; Nurden, A. T.; Padilla, S. Autologous Fibrin Scaffolds: When Platelet- and Plasma-Derived Biomolecules Meet Fibrin. *Biomaterials* **2019**, *192*, 440–460.
- (20) Samavedi, S.; Whittington, A. R.; Goldstein, A. S. Calcium Phosphate Ceramics in Bone Tissue Engineering: A Review of Properties and Their Influence on Cell Behavior. *Acta Biomater.* **2013**, *9*, 8037–8045.
- (21) Dorozhkin, S. V. Calcium Orthophosphates as Bioceramics: State of the Art. *J. Funct. Biomater.* **2010**, *1*, 22–107.
- (22) Habraken, W.; Habibovic, P.; Epple, M.; Bohner, M. Calcium Phosphates in Biomedical Applications: Materials for the Future? *Mater. Today* **2016**, *19*, 69–87.
- (23) Kilian, D.; Ahlfeld, T.; Akkineni, A. R.; Lode, A.; Gelinsky, M. Three-Dimensional Bioprinting of Volumetric Tissues and Organs. *MRS Bull.* **2017**, *42*, 585–592.
- (24) Kolesky, D. B.; Homan, K. A.; Skylar-Scott, M. A.; Lewis, J. A. Three-Dimensional Bioprinting of Thick Vascularized Tissues. *Proc. Natl. Acad. Sci. U. S. A.* **2016**, *113*, 3179–3184.
- (25) Ahlfeld, T.; Doberenz, F.; Kilian, D.; Vater, C.; Korn, P.; Lauer, G.; Lode, A.; Gelinsky, M. Bioprinting of Mineralized Constructs Utilizing Multichannel Plotting of a Self-Setting Calcium Phosphate Cement and a Cell-Laden Bioink. *Biofabrication* **2018**, *10*, 045002.
- (26) Heinemann, S.; Rössler, S.; Lemm, M.; Ruhnnow, M.; Nies, B. Properties of Injectable Ready-to-Use Calcium Phosphate Cement Based on Water-Immiscible Liquid. *Acta Biomater.* **2013**, *9*, 6199–6207.
- (27) Reitmaier, S.; Kovtun, A.; Schuelke, J.; Kanter, B.; Lemm, M.; Hoess, A.; Heinemann, S.; Nies, B.; Ignatius, A. Strontium(II) and Mechanical Loading Additively Augment Bone Formation in Calcium Phosphate Scaffolds. *J. Orthop. Res.* **2017**, *36*, 106–117.
- (28) Bernhardt, A.; Schumacher, M.; Gelinsky, M. Formation of Osteoclasts on Calcium Phosphate Bone Cements and Polystyrene Depends on Monocyte Isolation Conditions. *Tissue Eng., Part C* **2015**, *21*, 160–170.
- (29) Sheng, J.; Xu, Z. Three Decades of Research on Angiogenesis: A Review and Perspective. *Acta Biochim. Biophys. Sin.* **2016**, *48*, 399–410.
- (30) Rau, J. C.; Beaulieu, L. M.; Huntington, J. A.; Church, F. C. Serpins in Thrombosis, Hemostasis and Fibrinolysis. *J. Thromb. Haemostasis* **2007**, *5*, 102–115.
- (31) Upadhyay, J.; Farr, O. M.; Mantzoros, C. S. The Role of Leptin in Regulating Bone Metabolism. *Metab., Clin. Exp.* **2015**, *64*, 105–113.
- (32) Schütz, K.; Placht, A.-M.; Paul, B.; Brüggemeier, S.; Gelinsky, M.; Lode, A. Three-Dimensional Plotting of a Cell-Laden Alginate/Methylcellulose Blend: Towards Biofabrication of Tissue Engineering Constructs with Clinically Relevant Dimensions. *J. Tissue Eng. Regen. Med.* **2017**, *11*, 1574–1587.
- (33) Paxton, N.; Smolan, W.; Böck, T.; Melchels, F.; Groll, J.; Jungst, T. Proposal to Assess Printability of Bioinks for Extrusion-Based Bioprinting and Evaluation of Rheological Properties Governing Bioprintability. *Biofabrication* **2017**, *9*, 044107.
- (34) Kim, M. H.; Lee, Y. W.; Jung, W.-K.; Oh, J.; Nam, S. Y. Enhanced Rheological Behaviors of Alginate Hydrogels with Carrageenan for Extrusion-Based Bioprinting. *Journal of the Mechanical Behavior of Biomedical Materials* **2019**, *98*, 187–194.
- (35) Ribeiro, A.; Blokzijl, M. M.; Levato, R.; Visser, C. W.; Castilho, M.; Hennink, W. E.; Vermonden, T.; Malda, J. Assessing Bioink Shape Fidelity to Aid Material Development in 3D Bioprinting. *Biofabrication* **2018**, *10*, 014102.

- (36) Böcker, W.; Yin, Z.; Drosse, I.; Haasters, F.; Rossmann, O.; Wierer, M.; Popov, C.; Locher, M.; Mutschler, W.; Docheva, D.; Schieker, M. Introducing a Single-Cell-Derived Human Mesenchymal Stem Cell Line Expressing HTERT after Lentiviral Gene Transfer. *J. Cell. Mol. Med.* **2008**, *12*, 1347–1359.
- (37) Sun, L.; Pereira, D.; Wang, Q.; Barata, D. B.; Truckenmüller, R.; Li, Z.; Xu, X.; Habibovic, P. Controlling Growth and Osteogenic Differentiation of Osteoblasts on Microgrooved Polystyrene Surfaces. *PLoS One* **2016**, *11*, No. e0161466.
- (38) Ahlfeld, T.; Köhler, T.; Czichy, C.; Lode, A.; Gelinsky, M. A Methylcellulose Hydrogel as Support for 3D Plotting of Complex Shaped Calcium Phosphate Scaffolds. *Gels* **2018**, *4*, 68.
- (39) Guduric, V.; Metz, C.; Siadous, R.; Bareille, R.; Levato, R.; Engel, E.; Fricain, J.-C.; Devillard, R.; Luzanin, O.; Catros, S. Layer-by-Layer Bioassembly of Cellularized Poly(lactic Acid) Porous Membranes for Bone Tissue Engineering. *J. Mater. Sci.: Mater. Med.* **2017**, *28*, 78.
- (40) Quade, M.; Weber, D.; König, U.; Paul, B.; Simon, P.; Rösen-Wolff, A.; Schwartz-Albiez, R.; Gelinsky, M.; Lode, A. Heparin Modification of a Biomimetic Bone Matrix Modulates Osteogenic and Angiogenic Cell Response in Vitro. *Eur. Cell. Mater.* **2017**, *33*, 105–120.
- (41) Lowe, G. D.; Rumley, A.; Mackie, I. J. Plasma Fibrinogen. *Ann. Clin. Biochem.* **2004**, *41*, 430–440.
- (42) Laurens, N.; Koolwijk, P.; Maat, M. P. M. D. Fibrin Structure and Wound Healing. *J. Thromb. Haemostasis* **2006**, *4*, 932–939.
- (43) Gonzalez-Fernandez, T.; Nathan, S.; Hobbs, C.; Pitacco, P.; Freeman, F. E.; Cuniffe, G. M.; Dunne, N. J.; McCarthy, H. O.; Nicolosi, V.; O'Brien, F. J.; Kelly, D. J. Pore-Forming Bioinks to Enable Spatio-Temporally Defined Gene Delivery in Bioprinted Tissues. *J. Controlled Release* **2019**, *301*, 13–27.
- (44) Ahlfeld, T.; Cidonio, G.; Kilian, D.; Duin, S.; Akkineni, A. R.; Dawson, J. I.; Yang, S.; Lode, A.; Oreffo, R. O. C.; Gelinsky, M. Development of a Clay Based Bioink for 3D Cell Printing for Skeletal Application. *Biofabrication* **2017**, *9*, 034103.
- (45) Seidel, J.; Ahlfeld, T.; Adolph, M.; Kümmitz, S.; Steingroewer, J.; Krutz, F.; Bley, T.; Gelinsky, M.; Lode, A. Green Bioprinting: Extrusion-Based Fabrication of Plant Cell-Laden Biopolymer Hydrogel Scaffolds. *Biofabrication* **2017**, *9*, 045011.
- (46) Lee, K. Y.; Mooney, D. J. Alginate: Properties and Biomedical Applications. *Prog. Polym. Sci.* **2012**, *37*, 106–126.
- (47) Sannino, A.; Demitri, C.; Madaghiele, M. Biodegradable Cellulose-Based Hydrogels: Design and Applications. *Materials* **2009**, *2*, 353–373.
- (48) Hodder, E.; Duin, S.; Kilian, D.; Ahlfeld, T.; Seidel, J.; Nachtigall, C.; Bush, P.; Covill, D.; Gelinsky, M.; Lode, A. Investigating the Effect of Sterilisation Methods on the Physical Properties and Cytocompatibility of Methyl Cellulose Used in Combination with Alginate for 3D-Bioplotting of Chondrocytes. *J. Mater. Sci.: Mater. Med.* **2019**, *30*, 10.
- (49) Ode, A.; Duda, G. N.; Glaeser, J. D.; Matziolis, G.; Frauenschuh, S.; Perka, C.; Wilson, C. J.; Kasper, G. Toward Biomimetic Materials in Bone Regeneration: Functional Behavior of Mesenchymal Stem Cells on a Broad Spectrum of Extracellular Matrix Components. *J. Biomed. Mater. Res., Part A* **2010**, *95A*, 1114–1124.
- (50) Dejana, E.; Lampugnani, M. G.; Giorgi, M.; Gaboli, M.; Marchisio, P. C. Fibrinogen Induces Endothelial Cell Adhesion and Spreading via the Release of Endogenous Matrix Proteins and the Recruitment of More than One Integrin Receptor. *Blood* **1990**, *75*, 1509–1517.
- (51) Kang, H.-W.; Lee, S. J.; Ko, I. K.; Kengla, C.; Yoo, J. J.; Atala, A. A 3D Bioprinting System to Produce Human-Scale Tissue Constructs with Structural Integrity. *Nat. Biotechnol.* **2016**, *34*, nbt.3413.312.
- (52) Pourchet, L. J.; Thepot, A.; Albouy, M.; Courtial, E. J.; Boher, A.; Blum, L. J.; Marquette, C. A. Human Skin 3D Bioprinting Using Scaffold-Free Approach. *Adv. Healthcare Mater.* **2017**, *6*, 1601101.
- (53) Midha, S.; Dalela, M.; Sybil, D.; Patra, P.; Mohanty, S. Advances in Three-Dimensional Bioprinting of Bone: Progress and Challenges. *J. Tissue Eng. Regen. Med.* **2019**, *13*, 925–945.
- (54) Campos, D. F. D.; Blaaser, A.; Buellesbach, K.; Sen, K. S.; Xun, W.; Tillmann, W.; Fischer, H. Bioprinting Organotypic Hydrogels with Improved Mesenchymal Stem Cell Remodeling and Mineralization Properties for Bone Tissue Engineering. *Adv. Healthcare Mater.* **2016**, *5*, 1336–1345.
- (55) Wenz, A.; Borchers, K.; Tovar, G. E. M.; Kluger, P. J. Bone Matrix Production in Hydroxyapatite-Modified Hydrogels Suitable for Bone Bioprinting. *Biofabrication* **2017**, *9*, 044103.
- (56) Kim, W.; Kim, G. Collagen/Bioceramic-Based Composite Bioink to Fabricate a Porous 3D HASCs-Laden Structure for Bone Tissue Regeneration. *Biofabrication* **2020**, *12*, 015007.
- (57) Raja, N.; Yun, H. A Simultaneous 3D Printing Process for the Fabrication of Bioceramic and Cell-Laden Hydrogel Core/Shell Scaffolds with Potential Application in Bone Tissue Regeneration. *J. Mater. Chem. B* **2016**, *4*, 4707–4716.
- (58) Schuurman, W.; Khristov, V.; Pot, M. W.; van Weeren, P. R.; Dhert, W. J. A.; Malda, J. Bioprinting of Hybrid Tissue Constructs with Tailorable Mechanical Properties. *Biofabrication* **2011**, *3*, 021001.
- (59) Daly, A. C.; Cuniffe, G. M.; Sathy, B. N.; Jeon, O.; Alsborg, E.; Kelly, D. J. 3D Bioprinting of Developmentally Inspired Templates for Whole Bone Organ Engineering. *Adv. Healthcare Mater.* **2016**, *5*, 2353–2362.
- (60) Cuniffe, G. M.; Gonzalez-Fernandez, T.; Daly, A.; Sathy, B. N.; Jeon, O.; Alsborg, E.; Kelly, D. J. Three-Dimensional Bioprinting of Polycaprolactone Reinforced Gene Activated Bioinks for Bone Tissue Engineering. *Tissue Eng., Part A* **2017**, *23*, 891–900.
- (61) Piard, C.; Baker, H.; Kamalidinov, T.; Fisher, J. Bioprinted Osteon-like Scaffolds Enhance in Vivo Neovascularization. *Biofabrication* **2019**, *11*, 025013.
- (62) Akkineni, A. R.; Luo, Y.; Schumacher, M.; Nies, B.; Lode, A.; Gelinsky, M. 3D Plotting of Growth Factor Loaded Calcium Phosphate Cement Scaffolds. *Acta Biomater.* **2015**, *27*, 264–274.
- (63) Schumacher, M.; Lode, A.; Helth, A.; Gelinsky, M. A Novel Strontium(II)-Modified Calcium Phosphate Bone Cement Stimulates Human-Bone-Marrow-Derived Mesenchymal Stem Cell Proliferation and Osteogenic Differentiation in Vitro. *Acta Biomater.* **2013**, *9*, 9547–9557.
- (64) Hempel, U.; Reinstorf, A.; Poppe, M.; Fischer, U.; Gelinsky, M.; Pompe, W.; Wenzel, K. W. Proliferation and Differentiation of Osteoblasts on Biocement D Modified with Collagen Type I and Citric Acid. *J. Biomed. Mater. Res.* **2004**, *71B*, 130–143.
- (65) Song, Y.; Zhang, C.; Wang, P.; Wang, L.; Bao, C.; Weir, M. D.; Reynolds, M. A.; Ren, K.; Zhao, L.; Xu, H. H. K. Engineering Bone Regeneration with Novel Cell-Laden Hydrogel Microfiber-Injectable Calcium Phosphate Scaffold. *Mater. Sci. Eng., C* **2017**, *75*, 895–905.
- (66) Salenius, P. A Study of the Ph and Buffer Capacity of Blood, Plasma and Red Blood Cells. *Scand. J. Clin. Lab. Invest.* **1957**, *9*, 160–167.
- (67) Moore, H. B.; Moore, E. E.; Gonzalez, E.; Wiener, G.; Chapman, M. P.; Dzieciatkowska, M.; Savaia, A.; Banerjee, A.; Hansen, K. C.; Silliman, C. Plasma Is the Physiologic Buffer of Tissue Plasminogen Activator-Mediated Fibrinolysis: Rationale for Plasma-First Resuscitation after Life-Threatening Hemorrhage. *J. Am. Coll. Surg.* **2015**, *220*, 872–879.
- (68) Luo, Y.; Lode, A.; Sonntag, F.; Nies, B.; Gelinsky, M. Well-Ordered Biphasic Calcium Phosphate-Alginate Scaffolds Fabricated by Multi-Channel 3D Plotting under Mild Conditions. *J. Mater. Chem. B* **2013**, *1*, 4088–4098.
- (69) Ahlfeld, T.; Akkineni, A. R.; Förster, Y.; Köhler, T.; Knaack, S.; Gelinsky, M.; Lode, A. Design and Fabrication of Complex Scaffolds for Bone Defect Healing: Combined 3D Plotting of a Calcium Phosphate Cement and a Growth Factor-Loaded Hydrogel. *Ann. Biomed. Eng.* **2017**, *45*, 224–236.
- (70) Ahlfeld, T.; Schuster, F. P.; Förster, Y.; Quade, M.; Akkineni, A. R.; Rentsch, C.; Rammelt, S.; Gelinsky, M.; Lode, A. 3D Plotted Biphasic Bone Scaffolds for Growth Factor Delivery: Biological Characterization In Vitro and In Vivo. *Adv. Healthcare Mater.* **2019**, *8*, 1801512.
- (71) Mason, B. N.; Califano, J. P.; Reinhart-King, C. A. Matrix Stiffness: A Regulator of Cellular Behavior and Tissue Formation. In

Engineering Biomaterials for Regenerative Medicine; Springer, New York, NY, 2012; pp 19–37.

(72) Sobacchi, C.; Erreni, M.; Strina, D.; Palagano, E.; Villa, A.; Menale, C. 3D Bone Biomimetic Scaffolds for Basic and Translational Studies with Mesenchymal Stem Cells. *Int. J. Mol. Sci.* **2018**, *19*, 3150

(73) Lode, A.; Heiss, C.; Knapp, G.; Thomas, J.; Nies, B.; Gelinsky, M.; Schumacher, M. Strontium-Modified Premixed Calcium Phosphate Cements for the Therapy of Osteoporotic Bone Defects. *Acta Biomater.* **2018**, *65*, 475–485.

(74) Schindelin, J.; Arganda-Carreras, I.; Frise, E.; Kaynig, V.; Longair, M.; Pietzsch, T.; Preibisch, S.; Rueden, C.; Saalfeld, S.; Schmid, B.; Tinevez, J.-Y.; White, D. J.; Hartenstein, V.; Eliceiri, K.; Tomancak, P.; Cardona, A. Fiji: An Open-Source Platform for Biological-Image Analysis. *Nat. Methods* **2012**, *9*, 676–682.

(75) Bernhardt, A.; Wolf, S.; Weiser, E.; Vater, C.; Gelinsky, M. An Improved Method to Isolate Primary Human Osteocytes from Bone. *Biomed. Tech.* **2020**, *65*, 107–111.

(76) Neunzehn, J.; Weber, M.-T.; Wittenburg, G.; Lauer, G.; Hannig, C.; Wiesmann, H.-P. Dentin-like Tissue Formation and Biomineralization by Multicellular Human Pulp Cell Spheres in Vitro. *Head Face Med.* **2014**, *10*, 25.

Part III

CONCLUSIO

SUMMARY & CONCLUSION

7.1 BIOPRINTING OF BONE TISSUE CONSTRUCTS

Additive manufacturing of bone grafts is one of the most studied subjects in the field. Many cell-free approaches were investigated such as powder printing of CaP powders (Berger et al., 2015), stereolithography of CaP slurries (Wei et al., 2020) or fused deposition modeling of CaP particle-laden thermoplastics (Zhang et al., 2017). These technologies have in common, that the fabrication procedure involves usually sintering steps at temperatures above 900 °C or, in case of fused deposition modeling, a high temperature during fabrication. This circumstance prohibits the processing of biological substances such as proteins or cells. In case of powder printing, self-setting cement precursors can be processed and thus at least proteins can be incorporated into the printing process for some biomaterials. (Meininger et al., 2017)

The research conducted for bioprinting of cell-laden bone constructs can be categorized into three main concepts. First, bioprinted cells can be stimulated *in vitro*, allowing them to differentiate into osteoblasts which mineralize their surrounding artificial extracellular matrix. (Campos et al., 2016) Second, there is the strategy of direct supplementation of bioinks and biomaterial inks with bioactive substances to enhance the osteogenic property of the additively manufactured construct. A good overview about these composites was published by Milazzo *et al.* (Milazzo et al., 2019) It could be demonstrated that bioprinted cells in these composite constructs are able to differentiate towards the osteogenic lineage and induce mineralization. (Wenz et al., 2017; Kim & Kim, 2020) Third, multichannel printing of stiff materials in combination with softer bioinks was successfully applied for bone bioprinting as well. (Daly et al., 2016)

The approaches investigated in this thesis follow the approaches of the second (chapter 4) and the third strategy (chapters 5 & 6).

Laponite, a nanoclay which was shown before to induce bone formation (Wang et al., 2014), is a bioactive material which contributed positively to the cell viability (chapter 4). The advantage of this approach is the simple setup: Both, fabrication and post-processing can be performed easily and the technological requirements are rather simple. The simplicity of this approach might be crucial for translational aspects of this research. Although the study presented here, as well as similar approaches presented in literature (Wenz et al., 2017; Kim & Kim, 2020), concordantly report, that the mechanical stiffness increases thanks to the bioactive filler materials, the overall construct stiffness must be considered as too low for mimicking bone tissue. On the contrary it can be questioned whether a bioprinted implant must meet the same mechanical characteristics such as the target tissue since surgeons may take use of load-bearing osteosynthesis plates in combination with the implant, as demonstrated for a rat femur defect (Ahlfeld et al., 2019).

The chapters 5 & 6 of this thesis show the development of bone scaffolds based on multichannel plotting of CPC and a bioink. The strategy of multichannel extrusion printing (including not just 3D plotting, but also fused deposition modeling of thermoplastics as reinforcing shape-defining material) to fabricate multiphasic tissue engineered constructs was described for the first time in 2011 by SCHUURMAN *et al.* (Schuurman et al., 2011). Later, especially poly- ϵ -caprolactone (PCL) was used to print a grid-like structure, and subsequently the achieved macropores were robotically filled up with a soft bioink. (Stichler et al., 2017a; Daly et al., 2016). Also poloxamer hydrogels were designed for this purpose. (Melchels et al., 2016). Whereas for some of the obtained constructs without macropores synergistic effects between the reinforcing material and the bioink on mechanical behavior were reported, the macroporous constructs consisting of CPC and the bioink investigated here demonstrated no relevant mechanical enhancements compared to pure CPC scaffolds. The mechanical properties which were reported for PCL-based biphasic constructs usually are in the range of cartilage, but not in the range for bone. In case of the biphasic CPC constructs developed in this thesis, the mechanical properties were in the lower region of trabecular bone (Misch et al., 1999), and particularly higher compared to the Laponite-based constructs. In comparison to plotting of a bioink with an embedded bioactive filler material, the technological requirements and especially the post-processing of multichannel plotted constructs are rather ambitious, which is a clear limitation with regards to translation of this approach into clinical environments. However, since the plottability of CPC is better in comparison to the hydrogel-based bioinks, it is easier to fabricate constructs of high shape fidelity fitting to the defect-specific geometry (chapters 3 & 6).

At the interface of CPC and the alginate-methylcellulose bioink, a drop of cell viability was observed at early timepoints. A similar behavior was reported for thermoplastics. (Kim et al., 2016). However, since the melting temperature of PCL is around 60 °C, a printed strand cools down rather fast and a combination with bioprinting should be possible without big losses of cell viability. Interestingly, it was observed in both papers (chapters 5 & 6), that the bioprinted cells started to migrate from the bioink to the CPC strands. There they attached to the HAP matrix and proliferated. In case of the plasma-based bioink, the proliferation was enormous (up to 20-fold of the initial cell number). This might reveal a big advantage of biphasic CPC/bioink constructs: Commonly cell-free printed constructs are seeded afterwards with cells prior to implantation or *in situ* at the defect region obtaining a tissue engineered construct. Problematically the cell density strongly decreases from the borders to the center region of such a scaffold. The bioprinted approach investigated here could not just be seen as a way to functionalization, but also as an advanced cell delivery system which should be superior to commonly fabricated cell-free approaches.

7.2 TECHNOLOGICAL IMPROVEMENTS

An important functionality of a resorbable implant is its fitting into the patient-specific defect. In general, all additive manufacturing techniques have in common, that geometries can be achieved which are not feasible with other (top-down) approaches, like the molding of a

hydrogel, which does not allow control over inner geometries like cavities, but only about outer shape and dimensions. In contrast, additive manufacturing in medicine is used mainly to fabricate scaffolds/implants, which offer patient-specific shapes. This is considered as advantageous for the filling of the defect, the surgical procedure as well as the healing process after a patient's injury. Some additive manufacturing techniques like *Powder Printing* or *Selective Laser Sintering (SLS)* are already established in the clinical routine. This might be related to two reasons: (i) Both techniques allow the processing of materials which are able to withstand high loads, for example titanium splints for maxillofacial surgeries get produced by SLS. (ii) Both fabrication processes involve a powder bed which stabilizes the printed structures during the manufacturing process. This allows the fabrication of highly complex - and anatomically relevant - structures.

In contrast, the intrinsic property of three-dimensional plotting is the processing of materials, which have to be hardened (post-processing) after fabrication. A disadvantage of this fabrication method is, that several shapes like convex or concave formed surfaces, which are revealed by almost all anatomical features within the human body, cannot be processed as the plotted material would collapse in air. In chapter 3, a possible solution is shown to overcome that limitation. Multichannel plotting was used to fabricate structures, which in a usual plotting process (with only a single material involved) could not be fabricated. Next to the main structure, a support structure was plotted, which could be sacrificed after post-processing of the main structure. For this multichannel plotting approach, the spatial arrangement of main and support structure must have been defined according to anatomical features; exemplary a scaphoid bone was plotted with a support structure. This was achieved by transforming CT data into a CAD file, which could be applied to the multichannel plotter. These CAD data could be used to design a support structure on its surface. The file format *3mf* allows a translation of multiple materials within a CAD file to different channels of the multichannel plotter. By usage of the whole CAD/CAM-driven process from clinical CT data to a 3D plotted scaphoid bone, the technological gap was closed and for the first time a bioresorbable, patient-individual HAp implant could be fabricated by 3D plotting (chapter 3).

Other methods for the fabrication of convex or concave surfaces with bioplotting involve a support bath consisting of materials convenient for the scaffold ink. For example agarose (Mirdamadi et al., 2019), highly concentrated Laponite (Jin et al., 2017b) or gelatin (Lee et al., 2019) were successfully utilized for plotting applications. This printing method was shown to be feasible for the processing of several inks, but also has several disadvantages: there is a strong limitation of the materials in the printing process, as the support bath material must be removed without destroying the scaffold structure. This might be problematic as most support bath materials are also common scaffold materials and thus both, bath and plotted ink, comprise similar physicochemical properties. For example, gelatin-based bioinks could not easily be fabricated with agarose, as they would disintegrate during the agarose removing step. Crucially for CPC plotting, distinct aqueous environments (water content >50 %) would immediately start the setting reaction, not just in the extruded portion, but also in the plotting nozzle. This would lead to a setting of the cement at the tip, followed by needle clogging and interruption of the plotting process. Thus, a hydrophilic support bath would not be applicable for the fabrication of CPC scaffolds. To overcome that hurdle, Miranda et

a/ demonstrated that tricalcium phosphate-based scaffolds can be fabricated by plotting slurries into an oil-based bath. (Miranda et al., 2006) In the light of bioprinting, where cells are involved in the fabrication process, this hydrophobic and cell-inconvenient environment would probably lead to cell death, and is no alternative for multiphasic CPC/bioink constructs which have better osteoinductive properties. Thus, the concept of direct plotting of the support structure, which was developed in this thesis, is the only feasible technology for the biofabrication of multichannel plotted cell-laden CPC/bioink constructs, as demonstrated in chapter 6.

Cell-laden bioinks could be plotted in combination with the calcium phosphate cement (chapters 5 & 6). This was not achieved before. As described in chapter 5, the requirements for the optimal post-processing of CPC and bioinks are rather conflicting. Due to this reason the post-processings of CPC and an alginate-methylcellulose bioink were compared with respect to microcrack formation within CPC strands and cell viability within alginate-methylcellulose strands. A post-processing window could be defined which allows optimal setting of CPC strands without impairing cell viability within a bioink. This window involves 20 min incubation in water-saturated atmosphere subsequently followed by immersion into aqueous solution which in case of alginate-based bioinks was a CaCl_2 crosslinking solution. This novel concept could in general be transferred to any bioink which is plotted in combination with CPC.

7.3 BIOINK DEVELOPMENT

The development of bioinks is an essential challenge for bioprinting approaches. Following the Biofabrication window (chapter 1.6.5), many groups developed tools to enable the fabrication of bioinks which are compatible with the viability and function of encapsulated cells. For example, support-bath solutions have been developed like Freeform Reversible Embedding of Suspended Hydrogels (FRESH) bioprinting or Suspended Layer Additive Manufacturing (SLAM). (Lee et al., 2019; Senior et al., 2019) In both cases, low viscosity bioinks could be utilized which would not have been possible without the support structure. Although these methods are very smart, usage of multiple bioinks cannot be obtained without enormous effort, the combination with reinforcing biomaterial inks like CPC or poly- ϵ -caprolactone is impossible/has not been shown until today, growth factors would probably diffuse into the support bath and layer delamination is a huge problem. Due to this reason, most groups try to develop bioinks which can be fabricated using air as plotting medium. For UV crosslinkable materials, a technical solution was developed, allowing optimal precrosslinking of low viscosity inks during the plotting procedure. (Ouyang et al., 2017) However, this approach is highly sensitive to light and might only be applicable to more or less transparent bioinks which do not contain particles such as calcium phosphates. Therefore bioinks with convenient rheological behaviors such as enhanced viscosity and fast shear recovery and thus good shape fidelity after extrusion in air still can be seen as the most convenient approaches since they address the highest variety of applications and are not limited by the technology needed to process them.

Based on alginate-methylcellulose, a bioink developed before, (Schütz et al., 2017) two new bioinks were designed in the course of this thesis. The first bioink contained the nanoclay Laponite (chapter 4). Due to its high polarity, it interacted with alginate in the blend (Dávila & d'Ávila, 2019) and thus refined the rheological profile of the blend providing a better shear recovery of the ink after extrusion. Unlike for the Laponite-free alginate-methylcellulose blend, this prevented a strong fusion of strands in z-direction. Due to this reason, horizontal macropores between the plotted layers could be achieved, which is a sign for high shape fidelity. The methylcellulose, acting as rheological modifier, could be partly replaced by Laponite without loss of plottability of the bioink. This is advantageous, since the methylcellulose has no function in the ink after plotting, whereas the Laponite particles bind and release biologically active molecules, for example VEGF (chapter 4). The final solid content (9%) was lower than in the alginate-methylcellulose blend (12%). The reason for that remains speculative, but it might be an effect of further interactions of Laponite and the macromolecular chains of methylcellulose. Whereas alginate and methylcellulose do not interact with each other forming a semi-interpenetrated network, (Chimene et al., 2019; Ahlfeld et al., 2020), the Laponite nanodiscs might have the tendency to fix the macromolecules of both, alginate and methylcellulose, due to polar interactions. Thus the reason for the rheological refinement by the nanodiscs can be considered as drastically different from the effects evoked by methylcellulose, which were reviewed recently (Ahlfeld et al., 2020). Remarkably, a new study by Adib *et al.* confirms the findings presented in chapter 4, as they described similar effects for a bioink consisting of methacrylated gelatin, Laponite and methylcellulose. (Adib et al., 2020)

To the best knowledge of the author, Laponite has been used for cell-free printing applications at the same time (Jin et al., 2017a), but the publication shown as chapter 4 should be the first study demonstrating cellular behavior of bioprinted cells in a Laponite-containing bioink. Afterwards, many groups started using Laponite as rheological filler in a bioink. (Afewerki et al., 2019) The cell viability in the novel bioink was higher than in the Laponite-free bioink, furthermore the number of cells did not decrease over time. Additionally, model proteins could be loaded to the bioink prior to fabrication. They were released in a sustained manner and did not lose their biological activity over time. For bioprinting of bone tissue equivalents this might be a crucial step forward, since the bone formation process is actively promoted by Laponite (Shi et al., 2018), bioprinted cells in Laponite-alginate-methylcellulose promote bone formation and angiogenesis (Cidonio et al., 2020) and the release of biologically active growth factors occurs not just at early, but also at later time points, which is basically considered as beneficial due to the healing procedure of bone. (Lienemann et al., 2012; De Witte et al., 2018)

The second bioink was a plasma-modified variant of alginate-methylcellulose (chapter 6). Fresh frozen plasma is a product after centrifugation of full blood and contains a donor-specific variety of proteins and growth factors which can be termed as proteome. (Schwenk et al., 2017) This broadens the concept of patient-specific bioprinting: Next to the defect-adapted shape, which can be fabricated, and the cells which are donated by the patient her-/himself, also the bioink is specifically tailored to the patient's needs. The growth factor cocktail within the plasma, and hence also in the bioink, should allow mutual stimulation of

the various proteins. Furthermore, a main component of plasma is fibrinogen, which holds an RGD-motif enabling mesenchymal stem cells and pre-osteoblastic cells to attach and spread within the matrix which should be beneficial for osteoblastic maturation. (Ode et al., 2010) The plasma-alginate-methylcellulose bioink combined the high cytocompatibility of plasma with the good plottability of the alginate-methylcellulose blend. Platelet-rich plasma, another product obtained after centrifugation of full blood, was already used in bioprinting. (Faramarzi et al., 2018; Mendes et al., 2020) Both bioinks needed a technical support (CaCl₂ spraying or a support bath) with the drawbacks (like layer delamination) mentioned before. Further, fresh frozen plasma was used to bioprint functional human skin without the ambition to achieve high shape fidelity rather than a hierarchical assembly. (Cubo Mateo et al., 2016) Thus, the plasma-alginate-methylcellulose bioink which can be plotted in air, is an advanced bioink addressing a wide range of applications, for example multichannel plotting with CPC, which was also investigated in chapter 6.

7.4 LIMITATIONS & FUTURE RESEARCH DIRECTIONS

Bioprinting belongs to the field of personalized medicine. Concepts as described in chapter 6 are novel and thus still not certified for use in patients. The translation of bioprinted constructs into the clinics is rather complicated: Even though some printable biomaterials are certified for clinical use, it is not automatically given that their fabricated form is allowed as clinical product as well. For example, the CPC used here is clinically approved and can be applied as injectable paste. However, once it is plotted into any shape, it is seen as a new product which is not certified at this time point. Since every defect-adapted geometry would create a new fabrication procedure, every fabrication process would be needed to be certified again. Further, using cells which are derived from patients change the quality, properties and biological performance of a bioprinted construct, which must be considered and thus, again, impairs a fast translation into the clinics. The same applies to biomaterials which are derived from patients, for example the blood plasma. Although it is commonly accepted that personalized medicine might be a useful option for new therapies, patient-specific, bioprinted constructs must always be treated as new medical products and until now there are no tools to assess their quality and biological properties. Regarding the safety of patients and surgeons, these tools must be developed and ethically evaluated before a successful translation can be conducted.

This goes along with a consistent evaluation of the long-time behavior of the constructs *in vitro* and *in vivo*. Plotted CPC constructs were investigated thoroughly and, like many scaffolds consisting of HAp, have demonstrated rather long stability without significant degradation (Moussa et al., 2015; Reitmaier et al., 2018; Baranowski et al., 2018; Korn et al., 2020) For the biopolymers alginate and methylcellulose the degradation behavior *in vivo* is less understood. It is accepted, that the human body lacks producing cleaving enzymes for these biopolymers such as alginases and cellulases. (Sannino et al., 2009) Degradation of the constructs might occur due to release of calcium ions and subsequent swelling and dilution of the macromolecules in body fluids like blood. Methylcellulose can be

mechanically disrupted, dissolved and metabolized by macrophages. However, although these interactions are conceivable, other reactions cannot be excluded since long time *in vivo* studies are missing. It should be mentioned, that some groups have created concepts to oxidize polysaccharides in order to make them cleavable by human enzymes, also some bioprinted approaches were already described.(Zehnder et al., 2015; Lee et al., 2020b)

One of the major challenges in bone tissue engineering is the vascularization of the bone graft. It provides nutrients and oxygen to the cells. Although some subtle signs of vascularization could be achieved before by a gradient-like distribution of VEGF-laden biomaterial inks (Ahlfeld et al., 2017; Ahlfeld et al., 2019) and a concept for direct printing of a perfusable blood vessel was introduced in chapter 6, the problem still cannot be considered to be solved at this stage of research. Bioprinting offers several tools enabling vascularization of tissue engineered constructs. For example, fugitive inks were printed and surrounded by cell-laden hydrogels; after post-processing the inks were removed and perfused.(Kolesky et al., 2016) A similar approach was shown to be successful with an endothelial cell-laden gelatine bioink.(Ouyang et al., 2020) The combination of spatiotemporal growth factor delivery investigated earlier (Ahlfeld et al., 2017; Bittner et al., 2018) in combination with some of these approaches might be a worthwhile investigation in the future. Especially the gradient-like distribution of growth factor-laden inks, but also the tailorability of the protein release by Laponite could be advantageous for further developments. In addition, direct bioprinting of vessel-like structures will be of high interest in the future.

Thanks to the significant progress made in the field, there are now multiple techniques, biomaterial inks and bioinks, which can be processed, studied and used for further research. New approaches will investigate whether (bioprinted) cells are able to respond to a biofabricated structure, which until now has been demonstrated only rarely.(Levato et al., 2020) Further, it crystallizes out that not only one printing technique and one material for a single biofabricated construct might be suitable, but that the combination of several technologies can be advantageous.(Castilho et al., 2020; Dalton et al., 2020) This thesis contributed insights into multimaterial, bioprinted constructs for bone tissue engineering and should motivate other researchers to follow this path in order to advance the field of biofabrication for tissue engineering and regenerative medicine.

BIBLIOGRAPHY

- ASTM. 2004. Test Method for Time of Setting of Hydraulic-Cement Paste by Gillmore Needles. ASTM International. ASTM Designation: C266-04.
- Adib AA, Sheikhi A, Shahhosseini M, Simeunović A, Wu S, Castro CE, Zhao R, Khademhosseini A, Hoelzle DJ. 2020. Direct-write 3D printing and characterization of a GelMA-based biomaterial for intracorporeal tissue engineering. *Biofabrication*. [Epub ahead of print] DOI:10.1088/1758-5090/ab97a1.
- Afewerki S, Magalhães LSSM, Silva ADR, Stocco TD, Filho ECS, Marciano FR, Lobo AO. 2019. Bioprinting a Synthetic Smectic Clay for Orthopedic Applications. *Adv Healthc Mater* 8:1900158.
- Ahlfeld T, Guduric V, Duin S, Akkineni AR, Schütz K, Kilian D, Emmermacher J, Cubo-Mateo N, Dani S, Witzleben Mv, Spangenberg J, Abdelgaber R, Richter RF, Lode A, Gelinsky M. 2020. Methylcellulose – a versatile printing material that enables biofabrication of tissue equivalents with high shape fidelity. *Biomater Sci* 8:2102–2110.
- Ahlfeld T, Akkineni AR, Förster Y, Köhler T, Knaack S, Gelinsky M, Lode A. 2017. Design and Fabrication of Complex Scaffolds for Bone Defect Healing: Combined 3D Plotting of a Calcium Phosphate Cement and a Growth Factor-Loaded Hydrogel. *Ann Biomed Eng* 45:224–236.
- Ahlfeld T, Schuster FP, Förster Y, Quade M, Akkineni AR, Rentsch C, Rammelt S, Gelinsky M, Lode A. 2019. 3D Plotted Biphasic Bone Scaffolds for Growth Factor Delivery: Biological Characterization In Vitro and In Vivo. *Adv Healthc Mater* 8:1801512.
- Akkineni AR, Luo Y, Schumacher M, Nies B, Lode A, Gelinsky M. 2015. 3D plotting of growth factor loaded calcium phosphate cement scaffolds. *Acta Biomater* 27:264–274.
- Baranowski A, Klein A, Ritz U, Götz H, Mattyasovszky SG, Rommens PM, Hofmann A. 2018. Evaluation of Bone Sialoprotein Coating of Three-Dimensional Printed Calcium Phosphate Scaffolds in a Calvarial Defect Model in Mice. *Materials* 11:2336.
- Barba A, Diez-Escudero A, Maazouz Y, Rappe K, Espanol M, Montufar EB, Bonany M, Sadowska JM, Guillem-Marti J, Mägi C Öhman, Persson C, Manzanares MC, Franch J, Ginebra MP. 2017. Osteoinduction by Foamed and 3D-Printed Calcium Phosphate Scaffolds: Effect of Nanostructure and Pore Architecture. *ACS Appl Mater Interfac* 9:41722–41736.
- Becher TB, Braga CB, Bertuzzi DL, Ramos MD, Hassan A, Crespilho FN, Ornelas C. 2019. The structure–property relationship in LAPONITE® materials: from Wigner glasses to strong self-healing hydrogels formed by non-covalent interactions. *Soft Matter* 15:1278–1289.

- Berger M, Probst F, Schwartz C, Cornelsen M, Seitz H, Ehrenfeld M, Otto S. 2015. A concept for scaffold-based tissue engineering in alveolar cleft osteoplasty. *J Craniomaxillofac Surg* 43:830–836.
- Bernal PN, Delrot P, Loterie D, Li Y, Malda J, Moser C, Levato R. 2019. Volumetric Bioprinting of Complex Living-Tissue Constructs within Seconds. *Adv Mater* 31:1904209.
- Bernhardt A, Schumacher M, Gelinsky M. 2014. Formation of Osteoclasts on Calcium Phosphate Bone Cements and Polystyrene Depends on Monocyte Isolation Conditions. *Tissue Eng C Met* 21:160–170.
- Bittner SM, Guo JL, Mikos AG. 2018. Spatiotemporal control of growth factors in three-dimensional printed scaffolds. *Bioprinting* 12:e00032.
- Blaeser A, Duarte Campos DF, Puster U, Richtering W, Stevens MM, Fischer H. 2016. Controlling Shear Stress in 3D Bioprinting is a Key Factor to Balance Printing Resolution and Stem Cell Integrity. *Adv Healthc Mater* 5:326–333.
- Bohner M, Baroud G. 2005. Injectability of calcium phosphate pastes. *Biomaterials* 26:1553–1563.
- Britannica E. 2012. Cancellous bone (anatomy). *Encyclopedia Britannica*. Updated 2012 Accessed 22-01-2020.
- Campos DFD, Blaeser A, Buellesbach K, Sen KS, Xun W, Tillmann W, Fischer H. 2016. Bioprinting Organotypic Hydrogels with Improved Mesenchymal Stem Cell Remodeling and Mineralization Properties for Bone Tissue Engineering. *Adv Healthc Mater* 5:1336–1345.
- Castilho M, Ruijter M de, Beirne S, Villette CC, Ito K, Wallace GG, Malda J. 2020. Multitechnology Biofabrication: A New Approach for the Manufacturing of Functional Tissue Structures? *Trends in Biotechnology*. [Epub ahead of print] DOI: 10.1016/j.tibtech.2020.04.014.
- Chimene D, Kaunas R, Gaharwar AK. 2019. Hydrogel Bioink Reinforcement for Additive Manufacturing: A Focused Review of Emerging Strategies. *Adv Mater* 32:1902026.
- Chow L. 2001. Solubility of Calcium Phosphates. *Monographs in Oral Science*. Ed. by L Chow, E Eanes. Vol. 18. Basel: KARGER:94–111.
- Cidonio G, Glinka M, Kim YH, Kanczler J, Lanham SA, Ahlfeld T, Lode A, Dawson JI, Gelinsky M, Oreffo R. 2020. Nanoclay-based 3D printed scaffolds promote vascular ingrowth ex vivo and generate bone mineral tissue in vitro and in vivo. *Biofabrication* 12:035010.
- Colosi C, Shin SR, Manoharan V, Massa S, Costantini M, Barbetta A, Dokmeci MR, Dentini M, Khademhosseini A. 2016. Microfluidic Bioprinting of Heterogeneous 3D Tissue Constructs Using Low-Viscosity Bioink. *Adv Mater* 28:677–684.
- Cubo Mateo N, Garcia M, Cañizo J F del, Velasco D, Jorcano J. 2016. 3D bioprinting of functional human skin: Production and in vivo analysis. *Biofabrication* 9:015006.

- Curvello R, Raghuwanshi VS, Garnier G. 2019. Engineering nanocellulose hydrogels for biomedical applications. *Adv Coll Interf Sci* 267:47–61.
- Dalton PD, Woodfield TBF, Mironov V, Groll J. 2020. Advances in Hybrid Fabrication toward Hierarchical Tissue Constructs. *Adv Sci* 7:1902953.
- Daly AC, Cuniffe GM, Sathy BN, Jeon O, Alsberg E, Kelly DJ. 2016. 3D Bioprinting of Developmentally Inspired Templates for Whole Bone Organ Engineering. *Adv Healthc Mater* 5:2353–2362.
- Dawson JI, Oreffo ROC. 2013. Clay: New Opportunities for Tissue Regeneration and Bio-material Design. *Adv Mater* 25:4069–4086.
- De Witte TM, Fratila-Apachitei LE, Zadpoor AA, Peppas NA. 2018. Bone tissue engineering via growth factor delivery: from scaffolds to complex matrices. *Regen Biomater* 5:197–211.
- Demir Oğuz z, Ege D. 2018. Rheological and Mechanical Properties of Thermoresponsive Methylcellulose/Calcium Phosphate-Based Injectable Bone Substitutes. *Materials* 11:604.
- Demirci U, Montesano G. 2007. Single cell epitaxy by acoustic picolitre droplets. *Lab on a Chip* 7:1139–1145.
- Despang F, Börner A, Dittrich R, Tomandl G, Pompe W, Gelinsky M. 2005. Alginate/calcium phosphate scaffolds with oriented, tube-like pores. *Materialwissenschaft Werkstofftech* 36:761–767.
- Detsch R, Hagmeyer D, Neumann M, Schaefer S, Vortkamp A, Wuelling M, Ziegler G, Epple M. 2010. The resorption of nanocrystalline calcium phosphates by osteoclast-like cells. *Acta Biomater* 6:3223–3233.
- Detsch R, Blob S, Zehnder T, Boccaccini AR. 2016. Evaluation of cell inkjet printing technique for biofabrication. *BioNanoMaterials* 17:185–191.
- Diloksumpan P, Ruijter Md, Castilho M, Gbureck U, Vermonden T, Weeren PRv, Malda J, Levato R. 2020. Combining multi-scale 3D printing technologies to engineer reinforced hydrogel-ceramic interfaces. *Biofabrication* 12:025014.
- Ding X, Gao J, Wang Z, Awada H, Wang Y. 2016. A shear-thinning hydrogel that extends in vivo bioactivity of FGF2. *Biomaterials* 111:80–89.
- Dobos A, Hoorick JV, Steiger W, Gruber P, Markovic M, Andriotis OG, Rohatschek A, Dubruel P, Thurner PJ, Vlierberghe SV, Baudis S, Ovsianikov A. 2019. Thiol–Gelatin–Norbornene Bioink for Laser-Based High-Definition Bioprinting. *Adv Healthc Mater*:1900752.
- Dorozhkin SV. 2007. Calcium orthophosphates. *J Mater Sci* 42:1061–1095.
- Dorozhkin SV. 2011. Self-Setting Calcium Orthophosphate Formulations: Cements, Concretes, Pastes and Putties. *Int J Mat Chem* 1:1–48.

- Dorozhkin SV. 2015. Calcium orthophosphates (CaPO₄): occurrence and properties. *Prog Biomater* 5:9–70.
- Driessens FCM, Khairoun I, Boltong MG, Planell JA. 1997. Design of a calcium phosphate bone cement suitable for the fixation of metal endoprotheses. *Bioceramics* 10:279–281.
- Duin S, Schütz K, Ahlfeld T, Lehmann S, Lode A, Ludwig B, Gelinsky M. 2019. 3D Bioprinting of Functional Islets of Langerhans in an Alginate/Methylcellulose Hydrogel Blend. *Adv Healthc Mater* 8:1801631.
- Dávila JL, d'Ávila MA. 2019. Rheological evaluation of Laponite/alginate inks for 3D extrusion-based printing. *Int J Adv Manuf Technol* 101:675–686.
- Dzian A, Živčák J, Penciak R, Hudák R. 2018. Implantation of a 3D-printed titanium sternum in a patient with a sternal tumor. *World J Surg Oncol* 16:7.
- Emmermacher J, Spura D, Cziommer J, Kilian D, Wollborn T, Fritsching U, Steingroewer J, Walther T, Gelinsky M, Lode A. 2020. Engineering considerations on extrusion-based bioprinting: interactions of material behavior, mechanical forces and cells in the printing needle. *Biofabrication* 12:025022.
- Faramarzi N, Yazdi IK, Nabavinia M, Gemma A, Fanelli A, Caizzzone A, Ptaszek LM, Sinha I, Khademhosseini A, Ruskin JN, Tamayol A. 2018. Patient-Specific Bioinks for 3D Bioprinting of Tissue Engineering Scaffolds. *Adv Healthc Mater* 7:1701347.
- Fedorovich NE, De Wijn JR, Verbout AJ, Alblas J, Dhert WJ. 2008. Three-Dimensional Fiber Deposition of Cell-Laden, Viable, Patterned Constructs for Bone Tissue Printing. *Tissue Eng A* 14:127–133.
- Florencio-Silva R, Sasso GRdS, Sasso-Cerri E, Simões MJ, Cerri PS. 2015. Biology of Bone Tissue: Structure, Function, and Factors That Influence Bone Cells. *BioMed Res Int* 2015:1–17.
- Foundation IO. 2017a. *BROKEN BONES, BROKEN LIVES: A roadmap to solve the fragility fracture crisis in Europe*.
- Foundation IO. 2017b. *RUINIERT KNOCHEN, RUINIERTES LEBEN: Ein strategischer Plan zur Lösung der Fragilitätsfrakturkrise in Deutschland*.
- Frank-Kamenetskaya OV. 2008. Structure, Chemistry and Synthesis of Carbonate Apatites — The Main Components of Dental and Bone Tissues. In: Krivovichev SV (Eds) *Minerals as Advanced Materials I*. Springer Berlin Heidelberg, Berlin, Heidelberg, pp. 241–252.
- Gaharwar AK, Kishore V, Rivera C, Bullock W, Wu CJ, Akkus O, Schmidt G. 2012. Physically Crosslinked Nanocomposites from Silicate-Crosslinked PEO: Mechanical Properties and Osteogenic Differentiation of Human Mesenchymal Stem Cells. *Macromol Biosci* 12:779–793.
- Gan HY, Lam YC. 2013. Viscoelasticity. In: Li, Dongqing (Ed.) *Encyclopedia of Microfluidics and Nanofluidics*. Springer, pp. 1-12.

- Gao Q, Niu X, Shao L, Zhou L, Lin Z, Sun A, Fu J, Chen Z, Hu J, Liu Y, He Y. 2019. 3D printing of complex GelMA-based scaffolds with nanoclay. *Biofabrication* 11:035006.
- García-Gareta E, Coathup MJ, Blunn GW. 2015. Osteoinduction of bone grafting materials for bone repair and regeneration. *Bone* 81:112–121.
- Garimella R, Tague SE, Zhang J, Belibi F, Nahar N, Sun BH, Insogna K, Wang J, Anderson HC. 2008. Expression and Synthesis of Bone Morphogenetic Proteins by Osteoclasts: A Possible Path to Anabolic Bone Remodeling. *J Histochem Cytochem* 56:569–577.
- Gelinsky M. 2018. 6 - Biopolymer hydrogel bioinks. In: Thomas DJ, Jessop ZM, Whitaker IS (Eds) *3D Bioprinting for Reconstructive Surgery*. Woodhead Publishing, pp. 125–136.
- Ginebra MP, Canal C, Espanol M, Pastorino D, Montufar EB. 2012. Calcium phosphate cements as drug delivery materials. *Adv Drug Deliv Rev* 64:1090–1110.
- Gopinathan J, Noh I. 2018. Click Chemistry-Based Injectable Hydrogels and Bioprinting Inks for Tissue Engineering Applications. *Tissue Eng Regen Med* 15:531–546.
- Goto T, Katsui H. 2015. Chemical Vapor Deposition of Ca–P–O Film Coating. In: Sasaki K, Suzuki O, Takahashi N (Eds) *Interface Oral Health Science 2014*. Springer Japan, Tokyo, pp. 103–115.
- Groll J, Boland T, Blunk T, Burdick JA, Cho DW, Dalton PD, Derby B, Forgacs G, Li Q, Mironov VA, Moroni L, Nakamura M, Shu W, Takeuchi S, Vozzi G, Woodfield TBF, Xu T, Yoo JJ, Malda J. 2016. Biofabrication: reappraising the definition of an evolving field. *Biofabrication* 8:013001.
- Groll J, Burdick JA, Cho DW, Derby B, Gelinsky M, Heilshorn SC, Juengst T, Malda J, Mironov VA, Nakayama K, Ovsianikov A, Sun W, Takeuchi S, Yoo JJ, Woodfield TBF. 2018. A definition of bioinks and their distinction from biomaterial inks. *Biofabrication* 11:013001.
- Gudapati H, Dey M, Ozbolat I. 2016. A comprehensive review on droplet-based bioprinting: Past, present and future. *Biomaterials* 102:20–42.
- Guo H, Su J, Wei J, Kong H, Liu C. 2009. Biocompatibility and osteogenicity of degradable Ca-deficient hydroxyapatite scaffolds from calcium phosphate cement for bone tissue engineering. *Acta Biomater* 5:268–278.
- Heinemann S, Rössler S, Lemm M, Ruhnnow M, Nies B. 2013. Properties of injectable ready-to-use calcium phosphate cement based on water-immiscible liquid. *Acta Biomater* 9:6199–6207.
- Hing KA. 2004. Bone repair in the twenty-first century: biology, chemistry or engineering? In: Thompson JMT (Eds) *Philosophical Transactions of the Royal Society of London Series A: Mathematical, Physical and Engineering Sciences*, pp. 2821–2850.
- Hutmacher DW. 2000. Scaffolds in tissue engineering bone and cartilage. *Biomaterials* 21:2529–2543.
- Ishikawa K, Eanes ED. 1993. The Hydrolysis of Anhydrous Dicalcium Phosphate into Hydroxyapatite: *J Dent Res* 72:474–480.

- Jain D, Bar-Shalom D. 2014. Alginate drug delivery systems: application in context of pharmaceutical and biomedical research. *Drug Dev Ind Pharm* 40:1576–1584.
- Jerosch J, Bader A, Uhr G. 2002. Knochen: curasan Taschenatlas spezial. Stuttgart, Thieme.
- Jin Y, Compaan A, Chai W, Huang Y. 2017a. Functional Nanoclay Suspension for Printing-Then-Solidification of Liquid Materials. *ACS Appl Mater Interf* 9:20057–20066.
- Jin Y, Liu C, Chai W, Compaan A, Huang Y. 2017b. Self-Supporting Nanoclay as Internal Scaffold Material for Direct Printing of Soft Hydrogel Composite Structures in Air. *ACS Appl Mater Interf* 9:17456–17465.
- Jong SJ de, Eerdenbrugh B van, Nostrum CF van, Bosch JJ Kettenes-van den, Hennink WE. 2001. Physically crosslinked dextran hydrogels by stereocomplex formation of lactic acid oligomers: degradation and protein release behavior. *J Control Rel* 71:261–275.
- Kashirina A, Yao Y, Liu Y, Leng J. 2019. Biopolymers as bone substitutes: a review. *Biomater Sci* 7:3961–3983.
- Khairoun I, Boltong MG, Driessens FCM, Planell JA. 1997. Effect of calcium carbonate on clinical compliance of apatitic calcium phosphate bone cement. *J Biomed Mater Res* 38:356–360.
- Kilian D, Ahlfeld T, Akkineni AR, Bernhardt A, Gelinsky M, Lode A. 2020. 3D Bioprinting of osteochondral tissue substitutes – in vitro -chondrogenesis in multi-layered mineralized constructs. *Sci Rep* 10:8277.
- Kim BS, Jang J, Chae S, Gao G, Kong JS, Ahn M, Cho DW. 2016. Three-dimensional bioprinting of cell-laden constructs with polycaprolactone protective layers for using various thermoplastic polymers. *Biofabrication* 8:035013.
- Kim MH, Kim BS, Park H, Lee J, Park WH. 2018. Injectable methylcellulose hydrogel containing calcium phosphate nanoparticles for bone regeneration. *Int J Biol Macromol* 109:57–64.
- Kim SW, Kim DY, Roh HH, Kim HS, Lee JW, Lee KY. 2019. Three-Dimensional Bioprinting of Cell-Laden Constructs Using Polysaccharide-Based Self-Healing Hydrogels. *Biomacromolecules* 20:1860–1866.
- Kim W, Kim G. 2020. Collagen/bioceramic-based composite bioink to fabricate a porous 3D hASCs-laden structure for bone tissue regeneration. *Biofabrication* 12:015007.
- Kolesky DB, Homan KA, Skylar-Scott MA, Lewis JA. 2016. Three-dimensional bioprinting of thick vascularized tissues. *PNAS* 113:3179–3184.
- Korn P, Ahlfeld T, Lahmeyer F, Kilian D, Sembdner P, Stelzer R, Pradel W, Franke A, Rauner M, Range U, Stadlinger B, Lode A, Lauer G, Gelinsky M. 2020. 3D Printing of Bone Grafts for Cleft Alveolar Osteoplasty – In vivo Evaluation in a Preclinical Model. *Front Bioeng Biotechnol* 8:217.
- Landers R, Pfister A, Hübner U, John H, Schmelzeisen R, Mülhaupt R. 2002. Fabrication of soft tissue engineering scaffolds by means of rapid prototyping techniques. *J Mater Sci* 37:3107–3116.

- Landers R, Mülhaupt R. 2000. Desktop manufacturing of complex objects, prototypes and biomedical scaffolds by means of computer-assisted design combined with computer-guided 3D plotting of polymers and reactive oligomers. *Macromol Mater Eng* 282:17–21.
- Langer R, Vacanti JP. 1993. Tissue engineering. *Science* 260:920–926.
- Laurens N, Koolwijk P, Maat MPMD. 2006. Fibrin structure and wound healing. *J Thromb Haemost* 4:932–939.
- LeGeros RZ. 2008. Calcium Phosphate-Based Osteoinductive Materials. *Chem Rev* 108:4742–4753.
- Leberfinger AN, Moncal KK, Ravnic DJ, Ozbolat IT. 2017. 3D Printing for Cell Therapy Applications. In: Emerich DF, Orive G (Eds) *Cell Therapy: Current Status and Future Directions*. Springer International Publishing, Cham (Molecular and Translational Medicine), pp. 227–248.
- Lee A, Hudson AR, Shiwardski DJ, Tashman JW, Hinton TJ, Yerneni S, Bliley JM, Campbell PG, Feinberg AW. 2019. 3D bioprinting of collagen to rebuild components of the human heart. *Science* 365:482–487.
- Lee C, O’Connell CD, Onofrillo C, Choong PFM, Bella CD, Duchi S. 2020a. Human articular cartilage repair: Sources and detection of cytotoxicity and genotoxicity in photocrosslinkable hydrogel bioscaffolds. *Stem Cells Transl Med* 9:302–315.
- Lee KY, Mooney DJ. 2012. Alginate: properties and biomedical applications. *Prog Polym Sci* 37:106–126.
- Lee M, Bae K, Levinson C, Zenobi-Wong M. 2020b. Nanocomposite bioink exploits dynamic covalent bonds between nanoparticles and polysaccharides for precision bioprinting. *Biofabrication* 12:025025.
- Levato R, Jungst T, Scheuring RG, Blunk T, Groll J, Malda J. 2020. From Shape to Function: The Next Step in Bioprinting. *Adv Mater* 32:1906423.
- Ley C, Brendlé J, Walter A, Jacques P, Ibrahim A, Allonas X. 2015. On the interaction of triarylmethane dye crystal violet with LAPONITE® clay: using mineral nanoparticles to control the dye photophysics. *Phys Chem Chem Phys* 17:16677–16681.
- Lienemann PS, Lutolf MP, Ehrbar M. 2012. Biomimetic hydrogels for controlled biomolecule delivery to augment bone regeneration. *Adv Drug Deliv Rev* 64:1078–1089.
- Lim KS, Schon BS, Mekhileri NV, Brown GCJ, Chia CM, Prabakar S, Hooper GJ, Woodfield TBF. 2016. New Visible-Light Photoinitiating System for Improved Print Fidelity in Gelatin-Based Bioinks. *ACS Biomater Sci Eng* 2:1752–1762.
- Lode A, Heiss C, Knapp G, Thomas J, Nies B, Gelinsky M, Schumacher M. 2018. Strontium-modified premixed calcium phosphate cements for the therapy of osteoporotic bone defects. *Acta Biomater* 65:475–485.

- Lode A, Krujatz F, Brüggemeier S, Quade M, Schütz K, Knaack S, Weber J, Bley T, Gelinsky M. 2015. Green bioprinting: Fabrication of photosynthetic algae-laden hydrogel scaffolds for biotechnological and medical applications. *Eng Life Sci* 15:177–183.
- Lode A, Meissner K, Luo Y, Sonntag F, Glorius S, Nies B, Vater C, Despang F, Hanke T, Gelinsky M. 2014. Fabrication of porous scaffolds by three-dimensional plotting of a pasty calcium phosphate bone cement under mild conditions. *J Tissue Eng Regen Med* 8:682–693.
- Luo Y, Lode A, Sonntag F, Nies B, Gelinsky M. 2013. Well-ordered biphasic calcium phosphate–alginate scaffolds fabricated by multi-channel 3D plotting under mild conditions. *J Mater Chem B* 1:4088–4098.
- Maazouz Y, B. Montufar E, Guillem-Marti J, Fleps I, Öhman C, Persson C, P. Ginebra M. 2014. Robocasting of biomimetic hydroxyapatite scaffolds using self-setting inks. *J Mater Chem B* 2:5378–5386.
- MacMillan AK, Lamberti FV, Moulton JN, Geilich BM, Webster TJ. 2014. Similar healthy osteoclast and osteoblast activity on nanocrystalline hydroxyapatite and nanoparticles of tri-calcium phosphate compared to natural bone. *Int J Nanomed* 9:5672–5673.
- Malda J, Visser J, Melchels FP, Jüngst T, Hennink WE, Dhert WJA, Groll J, Hutmacher DW. 2013. 25th Anniversary Article: Engineering Hydrogels for Biofabrication. *Adv Mater* 25:5011–5028.
- Markovic M, Fowler BO, Tung MS. 2004. Preparation and Comprehensive Characterization of a Calcium Hydroxyapatite Reference Material. *J Res Natl Inst Stand Technol* 109:553–568.
- Matsuo K. 2009. Cross-talk among bone cells: *Curr Opin Nephro Hypertens* 18:292–297.
- Meininger S, Blum C, Schamel M, Barralet JE, Ignatius A, Gbureck U. 2017. Phytic acid as alternative setting retarder enhanced biological performance of dicalcium phosphate cement in vitro. *Sci Rep* 7:558.
- Melchels FPW, Blokzijl MM, Levato R, Peiffer QC, Ruijter Md, Hennink WE, Vermonden T, Malda J. 2016. Hydrogel-based reinforcement of 3D bioprinted constructs. *Biofabrication* 8:035004.
- Mendes BB, Gomez-Florit M, Hamilton AG, Detamore MS, Domingues RMA, Reis RL, Gomes M. 2020. Human platelet lysate-based nanocomposite bioink for bioprinting hierarchical fibrillar structures. *Biofabrication* 12:015012.
- Milazzo M, Negrini NC, Scialla S, Marelli B, Farè S, Danti S, Buehler MJ. 2019. Additive Manufacturing Approaches for Hydroxyapatite-Reinforced Composites. *Adv Func Mater* 29:1903055.
- Min LJ, Edgar TYS, Zicheng Z, Yee YW. 2015. Chapter 6 - Biomaterials for Bioprinting. In: Zhang LG, Fisher JP, Leong KW (Eds) *3D Bioprinting and Nanotechnology in Tissue Engineering and Regenerative Medicine*. Academic Press, pp. 129–148.

- Miranda P, Saiz E, Gryn K, Tomsia AP. 2006. Sintering and robocasting of β -tricalcium phosphate scaffolds for orthopaedic applications. *Acta Biomater* 2:457–466.
- Mirdamadi E, Muselimyan N, Koti P, Asfour H, Sarvazyan N. 2019. Agarose Slurry as a Support Medium for Bioprinting and Culturing Freestanding Cell-Laden Hydrogel Constructs. *3D Print Add Manuf* 6:158–164.
- Misch CE, Qu Z, Bidez MW. 1999. Mechanical properties of trabecular bone in the human mandible: Implications for dental implant treatment planning and surgical placement. *J Oral Maxillofac Surg* 57:700–706.
- Moroni L, Boland T, Burdick JA, Maria CD, Derby B, Forgacs G, Groll J, Li Q, Malda J, Mironov VA, Mota C, Nakamura M, Shu W, Takeuchi S, Woodfield TBF, Xu T, Yoo JJ, Vozzi G. 2018. Biofabrication: A Guide to Technology and Terminology. *Trends Biotechnol* 36:384–402.
- Mosesson MW. 2005. Fibrinogen and fibrin structure and functions. *J Thromb Haemost* 3:1894–1904.
- Moussa M, Carrel JP, Scherrer S, Cattani-Lorente M, Wiskott A, Durual S. 2015. Medium-Term Function of a 3D Printed TCP/HA Structure as a New Osteoconductive Scaffold for Vertical Bone Augmentation: A Simulation by BMP-2 Activation. *Materials* 8:2174–2190.
- Mørch YA, Donati I, Strand BL, Skjåk-Braek G. 2006. Effect of Ca^{2+} , Ba^{2+} , and Sr^{2+} on alginate microbeads. *Biomacromolecules* 7:1471–1480.
- Narayanan V, Sumathi S. 2019. Preparation, characterization and in vitro biological study of silk fiber/methylcellulose composite for bone tissue engineering applications. *Polym Bull* 76:2777–2800.
- Nasatto PL, Pignon F, Silveira JLM, Duarte MER, Nosedá MD, Rinaudo M. 2015a. Influence of Molar Mass and Concentration on the Thermogelation of Methylcelluloses. *Int J Polym Anal Charact* 20:110–118.
- Nasatto PL, Pignon F, Silveira JLM, Duarte MER, Nosedá MD, Rinaudo M. 2015b. Methylcellulose, a Cellulose Derivative with Original Physical Properties and Extended Applications. *Int J Polym Anal Charact* 7:777–803.
- Noori A, Ashrafi SJ, Vaez-Ghaemi R, Hatamian-Zaremi A, Webster TJ. 2017. A review of fibrin and fibrin composites for bone tissue engineering. *Int J Nanomed* 12:4937–4961.
- O'Neill R, McCarthy HO, Montufar EB, Ginebra MP, Wilson DI, Lennon A, Dunne N. 2017. Critical review: Injectability of calcium phosphate pastes and cements. *Acta Biomater* 50:1–19.
- Ode A, Duda GN, Glaeser JD, Matziolis G, Frauenschuh S, Perka C, Wilson CJ, Kasper G. 2010. Toward biomimetic materials in bone regeneration: Functional behavior of mesenchymal stem cells on a broad spectrum of extracellular matrix components. *J Biomed Mater Res A* 95A:1114–1124.

- Ouyang L, Armstrong JPK, Chen Q, Lin Y, Stevens MM. 2020. Void-Free 3D Bioprinting for In Situ Endothelialization and Microfluidic Perfusion. *Adv Func Mater* 30:1908349.
- Ouyang L, Highley CB, Sun W, Burdick JA. 2017. A Generalizable Strategy for the 3D Bioprinting of Hydrogels from Nonviscous Photo-crosslinkable Inks. *Adv Mater* 29:1604983.
- Palta S, Saroa R, Palta A. 2014. Overview of the coagulation system. *Indian J Anaesth* 58:515–523.
- Pereira HF, Cengiz IF, Silva FS, Reis RL, Oliveira JM. 2020. Scaffolds and coatings for bone regeneration. *J Mater Sci Mater Med* 31:27.
- Pietraszek A, Karewicz A, Widnic M, Lachowicz D, Gajewska M, Bernasik A, Nowakowska M. 2019. Halloysite-alkaline phosphatase system—A potential bioactive component of scaffold for bone tissue engineering. *Coll Surf B Biointerf* 173:1–8.
- Qu H, Fu H, Han Z, Sun Y. 2019. Biomaterials for bone tissue engineering scaffolds: a review. *RSC Adv* 9:26252–26262.
- Reitmaier S, Kovtun A, Schuelke J, Kanter B, Lemm M, Hoess A, Heinemann S, Nies B, Ignatius A. 2018. Strontium(II) and mechanical loading additively augment bone formation in calcium phosphate scaffolds. *J Orthop Res* 36:106–117.
- Ribeiro A, Blokzijl MM, Levato R, Visser CW, Castilho M, Hennink WE, Vermonden T, Malda J. 2018. Assessing bioink shape fidelity to aid material development in 3D bioprinting. *Biofabrication* 10:014102.
- Richter RF, Ahlfeld T, Gelinsky M, Lode A. 2019. Development and Characterization of Composites Consisting of Calcium Phosphate Cements and Mesoporous Bioactive Glass for Extrusion-Based Fabrication. *Materials* 12:2022.
- Rujitanapanich S, Kumpapan P, Wanjanoi P. 2014. Synthesis of Hydroxyapatite from Oyster Shell via Precipitation. *Energy Proc* 56:112–117.
- Sancilio S, Gallorini M, Di Nisio C, Marsich E, Di Pietro R, Schweikl H, Cataldi A. 2018. Alginate/Hydroxyapatite-Based Nanocomposite Scaffolds for Bone Tissue Engineering Improve Dental Pulp Biomineralization and Differentiation. *Stem Cells Int* 2:9643721.
- Sannino A, Demitri C, Madaghiele M. 2009. Biodegradable Cellulose-based Hydrogels: Design and Applications. *Materials* 2:353–373.
- Sariibrahimoglu K, Leeuwenburgh SCG, Wolke JGC, Yubao L, Jansen JA. 2012. Effect of calcium carbonate on hardening, physicochemical properties, and in vitro degradation of injectable calcium phosphate cements. *J Biomed Mater Res A* 100:712–719.
- Sarker B, Li W, Zheng K, Detsch R, Boccaccini AR. 2016. Designing Porous Bone Tissue Engineering Scaffolds with Enhanced Mechanical Properties from Composite Hydrogels Composed of Modified Alginate, Gelatin, and Bioactive Glass. *ACS Biomater Sci Eng* 2:2240–2254.
- Sarker B, Rompf J, Silva R, Lang N, Detsch R, Kaschta J, Fabry B, Boccaccini AR. 2015. Alginate-based hydrogels with improved adhesive properties for cell encapsulation. *Int J Biol Macromol* 78:72–78.

- Schütz K, Placht AM, Paul B, Brüggemeier S, Gelinsky M, Lode A. 2017. Three-dimensional plotting of a cell-laden alginate/methylcellulose blend: towards biofabrication of tissue engineering constructs with clinically relevant dimensions. *J Tissue Eng Regen Med* 11:1574–1587.
- Schumacher M, Henß A, Rohnke M, Gelinsky M. 2013. A novel and easy-to-prepare strontium(II) modified calcium phosphate bone cement with enhanced mechanical properties. *Acta Biomater* 9:7536–7544.
- Schumacher M. 2015. Entwicklung und Charakterisierung Strontium-modifizierter CaP-Knochenzemente zur Behandlung osteoporotischer Knochendefekte. Technische Universität Dresden, Faculty of Mechanical Science and Engineering, PhD thesis.
- Schumacher M, Gelinsky M. 2015. Strontium modified calcium phosphate cements – approaches towards targeted stimulation of bone turnover. *J Mater Chem B* 3:4626–4640.
- Schuurman W, Khristov V, Pot MW, Weeren PR van, Dhert WJA, Malda J. 2011. Bioprinting of hybrid tissue constructs with tailorable mechanical properties. *Biofabrication* 3:021001.
- Schwenk JM, Omenn GS, Sun Z, Campbell DS, Baker MS, Overall CM, Aebersold R, Moritz RL, Deutsch EW. 2017. The Human Plasma Proteome Draft of 2017: Building on the Human Plasma PeptideAtlas from Mass Spectrometry and Complementary Assays. *J Proteome Res* 16:4299–4310.
- Segura-Castillo J, Aguirre-Camacho H, González-Ojeda A, Michel-Perez J. 2005. Reduction of Bone Resorption by the Application of Fibrin Glue in the Reconstruction of the Alveolar Cleft. *J Craniofac Surg* 16:105–112.
- Senior JJ, Cooke ME, Grover LM, Smith AM. 2019. Fabrication of Complex Hydrogel Structures Using Suspended Layer Additive Manufacturing (SLAM). *Adv Func Mater* 29:1904845.
- Serra P, Piqué A. 2019. Laser-Induced Forward Transfer: Fundamentals and Applications. *Adv Mater Tech* 4:1800099.
- Sheikh Z, Abdallah MN, Hanafi AA, Misbahuddin S, Rashid H, Glogauer M. 2015. Mechanisms of in Vivo Degradation and Resorption of Calcium Phosphate Based Biomaterials. *Materials* 8:7913–7925.
- Shi P, Kim YH, Mousa M, Sanchez RR, Oreffo ROC, Dawson JI. 2018. Self-Assembling Nanoclay Diffusion Gels for Bioactive Osteogenic Microenvironments. *Adv Healthc Mater* 7:1800331.
- Stichler S, Böck T, Paxton NC, Bertlein S, Levato R, Schill V, Smolan W, Malda J, Tessmar J, Blunk T, Groll J. 2017a. Double printing of hyaluronic acid / poly(glycidol) hybrid hydrogels with poly(ϵ -caprolactone) for MSC chondrogenesis. *Biofabrication* 9:044108.
- Stichler S, Jungst T, Schamel M, Zilkowski I, Kuhlmann M, Böck T, Blunk T, Teßmar J, Groll J. 2017b. Thiol-ene Clickable Poly(glycidol) Hydrogels for Biofabrication. *Ann Biomed Eng* 45:273–285.

- Sun JY, Zhao X, Illeperuma WRK, Chaudhuri O, Oh KH, Mooney DJ, Vlassak JJ, Suo Z. 2012. Highly stretchable and tough hydrogels. *Nature* 489:133–136.
- Tawari SL, Koch DL, Cohen C. 2001. Electrical Double-Layer Effects on the Brownian Diffusivity and Aggregation Rate of Laponite Clay Particles. *J Coll Interf Sci* 240:54–66.
- Thirumala S, Gimble JM, Devireddy RV. 2013. Methylcellulose Based Thermally Reversible Hydrogel System for Tissue Engineering Applications. *Cells* 2:460–475.
- Thormann U, Ray S, Sommer U, ElKhassawna T, Rehling T, Hundgeburth M, Henß A, Rohnke M, Janek J, Lips KS, Heiss C, Schlewitz G, Szalay G, Schumacher M, Gelinsky M, Schnettler R, Alt V. 2013. Bone formation induced by strontium modified calcium phosphate cement in critical-size metaphyseal fracture defects in ovariectomized rats. *Biomaterials* 34:8589–8598.
- Thouverey C, Caverzasio J. 2015. Sclerostin inhibits osteoblast differentiation without affecting BMP2/SMAD1/5 or Wnt3a/ β -catenin signaling but through activation of platelet-derived growth factor receptor signaling in vitro. *Bonekey Rep* 4.
- Topuz F, Henke A, Richtering W, Groll J. 2012. Magnesium ions and alginate do form hydrogels: a rheological study. *Soft Matter* 8:4877–4881.
- Venkatesan J, Bhatnagar I, Manivasagan P, Kang KH, Kim SK. 2015. Alginate composites for bone tissue engineering: A review. *Int J Biol Macromol* 72:269–281.
- Wang C, Wang S, Li K, Ju Y, Li J, Zhang Y, Li J, Liu X, Shi X, Zhao Q. 2014. Preparation of Laponite Bioceramics for Potential Bone Tissue Engineering Applications. *PLoS One* 9:e99585.
- Wang L, Shelton R, Cooper P, Lawson M, Triffitt J, Barralet J. 2003. Evaluation of sodium alginate for bone marrow cell tissue engineering. *Biomaterials* 24:3475–3481.
- Wei Y, Zhao D, Cao Q, Wang J, Wu Y, Yuan B, Li X, Chen X, Zhou Y, Yang X, Zhu X, Tu C, Zhang X. 2020. Stereolithography-Based Additive Manufacturing of High-Performance Osteoinductive Calcium Phosphate Ceramics by a Digital Light-Processing System. *ACS Biomater Sci Eng* 6:1787–1797.
- Weisel JW, Litvinov RI. 2017. Fibrin Formation, Structure and Properties. *Subcell Biochem* 82:405–456.
- Wenz A, Borchers K, Tovar GEM, Kluger PJ. 2017. Bone matrix production in hydroxyapatite-modified hydrogels suitable for bone bioprinting. *Biofabrication* 9:044103.
- Wijenayaka AR, Kogawa M, Lim HP, Bonewald LF, Findlay DM, Atkins GJ. 2011. Sclerostin stimulates osteocyte support of osteoclast activity by a RANKL-dependent pathway. *PLoS ONE* 6:e25900.
- Wilson WC, Boland T. 2003. Cell and organ printing 1: protein and cell printers. *Anat Rec A Discov Mol Cell Evol Biol* 272:491–496.

- Witzler M, Büchner D, Shoushrah SH, Babczyk P, Baranova J, Witzleben S, Tobiasch E, Schulze M. 2019. Polysaccharide-Based Systems for Targeted Stem Cell Differentiation and Bone Regeneration. *Biomolecules* 9:840.
- Xu HH, Wang P, Wang L, Bao C, Chen Q, Weir MD, Chow LC, Zhao L, Zhou X, Reynolds MA. 2017. Calcium phosphate cements for bone engineering and their biological properties. *Bone Res* 5:17056.
- Yuasa T, Miyamoto Y, Ishikawa K, Takechi M, Momota Y, Tatehara S, Nagayama M. 2004. Effects of apatite cements on proliferation and differentiation of human osteoblasts in vitro. *Biomaterials* 25:1159–1166.
- Zehnder T, Sarker B, Boccaccini AR, Detsch R. 2015. Evaluation of an alginate-gelatine crosslinked hydrogel for bioplotting. *Biofabrication* 7:025001.
- Zhang H, Mao X, Zhao D, Jiang W, Du Z, Li Q, Jiang C, Han D. 2017. Three dimensional printed polylactic acid-hydroxyapatite composite scaffolds for prefabricating vascularized tissue engineered bone: An in vivo bioreactor model. *Sci Rep* 7:15255.
- Zipfel WR, Williams RM, Webb WW. 2003. Nonlinear magic: multiphoton microscopy in the biosciences. *Nat Biotech* 21:1369–1377.

DANKE

Eine Dissertation ist der Abschluss eines Lebensabschnitts, ab jetzt ist meine Ausbildung definitiv zu Ende. Daher sei mir ein kleiner Rückblick in mein Leben in Form einer Danksagung gestattet.

Am 22. September 1990 erblickte ich das Licht der Welt. Meinen Namen – oftmals falschgeschrieben und teils eigentümlich prononciert – erhielt ich von meinem Bruder. Dies entschied er allerdings erst kurz vor meiner Geburt. Bis zu diesem Zeitpunkt sollte ich Christian heißen. Als dann ein Tilman geboren wurde, musste meine Oma allerdings erstmal etwas besorgt herumtelefonieren, um zu wissen was passiert war. Diese kleine Episode beschreibt das herzliche und mitfühlende Miteinander in meiner Familie. Ich bin froh, dass ich von meinem Bruder, meinen Großeltern und natürlich vor allem meinen Eltern in jeder Phase meines Lebens begleitet wurde. Meine Jugendzeit war eine, wie sie nicht gewöhnlicher nicht sein konnte. Ich spielte Volleyball, bis ich irgendwann der Kleinste in der Mannschaft war und sicherlich auch wegen des geringeren Talents nur noch ein Reservespieler war. Später fand ich ein neues sportliches Zuhause im Tanzsport, den ich mit viel Ehrgeiz betrieb. Die vielleicht eindrucksvollste Lektion in der Schule war im Lateinunterricht. Wir behandelten Vergil, dem ein kluger Satz zugeschrieben wird: *Mens agitat molem*. Eine Einstellung für ein Leben als Wissenschaftler und nachdenkender Mensch. Unvergessen sind all die Jugendjahre, die ich mit dem intensiven Studiums der Bekämpfung dunkler Künste verband. Final konnte mein Schulpartner, Freund, und Lehrgeber endlich Voldemort besiegen und all die Tage, die ich ein knappes Jahrzehnt lang gewartet habe um zu wissen, wie die beste aller Geschichten ausgeht, schlossen sich tatsächlich als ich mein Abitur begann. Danke Jo, danke Harry!

Zum Studium der Werkstoffwissenschaft entschloss ich mich aufgrund von Keksen. Zunächst wollte ich Verkehrsingenieurwesen studieren. Ein Thema, was mich bis heute interessiert – wie kann man die Umwelt schützen, indem man Verkehrsströme steuert, optimiert und Alternativen zu klassischen Autos entwickelt. Ich besuchte eine Lehrveranstaltung in der Verkehrswirtschaft, die mehr als enttäuschend lief: Die Lehrmeinung der Professorin war, dass eine Privatisierung der Bahn das Allheilmittel sein würde um Verbilligung im Streckennetz zu erreichen und damit Leute vom Auto abzubringen. Als kleiner Abiturient habe ich die Einwände, die sich in mir spontan zusammenbrauten, heruntergeschluckt, war allerdings misstrauisch geworden. Es kam der Hochschultag, eine Erfindung, die Studenten extrem nervt, weil Präabiturienten an die Hochschulen dürfen und dabei Lehrveranstaltungen, Straßenbahnen und insbesondere die Mensen über Gebühr verstopfen. Ich suchte im Hörsaalzentrum die Präsentation der Verkehrswissenschaftler und fand den Stand recht schnell. Dort gab es aber weniger Information zu den Inhalten des Studiums, sondern nur eine Tabelle der Vorlesungen, unter denen ich mir natürlich so gut wie nichts vorstellen konnte. Und Kekse in Form von Ampelmännchen. Das war wirklich mehr als enttäuschend. Um den Tag nicht vollständig zu verschwenden, schloss ich mich einer Gruppe von Jungs an, die davon sprachen eine Probevorlesung im Berndt-Bau zu besuchen – der Heimat

der Werkstoffwissenschaft. Der damalige Leiter des Instituts hielt einen Werbevortrag über sein Studium. Er erzählte damals davon, dass es Wissenschaftlern erstmals gelungen ist, einzelne Atome so anzuordnen, dass sie das Wort „Atom“ bilden. Prinzipiell könnte das dazu beitragen, dass man in Zukunft jede gewünschte Eigenschaft eines Materials über dessen Atome einstellt. Ich weiß bis heute nicht mehr, was in diesem Vortrag noch erzählt wurde, aber dieser eine Fakt hat mich gefesselt – und das Ausstellen von Keksen war dagegen einfach erbärmlich. Wen die unglaubliche Arbeit dazu interessiert, sei auf den tollen Kurzfilm „A boy and his atom“ von Chris Lutz verwiesen. Es ist immer wieder fantastisch zu sehen, was Wissenschaftler produzieren und wie sie das Klischee unkreativer, verkopfter Menschen ad absurdum führen.

Das Studium der Werkstoffwissenschaft entpuppte sich jedoch als zäh. Viel wurde uns über Stahl erzählt und noch viel mehr, wie man Stahl legiert, damit er fester wird, oder elastischer oder plastisch verformbarer. Keramiken und Polymere, von denen ich wusste, dass sie sehr viel komplizierter zu beschreiben sind, spielten kaum bis gar keine Rolle. Mit der Zeit wuchs die Panik, ob mich überhaupt etwas interessieren würde oder ob ich mich doch hätte den Keksen zuwenden sollen. Eines Tages hielt Dr. Ute Bergmann eine Vorlesung und erwähnte, dass sie einen Studentenjob zu vergeben hätte und wer Interesse hätte, möge doch bitte danach kurz dableiben. Nach der Vorlesung umringte ich sie zusammen mit neun bis zehn Kommilitonen. Ich ahnte, dass sie das genauso wie mich überforderte und überlegte, dass sie ihre spontane Entscheidung jetzt wohl nur von Präsenz abhängig machen konnte, nicht etwa vom geeignetsten Kandidaten. Zu jener Zeit war ich noch sehr aktiv im Turniertanz, hatte also gelernt, wie man sich mit möglichst großer Präsenz verkauft ohne dabei reden zu müssen. Ich wandte den Trick sofort an und tatsächlich sagte Dr. Bergmann: „Nun, ich muss jetzt wohl einfach auswählen und deshalb haben Sie Glück“, zeigte auf mich und vereinbarte mit mir einen ersten Termin. Meine Aufgabe war aus heutiger Sicht relativ einfach: Ich sollte den Einwege- und Zweiwege-Effekt von Nitinol, einer Formgedächtnis-Legierung, studieren und ein Protokoll entwickeln, wie ich diesen Effekt der Legierung antrainiere. Zunächst sollte ich dies mit der großen Ofenausstattung des Instituts für Werkstoffwissenschaft machen, später nutzte ich einfach kochendes und kaltes Wasser, was genauso gut funktionierte. Ich möchte nicht zu tief ins Detail gehen, aber der Effekt basiert auf der Austenit-Martensit-Umwandlung an Zwillingskorngrenzen. Immer wenn ich Daten ausgewertet habe und damit zu Dr. Bergmann ging, schloss sie ihre Augen und erinnerte sich laut an die theoretischen Grundlagen, die unabhängig von Nitinol zu Zwillingskorngrenzen bekannt sind. Dieses Vorgehen verblüffte mich immer wieder aufs Neue und im Nachhinein besonders – ich habe dies nie mehr so erlebt, aber die Ergebnisse dieser Herangehensweise waren immer wieder bemerkenswert. In der Wissenschaft verliert man leider viel zu oft den Bezug zu den Grundlagen und ich glaube, dass diese Gedächtnistechnik viel mehr unserer Ideen erklärt, als wir es auf den ersten Blick für möglich halten.

Ich jobbte dann noch kurz am Fraunhofer Institut für Werkzeugmaschinen- und Umformtechnik. Mir ist bewusst, dass das ob meiner anfänglichen Kühle gegenüber Stählen ein wenig erheiternd klingen muss, aber tatsächlich arbeitete ich an Ni_2MnGa -Legierungen, die einen magnetischen Formgedächtniseffekt besitzen. Die Arbeiten bezogen sich hauptsächlich auf Mikroskopie, mechanische Tests und Patentrecherche, aber zumindest gewann ich

nochmal einen Einblick in diese Art der Metallforschung, was mich nur darin bestärkte einer anderen Disziplin Vorrang zu geben: den Biomaterialien.

Dr. Thomas Hanke gab in jenem Semester die Vorlesung über Biomaterialien und von Anfang an war vieles anders. Wirklich jedes Thema fand ich spannend, ganz gleich ob es die Einführung zur Extrazellulären Matrix war oder die Mikroskopie einzelner Zellen. Im Praktikum führten wir Rasterkraftmikroskopie an einer einzelnen Kollagenfibrille durch. Allein die Vorstellung, dass dies der Grundbaustein des Lebens ist und in so ziemlich jeder Spezies der Welt vorkommt, faszinierte mich. Und noch viel mehr die Aussage, dass es bis heute nicht möglich ist, Kollagen artifiziell herzustellen! In den Lebenswissenschaften bekommt man es oft zu spüren, wie perfekt die Natur sich ihre Bausteine zusammenbaut und wie gering bisher unsere Möglichkeiten sind, dies zu verstehen und entsprechend für regenerative Therapien zu nutzen.

In diesem Semester arbeitete ich erstmals eng mit Stefan Giron zusammen, ein genialer Mensch, der mir im Studium durch seine ehrliche, bescheidene und unglaublich kluge Art sehr ans Herz gewachsen ist. Er verdeutlicht mit was für besonderen Menschen ich studieren durfte. Einmal saßen wir in der sehr umfangreichen Vorlesungsreihe zu elektrischen und magnetischen Werkstoffen von Prof. Schulz und Prof. Schäfer. Ich glaube es war eine Vorlesung zum Thema „Itineranter Magnetismus“, und während wir einfältigen Studenten eifrig versuchten den Ausführungen und Formeln zu folgen und jedes Wort mitschrieben, saß Stefan einfach nur da und blickte aufmerksam auf die rechte Tafelhälfte. Nach einer kurzen Weile meldete er sich und fragte, ob man Elektronen nicht auch noch eine weitere Eigenschaft zubilligen müsse, die aber die Betrachtung an der Tafel ad absurdum führe. Professor Schäfer blickte auf die Tafel und schwieg erstmal für ein paar Minuten. Anschließend bat er um Verständnis, dass er diesen Gedanken so noch nie gefasst hatte und jetzt erstmal darüber nachdenken müsse. Menschen wie Stefan sind einzigartig und bereichernd, menschlich und fachlich. Es war mir bisher immer eine große Bereicherung mit solchen tollen Menschen zusammen arbeiten zu dürfen.

Im folgenden Semester begann die Vorlesung Tissue Engineering. So richtig konnte ich mir darunter nichts vorstellen, aber es war im Katalog der Biomaterialien und somit für mich geradezu prädestiniert. Die Einführung gab Michael Gelinsky, mein späterer Chef und Mentor. Die Idee des gesamten Verfahrens war mir von Anfang an klar und faszinierte mich. Wenn man den Körper nur gut genug anleitet, kann er selbst regenerieren. Und es ist unsere Aufgabe herauszufinden, wie wir das tun können. Es stand für mich die Praktikumsentscheidung an und ich durchsuchte das Web nach verschiedenen Gruppen und stieß auf Prof. Kluger, eine hervorragende Wissenschaftlerin aus dem Raum Stuttgart. Ich bewarb mich also und erhielt trotz wiederholter Nachfrage leider keine Antwort. Eines Tages kam Michael in die Vorlesung und meinte, dass ein Student für 3D-Druck gesucht würde. Noten in anderen Fächern seien nicht so wichtig, es ginge mehr um Motivation, Fleiß und Hingabe. Ich versuchte in meiner späteren Zeit immer diese Punkte zu erfüllen, was mir sicherlich mal mehr und mal weniger gut gelang. Nichtsdestotrotz hatte ich Glück, denn ich konnte den Praktikumsplatz bekommen. Wie sich später herausstellte war Prof. Kluger in der Zeit in Elternzeit, wer weiß wo ich sonst heute wäre und ob ich diese Arbeit vorlegen könnte.

Im Oktober 2013 fing ich meine Arbeit am Zentrum für Translationale Knochen-, Gelenk- und Weichgewebeforschung, kurz TFO, an. Der erste Arbeitstag begann etwas verwunderlich. Ich hatte Anja Lode und Rahul Akkineni, meine zwei Anleiter, bereits vorher getroffen und sollte nun da sein, um die ersten praktischen Einweisungen zu bekommen. Ich dachte mit einem Eintreffen gegen 9 Uhr sollte ich auf der sicheren Seite sein, dass ich nicht wirkte, als ob ich zu früh, aber auch nicht zu spät auf Arbeit ginge. Es dauerte schließlich zwei weitere Stunden, bis Rahul zur Tür reinkam. Rahul hat das System optimiert lange zu schlafen und dafür lange zu arbeiten. Mir wurde sofort bewusst, dass Wissenschaft kein Korsett wie Arbeitszeiten braucht, sondern die Freiheit so zu arbeiten, wie man es am Besten kann. Zunächst sollte ich mich mit core/shell-Strukturen beschäftigen, also Strukturen aus zwei Materialien, die einander einschließen. Rahul und ich arbeiteten damals mit dem Prototyp der Plotter, die wir heute verwenden. Es hat noch nichts richtig funktioniert, wir konnten einen Scaffold nur auf einen Punkt drucken und mussten auf semi-sterile Druckerfolien (für den Overheadprojektor) plotten. Die core/shell-Nadeln haben wir selbst produziert, indem wir alles an Plastik, was wir im Labor gefunden haben, aufschnitten, mit einem Campingkocher anschmolzen, mit Kleber verbanden und irgendwie die Nadeln ineinander wurstelten. Es ist erstaunlich, was wir mit diesen Mitteln erreichten – nach einem halben Jahr hatten wir fünf verschiedene Kombinationen von core/shell-Scaffolds hergestellt und mechanisch und mikroskopisch charakterisiert, außerdem konnten wir uns nun gezielt den Release von BSA anschauen. Zu der Zeit waren Rahul und ich die einzigen, die sich ausschließlich mit 3D-Druck beschäftigten. Kathleen und Sophie waren in der Lage den Drucker zu nutzen und machten auch einige tolle Experimente mit dem Drucken von Zellen, aber letztlich fluchten die beiden mehr über den Plotter (und vermutlich genauso über Rahul und mich und unsere Neigung unsere provisorischen Aufbauten am Arbeitsplatz zu hinterlassen), als das sie wirklich für den Drucker glühten.

Die praktische Arbeit an dem Beleg habe ich innerhalb des ersten halben Jahres abgeschlossen. Die Schreib- und Korrekturphase zog sich allerdings weitere Monate, in denen ich glücklicherweise beginnen durfte parallel an anderen Projekten zu arbeiten. Meine ersten Abgaben waren voller wager Beschreibungen, unzureichender Aussagen und ohne jegliche Struktur. Es ist Anjas Geduld zu verdanken, dass ich gerade im Verfassen wissenschaftlicher Texte viel gelernt habe und bis heute immer wieder dazu lerne. Im Sommer 2014 fragte mich Anja, ob ich nicht meine Diplomarbeit am TFO anfertigen wolle. Insgeheim hatte ich mich nur nicht getraut zu fragen, aber die Arbeit am Zentrum war mein Traum und ich konnte es kaum fassen, dass mein Wirken offensichtlich so geschätzt wurde, dass ich gefragt wurde, ob ich bleiben wollte, obwohl es doch anders herum viel normaler gewesen wäre. Darüber hinaus haben sich Michael und Anja immer bemüht, mir auch finanzielle Unterstützung zukommen zu lassen. Ich musste nie klagen – meine Großeltern und Eltern waren immer sehr großzügig zu mir – aber die Wertschätzung immer ein Gehalt zu bekommen, war mir eine Ehre und Verpflichtung zugleich. Leider fehlte mir für das Diplom auch noch der Kleine Beleg. Daher war der Deal, dass ich die Arbeiten für das Diplom bereits jetzt machte – weil damit ein Tierversuch verbunden war und den Kleinen Beleg im Anschluss anfertigte.

Es ging um die Erstellung eines Implantates für einen kritischen Rattenfemurdefekt auf Basis von Calciumphosphat-Knochenzementen. Ich kannte die zwei bisher dazu publizierten Manuskripte von Anja und Luo aus unserer Gruppe. Ich fing also an den Zement zu drucken – und scheiterte kläglich. Es war mir schier unerklärlich, wie die in den Arbeiten gezeigten Scaffolds zustande gekommen sein sollten. Rahul gab mir noch einige Tips zum Handling und zum Schluss konnte ich immerhin ein paar Layer bröckligen Zementes extrudieren. Auch das erste Meeting mit Yvonne Förster, die die Tiere operieren sollte, war eine reine Enttäuschung – der Scaffold sei zu groß und völlig rund und weil wir eine Schiene einbauen müssten, würde er eh nur schwer halten und es ist davon auszugehen, dass der Scaffold zerbröselt. Das war noch ganz weit weg von patientenindividueller Medizin und passgenauen Implantaten und die Enttäuschung muss mir im Gesicht gestanden haben, zumindest fühlte ich mich damals ziemlich hilflos. Wieder einmal war es Rahul, der mir den richtigen Weg aufzeigte. Ich solle nicht aufgeben, er hätte eine neue Art von Nadel gefunden und auch neuer Zement solle eintreffen. Und tatsächlich: Ein paar Wochen (und etliche Stunden Prozessoptimierung) später, konnten wir die Calciumphosphatzemente auf einmal in viel besseren Dimensionen und mit hoher Formgenauigkeit drucken. Wir nutzten mittlerweile das erste offizielle Modell von GESIM, der ulkigerweise das Label 2.1 trug. Die Software war zwar anders, aber der Drucker arbeitete wie bisher mit einfachen Liniencodes, die von einer Koordinate zur einer weiteren ein paar Parameter abfragten. Durch die viele Arbeit sind Rahul und ich zu diesem Zeitpunkt bereits dazu übergegangen, diese Codes selbst zu schreiben, was auch in diesem Fall extrem hilfreich war: So konnten wir die äußere Form und den inneren Aufbau der Scaffolds viel besser beeinflussen. Ich schrieb also die Linefile für alle 42 Schichten und über 250 Stränge des Scaffolds per Hand – die Koordinaten jeder Schicht hatte ich mir vorher tatsächlich auf einen Zettel notiert. Am Ende dieses Prozesses konnten wir einen perfekt passenden Scaffold kreieren, den wir darüber hinaus auch noch gezielt mit VEGF-beladenen Hydrogelen kombinierten. Dies war der Grundstock für meine erste Publikation.

Am 1. September 2014 fuhr ich wie jeden Tag mit dem Zug zur Arbeit. Mit mir fuhr eine junge Frau mit unglaublichem, zahnpastaweißem Lächeln. Ich lächelte sie an, sie lächelte zurück. Zwei Tage später klopfte sie mir, wieder im Zug, auf die Schulter, gab mir wortlos ihre Nummer, drehte sich um und verschwand in der Menge. Ein paar Tage später lud ich Luise dann zu einem ersten Essen ein.

In der Folge arbeitete ich parallel an der Diplomarbeit und dem Kleinen Beleg, der sich mit einem weiteren, sehr spannenden Thema beschäftigte: Der Entwicklung von magnetisch verformbaren Druckpasten. Die damals erzielten Ergebnisse waren die Grundlage für die Arbeit, mit der sich Janina Spangenberg und Charis Czichy später beschäftigen durften. Ich lernte dabei die Arbeit am μ CT und entdeckte eine kleine Leidenschaft für dreidimensionale Bildgebung. Insbesondere von meinem damaligen Betreuer am Institut für Magnetofluidynamik, Malte Schümann, lernte ich diverse Auswertemethoden, die ich auch heute noch verwende. Der Zeit dort ist auch zu verdanken, dass ich die qualitative Auswertung von Bilddaten und Image-Stacks verstanden habe, eine Arbeit die insbesondere im (dreidimensionalen) Bioprinting enorm wichtig ist.

Im August 2015 wurde ein Projekt bewilligt, welches in Zusammenarbeit mit Institut Für Textilmaschinen und Textile Hochleistungswerkstofftechnik auf die Beine gestellt wurde. Der Projektbeginn sollte Anfang des kommenden Jahres sein und wenn ich gerne am Institut bleiben wollte, dieses Mal als Doktorand, wäre das doch die perfekte Chance. Auch dieses Mal berührte es mich, dass Anja und Michael so um mich warben und natürlich wollte ich den Job unbedingt, also willigte ich in alle studentischen Arbeiten so schnell wie möglich abzuschließen, die Zeit war eh dafür reif.

In der Folge entwickelte sich ein wahrer Arbeits- und Schreibmarathon. Zunächst musste ich noch meinen Praktikumsbericht abgeben, was sicherlich hätte vorher geschehen können, aber dieser war mein Pfand die Studiendauer nach meinem Dünken zu verlängern. Also habe ich diesen schnell heruntergeschrieben und reichte ihn ein. Ich muss Jörg Neunzehn danken, den ich bereits von früher gut kannte und der zufälligerweise mit der Korrektur der Praktikumsberichte betraut war. Er rief mich im September an und berichtete mir davon, dass die Fakultät den Praktikumsbericht klassischerweise eher als Projektbericht und nicht – wie ich es geschrieben hatte – als chronologischen Bericht wünschte. Das Herz schlug mir bis zum Hals, wusste ich doch, dass die Anerkennung des Praktikums wichtig war, dass ich mich überhaupt für das Diplom anmelden konnte – was natürlich Bedingung für den Job war. Er meinte, er würde allerdings noch kurz ein Telefonat führen wollen und rufe wieder an. Kaum zehn Minuten später meldete er sich: „Du Tilman. . . das geht leider so nicht.“ In diesem Moment verabschiedete ich mich schon vom Schlaf der nächsten Nächte und fragte ihn, wie schnell er korrigieren könne, wenn ich in den nächsten Tagen einen neuen Bericht einreichen würde. „Das geht leider auch nicht. . . Weil es viel besser geht. Ich darf dir den Bericht anerkennen und mache das hiermit, weil wir uns so gut kennen.“ Gut gespielt Jörg – und auch hierfür nochmal großen, herzlichen Dank – diese Arbeit würde vermutlich ohne dein Wohlwollen und deinen Einsatz in diesem Moment nicht vorliegen. Damit war es leider noch nicht zu Ende: Wie ich voller Schrecken erkennen musste, war die Anmeldung für das Diplom gespickt mit verschiedenen Unterschriften auf einer Checkliste. Hierbei traf es sich, dass Prof. Wiesmann nicht nur mein Betreuer an der Fakultät, sondern auch Studiengangsleiter war. Doch wie ich leider feststellen musste, verweilte er im Urlaub. Frau Keil, die gute Seele am Max-Bergmann-Zentrum, konnte mir allerdings sagen, wann er wiederkäme, aber nicht ob er Zeit für mich hätte. Mein Plan war einfach: Ich musste ihn überreden den Text bereits zu lesen, bevor ich ihn offiziell eingereicht habe, damit die Verteidigung meiner Arbeit noch in diesem Jahr stattfinden konnte. Ich campierte also geschlagene zwei Stunden vor dem Büro von Prof. Wiesmann (der tatsächlich an dem Tag einen vollen Terminkalender voller Meetings hatte) und passte ihn, leider sehr unhöflich, auf dem Weg zum Klo ab und nutzte die folgenden drei Minuten, um ihm von meinem Problem und der möglichen Lösung zu erzählen. Mal wieder war es für mich pures Glück (!), dass er großes Verständnis hatte und auf den Deal einging. Die folgende Schreibphase war der pure Horror – ich schrieb einen Abschnitt, mailte ihn an Anja, sie korrigierte ihn, ich schickte ihr einen neuen, arbeitete die Korrekturen in den alten ein, schickte diese zur nochmaligen Kontrolle zurück usw.. Zum Schluss lag tatsächlich innerhalb eines Monats die gesamte Arbeit vor und es hat sich zum Glück terminlich alles gefunden, wenngleich Frau Damm im Prüfungsamt höchst erstaunt bemerkte, dass ich doch gestern erst meine Arbeit angemeldet habe und heute die

Diplomarbeit schon abgebe. Nunja, die Regeln haben es nicht verboten, also war wohl alles gut. Zum Abschluss verteidigte ich meine Arbeit kurz vor der Weihnachtspause 2015 und alles war gut. Luise, mit der ich mittlerweile zusammengezogen war, unterstützte mich mit aller Kraft, um diesen letzten Teil meines Studiums gut zu überstehen.

Mit Beginn meines ersten Jahres als Doktorand, stand dann gleich meine erste Reifeprüfung an. Prof. Malda aus Utrecht hatte uns eingeladen einen Artikel in einem kleineren Journal zu publizieren. Meine Diplomarbeit, die zu großen Teilen eher Optimierung eines bereits von Luo publizierten Systems war, eignete sich dafür. Die folgenden Wochen sollten mich für die gesamte weitere Zeit prägen. Die Art und Weise eine wissenschaftliche Veröffentlichung zu schreiben, die Genauigkeit, die man beim Diskutieren braucht, die Klarheit, um seine Forschung auch strukturiert darzustellen – all das lernte ich in dieser Zeit. Hier lernte ich am allermeisten von Anja wie man all diese Dinge angeht. Wieder einmal zeigte sie große Geduld und viel Talent und lehrte mich so, wie man Fachartikel verfasst und publiziert. Später brachte Michael mir bei, dass man trotz aller Details niemals den Blick auf die Einordnung in "das große Ganze" verlieren darf. Dies war sehr wichtig, da ich so lernte, dass ein Forschungsthema eher ein Kanon verschiedener Teilarbeiten ist. Mit Sarah und Julia kamen zwei neue Mitstreiter im Bioprinting hinzu und mittlerweile hatten wir auch eine größere Anzahl an Studenten, die sich mit verschiedenen Teilaspekten unserer Arbeiten beschäftigten. Es war eine gute Zeit: Ich lernte die Macht der Computertomographie und konnte diese Daten dreidimensional remodellieren und in der Folge auch drucken. Darüber hinaus kam mit Gianluca ein italienischer Doktorand aus einer britischen Arbeitsgruppe als Gastwissenschaftler und brachte ein neues Material in die Gruppe, welches mich bis heute begeistert: Laponit. Laponit ist ein synthetisches Mineral, welches eine heterogene Ladungsverteilung aufweist und daher Wachstumsfaktoren bindet und sehr gut manipulierbar freisetzt. Mit Gianluca habe ich die bestehende Bioink von Kathleen in ihrer Funktion erweitert und die daraus entstandene Arbeit ist wundervoll und ich zehre bis heute von dieser gelungenen Kooperation.

Neben Gianluca waren natürlich weitere Gastwissenschaftler am TFO und weil es auch einige Projekte mit 3D-Druck gab, hatte ich das Vergnügen mit Einigen von ihnen enger zusammenzuarbeiten. Ella Hodder kam aus Brighton und brachte die Fragestellung ein, ob wir denn das System aus Alginat und Methylcellulose schon hinsichtlich des Degradationsverhaltens richtig verstanden haben. Das war natürlich spannend, weil die Degradation durch physikalische, chemische und biologische Eigenschaft beeinflusst wird. Ich konnte meinen kleinen Teil zu der Arbeit von Sarah Duin und Ella beitragen, vor allem aber war es toll zu sehen, wie eine junge Wissenschaftlerin so akribisch an einem Thema arbeiten kann und trotz einiger Rückschläge nie die Faszination am Thema selbst verlor. Diese Begeisterungsfähigkeit soll mir immer eine Lehre für die Zukunft sein. Auch Maaïke Braham aus Utrecht kam zu dieser Zeit ans TFO. Sie arbeitete an einem Thema von dem ich anfangs viel zu wenig verstand und mich in den entsprechenden Meetings etwas Fehl am Platz fühlte: Der Kultivierung und Charakterisierung von Multikulturen von verschiedenen Knochen- und Myelomzellen. Ich war immer wieder fasziniert von all den Methoden, die sie scheinbar mühelos in der Zellkultur und der Mikroskopie anwandte, aber ich darf mir ein klein bisschen auf die Schulter klopfen, dass auch Maaïke fasziniert war, dass ich scheinbar

mühe los die filigransten Scaffolds aus CPC drucken konnte. Mittlerweile habe ich zum Glück viele Aspekte dieser Arbeit verstanden. Es ist toll, dass in einer Disziplin wie dem Tissue Engineering Biologen wie Maaike und Ingenieure wie ich miteinander arbeiten und voneinander lernen können. Fernanda Vechietti war eine Doktorandin bei uns, die an bioaktiven Oberflächenbeschichtungen von metallischen Implantaten arbeitete. Mit Fernanda verging die Zeit immer doppelt so schnell und es war toll mit ihr in der Gruppe zu arbeiten. Mit Aneta Pietraszek kam eine Wissenschaftlerin aus Polen zu uns ins Labor und wir arbeiteten an neuartigen druckbaren Pasten aus Chitosan mit Halloysit-Nanotubes. Eines Tages gelang es Michael ein sehr prestigeträchtiges Projekt einzuwerben: Unsere Forschungsgruppe würde sich mit dem Bioprinting im All beschäftigen. Dazu gelang es ihm Nieves Cubo in unser Team zu holen - eine Doktorandin aus Madrid, die bereits große internationale Bekanntheit erreicht hatte, weil es ihr gelungen war mit Hilfe von Blutplasma funktionale Haut zu drucken. Es dauerte nicht lang, bis Nieves und ich uns anfreundeten und wir entdeckten, dass wir unser Wissen perfekt kombinieren können. Mit Nieves war das Arbeiten fantastisch - wir ergänzten uns sehr gut und die Ergebnisse sprachen für sich. Es war eine riesige Freude mit Nieves zusammen zu forschen und ich hoffe, dass wir das auch in Zukunft tun werden.

In der Folge arbeitete ich an vielen kleinen Studien mit, die ich unmöglich alle benennen kann. Eine kleine Selektion sei mir aber zugestanden. Zusammen mit Corina Vater, Henriette Brettschneider und Stefan Zwingenberger hatte ich viele Einblicke in Tiermodelle von Maus über Ratte bis hin zum Minischwein. Mit den Möglichkeiten der 3D-Drucker konnten wir Sägelehren herstellen, die uns Kosten von über 300 Euro (pro Stück!) ersparten. Auch mechanische Studien der Mäuse- und Rattenfemura haben wir an unzähligen Tagen durchgeführt. Dabei lernte ich Julia Bolte kennen, eine unglaublich toughe, schlaue und tanzbegabte Doktorin und Wissenschaftlerin, deren Freundschaft ich nicht mehr missen möchte. Mit Julia Seidel arbeitete ich enger zusammen im spannenden Projekt des Green Bioprintings von Pflanzenzellen. Julia gehört zu den Personen, die mir immer am Meisten imponieren. Sie besitzt eine unglaublich schnelle Auffassungsgabe und kann so in jeder Diskussion ohne Probleme bestehen. Sie durchdenkt jedes Experiment und ist ein sehr kritischer Geist – was dem rasanten und teils zu schnellem Wissenschaftsbetrieb nur gut tun kann. Ich genieße es immer wieder mit Julia über die Wissenschaft und die Welt zu diskutieren, es gibt nur wenige Freunde mit denen man dies so gut und ausgiebig tun kann. David kam im Oktober 2016 ans TFO und ich überrumpelte ihn sogleich mit diversen Aufgaben um das Bioprinting. Er half mir, wo er nur konnte und in der Folge konnten wir uns gegenseitig bei zahlreichen kleineren und größeren Projekten unterstützen, die in diverse Publikationen mündeten. David ist ein unglaublich akribischer Wissenschaftler, dessen Einstellung zu seiner Arbeit, seine Genauigkeit und Klugheit einfach nur bewundernswert sind. Ich hoffe noch viele weitere spannende Themen mit ihm bearbeiten zu können.

Mit Luise war die Zeit schöner als je zuvor. Ich fragte sie, ob sie meine Frau werden wolle. Sie sagte ja. Als wir im Standesamt heirateten - eine kleine Zeremonie, allerdings ohne Musik oder lange Worte - standen auf einmal fast alle aus der Arbeitsgruppe vor der Tür um mit uns zu feiern. Mandy Quade hatte am Vorabend mit meiner Mutti ausgemacht, dass alle kommen würden und sich im Garten heimlich versammeln. Und als dann zum Polterabend

wirklich alle kamen, und Michael und Anja sogar vorzeitig ihr Transregio-Vorstandstreffen dafür verließen, war ich tief berührt.

Eine weitere Kooperation im medizinischen Bereich entspann sich mit Paula Korn, die heute an der Charité arbeitet. Mittlerweile hatten wir die Formgenauigkeit gedruckter Zementscaffolds soweit optimiert, dass wir auch feinste Strukturen mühelos erzeugen konnten. Paula hatte bereits in einer Studie zeigen können, dass einfüllbare Granulate nur begrenzt zur Regeneration von Lippen-, Kiefer- und Gaumenspalten taugen und war gespannt darauf, ob unser Material denn besser wäre. Daraufhin druckten und charakterisierten wir CPC-Scaffolds im Miniaturformat, die wir mit Zellen funktionalisierten. Bis heute werben wir gemeinsam Projekte ein und verbessern die Scaffolds immer mehr. Ich lernte in dieser Kooperation sehr viel und Paula ist eine tolle Kollegin, mit der wissenschaftliches Arbeiten sehr einfach ist und viel Spaß macht.

In meiner bisherigen Zeit am TFO hatte ich einige Studenten zu betreuen. Das war ein ungeheuer wichtiges Kapitel, welches mich sehr hat reifen lassen. Jeder Student hat natürlich seine eigene Vorstellung davon, wie er sich einbringen möchte und was er zu Leisten in der Lage ist. Es gibt die Herangehensweise, dass Studenten immer nur ein Thema optimieren dürfen oder ein bereits bearbeitetes Thema nachprüfen sollen, um darüber ihren Beleg zu schreiben. Das habe ich von vornherein abgelehnt. Ein Student sollte die Möglichkeit bekommen seine frischen, unverbrauchten, teils auch unkonventionellen Gedanken auch erforschen zu dürfen. Nicht jeder Student kam damit klar, da es bedeutete, dass "meine" Studenten sehr selbstständig arbeiten mussten, nachdem ihre Einarbeitungszeit endete. Ich hoffe man mag mir meine hohen Anforderungen verzeihen. Zumindest kann man sagen, dass alle - insbesondere ich - dadurch sehr viel gelernt haben. Caro untersuchte Zusammenhänge zwischen Porenstruktur geplotteter Scaffolds und ihrer mechanischen Stabilität. Tino bearbeitete einige Forschungsfragen zum Thema Supportstrukturen, aber fertigte auch Komposite aus CPC und Kollagen und fing an sich mit einem Biomaterial namens Zein zu beschäftigen. Akram bearbeitete Fragestellungen des AiF-Projektes zur Kombination von Hydrogelen und NSN-Chitosan-Vliesstoffstrukturen. Alexandra untersuchte Komposite aus Fibrin und CPC-Scaffolds. Falko arbeitete mit biphasigen Systemen aus CPC und bioinks. Klara führte Studien zu hypoxischen Bedingungen in einer Laponit-Alginat-Methylcellulose-bioink durch. Später kam Richard ins Labor und mit ihm das erste Mal die Erfahrung, dass ich einem Studenten nichts beibringen sondern allenfalls von ihm lernen kann. Seine Arbeit war und ist schlichtweg exzellent - und ich bin froh, dass wir Kollegen sind und weiterhin gemeinsam Projekte bearbeiten können.

Die Arbeitsgruppe im TFO ist im Grunde sehr nah und eng beieinander - man arbeitet mit Freunden und nicht nur mit Kollegen. Als wir die Labore neu organisierten, spülte mich mein Laborarbeitsplatz zu Max und seinem MEW-Drucker. Wie auch andere Physiker, beeindruckt Max mich durch seine Akribie und experimentelle Planung. Ein Ansatz ist nur dann gut, wenn er komplett durchdacht werden kann. In der sehr empirischen Biomaterialforschung ist das immer wieder ein toller Ansatz und Max beweist mit den Erfolgen seiner Arbeit und Experimente, dass diese Herangehensweise sehr hilfreich ist. Auch dies hat mich tief beeindruckt und ich lern(t)e davon. Später kam Sophie mit zu uns und zu Dritt war das Arbeiten umso lustiger.

Von Anne Bernhardt habe ich gelernt, wie sehr man sich für ein tiefes Detailwissen in der Wissenschaft begeistern kann. Sie war immer eine gute ZuhörerIn und noch bessere Ratgeberin für meine eigenen Probleme. Matthias Schumacher und Vera Guduric hatten immer gute Ideen, wie ich meine Experimente besser gestalten könnte. Ohne Ortrud Zieschang, Anna-Maria Placht, Silvia Cometta, Kathleen Schütz und Ulrike Weißflog wäre vieles, was auch in dieser Dissertation steckt, nicht möglich gewesen. Und unvergessen sind natürlich auch all jene, deren Name hier zwar nicht steht, die es mir aber dennoch sehr einfach gemacht, am TFO zu arbeiten.

Was wäre ein Leben ohne Freunde: Mit Felix, Sanne, Michi, Ulima und Clemo verbrachte ich viele Jahre jeden Sonntag Abend um Schlachten gegen finstere Fürsten, unheilige Dämonen und grünen Nebel zu führen. Wir erlebten die tollsten und lustigsten Abenteuer in Shetani Dunia und zum Schluss waren wir nicht nur Entdecker und Abenteurer, sondern auch Codeknacker und Befreier der magischen Welt. Andi und Charly und Philipp und Patricia waren immer da, wenn man sie brauchte. Auch wenn es auf Arbeit mal nicht so lief oder wenn man einfach mal ein bisschen tratschen wollte - immer waren sie für einen da. Ohne sie alle wäre diese Dissertation nicht möglich gewesen, da sie mir halfen mal abzuschalten und von der Arbeit wegzukommen.

Eines Tages machte Luise eine Kerze an, sagte ich solle mich hinsetzen und kochte mir mein Lieblingsessen. Dann nahm sie meinen Arm und legte ihn auf ihren Bauch. Sie eröffnete mir, dass wir bald nicht mehr alleine seien. Voller freudigen Erstaunens dämmerte mir, dass sie mir gerade Nachwuchs ankündigte. Wie sie dann aufklärte war unser Meerschweinchen trüchtig. Aber zwei Jahre später kam dann auch mein Sohn Elias zur Welt, und ich hätte nicht glücklicher sein können. Promovieren und gleichzeitig ein Baby zu haben ist nicht einfach. Luise nahm mir fast jede Last ab und zusammen haben wir drei alles unfassbar gemeistert. Ich bin glücklich, dass ich während meiner Promotionszeit eine neue Familie geschenkt bekommen habe.

Es gibt noch so viel mehr Menschen und vor allem Wissenschaftler, die mein Wirken geprägt haben. Ich danke allen hier Genannten und Nichtgenannten dafür, dass sie mich unterstützten und halfen, förderten und mit mir diskutierten. Diese Arbeit ist das Resultat von all jenen, die mich beeinflussten und beeindruckten und mit denen es eine Ehre war zusammenzuarbeiten. Wissenschaft ist aufregend und spannend und erlaubt einem immerwährendes Lernen. Ich genieße es in einem so multidisziplinären Feld zu arbeiten, in dem Mediziner, Ingenieure, Biologen, Chemiker, Physiker und Materialwissenschaftler ihr Wissen in einen Topf werfen, um daraus etwas Neues zu entwickeln. Und ich hoffe, dass ich dem Motto treu geblieben bin:

Mens agitat molem.

APPENDIX

ERKLÄRUNGEN ZUR ERÖFFNUNG DES PROMOTIONSVERFAHRENS

1. Hiermit versichere ich, dass ich die vorliegende Arbeit ohne unzulässige Hilfe Dritter und ohne Benutzung anderer als der angegebenen Hilfsmittel angefertigt habe; die aus fremden Quellen direkt oder indirekt übernommenen Gedanken sind als solche kenntlich gemacht. Ich versichere ferner, die "Richtlinien zur Sicherung guter wissenschaftlicher Praxis, zur Vermeidung wissenschaftlichen Fehlverhaltens und für den Umgang mit Verstößen" der Technischen Universität Dresden befolgt zu haben.
2. Bei der Auswahl und Auswertung des Materials sowie bei der Herstellung des Manuskripts habe ich Unterstützungsleistungen von folgenden Personen erhalten: Alle in den Publikationen (Kapitel 3-6) gelisteten Co-Autoren.
3. Weitere Personen waren an der geistigen Herstellung der vorliegenden Arbeit nicht beteiligt. Insbesondere habe ich nicht die Hilfe eines kommerziellen Promotionsberaters in Anspruch genommen. Dritte haben von mir weder unmittelbar noch mittelbar geldwerte Leistungen für Arbeiten erhalten, die im Zusammenhang mit dem Inhalt der vorgelegten Dissertation stehen.
4. Die Arbeit wurde bisher weder im Inland noch im Ausland in gleicher oder ähnlicher Form einer anderen Prüfungsbehörde vorgelegt.
5. Die Inhalte dieser Dissertation wurden in folgender Form veröffentlicht: Publikationen in peer-reviewed Journals, siehe chapter 'Preface', sowie Konferenzbeiträge, siehe Appendix.
6. Ich bestätige, dass es keine zurückliegenden erfolglosen Promotionsverfahren gab.
7. Ich bestätige, dass ich die Promotionsordnung der Medizinischen Fakultät der Technischen Universität Dresden anerkenne.
8. Ich habe die Zitierrichtlinien für Dissertationen an der Medizinischen Fakultät der Technischen Universität Dresden zur Kenntnis genommen und befolgt.

Dresden, 30.09.2020

Tilman von Stechow

Unterschrift des Doktoranden

ERKLÄRUNG ÜBER DIE EINHALTUNG GESETZLICHER BESTIMMUNGEN

Hiermit bestätige ich die Einhaltung der folgenden aktuellen gesetzlichen Vorgaben im Rahmen meiner Dissertation:

☐ das zustimmende Votum der Ethikkommission bei Klinischen Studien, epidemiologischen Untersuchungen mit Personenbezug oder Sachverhalten, die das Medizinproduktegesetz betreffen

Aktenzeichen der zuständigen Ethikkommission: *nicht zutreffend*

☐ die Einhaltung der Bestimmungen des Tierschutzgesetzes Aktenzeichen der Genehmigungsbehörde zum Vorhaben/zur Mitwirkung: *nicht zutreffend*

☒ die Einhaltung des Gentechnikgesetzes/Projektnummer: 55-8811.71/135

☒ die Einhaltung von Datenschutzbestimmungen der Medizinischen Fakultät und des Universitätsklinikums Carl Gustav Carus.

Dresden, 30.09.2020

Unterschrift des Doktoranden

AUSZUG AUS DEM JOURNAL CITATION REPORT

Für die in §10 festgelegten Regularien kommt das durch den *Journal Citation Reports 2020* festgelegte Fachgebiet *Biomedical Engineering* in Frage, welches die Studien der Kapitel 4 und 5 einschließt, welche im Journal *Biofabrication* (Impact Factor: 8,213, Rang 6/80) veröffentlicht wurden. Kapitel 6 wurde im Journal *ACS Applied Materials and Interfaces* veröffentlicht, welches in der Kategorie *Materials Science Multidisciplinary* mit einem Impact Factor von 8,758 auf Rang 33/314 gelistet ist. Die Voraussetzung für eine kumulative Dissertation nach §10 ist damit erfüllt.

CONFERENCES

CONFERENCE CONTRIBUTIONS The following list contains only conference contributions with TA as first (presenting) author.

2014. *Poster*. Annual Meeting of the German Society for Biomaterials. Dresden, Germany. **Ahlfeld T**, Akkineni AR, Lode A, Förster Y, Rentsch C, Rammelt S, Gelinsky M. Design of complex scaffolds consisting of calcium phosphate cement and hydrogel core/shell strands with respect to growth factor release, mechanical behaviour and cell adhesion. *BioNano Mater* 15:S1.

2015. *Oral*. Annual Conference of the International Society for Biofabrication. Utrecht, Netherlands. **Ahlfeld T**, Lode A, Akkineni AR, Förster Y, Brüggemeier S, Knaack S, Quade M, Rammelt S, Gelinsky M. 3D plotting of a biphasic scaffold consisting of a calcium phosphate cement and a growth factor loaded hydrogel blend.

2015. *Oral*. Annual Meeting of the German Society for Biomaterials. Freiburg, Germany. **Ahlfeld T**, Lode A, Förster Y, Akkineni AR, Schuster F, Brüggemeier S, Knaack S, Quade M, Rammelt S, Gelinsky M. 3D plotting of fine structured scaffolds consisting of a calcium phosphate cement and a growth factor loaded alginate-gellan gum hydrogel: fabrication and in vitro characterization. *BioNano Mater* 16:81-86.

2016. *Oral*. Annual Meeting of the German Society for Biomaterials. Aachen, Germany. **Ahlfeld T**, Cidonio G, Akkineni AR, Lode A, Dawson JI, Oreffo ROC, Gelinsky M. 3D-Plotten eines Alginat-Laponit-Methylcellulose-Komposits für die Biofabrikation. *BioNano Mater* 17:S1.

2017. *Oral*. Annual Conference of the International Society for Biofabrication. Beijing, People's Republic of China. **Ahlfeld T**, Doberenz F, Kilian D, Vater C, Korn P, Lode A, Gelinsky M. Bioprinting of Scaffolds for Repair of Bony Defects – Multichannel Plotting of a Calcium Phosphate Cement and a Cell-laden Alginate-based Bioink.

2017. *Oral*. Annual Meeting of the German Society for Biomaterials. Würzburg, Germany. **Ahlfeld T**, Doberenz F, Kilian D, Vater C, Korn P, Lode A, Gelinsky M. Towards Bioprinting of Biphasic Scaffolds for Bone Defects: Multichannel Printing of a Calcium Phosphate Cement and a Cell-laden Hydrogel. *Biomed Eng Biomed Tech* 62:25-33

2018. *Poster*. Conference on 3D Printing in Medicine. Mainz, Germany. **Ahlfeld T**, Korn P, Lode A, Gelinsky M. Low temperature printing of a self-setting calcium phosphate cement.

2018. *Oral*. Annual Conference of the International Society for Biofabrication. Würzburg, Germany. **Ahlfeld T**, Cubo-Mateo N, Kilian D, List A, Placht AM, Korn P, Lode A, Gelinsky M. 3D Bioprinting of Mineralized Tissue Equivalents – Combination of a Calcium Phosphate Cement with Different Bioinks.

2018. *Poster*. Annual Conference of the European Society for Biomaterials. Maastricht, Netherlands. **Ahlfeld T**, Akkineni AR, Kilian D, Korn P, Lode A, Gelinsky M. 3D bioplotting together with calcium phosphate cements.

2018. *Oral*. Deutscher Kongress für Orthopädie und Unfallchirurgie. Berlin, Germany. **Ahlfeld T**, Schumacher M, Gelinsky M, Lode A. 3D plotting of strontium modified calcium phosphate cements for regenerative bone implants. doi: 10.3205/18dkou489

2018. *Oral*. Annual Meeting of the German Society for Biomaterials. Braunschweig, Germany. **Ahlfeld T**, Kilian D, Köhler T, Czichy C, Mika L, Sembdner P, Korn P, Odenbach S, Stelzer R, Lode A, Gelinsky M. 3D plotting of anatomically relevant structures from calcium phosphate cements with methylcellulose as support material. *Biomed Eng Biomed Tech* 64:1-18

2019. *Poster*. Annual Conference of the European Society for Biomaterials and Annual Meeting of the German Society for Biomaterials. Dresden, Germany. Cubo N, **Ahlfeld T**, Cometta S, Guduric V, Bernhardt A, Akkineni AR, Lode A, Gelinsky M. A novel patient-individual bioink based on human plasma promotes the response of cells in bioprinted, mineralized constructs.

OTHER NOTEWORTHY PROCEEDINGS, PARTICIPATIONS AND LECTURES

2016. *Invited Lecture*. Aachen, Germany. Workshop Biofabrication in course of the Annual Meeting of the German Society for Biomaterials.

Gelinsky M, Akkineni AR, Schütz K, **Ahlfeld T**, Förster Y, Doberenz F, Brückner M and Lode A (2016). Multichannel 3D plotting for complex tissue equivalents and implants for defects at tissue interfaces. *Front Bioeng Biotechnol*. Conference Abstract: 10th World Biomaterials Congress. doi: 10.3389/conf.FBIOE.2016.01.00492

Brünler R, Aibibu D, Cherif C, **Ahlfeld T**, Gelinsky M. 2018. Patientenindividuelle faserbasierte Implantate für komplexe Gewebedefekte / Patient-specific and fiber-based implants for complex tissue defects. *Tech Text* 61:127-128 (E128-129)

Korn P, **Ahlfeld T**, Pradel W, Lode A, Franke A, Rauner M, Range U, Stadlinger B, Lauer G, Gelinsky M. 2019. 3D-bioprinting of bone grafts for alveolar defects—a preclinical pilot study. *Int J Oral Maxillofac Surg* 48:273

Kilian D, Sembdner P, **Ahlfeld T**, Schöne Christine, Lode A, Stelzer R, Gelinsky M, Holtzhausen S. 2019. Design und additive Fertigung von individualisierten biofunktionellen Implantaten in klinisch relevanten Dimensionen. *Entwerfen Entwickeln Erleben in Produktentwicklung und Design* 2019:253-256

2019. *Invited Lecture*. Arbeitskreis Biokeramik (Gemeinsamer Arbeitskreis der Deutschen Gesellschaft für Materialkunde e. V. und der Deutschen Keramischen Gesellschaft e. V.). Aachen, Germany. Biodruck mineralisierter Konstrukte durch die Kombination von zellbeladenen Hydrogelen und einem Calciumphosphatzement.

Hattab G, **Ahlfeld T**, Klimova A, Koeep A, Schuerer M, Speidel S. 2020. Data from Uniaxial Compression testing and validation scripts for Cauchy stress modeling to design anatomical silicone replicas. *Materials Cloud Archive* doi: 10.24435/materialscloud:2020.0019/v2